Fabrication of Polyamide Composites Using Nano-Copper Oxide Powder and Carbon Fibers

Abstract

The integration of nano-copper oxide (CuO) powder and carbon fibers into polyamide (PA) matrices offers a promising route to multifunctional composites with enhanced mechanical, tribological, and functional properties. This essay examines the fabrication strategies, interfacial engineering considerations, and performance outcomes of these hybrid composites. Nano-CuO serves dual roles as a functional filler and, through in-situ reduction, as a precursor for metallic copper nanoparticles that impart antistatic and antiwear characteristics . Carbon fibers provide structural reinforcement and, in combination with CuO, promote the formation of a self-lubricating transfer film containing elemental copper during friction . Key fabrication routes include in-situ polymerization, melt compounding, and hydrothermal deposition of CuO nanostructures directly onto carbon fiber surfaces. The synergistic effects observed in hybrid CuO/carbon fiber systems, including enhanced tensile strength, wear resistance, and flame retardancy, demonstrate the potential of these composites for automotive, electronic, and high-temperature applications .

Keywords: Polyamide; Nano-copper oxide; Carbon fiber; Hybrid composites; Interfacial adhesion

1. Introduction

Polyamide (PA) composites have become indispensable engineering materials due to their balanced mechanical properties, chemical resistance, and processing versatility. However, single-filler systems often cannot simultaneously address the diverse performance requirements of advanced applications, including structural integrity, wear resistance, thermal stability, and electrical conductivity. The combination of nano-copper oxide (CuO) powder with carbon fibers in a polyamide matrix represents a strategic hybrid approach that leverages complementary reinforcement mechanisms.

Nano-CuO is particularly attractive as a functional filler because of its low cost, chemical stability, and ability to be reduced to metallic copper under appropriate conditions . When incorporated into polyamide during in-situ polymerization, the amino end groups of PA6 can directly reduce CuO to metallic Cu nanoparticles without external reducing agents . This unique chemistry enables the formation of well-dispersed copper nanoparticles that are encapsulated by the polyamide matrix, providing both antistatic functionality and improved wear resistance .

Carbon fibers contribute high specific strength and stiffness, dimensional stability, and thermal conductivity. When combined with CuO nanoparticles, carbon fibers can promote tribochemical reactions that generate elemental copper in the transfer film during friction, substantially reducing wear . This synergy has been demonstrated in polyamide 1010 composites, where the hybrid filler system of 10% CuO and 20% carbon fiber yielded the highest wear resistance and tensile strength .

This essay examines the fabrication strategies for PA composites containing both nano-CuO and carbon fibers, the interfacial considerations that govern their performance, and the resulting property enhancements that make these materials attractive for demanding applications.

2. Fabrication Strategies

2.1 In-Situ Polymerization with CuO Reduction

The in-situ polymerization route exploits the weak reducing capability of polyamide amino groups to convert CuO directly to metallic copper during synthesis. Xu et al. demonstrated that when CuO is added to the ε-caprolactam polymerization system, the amino groups of the growing PA6 chains reduce CuO to metallic Cu without any external reducing agent . The resulting copper nanoparticles, with sizes of 4–5 nm, are uniformly dispersed and encapsulated by a layer of PA6 . This encapsulation serves dual purposes: preventing nanoparticle aggregation and protecting the copper from oxidation .

The CuO content significantly influences the crystalline form of PA6. At higher CuO dosages, the γ crystalline form becomes predominant in the resulting nano-Cu/PA6 composites . The optimal CuO content for balanced mechanical properties and wear resistance was determined to be 0.5%, at which the composite exhibited the best tensile strength and wear performance .

For composites that also incorporate carbon fibers, the in-situ polymerization approach can be adapted by introducing carbon fibers into the reaction mixture. However, the presence of carbon fibers may affect the polymerization kinetics and the reduction efficiency of CuO, requiring careful optimization of reaction conditions.

2.2 Melt Compounding

Melt compounding offers a more industrially scalable route for fabricating PA/CuO/carbon fiber composites. The process involves dry-blending the components followed by extrusion or injection molding. For semi-aromatic polyamide composites, a combination of glass fiber and carbon fiber was reinforced with nano-CuO as a synergistic flame-retardant agent . The composite containing 10 wt% CF and 20 wt% GF demonstrated optimal cost efficiency and antistatic performance .

The challenge in melt compounding lies in achieving uniform dispersion of nano-CuO, which tends to agglomerate due to high surface energy. Surface treatment of CuO or the use of compatibilizers may be necessary to achieve optimal dispersion.

2.3 Hydrothermal Deposition on Carbon Fibers

An alternative approach involves depositing CuO nanostructures directly onto carbon fiber surfaces before composite fabrication. Rai and Bajpai employed a hydrothermal technique to grow CuO nanostructures on woven carbon fibers, creating a nanostructured interphase that increased interfacial strength . This method produces a hierarchical reinforcement structure where the CuO nanostructures serve both as interfacial modifiers and as functional components.

The hydrothermal method offers advantages in terms of controlling the morphology and distribution of CuO on the fiber surface. CuO nanorods can be grown perpendicular to the fiber surface, creating mechanical interlocking with the polymer matrix . This approach has been shown to improve impact energy absorption and in-plane shear properties of carbon fiber composites .

3. Interfacial Engineering Considerations

The performance of hybrid PA/CuO/carbon fiber composites critically depends on the quality of interfacial adhesion. Poor interfacial bonding leads to ineffective stress transfer and premature failure.

The amide groups in polyamide can form hydrogen bonds with polar groups on the carbon fiber surface, but the inherently smooth and chemically inert surface of untreated carbon fibers limits this interaction. Surface modification of carbon fibers with coupling agents, plasma treatment, or sizing agents can enhance interfacial adhesion . Amide-functionalized emulsifiers have been shown to create cross-linked interphases that promote transcrystallization of PA6 at the interface, optimizing stress transfer .

The presence of CuO nanoparticles introduces additional interfacial complexity. When CuO is reduced in-situ, the resulting metallic copper nanoparticles are encapsulated by PA6, creating a core-shell structure that enhances both dispersibility and compatibility . The copper nanoparticles may also interact with the carbon fiber surface, potentially forming conductive pathways that contribute to antistatic properties.

During friction, carbon fibers promote the tribochemical reduction of CuO to elemental copper, which is incorporated into the transfer film . This copper-containing transfer film exhibits enhanced bonding strength to the counterface, reducing abrasive and adhesive wear .

4. Performance Enhancements

4.1 Mechanical Properties

The combination of CuO and carbon fibers produces synergistic mechanical reinforcement. In PA1010 composites, the hybrid system with 10% CuO and 20% CF exhibited the highest tensile strength and wear resistance . The copper nanoparticles contribute to mechanical enhancement through heterogeneous nucleation, which increases crystallinity and elastic modulus .

At optimal CuO content (0.3%), the tensile strength of PA6/Cu nanocomposites increased by 29.1%, while elongation at break improved by 62.4% . Impact toughness showed a maximum improvement of 170.5% at 0.7% nano-Cu content . The elastic modulus increased monotonically with CuO content, reaching an 85.4% improvement at 0.7% .

4.2 Tribological Properties

The tribological benefits of hybrid CuO/carbon fiber reinforcement are particularly significant. Carbon fibers carry a substantial portion of the applied load, reducing stress on the polyamide matrix. Meanwhile, CuO and its reduction product (elemental copper) modify the transfer film, creating a self-lubricating layer that reduces both friction and wear .

The wear scar diameter of nano-Cu/PA6 composites initially decreases with CuO content up to an optimal level, beyond which it slightly increases due to reduced mechanical strength at excessive filler loading . The optimal CuO content for wear resistance coincides with that for mechanical properties.

4.3 Functional Properties

Nano-CuO incorporation imparts antistatic characteristics to polyamide composites. The resistance value of PA6, which is above 10^{14} Ω, is drastically reduced to 10^{8} Ω in nano-Cu/PA6 composites due to the incorporation of metallic Cu nanoparticles . In semi-aromatic polyamide composites, the combination of carbon fibers and CuO significantly reduces surface resistivity .

Flame retardancy represents an additional functional benefit. Nano-CuO acts as a synergistic agent in condensed-phase flame-retardant mechanisms, enabling reduction of conventional flame retardant content while maintaining V-0 flammability ratings . The composite formulated with 8 wt% ADP, 1 wt% BN, and 0.5 wt% CuO achieved a limiting oxygen index of 39% .

5. Conclusion

The fabrication of polyamide composites using nano-copper oxide powder and carbon fibers represents a sophisticated approach to multifunctional material design. The unique chemistry of CuO reduction by polyamide amino groups enables the in-situ formation of well-dispersed metallic copper nanoparticles that are encapsulated by the polymer matrix, providing antistatic functionality and enhanced wear resistance. Carbon fibers contribute structural reinforcement and promote the formation of protective transfer films during friction.

Key fabrication routes include in-situ polymerization, melt compounding, and hydrothermal deposition of CuO onto carbon fiber surfaces. Each approach offers distinct advantages depending on the target application and manufacturing scale. Interfacial engineering remains critical, with surface modification of carbon fibers and control of CuO reduction chemistry being essential for optimal performance.

The resulting composites exhibit synergistic enhancements in mechanical strength, tribological performance, and functional properties including antistatic behavior and flame retardancy. These characteristics position PA/CuO/carbon fiber composites as promising candidates for automotive, electronic, and high-temperature applications where multifunctional performance is required.

References

[1] Q. Xu, X. Li, Z. Zhang, Preparation of copper nanoparticle-improved polyamide 6 composites by an in situ solution route with cupric oxide as the metallic copper source and investigation of their properties, New J. Chem. 39 (2015) 3015–3020.

[2] Interfacial amide functionalization induces transcrystallization and enhances mechanical properties in carbon fiber/polyamide 6 composites, Composites Part A (2026).

[3] S. Ye, S. Yang, G. Liu, Carbon fiber and glass fiber reinforced semi-aromatic polyamide composites with enhanced mechanical, electrical, and flame-retardancy properties, J. Appl. Polym. Sci. 142 (2025) e57466.

[4] R.S. Rai, V. Bajpai, Improvement of interfacial adhesion of CuO nanostructured carbon fiber reinforced polymer composites, Polym. Compos. 44 (2023) 1789–1804.

[5] Q. Xu, X. Li, Z. Zhang, Preparation of Cu nanoparticles-modified PA6 composites using CuO as filler, J. Iran. Chem. Soc. 11 (2014) 1717–1724.

[6] The tribological properties and wear mechanisms of carbon fiber and CuO reinforced polyamide 1010 composites, Tribology 22 (2002) 277–281.

[7] Metal oxide nanostructured woven carbon fiber/polymer composites, UNIST Thesis.

[8] Mechanical properties of PA6/Cu nanocomposites, Rev. Roum. Chim. (2019).

[9] Enhanced mechanical property of continuous carbon fiber/polyamide thermoplastic composites by combinational treatments of carbon fiber fabric, Composites Part B 250 (2023) 110451.