

RPP -Sathyamoorthy (JV)

S.F.No.: 454, Ragupathynaiken Palayam,
Poondurai Main Road,
Railway Colony Post,
Erode – 638002
GST: 22ABCFR8363C1ZF
Email – raipur.rppvscjv@rppiopl.com

Lr. No. RPP-SM-JV/RRW/300

Date: 28-02-2025

To,
The Team Leader,
M/s Aarvee Associates Architects Engineers & Consultants Pvt. Ltd
8-2-5, Ravula Residency, Srinagar colony Main Rd
Hyderabad 500082
Telangana, India
Email: aarvee@aarvee.net

Project: Major up-gradation of Raipur Railway Station of SECR on Engineering, Procurement and Construction (EPC) mode.

Subject: Request for No Objection Certificate (NOC) for Sika Mono Top®-1010 IN and Resikon Coastel (for use as protect on coating to reinforcement bars).

References:

1. LOA issued vide Lr No: Raipur Division – Gati Shakti / DyCE-GSU-R-T-18-23- 24/00634660101437 dt 20-Apr-24.
2. EPC Contract Agt No: SECR/R/GS/2024/0005 dt 03-Jul-24.

1. Pursuing to clause 1.4.2.7 (6) of schedule DC (Page 57), it is proposed to use the following products for protective coating on reinforcement.
 - a) SIKA Mono Top®-1010 IN.
 - b) RESIKON – COASTAL.
2. AE is requested to please issue NOC for use of protective coating of above mentioned products.

Thanking you and assuring our best services at all times.

For RPP - SATHYAMOORTHY (JV)

**ABHISHEK
GARG**

Digitally signed by ABHISHEK GARG
DN: c=IN, postalCode=492006, st=CHHATTISGARH,
street=HOUSE NO.14, RAIPUR, RAISHWARYA
RESIDENCY, 492006, I=RAIPUR, o=Personal,
serialNumber=76822a0f5a2882179d804d6892e9f4c1dae9c79a
2d9ffa5bae78752dc89fed5f,
pseudonym=352f77d325a9414383d15035e62b7d17,
2.5.4.20=2de5b815fcd453467bbebe28b403c16217deda1041c
3685bdf9d7fe881fa39f, email=ABHISHEKGARG@BARBRIK.IN,
cn=ABHISHEK GARG
Date: 2025.02.28 16:18:30 +05'30'

**Abhishek Garg
Project Coordinator
Authorized Signatory**

Encl: Technical Data Sheet of above products.

Copy to:

1. CPM/GSU/R for kind information please.
2. Dy CE/GSU/R for kind information please
3. Head Office, RPP Infra Projects Ltd, Email- tender.bo@rppiplt.com and project@rppiplt.com - For information please.



RESIKON- COASTAL

TECHNICAL DATA SHEET

INTRODUCTION	RESIKON- COASTAL is a chemically modified acrylic copolymer used in combination with Portland cement. These two components should be mixed at site with paddle type mixer to form slurry of creamy thick paint consistency. Water can be added in a small proportion to get workable consistency.	
AREAS OF APPLICATION	RESIKON COASTAL, provides corrosion protective system for steel structures in humid conditions, corrosive atmosphere like sea / salt water environment. It is suitable for bridge decks, water tanks (non-potable), drilling platforms and steel etc.	
FEATURES & BENEFITS	<ul style="list-style-type: none">▪ Ease of application▪ Excellent corrosion protection▪ Withstands 100 hrs of Salt Spray [as primer with top coat]▪ Pull of adhesion - > 1.8 Mpa [on rusted substrate]▪ Improves adhesion between concrete and rebars	
PHYSICAL PROPERTIES	Appearance	: Milky white liquid
	Polymer type	: Styrene-Acrylic
	% Total Solids	: 40 ± 1
	pH (as is)	: 8.0 – 9.5
	Viscosity by B4 FC at 30°C[sec]	: 12-15
	Film Property	: Excellent
	Compatibility with cement	: Excellent
INSTRUCTIONS FOR USE	The performance of coating depends upon the surface preparation and hence correct surface preparation is very important. Surface should be clean and free from oil, grease, poorly bonded coating, loose scale etc. Badly corroded	

	<p>surface should be treated with AMCOR RR (Rust Remover) before applying RESIKON COASTAL/cement coating system.</p> <p>The coating system for reinforcement steel bars can be prepared in the following manner.</p> <p>Portland cement / white cement : 1 kg. RESIKON COASTAL : 1 kg Water : To get workable consistency</p> <p>RESIKON COASTAL can also be mixed with cement and fine silica sand in the following manner.</p> <p>Cement : 1 kg. Fine silica : 0.3 kg. RESIKON COASTAL : 1 kg. Water : To get workable consistency</p> <p>Coating can be applied by brush, roller, spraying or by dipping. Minimum two coats are recommended, If dipping method is not used dry film thickness should be minimum 500 microns. The pot life of the mix varies from 1 to 1.5 hours depending on temperature and humidity</p>
COVERAGE	15 - 20 Sq. ft. per kg of RESIKON COASTAL
PACKING	1, 5 and 20 kg HDPE containers.
SHELF LIFE	RESIKON COASTAL can be stored in packed condition for one year.
SAFETY DATA	<p>HEALTH HAZARD: RESIKON COASTAL is basic in nature. It is recommended to take necessary precaution. Use rubber hand gloves, splash goggles etc. Direct contact with any part of the body, especially with eyes must be avoided. In case of contact or splash into eyes, wash with water immediately and consult a physician.</p> <p>FIRE HAZARD: By itself it cannot catch fire. If comes in contact with alkali, heat and fumes can generated.</p>

DISCLAIMER

This information is given to the best of our knowledge. There is no legally binding assurance of certain properties for a specific purpose. The customer is responsible for determining whether the product and Information provided here is appropriate for his use. It is the sole responsibility of the customer to ensure that any proprietary rights and existing laws and legislation are observed.

ANUVI CHEMICALS LIMITED (AN ISO 9001: 2015 COMPANY)

Sales office: 205/210/211, Narmada, Laxmi Industrial Premises,
Pokharan Road No.1, Vartak Nagar, Thane - 400 606,
Maharashtra. India.

Tel.:+91-22-25855379 / 25855714 **Website** www.resikon.com



PRODUCT DATA SHEET

Sika MonoTop®-1010 IN

Bonding primer and reinforcement corrosion protection cement based slurry containing recycled waste materials and corrosion inhibitors

DESCRIPTION

Sika MonoTop®-1010 IN is a 1-part, cementitious, polymer modified coating material used as bonding primer and reinforcement corrosion protection. It contains corrosion inhibitors as well as recycled waste materials which leads to a reduced carbon footprint compared to an equivalent performing mortar.

CHARACTERISTICS / ADVANTAGES

- Uses recycled waste materials
- Easy to use, just add water
- Good adhesion to concrete and steel
- Good resistance to water and chloride penetration
- Can be applied with a brush or by wet spray technique

USES

Sika MonoTop®-1010 IN may only be used by experienced professionals.

- Bonding primer as part of a concrete repair system
- Reinforcement corrosion protection as part of a concrete repair system
- Interior and exterior use

PRODUCT INFORMATION

Chemical base	Portland cement, cement replacement, re-dispersible polymer powder, selected aggregates and additives
Packaging	25 kg bag
Shelf life	12 months from date of production
Storage conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +35 °C.
Appearance / Colour	Grey powder

TECHNICAL INFORMATION

Compressive strength	~50 MPa after 28 days	(EN 12190)
Tensile adhesion strength	~2.0 MPa after 28 days	(EN 1542)
Shear Adhesion	Pass	(EN 15184)
Corrosion Test	Pass	(EN 15183)

SYSTEM INFORMATION

System structure

Sika MonoTop®-1010 IN is part of the range of Sika® mortars and comprising of:

Bonding Primer / Reinforcement Corrosion Protection

Sika MonoTop®-1010 IN

Repair Mortar

Sika MonoTop®-412 IN

Sika MonoTop®-122 F

Sika MonoTop®-3250 Thick Mortar

Sika MonoTop®-3130 Rapid IN

Fire Protection Mortar

Sikacrete®-213 F IN

Smoothing / levelling mortar

Sika MonoTop®-2500 Fair Finish

APPLICATION INFORMATION

Mixing ratio	Application type	Water : Powder	Quantity of water per bag
	brush application	0.20–0.21	5.00–5.25 L
	spraying application	0.19–0.20	4.75–5.00 L
Fresh mortar density	2.0 ± 0.05 kg/L		(EN ISO 2811-1)
Consumption	Bonding Primer	~1.5–2.0 kg of powder per m² per 1 mm layer thickness Depends on substrate roughness and thickness of layer applied.	
	Reinforcement Corrosion Protection	~2.0 kg of powder per m² per 1 mm layer thickness	
	Consumption depends on the roughness and absorbency of the substrate. This figure is theoretical and does not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.		
Layer thickness	Bonding Primer	Sufficient to coat the concrete surface in a thin layer filling pores and voids	
	Reinforcement Corrosion Protection	2 mm minimum thickness	
Ambient air temperature	+5 °C min. / +30 °C max.		
Substrate temperature	+5 °C min. / +30 °C max.		
Pot life	20 % water (machine applied)	~90 minutes	
	21 % water (manual application)	~120 minutes	
Waiting time / Overcoating	Apply concrete repair mortar wet on wet onto bonding primer. Apply concrete repair mortar wet on dry onto reinforcement corrosion protection.		

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

- Sika Method Statement: Concrete Repair Using Sika MonoTop® System
- EN 1504-7 - Reinforcement corrosion protection

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Concrete

- The concrete must be thoroughly clean, free from dust, loose material, surface contamination and materials which reduce bond or prevent suction or wetting by repair materials.
- De-laminated, weak, damaged and deteriorated concrete and where necessary sound concrete must be removed by suitable means.
- Ensure sufficient concrete is removed from around corroded reinforcement to allow cleaning for corrosion protection (where required) and compaction of the repair material.

Steel reinforcement

- Rust, scale, mortar, concrete, dust and other loose and deleterious material which reduces bond or contributes to corrosion must be removed.
- Surfaces must be prepared using abrasive blast cleaning techniques or high pressure water-blasting to Sa 2 (ISO 8501-1).

MIXING

Important: Do not add water over recommended dosage.

Mix with a low speed (< 500 rpm) electric single or double paddle mixer or by hand for small quantities.

1. Pour the recommended water quantity in a suitable mixing container.
2. While stirring slowly, add the powder to the water and mix thoroughly for at least for 3 minutes.

APPLICATION

Important: Avoid application in direct sun and/or strong wind and/or rain.

Sika India Pvt. Ltd.
620, Diamond Harbour Road
Commercial Complex II
Kolkata - 700 034
West Bengal, India

Contact:
Phone: +91 33 2447 2448
Fax: +91 33 2397 8688
info.india@in.sika.com
www.sika.in



Product Data Sheet
Sika MonoTop®-1010 IN
August 2022, Version 01.01
020302020010000067

Bonding primer

1. Thoroughly pre-wet the prepared substrate a recommended 2 hours before application. Keep the surface wet and do not allow to dry.
2. Before application remove excess water e.g. with a clean sponge. The surface must appear a dark matt appearance without glistening. Surface pores and voids must not contain water.
3. Using a suitable clean brush, roller or suitable spraying equipment, cover the substrate in a thin layer filling all unevenness, pits and voids.

Reinforcement corrosion protection

1. Using a suitable clean brush or spraying equipment, apply a first coat to cover the reinforcement bars ~1 mm thick.
2. When first coat is finger nail hard, apply a second layer ~1 mm thick.
3. If using a spray method, protect substrate from excessive over-spray. Wait until completely dry before applying repair mortar.

CURING TREATMENT

Reinforcement corrosion protection: protect fresh coating immediately from premature drying and contamination using an appropriate curing method.

CLEANING OF TOOLS

Clean all tools and equipment with water immediately after use. Hardened material can only be mechanically removed.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaMonoTop-1010IN-en-IN-(08-2022)-1-1.pdf