## XHEZC.SP423 Firestop Systems

Page Bottom

## **Firestop Systems**

See General Information for Firestop Systems


## System No. SP423

January 13, 2004

(For Horizontal or Vertical Separations)

F and FH Ratings - 3 h

FT and FTH Ratings - 0, 1 h (See Item 2)



- 1. **Floor or Wall Assembly** Min depth or thickness as necessary for required grade of fire separation but not less than 114 mm normal-density  $(2400\pm50 \text{ kg/m}^2)$  concrete. Floor may also be constructed of min 152 mm thick hollow-core precast concrete units having a fire resistance rating equal to or greater than that of the firestop system. Max size of opening 254 mm diam. When precast concrete units are used, max diam of opening 178 mm.
- 2. **Metallic Sleeve (optional)** Nom 254 mm OD (or smaller) Schedule 40 (or heavier) steel sleeve cast or grouted into floor or wall assembly flush with floor or wall surfaces. When steel sleeve is installed, the FT and FTH Rating is 0 h. Without steel sleeve, FT and FTH Rating is 1 h.
- 3. **Firestop System Components** (XHJZC). Type "A/D Firebarrier Mortar" compound prepared by mixing mortar powder with water at a ratio of 1 bag (7 kg) of powder to 2.5 kg of water in accordance with the manufacturer's instructions. The mortar compound is trowelled into the opening to a min thickness of 76 mm flush with top surface of floor or both surface of wall assembly.

## A/D FIRE PROTECTION SYSTEMS INC

4. **Forming Material (optional)** — Mineral wool insulation installed to prevent leakage of mortar compound while in liquid state fitted tightly against perimeter of opening. If left in place, will not affect assigned ratings.

Questions? Print this page Terms of Use Page Top

Copyright © 2016 Underwriters Laboratories of Canada Inc.

When the UL Leaf Mark is on the product, or when the word "Environment" is included in the UL Mark, please search the <u>UL Environment</u> <u>database</u> for additional information regarding this product's certification.

The appearance of a company's name or product in this database does not in itself assure that products so identified have been manufactured under ULC's Follow-Up Service. Only those products bearing the ULC Mark should be considered to be Listed and covered under ULC's Follow-Up Service. Always look for the Mark on the product.

ULC permits the reproduction of the material contained in the ULC Online Directories subject to the following conditions: 1. The Guide Information, Designs and/or Listings (files) must be presented in their entirety and in a non-misleading manner, without any manipulation of the data (or drawings). 2. The statement "Reprinted from the ULC Online Directories with permission from Underwriters Laboratories of Canada Inc." must appear adjacent to the extracted material. In addition, the reprinted material must include a copyright notice in the following format: "Copyright © 2016 Underwriters Laboratories of Canada Inc."

An independent organization working for a safer world with integrity, precision and knowledge.

