
Materials at which zener breakdown occurs

Heavily doped junction diodes

Consequence of high dopant density on width of depletion region

Small

Consequence of high dopant density on electric field of depletion region

High

Internal field emission in zener breakdown

Tunnel electrons from valance band to N region

Zener breakdown in semiconductors

Diode breakdown due to band to band tunneling of electrons