

# Find lattice constant

- Find FCC Cu lattice constant
- ASE, ASE-STATE-interface
  - ASE tutorial page: [https://wiki.fysik.dtu.dk/ase/tutorials/lattice\\_constant.html](https://wiki.fysik.dtu.dk/ase/tutorials/lattice_constant.html)
- Calculated 20 candidates, shifting gradually from the initial value 3.6 Å

Fit the energy using this expression(a: lattice constant)

$$E(a) = p_0 + p_1 a + p_2 a^2$$

optb86b-vdw	rev-vdw-df2
3.6089 Å	3.6157 Å

# Code

```
from state_interface.state import STATE
import os
import sys
from ase.build import bulk
from ase.io import Trajectory, read
import numpy as np

a0 = 3.6
eps = 0.01
traj = Trajectory('Cu.traj', 'w')
n_cpus = int(sys.argv[1])

energies = []
for i, a in enumerate(a0 * np.linspace(1 - eps, 1 + eps, 20)):
    slab = bulk('Cu', 'fcc', a=a)
    label = f'Cu{i}'
    input_file = f'{label}.in'
    output_file = f'{label}.out'
    pw_loc = './STATE'

    os.environ['ASE_STATE_COMMAND'] = f'mpirun -np {n_cpus} {pw_loc} < {input_file} > {output_file}'

    dft_calc = STATE(label=label, input_data=input_data)
    slab.calc = dft_calc
    energies.append(slab.get_potential_energy())
    traj.write(slab)

print(energies)
configs = read('Cu.traj@:')
a = np.array([2*config.cell[0, 1] for config in configs])
print(a)
# f(a) = p0 + p1*a + p2*a**2
functions = np.array([a**0, a, a**2])
p = np.linalg.lstsq(functions.T, energies, rcond=-1)[0]
#f'(a) = p1 + 2*p2*a
p1 = p[1]
p2 = 2*p[2]
a0 = -p1/p2
print(a0)
```




## STATE parameters

```
input_data = {'WF_OPT'      : 'DAV' ,
              'TYPE'       : 0 ,
              'NSPG'       : 1 ,
              'VERBOSITY'   : 'MEDIUM',
              'GMAX'       : 6.00 ,
              'GMAXP'      : 20.00 ,
              'KPOINT_MESH' : [16, 16, 16],
              'KPOINT_SHIFT' : ['OFF', 'OFF', 'OFF'],
              'NEG'        : 12,
              'NSCF'       : 200,
              'NSTEP'      : 200,
              'TASK'       : 'SCF',
              'WAY_MIX'    : 6,
              'MIX_WHAT'   : 1,
              'KBXMIX'     : 30,
              'MIX_ALPHA'  : 0.5,
              'DTIO'       : 100,
              'IMDALG'     : 2,
              'WIDTH'      : -0.0020,
              'FORCCR'     : '1.00D-03',
              'XCTYPE'     : 'optb86b',
              'DESTM'      : 1.00,
              'EDELTA'     : '1.00D-09',
              'PSEUDOS'    : [
                  ['Cu', 63.55, 'pot.Cu_pbe1'],
              ],
              'VDW-DF'     : {'QCUT' : 10, 'NQ' : '20'}
            }
```




# Calculate absorption energy

- CO on Cu(111)

optb86b-vdw

	bridge	ontop	fcc hollow
			
$E_{abs}(eV)$			
$d_{C-O}(\text{\AA})$			
$d_{Cu-C}(\text{\AA})$			

rev-vdw-df2

	bridge	ontop	fcc hollow
			
$E_{abs}(eV)$			
$d_{C-O}(\text{\AA})$			
$d_{Cu-C}(\text{\AA})$			

