



OPEN CELL SPRAY FOAM

Enverge EasySeal .5

Light-Density Open Cell Spray Polyurethane Foam

Manufactured by **Holcim Solutions and Products US, LLC** · Manufactured in Spring, Texas and Waukesha, Wisconsin ·
Country of origin: **United States**

Enverge EasySeal .5 is a spray-applied, two-component open cell polyurethane foam used to insulate and seal walls, attics, ceilings, crawl spaces and interior assemblies. Open cell foam expands to fill every void and bonds to the surrounding structure, forming a seamless thermal envelope with no gaps or seams. It is vapor-permeable, so the assembly retains the ability to dry.

R-3.8

per inch, aged
ASTM C518

>90%

open cell content
ASTM D6226

0.5 lb/ft³

nominal density
ASTM D1622

CDPH 01350

low-emitting certified
Indoor air quality

WHY WE SPECIFY IT

1 Certified for schools and healthcare environments

EasySeal .5 meets California Department of Public Health Standard 01350 for low-emitting materials — a certification whose criteria explicitly account for sensitive individuals including children and the elderly.

2 Continuous air seal

Air permeance below 0.002 L/s·m² at 3.5 inches. The foam flows into voids and seals cracks as it expands, eliminating the air leakage paths that make older homes drafty and expensive to heat.

3 Dimensionally stable across extremes

Less than 5% dimensional change at -40°F, at +200°F, and at 158°F with 100% relative humidity. It will not shrink away from framing or sag out of the cavity over time.

4 Wide service temperature range

Rated for ambient service from -40°F to 180°F, with intermittent exposure to 220°F. New England attics see the full range of that span.

HEALTH & INDOOR AIR QUALITY

- **CDPH Standard 01350 compliant.** EasySeal .5 is a low-VOC emitting material certified to the California Department of Public Health standard. This program applies strict certification criteria and builds in safety factors specifically to account for sensitive individuals such as children and the elderly, and certifies a product as acceptable for use in environments such as schools and healthcare facilities.
- **Referenced by CHPS and LEED.** The same 01350 certification is referenced by the Collaborative for High Performance Schools and the LEED Building Rating System as a low-emitting insulation credit.
- **No mold or fungal growth.** Tested to ASTM C1338 with no growth.
- **Our standard practice with children in the home.** We recommend families with young children, elderly members, or anyone chemically sensitive plan to be out of the house during spraying and for a full 24–48 hours afterward while the foam finishes curing.

TECHNICAL PROPERTIES

PROPERTY	VALUE	TEST METHOD
Apparent density	0.5 lb/ft³ nominal	ASTM D1622
R-Value (aged) at 75°F mean	3.8 per inch	ASTM C518
Open cell content	> 90% by volume	ASTM D6226
Compressive strength	< 5 lb/in²	ASTM D1621
Air permeance at 3.5 in.	< 0.002 L/s·m²	ASTM E2178
Water vapor permeance	~23 perm-in	ASTM E96
Fungi resistance	No growth	ASTM C1338
Dimensional stability at -40°F	< 5% change	ASTM D2126
Dimensional stability at +200°F	< 5% change	ASTM D2126
Dimensional stability, 158°F / 100% RH	< 5% change	ASTM D2126
Flame spread index (at 4 in.)	Class 1 (A) — < 25	ASTM E84
Smoke developed index (at 4 in.)	Class 1 (A) — < 450	ASTM E84
Service temperature range	-40°F to 180°F	220°F intermittent

CODE COMPLIANCE & CERTIFICATIONS

CSI master specification	07 21 19
Surface burning characteristics	ASTM E84 / NFPA 255 / UL 723 — Class 1 (A)
Ignition barrier	ICC-ES AC377 Appendix X — Pass with DC315 at 4 wet mils, or No-Burn ThB Plus at 6 mils
Thermal barrier	NFPA 286 — Pass with TPR2 at 20 wet mils, DC315 at 14 wet mils, or Flame Control 60-60A at 14 wet mils
Indoor air quality	CDPH Standard 01350 — low-emitting material
LEED	Low-emitting insulation per CA Section 01350

ENVIRONMENTAL & CONTENT

MANUFACTURER DOCUMENTATION

VOC compliance
Low-emitting insulation, CA Section 01350

Post-consumer recycled content
0%

Post-industrial recycled content
0%

Technical Data Sheet (TDS) envergesprayfoam.com → EasySeal

Safety Data Sheet (SDS) Parts A and B, available on request

Architectural specification sheet CSI 07 21 19

Full TDS and SDS for every product on your project are available on request, at no charge, same day.

COATING & ASSEMBLY NOTE

Where exposed foam requires a coating, the manufacturer's tested assemblies for EasySeal .5 are: as an ignition barrier, DC315 at 4 wet mils or No-Burn ThB Plus at 6 mils; as a thermal barrier under NFPA 286, TPR2 at 20 wet mils, DC315 at 14 wet mils, or Flame Control 60-60A at 14 wet mils.