



IGNITION & THERMAL BARRIER COATING

DC315

Water-Based Intumescent Fire Protective Coating

Manufactured by **International Fireproof Technology, Inc.** · 17528 Von Karman Avenue, Irvine, California 92614 · Country of origin: **United States**

Building code requires that spray foam be separated from living space by a 15-minute thermal barrier — normally half-inch drywall. Where drywall is impractical, such as an exposed attic or crawl space, an approved intumescent coating does the same job. DC315 is a single-component, water-based coating and the most extensively tested fire protective coating for spray foam on the market, with certified assemblies over all major brands and types of open and closed cell foam.

10.3 g/L

total VOC
EPA / AQMD compliant

0 / 10

flame spread / smoke
ASTM E84

ESR-3702

ICC-ES evaluation
Code approved

50 years

tested useful life
Fire performance retained

WHY WE SPECIFY IT

1 The most tested coating for spray foam

DC315 passed certified NFPA 286 testing over all major brands and types of open and closed cell spray foam. That breadth matters — a coating can only be used on a foam it has been full-scale tested over.

2 Near-zero flame spread

ASTM E84 results of flame spread 0 and smoke developed 10 — the lowest numbers available in this product category.

3 Proven long-term performance

Tested useful life shows fire performance is not compromised after 50 years. The protection does not degrade as the house ages.

4 Documented application thickness

We place metal test coupons through the work area — at least one per 400 square feet, dated and signed — and measure wet film thickness on them. Those coupons stay on file as proof the coating met the rate its code approval requires.

HEALTH & INDOOR AIR QUALITY

- **Total VOC of 10.3 g/L.** Standard interior latex paint typically runs 50–100 g/L. DC315 passed strict EPA VOC and AQMD air emission requirements.
- **Certified low-emitting under CA Section 01350.** DC315 passed CA-1350 testing, qualifying it as a low-emitting material for LEED and green building standards — the same standard applied to materials used in schools and healthcare facilities.
- **No formaldehyde; RoHS compliant.** Water-based with no flash point, cleaned with water.
- **ANSI 51 tested for incidental food contact.** An unusual credential for a fire coating, and a useful indicator of how inert the cured film is.

TECHNICAL PROPERTIES

PROPERTY	VALUE	TEST METHOD
Total VOC	10.3 g/L	—
VOC less water	18.6 g/L	—
Volume solids	67%	—
Colors available	Ice Gray, White, Charcoal Black	—
Dry to touch	1 - 2 hours at 77°F / 50% RH	—
Recoat time	4 - 8 hours at 77°F / 50% RH	—
Type of cure	Coalescence	—
Flash point	None	—
Maximum rate per coat	24 wet mils	—
Flame spread index	0	ASTM E84
Smoke developed index	10	ASTM E84

CODE COMPLIANCE & CERTIFICATIONS

ICC-ES evaluation report	ESR-3702 (USA)
Thermal barrier	NFPA 286 — complies with IBC / IRC 2603.9 and 803.1; coated assembly may be left exposed without gypsum board
Ignition barrier	ICC-ES AC377 Appendix X — meets requirements for unoccupied spaces
Exterior wall systems	NFPA 285 — UL File R40016, various architectural claddings; meets IBC 2603.5
Fire resistance rating	ASTM E119 / ULC S-101 — up to 60 minutes
Ignition resistant material	ASTM E2768 — 30 minutes
Third-party listing & life safety	QAI File B1117, third-party inspected. Meets NFPA 101 Life Safety Code.

ENVIRONMENTAL & CONTENT

CA Section 01350 (CA-1350)
Passed — low-emitting for LEED
EPA VOC and AQMD emissions
Passed
Formaldehyde
None
RoHS
Compliant

MANUFACTURER DOCUMENTATION

Technical Data Sheet (TDS)	painttoprotect.com → Technical Documents
Safety Data Sheet (SDS)	painttoprotect.com → DC315 SDS (USA)
ICC-ES Evaluation Report	ESR-3702 — icc-es.org
Application & Ventilation Guide	painttoprotect.com
Full TDS and SDS for every product on your project are available on request, at no charge, same day.	

COATING & ASSEMBLY NOTE

Coverage rate is product-specific. Every SPF insulation system has its own approved application rate under ICC-ES ESR-3702 — a coating must be full-scale tested over the exact foam it is applied to. We confirm the correct rate against the report for the foam installed on your project before we coat.