

Day 2 learner sheet — an invented bulk-to-boundary model

Keep the reference card at the end beside your work. Predict before uncovering the separate answer sheet; mark any hint, partner help or supplied result used. All required work is on paper. The numerical model is invented A/B at $T = 1000$ K and $p = 100000$ Pa. It is **not** a Ni-Cu assessment. Where a result is supplied, interpret and check it rather than claiming that you ran a solver. Links to the detailed lessons behind each step are in the source map for later study.

D0 • Bridge from Day 1 (09:00)

Yesterday, fixed T, p and one mole of invented A atoms let us compare two unary $g(T)$ branches and minimize G over allowed phase amounts. In the research map, binary composition and a boundary were still missing. That map said Ni-X; today $X = \text{Cu}$, but every number is still invented A/B. Today B is a second invented atom species. We keep **one** invented bulk phase, ALPHA, while learning the boundary bookkeeping. Its name does not identify a real crystal structure. ALPHA's pure-A value at 1000 K, -9000 J/mol, reuses Day 1's SOLID line $1000 - 10T$. Day 1's LIQUID ties with it at 1000 K, but today we deliberately allow only ALPHA.

Draw a three-box chain: **bulk composition** → **boundary sites** → **competing boundary states**. Under each arrow, write one quantity Day 1 lacked. Then circle the claim that Day 1 did support: (a) A's invented SOLID/LIQUID lines cross at 1000 K; (b) Ni-Cu segregates; (c) a boundary changes structure.

D1 • Count A and B before choosing an energy (09:15)

For a bulk containing n_A and n_B moles of atoms, define the B atom fraction $x = n_B / (n_A + n_B)$; A's fraction is $1 - x$. A *phase amount fraction* is different: it describes how much material occupies a candidate region. On our one-mole basis, $x = 0.10$ means 0.10 mol B and 0.90 mol A, not ten percent of image area and not yet ten percent of boundary sites. Keep the same atom basis when comparing energies in J/mol.

Worked count: two bulk regions have phase amount fractions $f_1 = f_2 = 0.5$ and B fractions $x_1 = 0.10$, $x_2 = 0.50$. Their overall fraction is $z = f_1 x_1 + f_2 x_2 = 0.30$. The A balance is $f_1(1 - x_1) + f_2(1 - x_2) = 0.70$. This is a balanced *trial allocation*, not proof that the regions coexist in equilibrium. The equilibrium comparison must also use their compatible Gibbs energies and every allowed candidate. Our boundary example later restricts the bulk to one ALPHA branch; it does not calculate which two bulk phases could coexist, or at which compositions.

1. For 2 mol of atoms at $z = 0.20$, find n_A and n_B .
2. With $x_1 = 0.10$, $x_2 = 0.50$ and $z = 0.20$, find f_2 from both fraction balances. Check that $f_1 + f_2 = 1$.
3. Reject or repair: "The ALPHA composition $x = 0.20$ means 20% of the sample's *area* is ALPHA." What information is missing?

D2 • One ideal bulk curve (10:00)

We use **the ideal ALPHA model** at 1000 K. Its two pure-component endmember Gibbs energies are $g_A = -9000$ and $g_B = 3000$ J/mol atoms. Their difference is 12000 J/mol. For an interior composition x , with natural logarithm and $R = 8.3145$ J/(mol K),

$$q(x) = (1 - x) \ln(1 - x) + x \ln x,$$

$$g_b(x) = -9000 + 12000x + 8314.5q(x) \quad \text{J/mol atoms.}$$

At a pure endpoint use the limit $0 \ln 0 = 0$; do not ask a calculator for $\ln 0$. The first two terms are the chosen reference energies; the last is ideal *mixing Gibbs energy*. It is negative for $0 < x < 1$, even though this ideal model's enthalpy **of mixing** is zero. That does not make total enthalpy or total Gibbs energy zero. No measured alloy value is hidden here.

Worked at $x = 0.10$: $q = -0.32508297$; hence the mixing term is about -2702.902 J/mol and $g_b \approx -10502.902$ J/mol atoms. For one mole of atoms, total $G \approx -10502.902$ J. For another amount, multiply by that amount in mol; do not multiply J/mol by a raw atom count.

1. At $x = 0.20$, use $q(0.20) = -0.50040242$ to find the reference term, mixing term and g_b . Why is g_b not just $0.8g_A + 0.2g_B$?
2. A report reads -10.50 **kJ/mol** and another reads -10502.902 **J/mol** at $x = 0.10$. Are they necessarily different models? State the conversion and whether the rounding supports equality at the printed precision.

D3 · What exchanges when one B replaces one A? (10:45)

At fixed T, p , the chemical potential μ_i is the change in total G on adding component i while the other component amount is fixed. At fixed *total* occupied sites, replacing A by B changes G with the difference $\mu_B - \mu_A$, not with μ_B alone. Write $g'_b = dg_b/dx$ for the slope of the molar bulk curve. For a smooth curve the following hold; today they are shown, not derived: $g'_b = \mu_B - \mu_A$ and

$$\mu_A = g_b - xg'_b, \quad \mu_B = g_b + (1 - x)g'_b.$$

For this ideal ALPHA at interior x the expressions simplify to

$$\mu_A = -9000 + 8314.5 \ln(1 - x), \quad \mu_B = 3000 + 8314.5 \ln x,$$

$$\mu_B - \mu_A = 12000 + 8314.5 \ln \frac{x}{1 - x}.$$

At $x_b = 0.10$, the supplied values are $\mu_A \approx -9876.020$ and $\mu_B \approx -16144.844$ J/mol atoms, so their difference is about -6268.824 J/mol. A negative exchange difference is consistent with these chosen references; it is not a universal statement that B atoms are favorable at every boundary. A complete equilibrium also checks the stable bulk phase under the imposed conditions. We use the ideal ALPHA model conditionally.

1. Subtract the two supplied μ values and check the sign against $12000 + 8314.5 \ln(0.10/0.90)$. Why would subtracting μ_B alone at a filled boundary be the wrong exchange accounting?
2. At $x_b = 0.20$, use $\ln(0.20/0.80) = -1.38629436$. Is the exchange difference positive or negative? A sign change in this difference alone is **not** a bulk phase transition; explain why.

D4 · Define the defect and its area basis (11:30)

Our invented periodic teaching cell has **two equivalent planar boundaries** ($n_{gb} = 2$). Each has $N_s = 100$ occupied, substitutional sites and area $a_{gb} = 20 \text{ nm}^2$. The bulk has $N_b = 8000$ occupied sites. Thus there are 200 boundary sites, 8200 total sites and 40 nm^2 total boundary area. Both boundaries share mean B-site occupancy $\theta \in [0, 1]$. These are average counts that treat every boundary site alike; a single atomic snapshot would have whole-number counts.

At bulk B fraction x_b :

Region	B count	A count
Bulk	$8000x_b$	$8000(1 - x_b)$
Both boundaries	200θ	$200(1 - \theta)$

We choose an **equal-site excess**: subtract a hypothetical bulk reference with B fraction x_b filling the same 8200 sites. With Avogadro's constant $N_{Av} = 6.02214076 \times 10^{23} \text{ mol}^{-1}$,

$$\Gamma_B = \frac{8000x_b + 200\theta - 8200x_b}{(40 \times 10^{-18} \text{ m}^2)N_{Av}} = \frac{100(\theta - x_b)}{(20 \times 10^{-18} \text{ m}^2)N_{Av}}.$$

The numerator is an **excess B count**; dividing by area alone gives atoms/nm². (Optional: dividing by N_{Av} after converting nm² to m² gives mol/m².) This convention assumes every site holds one atom, as in the bulk; a real boundary with a different atom density may need a different reference. Occupancy θ and excess Γ_B are different.

Worked trial: $x_b = 0.10$, $\theta = 0.15$ gives 800 B in bulk and 30 at both boundaries, versus 820 in the 8200-site reference. Excess is ten B over 40 nm^2 , or **0.25 atom/nm²**. It is not $30/20$, which would combine both boundaries' B count with one boundary's area.

1. Find both A counts and verify A atoms + B atoms = 8200 for this trial.
2. If $\theta = x_b$, what is excess? If $\theta = 0.08$ at $x_b = 0.10$, compute its sign and atom/nm² value. Does negative excess mean a negative number of B atoms?

D5 · An open reservoir selects one occupancy (13:15)

Suppose a very large ALPHA bulk fixes $x_b = 0.10$ and both chemical potentials while A and B exchange with the two boundaries. Each B arriving at a filled boundary replaces one A; the cell alone does **not** keep a fixed B count. Define the invented boundary-site molar Gibbs function $g_s(\theta) = g_b(\theta) + \delta\theta$, with preference $\delta = -5000 \text{ J/mol boundary sites}$. There is one candidate boundary structure here and no structural baseline.

This is Day 1's W3 idea again: the conditions choose the potential. A reservoir fixing μ_A and μ_B selects $g_s - (1 - \theta)\mu_A - \theta\mu_B$ rather than g_s alone. So for the open question minimize this *excess grand potential* per mole of boundary sites, subtracting **both** component reservoirs:

$$\begin{aligned}\phi(\theta) &= g_s(\theta) - (1 - \theta)\mu_A - \theta\mu_B \\ &= 8314.5 \left[(1 - \theta) \ln \frac{1 - \theta}{1 - x_b} + \theta \ln \frac{\theta}{x_b} \right] + \delta\theta.\end{aligned}$$

The first bracket penalizes departing from the reservoir occupancy; the negative preference favors B. This one-state function curves upward everywhere, so it has a single minimum, which obeys the A-for-B **odds** relation

$$\frac{\theta_*}{1 - \theta_*} = \frac{x_b}{1 - x_b} \exp[-\delta/8314.5].$$

For this declared preference, $\exp(5000/8314.5) = 1.82459687$ is supplied; no exponential key is required. At $x_b = 0.10$, the selected $\theta_* \approx 0.16856026$. This is a site fraction, not a material segregation measurement. The chosen equal-site excess is about **0.342801 atom/nm²**, or 5.69235×10^{-7} mol/m². The open cell gains about $200(0.16856026 - 0.10) = 13.7121$ B atoms relative to a 0.10-filled boundary; the reservoir loses that expected B count and takes the exchanged A.

1. Use the supplied factor to calculate the odds and occupancy. Why is the equilibrium θ_* above x_b ? What happens when $\delta = 0$?
2. Reject: "The boundary has 0.16856 mol B, and ϕ_* is its absolute grain-boundary free energy." Name both errors.

D6 • A finite closed cell has a different balance (14:00)

Now isolate the **8200-site cell** from matter exchange. Start with bulk $x_0 = 0.10$ and both boundaries at $\theta_0 = 0.25$. Total B is $8000(0.10) + 200(0.25) = 850$; total A is 7350. If boundary occupancy changes, the bulk fraction must follow

$$x_b(\theta) = \frac{850 - 200\theta}{8000}.$$

The closed objective is the same cell's **total** energy,

$$G_{\text{cell}}(\theta) = \frac{8000g_b[x_b(\theta)] + 200g_s(\theta)}{N_{\text{Av}}} \text{ J},$$

or its fixed-total-site normalization $\bar{g} = G_{\text{cell}}N_{\text{Av}}/8200$ in J/mol **all cell sites**. No reservoir subtraction belongs in this closed energy. A numerical minimization of this exact invented cell, cross-checked with the exchange condition, supplies $\theta_* \approx 0.1716075$ and $x_b(\theta_*) \approx 0.10195981$. They are **supplied model results**; we check their balance on paper rather than pretending to have reproduced the solver. The closed occupancy differs from D5's fixed-reservoir result.

1. At trial $\theta = 0.35$, calculate x_b , bulk B and boundary B; check the total. Reject a report that keeps $x_b = 0.10$ for this trial.
2. With the supplied selected pair, estimate bulk and boundary B counts. Why must a comparison between two closed states use the *same* total B even if their final x_b values differ?

D7 • Compare two boundary structures on one basis (14:45)

This follows Day 1's CALPHAD logic: **define the Gibbs functions, evaluate every allowed candidate, then minimize subject to the physical constraints**. Giving a candidate a phase name in a database would not supply missing parameters or validate its physical identity. Here the functions are printed explicitly, so the paper route can focus on what a state comparison means.

Our candidate **boundary states** I and II share T, p , the 8000 bulk sites, two equivalent 100-site/20-nm² boundaries, atom references, area and the same one-phase ALPHA bulk.

Both are uniform alternatives for the two boundaries, not a model of coexisting domains. Their site functions are $g_{s,i}(\theta) = g_b(\theta) + \eta_i + \delta_i\theta$:

State	Baseline η_i , J/mol boundary sites	Preference δ_i , J/mol boundary sites
I	0	−5000
II	+2000	−10000

The +2000 baseline must enter State II's total energy even though it does not change its best occupancy at a fixed inventory. On the all-site basis it contributes $200(2000)/8200 = 48.78049$ J/mol **all sites**. For each starting bulk x_0 , both alternatives start with $\theta_0 = 0.25$, hence share $B_{\text{tot}} = 8000x_0 + 50$; then *each* state is minimized separately.

Supplied checked model results (energies include State II's baseline):

x_0	Shared B total	State I: $\theta_I^*, \bar{g}_I^*$ J/mol all sites	State II: $\theta_{II}^*, \bar{g}_{II}^*$ J/mol all sites
0.10	850	0.1716075, −10541.72679	0.2689826, −10519.50695
0.25	2050	0.3742813, −10713.32958	0.5170377, −10718.80845

Define $D = \bar{g}_{II}^* - \bar{g}_I^*$ **at the same** x_0 . Positive D selects I among these two uniform candidates; negative D selects II. The full synthetic model has a uniform-branch ordering crossing near $x_0 = 0.21619$. That model number alone is **not** evidence for a real interface phase transition: mixed-boundary coexistence, structural identification, appropriate excess thermodynamics, kinetics and material evidence are absent.

1. Subtract the supplied energies for both rows; state the favored candidate. Why must we not compare State I at $x_0 = 0.10$ to State II at $x_0 = 0.25$?
2. For the first row, compute State II's bulk B count from its occupancy and verify the shared total 850. Explain why forcing both states to the *same final* bulk fraction would violate at least one balance.
3. A report omits η_{II} but keeps the printed State II energy. Name the inconsistency and convert the missing baseline to the all-site basis.

D8 • What would make this a material case? (15:30)

CALPHAD uses thermodynamic models and evidence to compare allowed phases under stated conditions. The form of our toy calculation suggests a research route, not a right to insert arbitrary real-material parameters. The worked examples (Tasks 01, 03 and 04) supply a published Cu–Ni bulk database and a simulated energy curve for one pure-Ni twin boundary, but **no matched real Ni–Cu boundary dataset**: no specified Ni–Cu boundary with measured composition or excess, and no boundary model fitted to such data.

Step	Evidence needed before a real claim
Case and source	Exact alloy, observable, boundary geometry, and a source we may use
Bulk model	Complete compatible bulk phase model, references/range and stable μ_A, μ_B

Step	Evidence needed before a real claim
Boundary model	Matched boundary sites/area/state free energies or excesses, conditions and independent evidence
Calculation and comparison	A planned physical/numerical run with inputs we may use, conservation checks, comparison with data not used to build the model, and a check by someone else

Sort these statements into **toy-model result**, **missing evidence**, or **unsupported real claim**: (a) State I is lower at the 850-B toy cell; (b) a validated Ni-Cu bulk model with a stable reservoir at the case point; (c) Ni-Cu boundaries switch structure at $x_0 = 0.21619$; (d) two compatible real boundary-state free-energy functions measured from one common reference (including the same stress state). If only one real state were validated, what narrower question might be asked? Why do two states and an energy crossing still need an interface coexistence analysis for a physical transition claim?

D9 • Integrate on a fresh card (16:00)

Use the **same invented parameters** at a new open reservoir $x_b = 0.20$. The supplied factor remains 1.82459687. Separately, consider a new **closed** 8200-site cell with $x_0 = 0.20$, $\theta_0 = 0.20$ and trial $\theta = 0.40$. These are different experiments, even though both start with the number 0.20.

1. Open: calculate θ_* from the odds relation and the selected equal-site excess in atoms/nm². Show the 40 nm² area check.
2. Closed: calculate total B, the trial bulk B count and final x_b . Reject “keep $x_b = 0.20$ because the open reservoir did.”
3. A colleague calls the D7 crossing a measured Ni-Cu defect-phase transition and predicts a strengthening effect. Write two sentences: one supported toy-model statement and one exact missing-evidence reason.

D10 • Supported exit (16:30)

Use this sheet and a calculator if helpful. State any hint or supplied output used; the exit is for selecting next practice, not certification.

1. At fixed T, p , name the potential for our closed cell. State what is conserved in an open boundary exchange and in a finite closed cell.
2. With $x_b = 0.10$ and **zero** preference, give θ_* and the equal-site excess. Why is this a model limit rather than a real observation?
3. At $x_0 = 0.10$ in D7, calculate D , name the lower uniform candidate, and list two missing conditions for a physical interface transition.
4. Name the worked example (Tasks 00–05) or detailed lesson you want to try next and a concrete question for it. Can the two primers alone validate a Ni-Cu prediction?

Keep-beside-you reference card

Symbol / rule	Meaning and basis
x, z	Local and overall bulk B atom fractions, dimensionless
g_b, G	Bulk Gibbs energy J/mol atoms; total Gibbs energy J
R, T	8.3145 J/(mol K), 1000 K in this invented Day 2 model
$g'_b = dg_b/dx$	Slope of the bulk curve; equals $\mu_B - \mu_A$, the A-for-B exchange at fixed occupied sites, J/mol atoms
x_b, θ	Bulk B fraction and boundary B-site fraction; not area fractions
N_b, N_s, a_{gb}, n_{gb}	8000 bulk sites; 100 sites and 20 nm ² per boundary; $n_{gb} = 2$ boundaries
N_{Av}	$6.02214076 \times 10^{23} \text{ mol}^{-1}$; converts atom counts to mol
Γ_B	Chosen equal-site B excess, $5(\theta - x_b)$ atom/nm ² here
Open	Reservoir fixes x_b, μ_A, μ_B ; cell A/B may exchange
Closed	Cell fixes B_{tot}, A_{tot} ; x_b changes with θ
$\bar{g}, D$	Closed energy J/mol all cell sites; $D = \bar{g}_{II}^* - \bar{g}_I^*$ at one inventory

Useful supplied arithmetic: $\ln(0.10/0.90) = -2.19722458$, $\ln(0.20/0.80) = -1.38629436$, $\exp(5000/8314.5) = 1.82459687$, and $1 \text{ nm}^2 = 10^{-18} \text{ m}^2$. No solver or live internet is needed. The source/contract lineage and optional detailed lessons are in the source map.