

Laboratory Test Report

Meridian Packaging International — In-house Laboratory, Chennai

Report no. MPI/LAB/2026/0771 · Date 28 August 2026

Test method: TAPPI T810 om-11, bursting strength of corrugated board.

Specimen: 5-ply BC flute, 180 gsm machine-finished kraft liner.

Result: mean bursting strength 1,400 kPa across ten specimens (range 1,352 to 1,461 kPa), conditioned at 23°C and 50% RH.

Note: This result is not directly comparable to an Edge Crush Test value expressed in kN/m. The two methods measure different failure modes and no general conversion exists between them.