TECHNICAL DATASHEET

ASCOTITE MEGABOND

2-Part, High Strength High Viscous, Multipurpose Epoxy Adhesives



PRODUCT INTRODUCTION

ASCOTITE MEGABOND is high-strength 2-part high viscous thixotropic epoxy adhesive for bonding small or medium areas of similar and dissimilar types of substrates like concrete, metal, wood, ply, granite, natural stone, jewelry stone, textile etc. It is an ideal product for bonding materials together.

RECOMMENDED APPLICATION	02
TECHNICAL DATA	02
PRODUCT KEY FEATURES	02
APPLICATION METHODS	03
SURFACE PREPARATION	03
MIXING	03
APPLICATION	03
CLEANING	03
PACKAGING	03
SHELF LIFE	03
LIMITATIONS	03

Version 1 : March 2024

KEY FEATURES

1. Economical ; Non toxic
2. Bonds similar and dissimilar materials
3. Excellent thermal resistance; insulating property
4. High bond strength in static and dynamic states
5. Excellent bond and thermal stability
6. Long pot life
7. Chemical resistant

RECOMMENDED APPLICATIONS

1. Automobile, railways, utility vehicle parts
2. PCB, electrical and electronics
3. Concrete, marble, stone , granite
4. Ceramic, glass, metal, plastic, composite
5. Refrigerator, washing machine, Mixer , grinder
6. Fixing of leakage in drain, hose pipe, joint seal
7. Bangles, jewellery, handicraft, stone fixing

TECHNICAL PROPERTIES

ASTM D 2196 , ASTM D 2471, ASTM D 5895, ASTM D 1002

Appearance	Resin : Clear, viscous ; Hardener : Light yellow, viscous
Chemical Base	Epoxy resin ; Polyamide hardener
Mixing Ratio	Resin : Hardener = 1.0 : 0.8 (by weight)
Pot Life	75 ± 15 minutes
Density	1.05 ± 0.1 gm/cm^3
Mixed viscosity (cps)	35000 to 40000
Set to touch Dry	up to 4 hours
Compressive Strength (MPa) (7 Days)	≥ 100
Pull Off Strength (MPa) (1 Day)	≥ 1.5 (Concrete Failure)
Hardness, Shore D (7 Days)	80

The values obtained are from laboratory testing conditions and at 27 ± 2°C. On site tests may show slight variation due to site

APPLICATION METHODS:

1. Surface Preparation

The substrate must be clean, dry, sound and free of all contamination such as dirt, oil, grease, & coatings etc. which hinder an adhesion.

In many cases, surface roughening prior to bonding improves strength of bonded joint. It is generally advised when working with rubber and metals. Weak concrete must be removed and surface defects such as blowholes and voids must be fully exposed.

2. Mixing

Only mix the amount of material that can be used within the pot life. The resin and the hardener need to be mechanically mixed before use in the ratio of weight and/or volume in compliance with technical specifications until a homogeneous color is reached.

3. Application

It can easily applied with spatula or putty knife. A layer of adhesive should be 0.05 to 0.10 mm thick will normally impart the greatest lap shear strength to a joint.

4. Limitations

i. Not suitable where a flexibility is required.

ii. Not suitable for heat exposure above 150°C.

iii. Does not perform well to some plastics such as polyethylene, polypropylene, etc.

iv. Water immersion, potable water

5. Cleaning

Excess of product can be removed with suitable solvent based cleaner compatible with the substrates to bond. Application tools and dosing systems shall be cleaned before the product is hardened. Cured product can be removed only mechanically. Tools and equipment should be cleaned immediately after use with appropriate solvent.

6. Packaging

Available in 450 gm, 0.9 Kg & 1.8 Kg Set

7. Coverage

Depending on application

8. Storage & Shelf Life

Store in cool and dry warehouse condition. Do not expose to direct sunlight. **ASCOTITE MEGABOND** epoxy adhesive components should be stored in their original, sealed containers at room temperature. Shelf life in these conditions is 12 months in unopened original containers.

DISCLAIMER:

While the technical details & recommendations contained in this document and the related details given by the representatives of the company correspond to the best of our knowledge & experience, all the above information must in any case be considered as merely indicative and subject to confirmation. Users are recommended to conduct a product suitability test before it is used at full scale. In any case, the consumer alone is entirely liable for any consequences resulting from using the product. For the most up-to-date TDS, please visit our website at www.ascolite.in. Our company policy is one of ongoing R&D; therefore, we reserve the right to update this information without prior notice at any time. As the correct identification of the problems, the quality of other materials used, on-site environmental conditions and the workmanship on-site are factors beyond our control, there is no express or implied guarantee/warranty as to the results achieved. The company assumes no liability or consequential damage arising from the use of our products for unsatisfactory results. Site visits are not a supervisory responsibility wherever provided. Suggestions made either verbally or in writing by the company may be followed, modified or rejected by the owner, engineer or contractor, since they are solely responsible for carrying out procedures appropriate to a specific application.