



## MAT PINK

Applied to clear glass, the Mat Pink film bestows a mat pink tint to the glass without diminishing its transparent properties. It is the perfect way to enliven any interior glazing (such as partitions, shower screens, etc.) with a touch of colour.



Warranty  
**5 YEARS**



Fire-resistance rating  
**M1**



Storage from -5°C to +40°C  
**3 YEARS**



REACH RoHS compliant  
**RESPECTED**

## WIDTHS AVAILABLE:

↔ **152 cm**

## TECHNICAL DATASHEET


Data calculated based on film applied to clear glass 3 mm thick (\*on double glazing 4-16-4)

Ultraviolet transmission	1 %
Visible light transmission	45 %
Reflection of external visible light	11 %
Reflection of internal visible light	11 %
Total solar energy rejected	32 %
Total solar energy rejected 2*	29 %
Solar ratio :	
Solar energy reflection	9 %
Solar energy absorption	43 %
Solar energy transmission	48 %
Reduction in Solar Glare	55 %
g-value	0.69
u-value	5.7
Shading coefficient	
Installation type : Interior	
Roll length	30,5 m
Film composition	PET
Thickness	60 µ

Colour from the outside : ROSE

## CONSTRUCTION

1. Frosted polyester with satin surface
2. Bonding adhesive
3. High optical quality polyester
4. PS adhesive, glass polymerization within 15 days
5. Protection release liner, disposable after installation



## MAINTENANCE INSTRUCTIONS

Soapy water solution (ref. 600-F0355 Film on), do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

*Non-contractual data. We reserve the right to modify the composition of our films at any time. Consult our warranty documents.*

## INSTALLATION ADVICE

Vertical installation and on standard glass surface\*

Clear single pane	✓
Tinted single pane	!
Reflective tinted single pane	✓
Clear double pane	!
Tinted double pane	!
Reflective tinted double pane	✓
Gas-filled double pane - Low E	!
STADIP EXT. clear double pane	!
STADIP INT. clear double pane	✗

✓ Yes    ! Caution    ✗ Not recommended

\*Recommendations provided on the basis of a glazed surface covering up to 2.5m<sup>2</sup>, contact us for definitive details or to obtain a thermal shock analysis report.