



DRAFT EAST AFRICAN STANDARD

**DEAS 412-1:2018- Steel for the reinforcement of concrete —Part
1: Plain bars**

EAST AFRICAN COMMUNITY

Copyright notice

This EAC document is copyright-protected by EAC. While the reproduction of this document by participants in the EAC standards development process is permitted without prior permission from EAC, neither this document nor any extract from it may be reproduced, stored or transmitted in any form for any other purpose without prior written permission from EAC.

Requests for permission to reproduce this document for the purpose of selling it should be addressed as shown below or to EAC's member body in the country of the requester:

© East African Community 2016 — All rights reserved
East African Community
P.O.Box 1096
Arusha
Tanzania
Tel: 255 27 2504253/8
Fax: 255 27 2504481/2504255
E-mail: eac@eachq.org
Web: www.eac-quality.net

Reproduction for sales purposes may be subject to royalty payments or a licensing agreement. Violators may be prosecuted.

Foreword

Development of the East African Standards has been necessitated by the need for harmonizing requirements governing quality of products and services in the East African Community. It is envisaged that through harmonized standardization, trade barriers that are encountered when goods and services are exchanged within the Community will be removed.

In order to achieve this objective, the Community established an East African Standards Committee mandated to develop and issue East African Standards.

The Committee is composed of representatives of the National Standards Bodies in Partner States, together with the representatives from the private sectors and consumer organizations. Draft East African Standards are circulated to stakeholders through the National Standards Bodies in the Partner States. The comments received are discussed and incorporated before finalization of standards, in accordance with the procedures of the Community.

East African Standards are subject to review, to keep pace with technological advances. Users of the East African Standards are therefore expected to ensure that they always have the latest versions of the standards they are implementing.

DEAS 412-1:2018 was prepared by Technical Committee EASC/TC 035 *TC Steel and Steel Products*

FOR PUBLIC REVIEW ONLY

Steel for the reinforcement of concrete —Part 1: Plain bars

1 Scope

This part of East Africa Draft Standard specifies technical requirements for plain bars to be used as reinforcement in non- structural concrete.

This part of East Africa Draft Standard covers nine steel grades not intended for welding which are B240A-P, B240B-P, B240C-P, B240D-P, B300A- P, B300B-P, B300C-P, B300D-P and B420D-P, and one steel grade intended for welding which is B420DWP. The production process is at the discretion of the manufacturer. It also applies to plain bars supplied in coil form. The requirements of this part of ISO 6935 apply to straightened product. The steel grades are designated with steel names allocated in accordance with ISO/TS 4949.

NOTE The first “B” stands for steel for reinforcing concrete. The next 3 digits represent the specified characteristic value of upper yield strength. The fifth letter stands for ductility class (4.4). The next symbol relates to welding; “-” means not intended for welding and “W” means intended for welding. The last “P” stands for plain bar.

This part of East Africa Draft Standard covers products delivered in straight lengths.

Plain bars produced from finished products, such as plates and railway rails, are excluded.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 404, *Steel and steel products — General technical delivery requirements*

ISO/TS 4949, *Steel names based on letter symbols*

ISO/TR 9769, *Steel and iron — Review of available methods of analysis*

ISO 10144, *Certification scheme for steel bars and wires for the reinforcement of concrete structures*

ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition*

ISO 15630- 1, *Steel for the reinforcement of concrete and prestressing of concrete — Test methods — Part 1: Reinforcing bars, wire rod and wire*

3 Symbols

The symbols used in this part of East Africa Draft Standard are listed in Table 1.

Table 1 — Symbols

Symbol	Unit	Description	Reference
A_5	%	Percentage elongation after fracture	7.1, 8.1
A_{gt}	%	Percentage total elongation at maximum force	7.1, 8.1
A_n	mm ²	Nominal cross-sectional area	Clause 5, 8.1
d	mm	Nominal diameter of the bar	Clause 5, 8.1, 8.2, Clause 9
f_k	—	Required characteristic value	11.3.2.3.1
k, k'	—	Indices	11.3.2.3.1
m_n	—	Mean value of n individual values	11.3.2.3.1
n	—	Number of individual values	11.3.2.3.1
R_{eH}	N/mm ²	Upper yield strength	7.1
R_m	N/mm ²	Tensile strength	7.1
$R_{p0,2}$	N/mm ²	0,2 % proof strength, non-proportional extension	7.1
s_n	—	Standard deviation for n individual values	11.3.2.3.1
x_i	—	Individual value	11.3.2.3.1

4 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

4.1

cast analysis

chemical analysis representative of the cast determined by the steelmaker in accordance with own procedures

4.2

certification scheme

certification system as related to specified products, processes or services to which the same particular standards and rules, and the same procedure, apply

4.3

characteristic value

value having a prescribed probability of not being attained in a hypothetical unlimited test series

NOTE 1 Equivalent to fractile, which is defined in ISO 3534-1.

NOTE 2 A nominal value is used as the characteristic value in some circumstances.

4.4

ductility class

classification of the ductility properties of reinforcing steels based on the value of the ratio of tensile strength to yield strength, as well as the elongation measured either as A_{gt} or as A_5

NOTE See Table 5.

4.5

product analysis

chemical analysis carried out on the product (ISO 16020:2005)

5 Dimensions, masses per unit length and permissible deviations

Dimensions, mass per unit length and permissible deviations are given in Table 2. The delivery length of straight bars shall be 6 m or 12 m for the general market, However manufacturer and purchaser may agree on special ordered lengths upon notification to the regulator, permissible deviation on delivery length from rolling mill shall be $^{+100}_0$ mm.

Table 2 — Dimensions, mass per unit length and permissible deviations

Nominal bar diameter d mm	Nominal cross-sectional area ^a A_n mm ²	Mass per unit length	
		Requirement ^b kg/m	Permissible deviation ^c %
6	28,3	0,222	± 6
8	50,3	0,395	± 6
10	78,5	0,617	± 5
12	113	0,888	± 5
14	154	1,21	± 5
16	201	1,58	± 5
20	314	2,47	± 5
22	380	2,98	± 5
^a $A_n = 0,7854 \times d^2$ ^b Mass per unit length = $7,85 \times 10^{-3} \times A_n$ ^c Permissible deviation refers to a single bar.			

6 Chemical composition

The chemical composition of the steel, as determined by cast analysis, shall conform to Table 3.

The carbon equivalent, CEV, is calculated according to the following formula.

$$CEV = C + \frac{Mn}{6} + \frac{(Cr + V + Mo)}{5} + \frac{(Cu + Ni)}{15} \quad (1)$$

where C, Mn, Cr, V, Mo, Cu and Ni are the mass fractions, expressed as percentages, of the respective chemical elements of the steel.

The permissible deviation of the product analysis relative to the cast analysis as specified in Table 3 are given in Table 4.

**Table 3 — Chemical composition based on cast analysis —
Maximum values of mass fractions, in percentage**

Steel grade	C	Si	Mn	P	S	N	CEV ^a
B240A-P B240B-P B240C-P	—	—	—	0,060	0,060	—	—
B300A-P B300B-P B300C-P	—	—	—	0,050	0,050	—	—
B420D-P B420DWP ^b	0,30	0,55	1,50	0,040	0,040	0,012	0,56
^a Other CEV formulae and values may be used by agreement between the manufacturer and purchaser. ^b Alloy elements, such as Cu, Ni, Cr, Mo, V, Nb, Ti and Zr, may be added by agreement between the manufacturer and purchaser.							

**Table 4 — Chemical composition based on product analysis —
Permissible deviation of the product analysis in percentage by mass**

Elements	Specified maximum value in cast analysis in Table 3	Permissible deviation in product analysis from the specified limits of the cast analysis in Table 3
	%	%
C	> 0,25	+ 0,03
Si	u 0,60	+ 0,05
Mn	u 1,65	+ 0,06
P	u 0,05	+ 0,008
	> 0,05	+ 0,010
S	u 0,05	+ 0,008
	> 0,05	+ 0,010

7 Mechanical properties

7.1 Tensile properties

The tensile test shall be performed in accordance with 8.1.

The material shall conform to the requirements for tensile properties specified in Table 5.

In the context of this part of DEAS 412-1, the characteristic value is (unless otherwise indicated) the lower or upper limit of the statistical tolerance interval at which there is a 90 % probability ($1 - \alpha = 0,90$) that 95 % ($p = 0,95$) of the values are at or above this lower limit, or are at or below this upper limit, respectively. This definition refers to the long-term quality level of production.

By agreement between the manufacturer and purchaser, the values shown in Table 5 may be used as specified minimum and/or maximum values.

Table 5 — Tensile properties

Ductility class	Steel grade	Specified characteristic value of upper yield strength		Specified characteristic value of tensile strength	Ductility properties		
		R_{eH} N/mm ²		R_m N/mm ²	Specified characteristic value of R_m/R_{eH}	Specified characteristic value of elongation ^a	
		Minimum	Maximum	Maximum		%	
						A_5 Minimum	A_{gt} Minimum
A	B240A-P	240	—	—	1,02	20	2
	B300A-P	300	—			16	
B	B240B-P	240	—	—	1,08	20	5
	B300B-P	300	—			16	
C	B240C-P	240	—	—	1,15	20	7
	B300C-P	300	—			16	
D	B240D-P	240	—	520	1,25	22	8
	B300D-P	300	—	600		19	
	B420D-P	420	540	—		16	
	B420DWP						

^a By agreement between the manufacturer and purchaser, the type of elongation shall be selected between A_5 and A_{gt} . If the type of elongation is not specified by agreement, A_{gt} should be used.

If a yield phenomenon is not present, the 0,2 % proof strength ($R_{p0,2}$) shall be determined.

7.2 Bending properties

After testing in accordance with 8.2, the bar shall show neither rupture nor cracks visible to a person of normal or corrected vision.

8 Testing

8.1 Tensile test

The tensile test shall be carried out in accordance with ISO 15630-1.

For the determination of percentage elongation after fracture, A_5 , the original gauge length shall be 5 times the nominal diameter.

For the determination of percentage total elongation at maximum force, A_{gt} , equidistant marks shall be made on the free length of the test piece. The distance between the marks shall be 20 mm, 10 mm or 5 mm, depending on the bar diameter.

For determination of tensile properties, the nominal cross-sectional area of the bar shall be used.

8.2 Bend test

The bend test shall be carried out in accordance with ISO 15630-1.

The test piece shall be bent to an angle between 160° and 180° over a mandrel of the diameter specified in Table 6.

Table 6 — Mandrel diameter to be used for the bend test

Dimensions in millimetres

Nominal diameter d	Mandrel diameter (max.) ^{a b}
≤ 16	$3d$
$16 < d \leq 22$	$6d$
<p>a By agreement between the manufacturer and purchaser, larger mandrel diameters may be used.</p> <p>b For nominal diameters, larger than 22 mm, the mandrel diameters in bend tests shall be agreed between the manufacturer and purchaser.</p>	

8.3 Chemical analysis

In general, the chemical composition is determined by spectrometric methods.

In case of dispute about the analytical method, the chemical composition shall be determined by an appropriate referee method specified in one of the International Standards.

9 Designation

Plain bars according to this part of East Africa Draft Standard shall be designated in the following order:

- reinforcing steel;
- a reference to this part of DEAS 412-1:2018;
- nominal diameter, in millimetres, according to Table 1;
- steel grade.

10 Marking

10.1 Each bar and each bundle shall be legibly and indelibly marked as follows;

10.2 Each bar shall be marked with manufacturers name or logo, steel grade and nominal diameter

10.3 Each bundle shall be marked with manufacturers name or logo, steel grade, nominal diameter and batch /cast number.

10.4 Special orders bars in addition to the above marking shall bear the marking SP.

11 Evaluation of conformity

11.1 General

Certification and inspection of reinforcement shall be performed

9.1 in accordance with a certification scheme monitored by an external body, or

9.2 according to acceptance testing of a specific delivery.

11.2 Certification scheme

In the case of a certification scheme, certification and inspection shall be performed in accordance with ISO 10144.

11.3 Acceptance testing of a specific delivery

11.3.1 General

Provisions regarding the nature, extent and evaluation of acceptance testing on deliveries of reinforcing steel not subject to a certification scheme are given in 11.3.2 and 11.3.3.

Acceptance testing of a specific delivery shall be performed according to 11.3.2.

By agreement between the manufacturer and purchaser, 11.3.3 may be used.

11.3.2 Verification of characteristic values

11.3.2.1 Organization

The tests shall be organized and carried out according to an agreement between the purchaser and manufacturer, taking into consideration the national rules of the receiving country.

11.3.2.2 Extent of sampling and testing

For the purpose of testing, the delivery shall be subdivided into test units with a maximum mass of 50 t or a fraction thereof. Each test unit shall consist of products of the same steel grade and the same nominal diameter from the same cast. The manufacturer shall confirm in the test report that all samples in the test unit originate from the same cast. The chemical composition (cast analysis) shall be stated in this test report.

Test pieces shall be taken from each test unit as follows:

9.4 two test pieces from various bars, for testing the chemical composition (product analysis);

9.5 a minimum of 15 test pieces (if appropriate, 60 test pieces, see 11.3.2.3.1) from various bars for testing all other properties specified in this part of East Africa Draft Standard.

11.3.2.3 Evaluation of the results

11.3.2.3.1 Inspection by variables

For properties, which are specified as characteristic values, the following shall be determined:

- c) all individual values x_i of the 15 test pieces ($n = 15$);
- d) the mean value m_{15} (for $n = 15$);
- e) the standard deviation s_{15} (for $n = 15$).

The test unit corresponds to the requirements, if the condition stated below is fulfilled for all properties:

$$m_{15} - 2,33 \times s_{15} \geq f_k \quad (2)$$

where

f_k is the specified characteristic value;

2,33 is the value for the acceptability index k for $n = 15$ for a failure rate of 5 % ($p = 0,95$) at a probability of 90 % ($1 - \alpha = 0,90$).

$$s_{15} = \sqrt{\frac{\sum (x_i - m_{15})^2}{14}} \quad (3)$$

If the condition stated above is not fulfilled, the index

$$k' = \frac{m_{15} - f_k}{s_{15}} \quad (4)$$

is determined from the test results available. Where $k' \geq 2$, testing can be continued. In this case, 45 further test pieces shall be taken and tested from different bars in the test unit, so that a total of 60 test results are available ($n = 60$).

The test unit shall be considered to comply with the requirements, if the condition stated below is fulfilled for all properties:

$$m_{60} - 1,93 \times s_{60} \geq f_k \quad (5)$$

where 1,93 is the value for the acceptability index k for $n = 60$ for a failure rate of 5 % ($p = 0,95$) at a probability of 90 % ($1 - \alpha = 0,90$).

11.3.2.3.2 Inspection by attributes

When testing, properties are specified as maximum or minimum values, all results determined on the 15 test pieces shall comply with the requirements of the product standard. In this case, the test unit shall be considered to comply with the requirements.

The tests may be continued when at most 2 results not conforming to the conditions occur. In this case, 45 further test pieces from various bars in the test unit shall be tested, so that a total of 60 test results are available. The test unit complies with the requirements, if not more than 2 of the 60 results do not conform to the conditions.

11.3.2.3.3 Chemical composition

Both test pieces shall comply with the requirements in this part of East Africa Draft Standard.

11.3.3 Verification of specified minimum/maximum values

Tests shall be carried out according to the following.

- a) Bars of the same cast shall constitute one group. For every 50 t or fraction thereof, one tensile test and one bend test shall be carried out for each bar diameter.
- b) Each individual test result shall meet the required values in Table 4, and the required bending properties in 7.2.
- c) One cast analysis shall be carried out for every cast to verify chemical composition (Clause 6). Samples shall be taken in accordance with ISO 14284.
- d) If any test result does not meet the requirements, retests may be carried out, according to ISO 404.
- e) The manufacturer shall submit a test report stating that the products of the delivery satisfy the chemical and mechanical properties defined in Clauses 6 and 7, and a confirmation that the other requirements of this part of DEAS 412-1:2018 are fulfilled.

11.3.4 Test report

The test report shall contain the following information:

- a) designation of the reinforcing steel in accordance with this part of East Africa Draft Standard;
- b) marking details (on the tag, painting, etc.);
- c) date of testing;
- d) mass of the test unit;
- e) test results.