

NABL ACCREDITED LABORATORY TEST REPORT

PaperTest Labs, Pune — NABL T-4471 — Report PTL/26/8812 dt 12-Jul-2026

Sample: 5-ply corrugated board, 150/120 GSM construction — Meghdoot
Corrugators Pvt Ltd, Chakan

Bursting Strength (IS 1060): 22.4 kgf/cm² | Bursting Factor: 22.1

Edge Crush Test (IS 4006): 6.9 kN/m

Cobb 30min: 118 g/m² | Moisture: 7.4%

Result: Conforms to declared grade. Valid for the board grade, not per-shipment.