
Adsorption isotherm at 87 K for ALOLIX_charged
Argon uptake (mol/kg)
0
5
10
15
20
0.0
0.2
0.4
0.6
0.8
1.0
Pressure (bar)