
Adsorption isotherm at 87 K for TANBAN_charged
Argon uptake (mol/kg)
1
2
3
4
0.0
0.2
0.4
0.6
0.8
1.0
Pressure (bar)