
Baird

Author: semclass
Creation: 04/21/2026 3:49:05 PM

Sample Name: Si-100

Area 2


Live Map 1



2% SiK/AlK/CaK (1182 Pixels)
0% Unallocated (41 Pixels)
97% SiK (52843 Pixels)
0% SiK/C K/AlK (91 Pixels)
0% SiK/FeK/O K (115 Pixels)




Notes:



Image

ElementOverlay



0% C K


1% O K

2% AlK


96% SiK

1% CaK


1% FeK




C K_ROI (64)




O K_ROI (97)




AlK_ROI (172)



SiK_ROI (580)




CaK_ROI (51)



FeK_ROI (96)

kV: 15	Mag: 2002	Takeoff: 35	Live Time(s): 499.3	Amp Time(µs): 1.92	Resolution:(eV) 130.4

Sum Spectrum




Lsec: 499.3 885 Cnts 8.920 keV Det: Octane Plus

eZAF Smart Quant Results

Element	Weight %	Atomic %	Net Int.	Error %	Kratio	Z	A	F
C K	2.22	5.04	43.10	11.78	0.0020	1.1580	0.0760	1.0000
O K	0.70	1.20	88.90	9.62	0.0021	1.1048	0.2683	1.0000
AlK	1.49	1.51	870.50	2.10	0.0141	0.9772	0.9491	1.0153
SiK	94.10	91.46	53803.10	1.60	0.9175	0.9976	0.9772	1.0001
CaK	0.36	0.24	77.10	31.04	0.0030	0.9363	0.8974	1.0089
FeK	1.13	0.55	98.80	6.83	0.0097	0.8268	0.9906	1.0543

kV: 15	Mag: 2002	Takeoff: 35	Live Time(s): 10.9	Amp Time(µs): 1.92	Resolution:(eV) 130.4

Phase: **SiK/AlK/CaK**




Lsec: 10.9 31 Cnts 8.920 keV Det: Octane Plus

eZAF Smart Quant Results

Element	Weight %	Atomic %	Net Int.	Error %	Kratio	Z	A	F
C K	1.02	2.40	34.00	26.95	0.0013	1.1812	0.1098	1.0000
O K	11.21	19.77	1774.20	9.40	0.0358	1.1278	0.2831	1.0000
AlK	14.23	14.88	8025.80	3.91	0.1117	0.9988	0.7825	1.0049
SiK	48.19	48.40	25817.30	3.81	0.3797	1.0199	0.7715	1.0014
CaK	8.77	6.17	2332.70	3.96	0.0791	0.9584	0.9279	1.0148
FeK	16.58	8.38	1676.20	3.96	0.1426	0.8477	0.9911	1.0233

kV: 15	Mag: 2002	Takeoff: 35	Live Time(s): 0.4	Amp Time(µs): 1.92	Resolution:(eV) 130.4

Phase: **Unallocated**




Lsec: 0.4 0 Cnts 8.920 keV Det: Octane Plus

eZAF Smart Quant Results

Element	Weight %	Atomic %	Net Int.	Error %	Kratio	Z	A	F
C K	26.27	50.18	106.40	29.07	0.0474	1.1543	0.1563	1.0000
O K	2.29	3.29	25.80	99.99	0.0059	1.1020	0.2351	1.0000
AlK	6.45	5.48	293.50	19.67	0.0466	0.9759	0.7383	1.0040
SiK	32.45	26.51	1525.80	8.78	0.2561	0.9966	0.7905	1.0018
CaK	7.17	4.10	168.60	23.45	0.0653	0.9367	0.9531	1.0200
FeK	25.38	10.43	219.50	19.97	0.2130	0.8285	0.9972	1.0159

kV: 15	Mag: 2002	Takeoff: 35	Live Time(s): 486.2	Amp Time(µs): 1.92	Resolution:(eV) 130.4

Phase: SiK




Lsec: 486.2 854 Cnts 8.920 keV Det: Octane Plus

eZAF Smart Quant Results

Element	Weight %	Atomic %	Net Int.	Error %	Kratio	Z	A	F
C K	1.97	4.50	38.00	12.04	0.0017	1.1583	0.0757	1.0000
O K	0.41	0.70	50.80	10.98	0.0012	1.1052	0.2656	1.0000
AlK	1.20	1.22	701.10	2.16	0.0114	0.9775	0.9521	1.0157
SiK	94.97	92.73	54354.10	1.55	0.9307	0.9979	0.9818	1.0001
CaK	0.70	0.48	150.80	12.41	0.0060	0.9366	0.8968	1.0085
FeK	0.74	0.37	65.00	8.46	0.0064	0.8271	0.9903	1.0551

kV: 15	Mag: 2002	Takeoff: 35	Live Time(s): 0.8	Amp Time(µs): 1.92	Resolution:(eV) 130.4

Phase: **SiK/C K/AlK**




Lsec: 0.8 0 Cnts 8.920 keV Det: Octane Plus

eZAF Smart Quant Results

Element	Weight %	Atomic %	Net Int.	Error %	Kratio	Z	A	F
C K	73.37	85.48	2832.20	10.13	0.2545	1.0362	0.3347	1.0000
O K	5.65	4.94	207.00	27.36	0.0096	0.9856	0.1726	1.0000
AlK	1.27	0.66	303.90	22.68	0.0097	0.8681	0.8776	1.0074
SiK	15.69	7.82	3845.10	4.71	0.1301	0.8859	0.9336	1.0025
CaK	0.93	0.32	101.50	62.92	0.0079	0.8297	1.0020	1.0281
FeK	3.10	0.78	126.30	50.66	0.0247	0.7306	1.0111	1.0799

kV: 15	Mag: 2002	Takeoff: 35	Live Time(s): 1.1	Amp Time(µs): 1.92	Resolution:(eV) 130.4

Phase: **SiK/FeK/O K**



Lsec: 1.1 0 Cnts 8.920 keV Det: Octane Plus

eZAF Smart Quant Results

Element	Weight %	Atomic %	Net Int.	Error %	Kratio	Z	A	F
C K	0.81	2.47	50.20	92.97	0.0016	1.2599	0.1555	1.0000
O K	8.42	19.36	2752.30	9.30	0.0447	1.2050	0.4407	1.0000
AlK	0.24	0.33	131.60	66.24	0.0015	1.0707	0.5674	1.0026
SiK	27.77	36.37	17657.50	5.34	0.2091	1.0940	0.6870	1.0020
CaK	0.56	0.52	205.00	56.63	0.0056	1.0316	0.9389	1.0300
FeK	62.20	40.96	8349.60	3.79	0.5720	0.9171	0.9980	1.0047