Technical Proposal

Cost-Aware Design of Seawater-Resistant Copper Alloy Powders for Blown-Powder Directed Energy Deposition

Office of Naval Research (ONR)
Fiscal Year 2027 Young Investigator Program (YIP)

NOFO number	N0001426SF004
Title	Cost-Aware Design of Seawater-Resistant Copper Alloy Powders for Blown-Powder Directed Energy Deposition
Prime applicant	Brigham Young University (BYU), Provo, Utah
Subawardees	None
ONR S&T Focus Areas	Primary: Manufacturing (Integrated Manufacturing and Sustainment Technologies). Secondary: Materials and Electronics (Sustainable and Operationally Robust Materials).
ONR program	Materials & Processes for Additive Manufacturing, Code 332 (Dr. Charles Fisher)
Technical contact	Sterling G. Baird, Ph.D., Assistant Professor, Department of Mechanical Engineering, Brigham Young University, 350 EB, Provo, UT 84602. Phone (801) 422-5344. Email sterling.baird@byu.edu
Administrative and business contact	[TODO Sterling: name, title, address, phone, and email of the BYU Research Administration officer who signs as the Authorized Organization Representative]
Period of performance	Base period only, 36 months: 1 April 2027 to 31 March 2030. No option periods.
Requested amount	$747,651 total: $248,959, $248,828, and $249,864 in the three 12-month periods [TODO Sterling: these are the aluminum version's figures; re-price the LPBF builds as DED sessions, then final figures from BYU Research Administration]

Contents

1 Technical Approach **1**

1.1 Problem and objectives 1
1.2 Copper alloys in naval seawater service 2
1.3 Scientific concepts 3
1.4 Comparison with other approaches 4
1.5 Preliminary results 4
1.6 Method advances 5
1.7 Hypotheses and rejection criteria 6
1.8 Research plan 7
1.9 Expected results and new knowledge 8
1.10 Future Naval Relevance 9
1.11 Project Schedule and Milestones 10
1.12 Goals and Benchmarks 10
1.13 Gold Standard Science 11

2 Management Approach **11**

3 Principal Investigator Qualifications **12**

Principal Investigator's Curriculum Vitae (excluded from page limit) **CV-1**

Letter of Support (excluded from page limit) **L-1**

4 Responsibility **13**

5 Data Management Plan **D-1**

Current and Pending Support (excluded from page limit) **S-1**

Cited References (excluded from page limit) **R-1**

1. Technical Approach

1.1 Problem and objectives

Much of the Navy's seawater service runs on two kinds of copper alloy. Copper-nickel alloys, 90-10 (UNS C70600) and 70-30 (UNS C71500), carry seawater in piping, condensers, and heat exchangers, and nickel-aluminum bronze (NAB, UNS C95800) is cast into propellers, valves, and pump parts [1, 2, 3]. Both were developed for casting or wrought processing. Directed energy deposition (DED), in which a laser melts a stream of powder blown into a moving melt pool, can build large parts and restore worn or damaged ones without a foundry [4]. DED, however, cools each layer from the melt within seconds and reheats it many times as later layers pass, so it produces microstructures these alloys were never designed for. In NAB, fast cooling retains a martensitic phase that corrodes selectively in seawater [5], and the Navy's specification for NAB deposited by wire-arc DED requires the same 6-hour anneal as castings [6]. That step is costly for a large part and impractical for many repairs made in place. The Navy's specifications for printed copper alloys all use the cast compositions [7, 8, 6]; to our knowledge, no seawater copper alloy has yet been designed for blown-powder DED.

Designing one runs through a chain of steps: a thermodynamic calculation, a powder, deposited test specimens, microscopy, and property tests. The costs of the steps differ greatly. A thermodynamic calculation takes minutes, a powder lot a day, a DED session days including turnaround, and a corrosion immersion weeks; the protective film that gives copper-nickel its resistance takes weeks to months to mature [9]. Experimental campaigns often send each candidate through the whole chain, spending much of the budget on full tests of candidates that a cheap early measurement could have ruled out. Computational campaigns often work as a funnel: many simulations, then a few candidates passed on to experiments. If the simulation misses a physical effect, the funnel discards good candidates before any experiment can catch the error.

The powder is a second obstacle. Single-stream blown-powder DED, the form in use today, feeds a pre-alloyed powder from one hopper, so each new composition needs its own powder lot in a size range that flows through the nozzle. Industrial gas atomizers make powder in lots of tens of kilograms or more, so new compositions are rarely tried [TODO Sterling: cite a minimum lot size, e.g., a vendor's]. Our ultrasonic atomizer makes a lot of a new composition in a day from about half a kilogram of feedstock (Section 1.8.2). That turns the powder from a purchase into a step the search can choose, and it lets the search design the powder along with the alloy.

This project asks a basic question. When the steps of a materials workflow differ in cost by orders of magnitude, and results arrive at different times, how should one choose the next measurement and the next candidate? It answers the question on a concrete design problem: a pre-alloyed copper alloy powder for single-stream blown-powder DED that deposits without cracks or pores, on itself and on the alloys it would repair, and that resists seawater as deposited, without heat treatment, at least as well as 70-30 copper-nickel. The project has five objectives:

1. Extend a cost-aware search method that learns from partial results to several competing objectives: dense and crack-free deposits, strength, ductility, and resistance to corrosion in seawater.
2. Extend it to many experiments in progress at once, with results that return at different times.

3. Give it physics computed for the process, thermodynamic calculations evaluated along the thermal history of a DED deposit, and measure what that physics is worth.
4. Demonstrate the method on a physical workflow that designs copper alloy powders for blown-powder DED, from powder to deposit, repair coupon, tensile test, and seawater corrosion test, and test whether its stated confidence in a candidate matches what the deposits and tests later show.
5. Measure how well a one-hour electrochemical screen predicts immersion tests that take weeks, so that the long tests run only where they can change a decision.

1.2 Copper alloys in naval seawater service

Navy specifications cover copper-nickel tube for the piping systems of surface ships and submarines [1] and NAB castings for seawater service [2], and NAB is widely used for valve bodies, pump casings, and impellers, with a large market in submarine fleets [3]. Copper-nickel owes its resistance to a thin, adherent film of corrosion products, mainly cuprous oxide with nickel and iron, that builds up over weeks to months of exposure [9]. NAB is a cast alloy of copper with about 9% aluminum and 4 to 5% each of iron and nickel (by weight). Its microstructure of α grains and several intermetallic κ phases resists seawater well, but the α phase in the lamellar $\alpha+\kappa$ eutectoid, and any retained β phase, corrode selectively, above all in crevices [10, 11]. Navy NAB castings therefore get a temper anneal at 1250 ± 50 °F (about 677 °C) for at least 6 hours, propellers excepted [2], which improves their corrosion resistance [3].

Printing changes these microstructures, and printing changes how alloys corrode [12]. [TODO Sterling: NAB and copper-nickel AM literature: as-built microstructure and corrosion, being checked] NAVSEA has written specifications for 70-30 copper-nickel made by wire-arc DED and by laser powder bed fusion, and for NAB made by wire-arc DED, each as an alternative to castings and each with the existing composition [7, 8, 6]. We found none for either alloy made by blown-powder laser DED. In 2023 a Navy official pointed out, as reported by Defense News, that for metals specific to naval use, "including copper-nickel and some steel alloys, more research is needed on what happens when these materials are used for printing, particularly how it affects the metals' fatigue and corrosion properties" [13]. A composition chosen for casting is not necessarily the best one for DED, and each composition and set of deposition settings needs its own tests.

Corrosion tests of copper alloys follow the same cost pattern as the rest of the workflow. Open-circuit potential, linear polarization, and impedance measurements in substitute ocean water [14] take about an hour and give a corrosion rate and a measure of the surface film [15, 16]. Immersion tests with mass loss [17, 18] and cross-sections that measure the depth of selective attack take weeks. Tests in flowing seawater, which set the velocity limits used in piping design, take months. The search can therefore treat corrosion the way it treats cracking and strength: a cheap screen for many candidates and long tests for a few. The cheap screen can mislead, though. An hour-long measurement on a fresh surface sees neither the film that forms over weeks on copper-nickel nor slow selective attack in NAB. Knowing when the screen can be trusted is part of the research.

Supply and melting add one more objective. Nickel has been on the U.S. list of critical minerals since 2022, and copper joined it in 2025 [19, 20]. Nickel also raises the melting range: 70-30 copper-nickel melts between about 1,171 and 1,238 °C, 90-10 between 1,099 and 1,149 °C, and NAB between 1,043 and 1,060 °C [21]. A replacement for 70-30 copper-nickel that needs less




Figure 1. The workflow as linked models, with typical times per result in italics (DED sessions include turnaround at the facility; deposits are tracks, walls, blocks, and repair coupons). Composition enters at the first two steps, atomizer settings at the second, and deposition settings (laser power, travel speed, powder feed rate) at the third; the heat flow model also takes the deposition settings. After microscopy the network branches to tensile tests and to corrosion tests. Dashed arrow: each result updates the models, which choose the next experiments and steps by expected gain per cost.

nickel would use less of a critical mineral and would be easier to atomize and deposit. The search will carry nickel content as an objective to minimize where the corrosion trade-offs allow.

1.3 Scientific concepts

The search method treats the workflow as a network of linked models [22]. Each step gets its own statistical model, a Gaussian process, which predicts the outputs of that step together with their uncertainty. The models are linked in the same order as the steps (Fig. 1), so the outputs of one step are inputs to the next and uncertainty carries through the whole network. Because each step has its own model, the network learns from partial results, and a candidate can stop at any step. Buathong et al. added a cost-aware rule to this network [23]. For each possible experiment, the rule estimates how much the result is expected to improve the search, divides that by the experiment's cost, and runs the best one.

The physics comes first, in the manner of integrated computational materials engineering (ICME) [24, 25]: calculations decide where experiments go, and experiments correct the calculations. Calculation of phase diagrams (CALPHAD) in Thermo-Calc and pycalphad [26, 27] gives the liquidus and freezing range of each composition and an index of how prone it is to cracking as it solidifies [28]. It also gives the segregation of nickel, iron, and aluminum between dendrites and the phases stable at each temperature, including the β and κ phases of the bronzes. DED adds a thermal history. A moving point-source model of heat flow [29], calibrated to measured melt-pool sizes, gives for each set of deposition settings the cooling rate through solidification and the peak temperatures that later passes impose on each layer. The CALPHAD calculations are then evaluated at those temperatures, to estimate which phases can form as the deposit solidifies and which can form or dissolve as it is reheated. These outputs enter the statistical models as inputs with learned weights, so the search can discount any of them that proves uninformative. The calculations run continuously on BYU high-performance computing, and each new result is available to the next decision.




Figure 2. Synthetic workflow used for Fig. 3, built for the aluminum version of this workflow: a hand-written function for each box and a rough total cost (time, materials, supplies) for each step. Burden is a penalty on scarce elements such as scandium. The nucleant (Zr, Sc) cuts cracking, an effect the CALPHAD crack screen does not see. Task 1 replaces these functions with copper and DED ones.

1.4 Comparison with other approaches

To our knowledge, neither a multi-objective nor an asynchronous version of cost-aware, partial-evaluation optimization of linked models has been developed, and none has been demonstrated on a physical alloy workflow. Published tests of the linked-model methods use test functions and simulators [22, 23]. Multi-stage Bayesian optimization for self-driving laboratories was tested on synthetic and retrospective data with one objective [30]. Cost-aware batch optimization of refractory alloys treats measurements of unequal cost as separate sources rather than linked steps, in a computational campaign [31]. Closed-loop campaigns on printed alloys use one model and a fixed set of measurements [32]. Alloys designed for printing by computation, such as an oxide-dispersion-strengthened NiCoCr alloy [33] and high-strength aluminum alloys [34, 35], were designed and then printed as single compositions. Standard multi-objective Bayesian optimization handles competing properties and batches [36] but treats the whole chain as one costly experiment. Printed copper alloys for seawater have used the cast or wrought compositions [7, 8, 6], and their corrosion studies characterize one alloy and one process at a time [37]. Autonomous and high-throughput corrosion work has used a scanning droplet cell to screen coatings and has run fast screens before slower, more thorough tests [38, 39], but without deciding, candidate by candidate, when a long test is worth its cost. This project combines the linked network, the cost per step, physics computed for the process, several objectives including corrosion, and results that arrive out of order, and tests the combination on real deposits.

1.5 Preliminary results

Since the lab started at BYU in December 2025, we have set up a CALPHAD workflow on BYU high-performance computing, installed the ultrasonic atomizer, and completed a powder-to-part demonstration on a baseline aluminum alloy. Atomized powder, laser powder bed fusion builds, scanning electron microscopy (SEM) and energy-dispersive X-ray spectroscopy (EDS) results, and tensile data are in hand. The atomizer's induction module also melts copper alloys. NAB and 90-10 copper-nickel melt well below its upper limit, and 70-30 copper-nickel melts near it [TODO Sterling: confirm the module's maximum melt temperature and add the first copper alloy powder (SEM image and size distribution) if a run is possible before 23 October; 7 pages of the 20-page limit are still free.]




Figure 3. Best result found versus spend in simulations where the CALPHAD crack screen ignores zirconium (means of 20 campaigns, ±1 standard error). Red searches choose the next step; gray ones follow a fixed order. pKGFN is the cost-aware method [23] and BOFN the linked-model method [22]; reuse reprints earlier powders.

We also simulated the cost-aware method on a synthetic version of the workflow (Figs. 2 and 3), built for the aluminum version of this project. With the crack screen ignoring zirconium, screening and then tuning the process stalled at 63% of the optimum after $100,000. The cost-aware search, and a simpler one that reused powders, reached that level after about $26,500 (3.8 times less spend; 90% confidence interval 2.0 to 5.7). Searches that ran every candidate through the full chain caught up later, and screening kept pace when its physics was right. The simulation is hand-built and noise-free, with one objective, no corrosion branch, no process physics, and one experiment at a time, so it does not test the advances proposed here. It does show that letting the search choose the step can pay off when the physics model is incomplete. The DED workflow has the same structure: a physics screen that can miss effects, a powder step, a deposition step, and tests.

1.6 Method advances

Advance 1: several competing objectives. The published cost-aware method optimizes a single objective. A copper alloy for DED repair must balance deposit quality (dense, crack-free, and sound at the fusion line with the part it repairs), strength, ductility, and corrosion resistance in seawater, with no weighting known in advance. We will extend the cost-aware rule to several objectives. The expected improvement in one objective will be replaced by the expected growth of the set of best trade-offs (the Pareto front), measured by hypervolume as in multi-objective Bayesian optimization [36], and divided by cost as before. The difficulty is that each cheap measurement informs some objectives strongly and others weakly. Single tracks show cracking and dilution well but say little about strength or corrosion, and a polarization measurement says much about corrosion rate and nothing about strength. The rule has to account for that through the network. We will derive the rule, check it against brute-force estimates on small problems, and measure its computing time on BYU high-performance computing.

Advance 2: results that arrive out of order. The published method chooses one experiment at a time and waits for its result. In this workflow a DED session deposits many specimens, microscopy results arrive days later, immersion tests run for weeks, and thermodynamic calculations finish in minutes. We will extend the rule to batches whose results arrive at different times, so that new experiments are chosen while others are still pending. Pending experiments will enter the models as simulated results drawn from the current predictions, a standard way to avoid choosing the same experiment twice [40]. We will also test how stable the choices are when a late result contradicts early ones. For example, a block that looked dense on its surface may show cracks under the microscope, or an alloy that passed the polarization screen may show selective attack after a month of immersion.

Advance 3: physics computed for the process. Standard CALPHAD inputs describe equilibrium, or solidification without diffusion in the solid, and ignore the thermal history of the process [41]. We will add inputs computed along the DED thermal history (Section 1.3): cooling rate through solidification, the peak temperatures of reheating, and the phases that CALPHAD allows at those temperatures. Hypothesis H3 tests whether these inputs make the models' predictions more reliable than equilibrium inputs, and whether equilibrium inputs beat data alone. The answer measures what incomplete, process-aware physics is worth inside a search, which sets how much simulation a campaign should buy before it buys experiments.

Advance 4: a physical workflow from powder to repair. We will demonstrate the advances on a physical workflow (Fig. 1) in which the search chooses the composition, the atomizer settings, and the deposition settings, and decides at each step whether a candidate goes on. After microscopy, specimens go to tensile tests, or to the corrosion screen and, for selected candidates, to immersion tests. Candidates that deposit well get a repair coupon: a deposit on cast NAB or wrought copper-nickel plate, checked for cracks, dilution, and hardness across the fusion line. The demonstration includes real deposit-to-deposit scatter, outputs computed from microscopy images, and three inputs that enter at different steps.

Advance 5: checking what the screens discard. A cheap screen saves money only if it does not discard good candidates, and Section 1.2 shows that a short corrosion screen can also pass bad ones. Each round, the search will send a small random share of the candidates it would stop, about one in ten, on to the next step anyway. These audited candidates measure how often each screen is wrong, and they keep the models from learning only from candidates that the screens favored.

1.7 Hypotheses and rejection criteria

H1 (cost). The cost-aware, multi-objective search that handles pending results will reach a target set of trade-offs at lower total cost than standard batch multi-objective Bayesian optimization, which carries every candidate through the full chain. H1 will be rejected if, across matched campaigns with the same budget, the median cost to reach the target is not lower than the full-chain baseline's.

H2 (calibration). The predicted probabilities that a candidate will deposit dense and crack-free, fuse to the repair substrate without cracks, and stay close to its intended composition will match the observed rates on held-out deposits. H2 will be rejected if observed success rates differ from predicted probabilities by more than 10 percentage points.

H3 (process-aware physics). CALPHAD outputs evaluated along the DED thermal history will improve that calibration over CALPHAD outputs at equilibrium, which will in turn improve it over models trained on data alone. H3 will be rejected if the process-aware inputs do not reduce calibration error on held-out deposits compared with the equilibrium inputs.

H4 (pending results). Choosing new experiments while others are pending will reach the target in less calendar time than waiting for each batch to finish, at equal spend. H4 will be rejected if, in median calendar time, the version that works around pending results is no faster than the version that waits.

H5 (corrosion screen). Corrosion rates, breakdown potentials, and impedance from the one-hour screen, together with composition and microstructure, will predict which candidates pass a 30-day immersion test, defined as a mass loss no greater than that of the 70-30 copper-nickel reference

and selective attack no deeper than [TODO Sterling: depth]. H5 will be rejected if, among tested candidates (audited ones included), those that the model ranks in the top half pass no more often than those in the bottom half.

The targets, baselines, budgets, and number of matched campaigns will be fixed and posted before each test starts [TODO Sterling: confirm a public pre-registration site, e.g., OSF]. H1 and H4 are tested first on simulated and retrospective benchmarks, where many matched campaigns are affordable, and then in live campaigns, where only a few are.

1.8 Research plan

Task 1: methods (Ph.D. student 1). Derive and implement the multi-objective rule (Advance 1), the rule for pending results (Advance 2), the process-aware physics inputs (Advance 3), and the audit of screened-out candidates (Advance 5). Build simulated benchmarks that replace the functions of Fig. 2 with copper and DED ones, with noise, several objectives, a corrosion branch, and delays drawn from measured turnaround times. Build retrospective benchmarks from the lab's aluminum data and from the copper data that Task 2 adds each year.

Task 2: experimental platform (Ph.D. student 2). Powder for each candidate will be made in our laboratory. Oxygen-free copper bar is machined into cups that hold the charge. Nickel, iron, manganese, aluminum, and other additions are weighed in to 0.1 mg as pure metals or copper master alloys, about 0.5 kg per composition [TODO Sterling: confirm the charge size and crucible material for copper alloys]. The charge is melted in the induction module of the ultrasonic atomizer (AMAZEMET rePOWDER) and dripped onto a vibrating plate, where it breaks into droplets. The median droplet size follows the wavelength of capillary waves on the plate, so it falls as the frequency to the power $-2/3$ [42]. For a copper melt, Lang's relation gives a median near 75 μm at 20 kHz, inside the size range that blown-powder nozzles feed [43] [TODO Sterling: confirm the plate frequencies available on our unit and the size range the DED system accepts]. Each lot is sieved to that range and checked for size distribution (laser diffraction), flow and apparent density with a Hall funnel [44, 45], shape and satellites (SEM), and oxygen content [TODO Sterling: name the oxygen analysis, e.g., inert-gas fusion at a service laboratory]. The search chooses the atomizer settings along with the composition, so the powder, not only the alloy, is designed for blown powder.

DED sessions will be bought from [TODO Sterling: name the facility with a single-stream, blown-powder laser DED system, the system model, and the price per session]. A first session for each chosen powder deposits single tracks at several laser powers, travel speeds, and powder feed rates (melt-pool size, dilution, cracking, and the share of the powder caught in the melt pool), thin walls (cracking and heat buildup), and small blocks (density and porosity). Powders whose blocks reach 99% relative density can get a second session with blocks for sub-size tensile bars (ASTM E8/E8M) and corrosion coupons at the chosen settings, and a repair coupon on cast NAB or wrought copper-nickel plate. Commercial 70-30 copper-nickel and NAB powders, deposited the same way, are the baselines [TODO Sterling: confirm commercial powder sources]. The search decides which powders are deposited at all, since the atomizer makes powder faster than the budget can deposit it.

Selected deposits will be examined by SEM, by EDS and inductively coupled plasma mass spectrometry for composition (manganese and aluminum can be lost to evaporation and oxidation [41]),

and by electron backscatter diffraction (EBSD) for grain size, texture, and phase fractions, including martensitic β' in the bronzes, at BYU. Replicate tracks and blocks at fixed settings will measure deposit-to-deposit scatter. Image analysis scripts will turn micrographs into porosity, crack length, dilution, grain size, and phase fractions with stated uncertainty.

Corrosion tests follow the same staging. Polished faces get open-circuit potential, linear polarization, impedance, and cyclic polarization measurements in substitute ocean water [14, 15, 46] on a potentiostat dedicated to the loop, so that the search can schedule the screen like any other step. ASTM G61 is written for iron-, nickel-, and cobalt-based alloys, so the project will report how its procedure behaves on deposited copper alloys. Wrought 70-30 copper-nickel and heat-treated cast NAB are measured as references in every round. Candidates that the search selects get 30-day immersion tests with mass loss [17, 18] and cross-sections that measure the depth of selective attack; the leading candidates get crevice and longer immersion tests [TODO Sterling: confirm the durations, and natural or substitute seawater]. Tests in flowing seawater, which take months, are left to Navy laboratories for the final candidates (Section 1.10).

The alloy space starts from two families. The first is copper-nickel with 10 to 30% nickel and additions of iron, manganese, and chromium. The second is aluminum bronze with nickel, iron, and manganese, where the aim is a composition whose as-deposited microstructure avoids the phases that corrode selectively. Compositions are bounded by the atomizer's melting limit, and nickel content is carried as an objective [TODO Sterling: confirm the alloy families and the element ranges to search].

Task 3: live campaigns and hypothesis tests (both students). Run live campaigns in which the search chooses each experiment and step. Compare it on equal budgets with random selection and with standard batch multi-objective Bayesian optimization over the full chain. Test H2 and H3 on held-out deposits, H5 on the audited and selected candidates, and H1 and H4 in matched campaigns.

Task 4: release and transition. Release the software, data, and models each year (Section 5). Write a short guide for applying the method to other alloys, deposition processes, and test sequences, aimed at Navy laboratory and depot engineers. For each final candidate, publish a powder specification, the deposition settings, and the tensile, corrosion, and repair-coupon data, and share them with Navy materials engineers, who can decide which candidates merit flowing-seawater and service tests.

1.9 Expected results and new knowledge

If successful, the project will produce:

1. The first cost-aware method of this kind for competing properties and staggered results.
2. A measured answer to how much a staged, cost-aware search saves over full-chain testing on a real alloy workflow.
3. A measured value of process-aware physics: how much CALPHAD evaluated along the DED thermal history improves predictions over equilibrium calculations and over data alone.
4. Corrosion data for copper alloys deposited by DED, and a measured link between a one-hour electrochemical screen and immersion tests that take weeks.

5. New copper alloy compositions designed for blown-powder DED, each with its powder specification, deposition settings, tensile properties, corrosion behavior, and repair coupons, using less nickel where the trade-offs allow.

Results that reject a hypothesis are also new knowledge. For example, if H1 fails, the data will show which step's cost or noise erased the advantage; if H3 fails, they will show which process effects the calculations missed; if H5 fails, they will show which microstructural features the screen missed.

1.10 Future Naval Relevance

ONR S&T Focus Areas. The primary focus area is Manufacturing, research area Integrated Manufacturing and Sustainment Technologies. The secondary focus area is Materials and Electronics, research area Sustainable and Operationally Robust Materials. Within Code 332 the project fits the program Materials & Processes for Additive Manufacturing [47]. That program lists five thrusts: "(i) rapid qualification frameworks; (ii) tailored AM materials and processes; (iii) large scale AM; (iv) additive repair and (v) AM and digital logistics." Its research challenges include to "develop and validate computational approaches for AM materials and processes for engineering applications" and to "develop large-scale AM processes for naval materials of interest" [47]. The project serves thrusts (ii) to (iv) with an alloy designed for a large-scale process that also repairs, and thrust (i) with a search method that decides which test to run next and states its confidence in the outcome. It is ICME for additive manufacturing, the approach ONR's Structural Metals program calls "an efficient rigorous framework for optimizing processing and manufacturing schemes" [48]: computation first, and experiments where they change a decision. It also fits two other Code 332 programs: Corrosion Science and Corrosion Control Technologies, which asks for a "fundamental understanding of corrosion mechanism in additive manufactured (AM) alloys" [49], and Computer-Aided Materials Design, whose thrusts include high-throughput screening concepts and informatics [50].

Copper alloys, castings, and repair. The slow production of large castings "has historically gated progress and throughput for both the Columbia and Virginia submarine programs" [51], and the Navy is replacing castings with printed parts. In August 2026 it set out "a streamlined, repeatable technical pathway to substitute legacy cast and wrought parts with 3D-printed metallic materials" [52]. A printed copper-nickel deck drain, made "to provide an alternative to traditional copper-nickel castings," has been installed on a new-construction submarine [53, 54], and the Navy's Maritime Industrial Base program has made copper-nickel ship-service ball valves by wire-arc deposition [55]. These parts use the cast compositions. A copper alloy designed for blown-powder DED, one that resists seawater as deposited, would let a shipyard or depot build a part that now waits on a casting, or restore a worn part in place without the heat treatment the cast alloys need. ONR's corrosion program asks for this kind of work: "modify the chemistry of feed stock materials to enhance AM processing and corrosion resistance of additive-manufactured alloys" [49].

The longer horizon. The project designs for single-stream, pre-alloyed powder, which existing DED systems can use now. The same models can later choose blends of elemental and master-alloy powders fed from several hoppers and alloyed in the melt pool, which would let a depot make a new composition without a new powder lot. The guide of Task 4 will describe that extension. The method needs only a network of steps, their costs, and their measurements, so it also applies to wire-arc and laser-wire deposition and to other Navy alloys, including titanium. A plasma melting

module for our atomizer (not part of this request) would extend the powder work to alloys that melt above the induction module's limit.

Navy engagement and people. The PI presented autonomous experimentation for alloy discovery at the Naval Surface Warfare Center (NSWC) Carderock Division on 14 October 2026 [TODO Sterling: name any Carderock contacts who agree to be listed]. The PI will apply to the Summer Faculty Research Program to spend a summer at a Navy laboratory [TODO Sterling: confirm; the 2027 application closes 14 December 2026]. The project will train two Ph.D. students and undergraduates in powder making, deposition, characterization, corrosion testing, and autonomous experimentation. We will encourage them to apply to the Naval Research Enterprise Internship Program and the SMART and NDSEG programs, which the NOFO names as goals of the YIP.

1.11 Project Schedule and Milestones

Table 1 lists the schedule by year. The award start date is 1 April 2027.

Table 1. Schedule and milestones (Y = project year, starting 1 April 2027).

Year	Work	Milestone (month)
Y1	Derive the multi-objective rule; build simulated and retrospective benchmarks; build the process-aware physics inputs; first copper powder lots in the DED size range; deposit the commercial baselines and replicate them to measure scatter; set up the corrosion screen on wrought and cast references; automate image analysis.	M1: first copper powder lot sieved and checked (4). M2: baseline deposits and scatter measured (7). M3: corrosion screen repeatability measured (8). M4: multi-objective rule passes small-problem checks (9). M5: benchmarks frozen and posted (12).
Y2	Derive the rule for pending results; first live campaign with tensile, corrosion, and repair branches; first 30-day immersions; test H2 and H3 on held-out deposits.	M6: first live campaign done (18). M7: H2 and H3 tested (22). M8: methods paper and software release 1 (24).
Y3	Matched live campaigns against the full-chain baseline; test H1, H4, and H5; release software, data, and guide; share powder, deposition, corrosion, and repair data with Navy engineers.	M9: matched campaigns done (32). M10: H1, H4, and H5 tested (34). M11: final release and report (36).

1.12 Goals and Benchmarks

Table 2 lists each goal and the benchmark used to measure progress. Progress will be reported at each ONR program review.

Table 2. Goals and the benchmarks that measure them.

Goal	Benchmark
Multi-objective cost-aware rule	Matches brute-force estimates on small problems; finds a larger set of trade-offs per dollar than full-chain multi-objective search on the simulated benchmark.
Rule for pending results	Same final quality as the one-at-a-time rule in less calendar time on the simulated benchmark with measured delays (H4).
Calibrated predictions	Observed success rates within 10 percentage points of predicted probabilities on held-out deposits (H2).
Process-aware physics	Lower calibration error with thermal-history inputs than with equilibrium inputs, and with equilibrium inputs than without (H3).
Powder for blown-powder DED	Every deposited composition made in-house, sieved to the DED size range, with its size distribution, flow, and oxygen content recorded.
Corrosion screen	Top-ranked candidates pass the 30-day immersion test more often than bottom-ranked ones (H5).
Lower cost on real deposits	Lower median cost to reach the target than the full-chain baseline in matched live campaigns (H1).
New alloys	At least [TODO Sterling: number] new compositions deposited dense and crack-free, with tensile, corrosion, and repair-coupon data, beyond the commercial baselines.
Open release	Software, data, and models posted each year with tests and documentation.

1.13 Gold Standard Science

Executive Order 14303 lists nine tenets of Gold Standard Science [56]. Such science is reproducible, transparent, communicative of error and uncertainty, collaborative and interdisciplinary, and skeptical of its findings and assumptions. It is also structured for falsifiability of hypotheses, subject to unbiased peer review, accepting of negative results as positive outcomes, and without conflicts of interest. The plan follows each point. Each hypothesis above has a stated rejection criterion, and the targets and baselines are fixed before each test. Every prediction carries an uncertainty, and the calibration tests (H2, H3) check whether that uncertainty is honest. The audit of screened-out candidates (Advance 5) tests the screens' own assumptions. Replicate deposits and reference specimens measure scatter so that it is not mistaken for a real effect. Code, data, and models are released each year so others can rerun every analysis. Results that reject a hypothesis will be published like any other result. The PI's record supports this: the PI co-authored a review of self-driving laboratories and led open benchmark and software projects (see Section 3).

2. Management Approach

This is a single-PI project with no co-PIs or subawards. The PI will lead the method development, set the campaign plans, and supervise all students. Ph.D. student 1 will lead Task 1 (methods, physics inputs, benchmarks, software). Ph.D. student 2 will lead Task 2 (powder, deposits, microscopy, tensile and corrosion tests). An undergraduate researcher will help make and check

powder, prepare specimens, and run the corrosion screen. Both Ph.D. students share Task 3, so the methods are tested on the data they will face.

DED sessions are bought at a set rate from [TODO Sterling: facility], and any outside tests from a commercial laboratory; neither is a subaward. [TODO Sterling: number] sessions per year fit the budget. All other work is at BYU: the PI's atomizer laboratory, the BYU Microscopy Center (SEM, EDS, EBSD), and BYU high-performance computing. The team meets weekly to review new results and choose the next experiments. A shared data pipeline records every step, so the search always sees the latest results. The schedule and milestones are in Table 1.

Risks and responses. If the multi-objective rule is too slow to compute, we will use a cheaper approximation and measure the loss on the simulated benchmark. If deposit scatter is large, more replicates will be added and the scatter will enter the models directly. If a composition cannot be atomized, for example because it melts too close to the module's limit, the search records the failure as a result, since predicting which compositions can be made is part of the task. If a lot flows poorly, the search sees that at the powder step and can change the atomizer settings before paying for a deposit. If DED turnaround is slow, the rule for pending results is designed for exactly that case. If the electrochemical screen predicts the immersion tests poorly (H5 rejected), the search will rely more on immersion, at higher cost, and the audited candidates will show which features the screen missed.

3. Principal Investigator Qualifications

Sterling G. Baird received a Ph.D. in Materials Science and Engineering from the University of Utah in August 2023. He has been an Assistant Professor of Mechanical Engineering at BYU since December 2025, his first tenure-track position. Before BYU, he was Director of Training and Programs and then a Principal Investigator and Staff Scientist at the Acceleration Consortium, University of Toronto, where he built the Acceleration Consortium's development laboratory, including about $600,000 of equipment.

The PI's work combines Bayesian optimization with laboratory hardware. He developed Honegumi, which helps experimentalists set up Bayesian optimization, consulted for Meta on the version 1.0 release of the Ax platform, and organized an international Bayesian optimization hackathon. He co-authored the structural materials section of the *Chemical Reviews* survey of self-driving laboratories and led a review of low-cost self-driving laboratories. His graduate work used Bayesian inference with propagated uncertainty to model grain boundaries. He also designed a semi-automated induction furnace for temperatures up to 2500 °C. At BYU he supervises eight undergraduate researchers and has set up the CALPHAD workflow, the atomizer, and the powder-to-part demonstration described in Section 1.5. [TODO Sterling: add any corrosion or electrochemistry experience; if there is none, say how the students will learn the corrosion methods, e.g., a BYU colleague's training or a Navy laboratory visit. Add any DED or welding experience.] The CV lists all publications and presentations.

Principal Investigator's Curriculum Vitae

[TODO Sterling: insert the full CV PDF here.]

Letter of Support

[TODO Sterling: insert the signed letter from the BYU official here as a PDF page (draft in support-letter-draft.md; it names aluminum, so revise it for this version).]

4. Responsibility

Resources. The PI's laboratory at BYU holds the ultrasonic atomizer and the equipment for powder handling and specimen preparation [TODO Sterling: list the main items bought with start-up funds]. A potentiostat for the corrosion screen is requested in Year 1. The BYU Microscopy Center provides SEM, EDS, and EBSD, and BYU provides high-performance computing. DED sessions are bought as a service, as described under Task 2. Tensile tests use [TODO Sterling: name the BYU load frame or test service].

Ability to comply. The PI's current commitments are teaching, start-up research, and the pending requests listed under current and pending support. The effort proposed here fits within those commitments.

Performance history. [TODO Sterling: list any federal awards managed as PI or key person; if none, state that this would be the PI's first federal award as PI and that BYU Research Administration manages the award.]

Integrity and business ethics. The PI has no findings of research misconduct and follows BYU's policies on research integrity and conflicts of interest. [TODO Sterling: confirm.]

Qualifications and eligibility. The PI received his Ph.D. after 1 January 2019, holds his first full-time tenure-track position, and has not received an ONR YIP award. [TODO Sterling: confirm U.S. citizenship or permanent residency.] BYU is registered in SAM.gov (UEI JWSYC7RUMJD1, CAGE 52534) [TODO Sterling: BYU's SAM registration is listed as ending 4 March 2027, before the award start; confirm that RAO will renew it].

Organization and controls. BYU Research Administration manages federal awards, with accounting, purchasing, and property control systems [TODO Sterling: confirm wording with BYU Research Administration]. Laboratory safety follows BYU Risk Management and Safety procedures. Metal powders are handled under the lab's written powder safety plan; nickel-bearing powders are handled in a fume hood or glove bag with respiratory protection [TODO Sterling: confirm the plan and the handling steps for nickel powder]. Corrosion tests use salt solutions; the dilute acids used to clean immersion coupons [18] are handled in a fume hood under BYU chemical safety procedures.

5. Data Management Plan

Types of data, software, and other materials. Thermodynamic and heat flow calculation results; atomizer settings and powder size, flow, density, and oxygen records; DED deposition settings and session logs; optical and electron micrographs, EDS spectra, and EBSD maps; tensile and hardness data; polarization and impedance data, immersion mass losses, and cross-sections of corrosion attack; the search software, benchmark problems, and trained models.

How the data will be acquired. Calculations run on BYU high-performance computing. Powder is made in the PI's laboratory. DED sessions are bought as a service (Section 2). Microscopy, corrosion screens, immersion tests, and mechanical tests are done at BYU.

Time and location. Data are collected at BYU and at the DED facility from April 2027 to March 2030.

Processing. Scripts kept under version control turn raw images and test records into derived quantities (porosity, crack length, dilution, grain size, phase fractions, strength, corrosion rate, attack depth) with stated uncertainty. Each derived value links to its raw files.

File formats and naming. Open formats: CSV and JSON for tables, TIFF for images, and the instruments' native formats alongside open exports. Each sample receives an identifier that encodes powder lot, deposition session, and specimen, used in every file name.

Quality assurance and control. Replicate deposits measure scatter; reference specimens of wrought 70-30 copper-nickel and cast NAB are measured in every round of corrosion screening; scripts are tested; and the same benchmarks are rerun before each software release.

Existing data. The retrospective benchmarks use the lab's own aluminum data from 2026, with its origin recorded in the metadata.

Standards. Metadata will record composition, powder properties, process settings, instrument settings, and the ASTM method behind each test in a documented schema [TODO Sterling: choose a schema, e.g., one used by the NIST AM Bench or Materials Data Facility].

Preservation. Data and software will be deposited in public repositories (for example, Zenodo with a DOI, and GitHub for code) at each annual release and kept for at least 10 years.

Balance of value and cost. Raw session logs and micrographs will be kept in full; very large intermediate files that scripts can regenerate will not be archived.

Release restrictions. Results are expected to be fundamental research. Any data that cannot be cleared for public release under DoD Instruction 5230.09 will not be made public.

Current and Pending Support (summary)

Current. [TODO Sterling: list current awards, if any, including BYU internal funds that must be reported under the common form.]

Pending. AFOSR FY2027 Young Investigator Program, white paper submitted 9 October 2026 (NOFO FA955026S0003, Dynamic Data and Information Processing, Dr. Erik Blasch). Title: "Dynamic Data-Driven Selection of Experiments for Laser-Printed Aluminum Alloys." Up to $150,000 per year for 36 months. The two share the search method. This proposal applies it to copper alloys for blown-powder DED, with corrosion and repair branches; the AFOSR work applies it to aluminum alloys for laser powder bed fusion, so the experimental work does not overlap. [TODO Sterling: state how the method work (Task 1) would be divided if both are selected. Add any other proposals submitted before 30 October, and list collaborators, even unfunded ones (NOFO p. 38).]

References

[1] MIL-T-16420K, *Tube, Copper-Nickel Alloy, Seamless and Welded (Copper Alloy Numbers 715 and 706)*, Naval Sea Systems Command (validation notice 18 Feb 2026). https://quicksearch.dla.mil/qsDocDetails.aspx?ident_number=11860

[2] MIL-B-24480A, *Bronze, Nickel-Aluminum (UNS No. C95800) Castings for Seawater Service*, Naval Sea Systems Command (20 Jun 1985; validation notice 24 Dec 2020). https://quicksearch.dla.mil/qsDocDetails.aspx?ident_number=17349

[3] Copper Development Association, *Guide to Nickel Aluminium Bronze for Engineers*, CDA Publication 222 (January 2016). https://www.copper.org/applications/marine/nickel_al_bronze/pub-222-nickel-al-bronze-guide-engineers.pdf

[4] [MISSING REFERENCE saboori2019]

[5] [MISSING REFERENCE NAB-AM-MICRO]

[6] MIL-PRF-32816, *Nickel Aluminum Bronze, Wire Arc, Directed Energy Deposition, Additively Manufactured*, Naval Sea Systems Command (29 Jun 2026). https://quicksearch.dla.mil/qsDocDetails.aspx?ident_number=287090

[7] MIL-PRF-32804, *Copper-Nickel (70-30), Wire Arc, Directed Energy Deposition, Additively Manufactured*, Naval Sea Systems Command (27 Oct 2025). https://quicksearch.dla.mil/qsDocDetails.aspx?ident_number=286541

[8] MIL-PRF-32815, performance specification for additively manufactured 70-30 copper-nickel made by laser powder bed fusion, Naval Sea Systems Command (29 Jun 2026). https://quicksearch.dla.mil/qsDocDetails.aspx?ident_number=287089

[9] [MISSING REFERENCE ma2015]

[10] [MISSING REFERENCE wharton2005]

[11] [MISSING REFERENCE culpan1979]

[12] G. Sander, J. Tan, P. Balan, O. Gharbi, D. R. Feenstra, L. Singer, S. Thomas, R. G. Kelly, J. R. Scully, and N. Birbilis, "Corrosion of additively manufactured alloys: A review," *Corrosion* **74**(12), 1318-1350 (2018). doi:10.5006/2926

[13] M. Eckstein, "Shipbuilding industry looks to 3D printing to accelerate pace," *Defense News* (2 Feb 2023). https://www.defensenews.com/naval/2023/02/02/shipbuilding-industry-looks-to-3d-printing-to-accelerate-pace/

[14] ASTM D1141, *Standard Practice for the Preparation of Substitute Ocean Water*, ASTM International.

[15] ASTM G59, *Standard Test Method for Conducting Potentiodynamic Polarization Resistance Measurements*, ASTM International.

[16] ASTM G102, *Standard Practice for Calculation of Corrosion Rates and Related Information from Electrochemical Measurements*, ASTM International.

[17] ASTM G31, *Standard Guide for Laboratory Immersion Corrosion Testing of Metals*, ASTM International.

[18] ASTM G1, *Standard Practice for Preparing, Cleaning, and Evaluating Corrosion Test Specimens*, ASTM International.

[19] U.S. Department of the Interior, "2022 final list of critical minerals," *Federal Register* **87**, 10381 (24 Feb 2022). https://www.federalregister.gov/documents/2022/02/24/2022-04027/2022-final-list-of-critical-minerals

[20] U.S. Department of the Interior, "Final 2025 list of critical minerals," *Federal Register* **90**, 50494 (7 Nov 2025). https://www.federalregister.gov/documents/2025/11/07/2025-19813/final-2025-list-of-critical-minerals

[21] Copper Development Association, alloy data sheets for C70600, C71500, and C95800, physical properties (liquidus and solidus given in °F; read from Internet Archive snapshots of 2025 and 2026). https://alloys.copper.org/alloy/C71500

[22] R. Astudillo and P. I. Frazier, "Bayesian optimization of function networks," *Advances in Neural Information Processing Systems* **34**, 14463-14475 (2021). arXiv:2112.15311

[23] P. Buathong, J. Wan, R. Astudillo, S. Daulton, M. Balandat, and P. I. Frazier, "Bayesian optimization of function networks with partial evaluations," *Proc. 41st Int. Conf. Machine Learning (ICML)*, PMLR **235**, 4752-4784 (2024). proceedings.mlr.press/v235/buathong24a.html

[24] [MISSING REFERENCE olson1997]

[25] [MISSING REFERENCE nrc2008]

[26] J.-O. Andersson, T. Helander, L. Höglund, P. Shi, and B. Sundman, "Thermo-Calc & DICTRA, computational tools for materials science," *Calphad* **26**(2), 273-312 (2002). doi:10.1016/S0364-5916(02)00037-8

[27] R. Otis and Z.-K. Liu, "pycalphad: CALPHAD-based computational thermodynamics in Python," *J. Open Res. Softw.* **5**(1), 1 (2017). doi:10.5334/jors.140

[28] S. Kou, "A criterion for cracking during solidification," *Acta Mater.* **88**, 366-374 (2015). doi:10.1016/j.actamat.2015.01.034

[29] D. Rosenthal, "The theory of moving sources of heat and its application to metal treatments," *Trans. ASME* **68**(8), 849-865 (1946). doi:10.1115/1.4018624

[30] L. Torresi and P. Friederich, "Multi-stage Bayesian optimisation for dynamic decision-making in self-driving labs," *Digital Discovery* **5**, 1900-1912 (2026). doi:10.1039/d5dd00572h

[31] S. M. A. A. Alvi, B. Vela, V. Attari, J. Janssen, D. Perez, D. Allaire, and R. Arróyave, "Deep Gaussian process-based cost-aware batch Bayesian optimization for complex materials design campaigns," *npj Comput. Mater.* **12**, 105 (2026). doi:10.1038/s41524-026-01981-7

[32] A. Talbot, S. S. Dash, J. Li, C. Cheng, M. Ramesh, X. Shang, J. Zhang, C. Cojocaru, J. Hattrick-Simpers, and Y. Zou, "Active learning for the accelerated discovery of complex concentrated NiCoCr alloys in additive manufacturing," *npj Adv. Manuf.* (2026), published online 23 Jun 2026. doi:10.1038/s44334-026-00098-5

[33] [MISSING REFERENCE smith2023]

[34] S. Thapliyal, M. Komarasamy, S. Shukla, L. Zhou, H. Hyer, S. Park, Y. Sohn, and R. S. Mishra, "An integrated computational materials engineering-anchored closed-loop method for design of aluminum alloys for additive manufacturing," *Materialia* **9**, 100574 (2020). doi:10.1016/j.mtla.2019.100574

[35] S. M. Taheri-Mousavi, M. Xu, F. Hengsbach, C. Houser, Z. Ge, B. Glaser, S. Wei, M. Schaper, J. M. LeBeau, G. B. Olson, and A. J. Hart, "Additively manufacturable high-strength aluminum alloys with coarsening-resistant microstructures achieved via rapid solidification," *Adv. Mater.* **38**(4), e09507 (2026), published online 2 Oct 2025. doi:10.1002/adma.202509507

[36] S. Daulton, M. Balandat, and E. Bakshy, "Parallel Bayesian optimization of multiple noisy objectives with expected hypervolume improvement," *Advances in Neural Information Processing Systems* **34** (2021). arXiv:2105.08195

[37] [MISSING REFERENCE NAB-AM-CORR]

[38] B. DeCost, H. Joress, S. Sarker, A. Mehta, and J. Hattrick-Simpers, "Towards automated design of corrosion resistant alloy coatings with an autonomous scanning droplet cell," *JOM* **74**, 2941-2950 (2022). doi:10.1007/s11837-022-05367-0

[39] D. Sur, E. F. Holcombe, W. H. Blades, E. A. Anber, D. L. Foley, B. L. DeCost, J. Liu, J. Hattrick-Simpers, *et al.*, "An experimental high-throughput to high-fidelity study towards discovering Al-Cr containing corrosion-resistant compositionally complex alloys," *High Entropy Alloys Mater.* **1**, 336-353 (2023). doi:10.1007/s44210-023-00020-0

[40] J. Snoek, H. Larochelle, and R. P. Adams, "Practical Bayesian optimization of machine learning algorithms," *Advances in Neural Information Processing Systems* **25** (2012). arXiv:1206.2944

[41] T. DebRoy, H. L. Wei, J. S. Zuback, T. Mukherjee, J. W. Elmer, J. O. Milewski, A. M. Beese, A. Wilson-Heid, A. De, and W. Zhang, "Additive manufacturing of metallic components: Process, structure and properties," *Prog. Mater. Sci.* **92**, 112-224 (2018). doi:10.1016/j.pmatsci.2017.10.001

[42] [MISSING REFERENCE lang1962]

[43] [MISSING REFERENCE CITE-DED-PSD]

[44] ASTM B213, *Standard Test Methods for Flow Rate of Metal Powders Using the Hall Flowmeter Funnel*, ASTM International.

[45] ASTM B212, *Standard Test Method for Apparent Density of Free-Flowing Metal Powders Using the Hall Flowmeter Funnel*, ASTM International.

[46] ASTM G61, *Standard Test Method for Conducting Cyclic Potentiodynamic Polarization Measurements for Localized Corrosion Susceptibility of Iron-, Nickel-, or Cobalt-Based Alloys*, ASTM International.

[47] Office of Naval Research, "Materials & Processes for Additive Manufacturing," Code 33 Manufacturing Focus Area (accessed 17 Oct 2026). https://www.onr.navy.mil/organization/departments/code-33/manufacturing-focus-area/additive-manufacturing

[48] Office of Naval Research, “Structural Metals,” Code 33 Materials Focus Area (updated November 2020; accessed 17 Oct 2026). https://www.onr.navy.mil/organization/departments/code-33/materials-focus-area/structural-metals

[49] Office of Naval Research, “Corrosion Science and Corrosion Control Technologies,” Code 33 Materials Focus Area (accessed 17 Oct 2026). https://www.onr.navy.mil/organization/departments/code-33/materials-focus-area/corrosion-science-and-corrosion-control

[50] Office of Naval Research, “Computer-Aided Materials Design (CAMD),” Code 33 Materials Focus Area (accessed 10 Oct 2026). https://www.onr.navy.mil/organization/departments/code-33/materials-focus-area/computer-aided-materials-design

[51] NAVSUP Weapon Systems Support, “Shattering bottlenecks: NAVSUP WSS partners with DLA and NAVSEA on submarine advanced manufacturing,” DVIDS (30 Jun 2026). https://www.dvidshub.net/news/569018/shattering-bottlenecks-navsup-wss-partners-with-dla-and-navsea-submarine-advanced-manufacturing

[52] U.S. Navy, “Navy removes bureaucratic barriers to accelerate 3D printing and accelerate submarine production,” press release (21 Aug 2026), on Project Peculiar Document 802-8436658. https://www.navy.mil/Press-Office/Press-Releases/display-pressreleases/Article/4580193/navy-removes-bureaucratic-barriers-to-accelerate-3d-printing-and-accelerate-sub/

[53] HII, “HII partners to advance additive manufacturing on a Virginia-class submarine,” news release (25 Sep 2023). https://www.hii.com/news/hii-additive-manufacturing-virginia-class-submarine-newport-news-shipbuilding-2023

[54] Newport News Shipbuilding, “One small part for the Virginia-class submarine program, one giant leap for additive manufacturing,” NNS To Go (17 Sep 2025). https://www.nnstogo.com/articles/one-small-part-for-the-virginia-class-submarine-program-one-giant-leap-for-additive-manufacturing/

[55] Navy Maritime Industrial Base Program, “Navy’s MIB program celebrates year of focused effort to strengthen maritime industrial capability and capacity,” DVIDS (5 Sep 2025). https://www.dvidshub.net/news/549872/navys-mib-program-celebrates-year-focused-effort-strengthen-maritime-industrial-capability-and-capacity

[56] Executive Order 14303, “Restoring Gold Standard Science,” *Federal Register* **90**, 22601 (29 May 2025). https://www.federalregister.gov/documents/2025/05/29/2025-09802/restoring-gold-standard-science