
XRD: FeS Mackinawite
(ex-situ characterization)
Intensity (a.u.)
2θ (degrees)
30.0°
33.8°
Raman: FeS Mackinawite
(ex-situ characterization)
Intensity (a.u.)
Raman Shift (cm⁻¹)
208
283
321
370
EDS: FeS Precipitate
Elemental Analysis
Counts
Energy (keV)
Fe Lα
C Kα
S Kα
Fe Kα
Fe Kβ