

(a)
sgbaird
29 Sep 2026, 22:36 UTC
@claude dispense 8 grams of the AlSi10Mg that we just loaded. You can use the most recent optimized parameters. It flows pretty well, maybe not quite as good as salt, but still pretty decent.
claude[bot]
22:37 UTC
Dispensed 8 g of AlSi10Mg: 7.993 g delivered in 315 s. 7.9928 g against an 8.000 g target, 7.2 mg short (−0.09 %). The firmware reported ok.
(b)
agent or person
Dose request (target mass)
Three-phase controller (microcontroller)
Auger rotation, solenoid taps, tilt servos
powder
Analytical balance
measured mass, read after every step
Before: empty cup
Bulk: 45° tilt, 55 rpm, to 0.5 g short
Fine: 22.5° tilt, 45° steps, to 50 mg short
Tap: horizontal, 2 taps per cycle, to ±5 mg
Done
(c)
Mass in the cup (mg)
0
200
400
600
800
1000
996 mg
0
20
40
60
80
100
120
140
160
Time since the dose started (s)