

(a)
sgbaird
29 Sep 2026, 22:36 UTC
@claude dispense 8 grams of the AlSi10Mg that we just loaded. You can use the most recent optimized parameters. It flows pretty well, maybe not quite as good as salt, but still pretty decent.
claude[bot]
22:37 UTC
Dispensed 8 g of AlSi10Mg: 7.993 g delivered in 315 s. 7.9928 g against an 8.000 g target, 7.2 mg short (−0.09 %). The firmware reported ok.
Dispensing 8 g of Al 4047 (9fxeqt)
Review how the AlSi10Mg dose was run a
the firmware for a "two taps per cycle" opt
Phone, 30 Sep: the agent's checklist for an 8 g dose
(b)
agent or person
Dose request (target mass)
Analytical balance
measured mass
powder
Three-phase controller (microcontroller)
Auger rotation, solenoid taps, tilt servos
Before: empty cup
Bulk: 45° tilt, 55 rpm, to 0.5 g short
Fine: 22.5° tilt, 45° steps, to 50 mg short
Tap: horizontal, 2 taps per cycle, to ±5 mg
Done
(c)
Mass in the cup (mg)
1000
800
600
400
200
0
996 mg
0
20
40
60
80
100
120
140
160
Time since the dose started (s)