Marcus E. Madsen*
Department of Mechanical Engineering,
Brigham Young University,
Provo, UT 84602, USA

Audrey K. Christiansen*
Department of Mechanical Engineering,
Brigham Young University,
Provo, UT 84602, USA

Jinkwan Han*
Department of Mechanical Engineering,
Brigham Young University,
Provo, UT 84602, USA

Jeffrey R. Hill†‡[1]
Department of Mechanical Engineering,
Brigham Young University,
Provo, UT 84602, USA
email: jeff.hill@byu.edu

Sterling G. Baird†‡[1]
Department of Mechanical Engineering,
Brigham Young University,
Provo, UT 84602, USA
email: sterling.baird@byu.edu

Experiment-Driven Bayesian Optimization of the Impact Response of Multi-Material 3D-Printed Tensegrity-Inspired Structures

Tensegrity-inspired structures of rigid and soft members could cushion impacts, but the shock they transmit is hard to predict by simulation. We report a Bayesian optimization campaign, driven by drop tests, over three-strut prisms printed in one piece from polylactic acid and thermoplastic polyurethane. The search space begins with five geometry variables and, from the third batch, adds infill densities and filament settings. Each candidate is rescaled to a common mass, printed, and drop-tested repeatedly (101 drops per article in the seed batch, about twenty later). The optimizer seeks low transmissibility (the top-to-base ratio of filtered peak accelerations) and a high velocity loss index (the fraction of impact velocity not returned at the top). Most printed articles amplify the peak shock, so the question became which designs reduce it. Over a quasi-random seed batch and three model-recommended batches (35 articles), the dominated hypervolume grew 65 percent and the model chose every design on the final Pareto front. The fourth batch's best-predicted design lowered transmissibility to a record 0.803, ten percent below the best seed article. Reprinting one batch moved individual results by more than the drop-to-drop scatter, so we treat single-print extremes as provisional until replicated. [Placeholder: third-print and replicate-study outcome pending.]

Keywords: tensegrity, multi-material 3D printing, Bayesian optimization, impact mitigation, design of experiments

Draft note (remove before submission): this draft is written at the intended final scope of the study, and any value printed in this violet color is a synthetic placeholder rather than a measurement. As of 2026-09-15 the Results contain no violet values: all four reported batches (35 articles) are measured data from the committed campaign record. The abstract and the Conclusions each carry one violet placeholder (added 2026-10-10) for the outcome of the third print and the replicate study listed below. Still pending, and written as future work rather than as results: the re-seat confirmation of the batch-4 record article, any batches beyond the fourth, the third print of the batch-3 designs, the replicate rank-stability study (best-, mid-, and worst-predicted in-sample designs in nominal triplicate), the quasi-static crush campaign, the metal-analog comparison, and the archival (Zenodo) code release.

1 Introduction

Tensegrity structures are assemblies of rigid compression members suspended within a continuous network of tension members; their defining property, that no two rigid bars touch, yields lightweight assemblies with remarkable strength-to-weight ratios and tunable nonlinear mechanical responses [1, 2]. These properties have made tensegrity attractive across scales, from metamaterial unit cells [3–5] to compliant impact-absorbing robots developed for planetary landing [6–10]. Recent work has shown that *tensegrity-inspired* unit cells can be directly 3D-printed and exhibit load-limiting plateaus under drop-weight impact [11], opening a path toward additively manufactured architected absorbers. Throughout, we use *tensegrity-inspired* for printable cells that borrow the separated compression-member and tension-network geometry of tensegrity while relaxing defining mechanical conditions of classical tensegrity. In the present specimens, the TPU tension elements are extensible, the PLA struts may share printed junctions, and no pretension is activated or measured. We therefore do not claim classical tensegrity, prestress-stabilized behavior, or equivalence to an ideal cable-strut prism.

Multi-material fused-deposition modeling (FDM) that pairs a rigid polymer such as polylactic acid (PLA) with a soft, rate-dependent elastomer such as thermoplastic polyurethane (TPU) has been used to fabricate rigid-soft architected energy absorbers on a single platform: thick-panel origami metamaterials with PLA panels and TPU hinges [12] and ABS/TPU honeycombs with tunable stiff/flexible proportions [13]. The same rigid-soft co-printing capability makes it possible to rapidly fabricate diverse tensegrity-inspired geometries, which adopt a discrete-compression/continuous-tension topology rather than an origami or honeycomb one. Although extruded TPU does not behave as an idealized inextensible cable, its rate-dependent damping is a desirable property for impact-absorption applications and complements the elastic stiffness of the PLA compression members rather than competing with it.

Designing such architected absorbers is fundamentally a *design-of-experiments* problem: the configuration space spanned by strut geometry, tension-element cross-section, connectivity, and unit-cell tiling is large; each candidate must be physically printed and tested; and the relevant impact-performance metrics (the shock transmitted across the structure and the velocity it gives back to the protected payload) are noisy and partially correlated. Bayesian optimization (BO) is well-matched to this regime, having driven breakthroughs from hyperparameter tuning of AlphaGo [14] to sustainable concrete [15], autonomous discovery of organic laser emitters [16], and architected materials [17, 18]. The gap this paper addresses is the combination of these two ideas: Pajunen

[1]Corresponding Author.
October 11, 2026

et al. [11] printed tensegrity-inspired cells under a single fabrication condition with no optimization loop, and Mo et al. [17] closed a multifidelity BO loop entirely in simulation. Among the studies reviewed here, prior work separately demonstrates physical impact testing of printed tensegrity-inspired structures, rigid-flexible additive fabrication, and Bayesian optimization of architected materials; we found no prior report combining these elements in a BO campaign over co-printed multi-material tensegrity-inspired hardware with physical impact measurements as the optimization ground truth. The campaign reported here closes the recommend, fabricate, measure, and update cycle three times over: a Sobol seed batch trains the surrogate, and each of three successive model-recommended batches was fabricated, tested under the identical protocol, and folded back into the refit that produced the next.

We emphasize one framing point at the outset: the printed PLA/TPU T_3 prism studied here is a testbed for developing and validating the closed-loop workflow, not flight hardware, and not the end of the design space we intend to search. The planetary-lander setting motivates the objectives (limit the shock delivered to a payload, limit the velocity returned to it) and the constant-mass fairness constraint, but the contribution is the loop itself: a stepping stone toward optimizing tensegrity-inspired structures generally, agnostic to the eventual application scale.

Contributions. This paper makes the following contributions:

(1) A parameterized family of multi-material 3D-printable tensegrity-inspired unit cells that uses TPU in place of the tension elements of the traditional tensegrity topology, with PLA members that carry compression most of the time (the cells are not prestressed, so neither member type acts as a pure tension or compression element; under impact some tendons stretch while others buckle). The TPU tendons are anchored *inside* the ends of each PLA strut, the strut acting as a rigid cage in which the cables meeting at a given end join before exiting through discrete outlets. This study reports the resulting printable joint geometry; pull-out strength and fatigue life remain untested and are an area of planned follow-on work. Candidate designs are compared fairly through a constant-mass projection that rescales every geometry to a common material budget before printing (Section 3.1).

(2) A characterized drop-tower protocol and objective stack for printed impact absorbers: repeated instrumented drops per article (101 stabilized captures in the seed batch, about twenty recorded drops in later batches, a reduction justified by the measured within-session variance in Section 3.3), standardized SAE J211 filtering [19], and two per-article objectives, the CFC-180 transmissibility and the velocity loss index (optimized in a mass-weighted form), each characterized for repeatability before entering the optimizer.

(3) An experiment-driven BO loop, built on BoTorch/Ax [20, 21] with a fully Bayesian sparse-prior surrogate (SAASBO) [22], that ingests the physical drop measurements, models per-print mass explicitly, and recommended each next batch of designs to fabricate. All four measured batches (35 articles) are reported here; the final Pareto front is entirely model-chosen, and the fourth batch's best-predicted design set the program attenuation record (Sections 3.4 and 4).

(4) A measured error budget for drop-tower ranking of printed articles: a second print-and-test pass of one full nine-design batch (360 additional drops) showing that article seating and print-to-print variation, not within-session scatter, set the floor for design-level claims, and the between-seat replication rule adopted in response (Section 4.2).

The completed evidence in this paper is restricted to single-cell, fixed-topology T_3-prism-inspired specimens under one *axial* drop condition; quasi-static testing is planned as an extension for future work. Off-axis and combined loading, controlled fatigue and damage-accumulation testing, multi-cell behavior, and landing-attitude variability are likewise future work (Section 5), and the novelty and generality claims above are scoped to this restricted prototype design space rather than to tensegrity-inspired absorbers in general.

The remainder of the paper is organized as follows. Section 2 reviews tensegrity mechanics, multi-material 3D printing for energy absorption, and Bayesian optimization with an emphasis on multi-objective and noise-robust acquisition functions. Section 3 introduces the design parameterization, fabrication workflow, drop-tower protocol and objectives, and BO loop, and states the planned metal-analog comparison. Section 4 reports all four measured batches, the surrogate audits, and the replication findings, and Section 5 discusses the implications and limitations of the approach. Section 6 concludes.

2 Background

2.1 Tensegrity-Inspired Architectures for Energy Absorption. Tensegrity prisms and their planar extensions exhibit softening-stiffening response under compression [3–5], characteristics desirable for impact mitigation because the structure can absorb a large fraction of the input energy at a controlled, sub-injurious force plateau. Santos [23] recently characterized a tensegrity energy-dissipation metamaterial reporting equivalent viscous damping on the order of ~23% with negligible residual strain per impact, underscoring the suitability of tensegrity-inspired architectures for repeated-impact use cases. The space program literature documents large-scale tensegrity-inspired absorbers for planetary landing [6–10] and a long history of crushable energy-absorbing landing systems [24–26]. Pajunen et al. [11] demonstrated that truncated-tetrahedral tensegrity-inspired unit cells can be directly 3D-printed and exhibit load-limiting plateaus, motivating the present focus on additively manufactured TPU/PLA composites. More recent work on dynamically loaded additively-manufactured energy-absorbing lattices [27], together with Intrigila et al.'s bistable tensegrity-like unit cell for lattice metamaterials [28] as the closest published analog, confirms that this architecture class also responds favorably under impact and quasi-static loading, although neither study employed multi-material FDM or closed-loop design optimization. Table 1 situates the present work against selected prior efforts spanning the three elements combined here (impact-tested printed tensegrity-inspired structures, rigid-flexible fabrication, and BO of architected materials), making explicit that, among the studies reviewed, no single prior study combines a multi-material FDM tensegrity-inspired architecture with an *experiment*-driven optimization loop.

2.2 Multi-Material 3D Printing of PLA/TPU Composites. Multi-material rigid-soft FDM enables stiff/compliant combinations on a single platform with tunable energy absorption, demonstrated for thick-panel origami with PLA (or ABS/CFRP) panels and TPU hinges [12] and for ABS-TPU honeycombs [13]. Neither study is itself a tensegrity, but both establish the rigid-soft co-printing route we adopt. Ye et al. [12] introduced a *wrapping-based* strategy in which rigid cores are encapsulated by continuous soft skins, reported to reduce interface delamination under cyclic loading, something we take inspiration from in our designs. Beyond these rigid-soft demonstrations, a growing body of work confirms that genuinely tensegrity-inspired architectures can be additively manufactured and exhibit programmable mechanical response. Bauer et al. [32] showed that 3D-printed tensegrity metamaterials delocalize deformation to resist catastrophic failure, while Pajunen et al. [33] tuned acoustic bandgaps in 3D-printed tensegrity-inspired lattices through pre-strain, and Sabouni-Zawadzka et al. [34] experimentally characterized 3D-printed tensegrity-inspired metamaterials built on the simplex module. More directly relevant to impact, Almeida




Fig. 1 Closed-loop, experiment-driven design framework. Parameterized PLA/TPU tensegrity-inspired unit cells are printed, characterized by repeated instrumented drop-weight impacts, and the resulting performance data drive a Gaussian-process surrogate that recommends the next batch of designs to fabricate.

et al. [29] and Davami et al. [30] characterized the high-strain-rate and dynamic response of additively manufactured tensegrity-inspired structures, and Wang et al. [31] reported an integrated fabrication-and-validation workflow for tensegrity-inspired rigid-flexible metamaterials. Collectively these studies establish the additive-manufacturability, tunability, and impact relevance of the architecture class adopted here, none combining multi-material FDM with an experiment-driven optimization loop. Recent multi-material PLA/TPU sandwich and layered composites [35] report quantitative bounds on stiffness, strength, and energy absorption for the same PLA-TPU pair used here, while FDM PLA fatigue data [36, 37] inform conservative design bounds for the rigid struts. Architected multi-material lattices with co-printed compliant skins have been explicitly designed for high specific energy absorption [38]; recent surveys catalogue the rapidly expanding additively manufactured polymeric energy-absorption literature [39, 40].

2.3 Bayesian Optimization for Architected-Material Design.

Bayesian optimization is a sequential, model-based strategy for optimizing expensive black-box functions using a Gaussian-process surrogate [41, 42]. Modern implementations such as BoTorch [20] and the Ax platform built atop it [21] support parallel batched evaluations and a wide variety of acquisition functions; recent algorithmic advances include log-EI for numerical robustness [43], noisy expected hypervolume improvement for multi-objective settings [44], input-noise-robust acquisitions [45], and evolution-guided constrained multi-objective BO for self-driving labs [46]. Mixed/categorical search spaces, needed for the planned connectivity-topology extension rather than the continuous T_3-prism prototype studied here, have dedicated treatments in BOCS [47] and the one-hot-with-rounded-kernel construction of [48]. BO has been applied to architected-material design [17] and to additive manufacturing [18]. Mo et al. [17] in particular established a multifidelity BO framework for architected materials by fusing low-fidelity simulations with high-fidelity ground truth via nonlinear information-fusion priors [49]; the present work shifts the emphasis from simulation surrogates to direct experimental data, appropriate for materials whose constitutive response is difficult to calibrate from first principles.

3 Materials and Methods

3.1 Design Parameterization. We parameterize a family of tensegrity-inspired unit cells via four groups of design variables. For the working T_3-prism prototype that defines the initial BO search space (Section 3.4), only the first two groups are active and all of their variables are *continuous*; the connectivity-topology and tiling groups are held fixed for this prototype and are listed here as planned extensions of the design family:

- **PLA compression members.** Strut diameter d_s and length ℓ_s, with the slenderness ratio ℓ_s/d_s bounded away from buckling-dominated regimes.
- **TPU tension elements.** Cross-sectional area A_t (or equivalent diameter d_t for circular cross-sections).
- **Connectivity topology (future extension).** Selected from a discrete set of candidate unit cells (e.g., truncated-tetrahedral, prism-based, and octahedral variants); when activated, the design vector would encode this as a categorical choice. It is held fixed at the T_3 prism for the present campaign.
- **Unit-cell tiling (future extension).** Number of cells $N_x \times N_y \times N_z$ and the orientation of each cell relative to the impact direction; held fixed at a single cell here.

Table 1 Positioning of this work against selected prior efforts spanning the elements combined here. The present campaign uses physical drop measurements of the transmissibility (t_{180}) and a mass-weighted form of the velocity loss index (E_{reb}, Eq. (1)) as its BO responses; it does not optimize specific energy absorption or crush energy.

Study	Architecture	Fabrication	Optimization	Response optimized	Ground truth
Pajunen et al. 2019 [11]	Truncated-tetrahedral tensegrity-inspired	Single-material 3D print	None (single condition)	n/a	Experiment (drop impact)
Intrigila et al. 2022 [28]	Bistable tensegrity-like lattice unit cell	Single-material 3D print	None	n/a	Experiment (quasi-static compr.)
Mo et al. 2023 [17]	Architected lattices	n/a (simulation)	Multifidelity BO	Simulated response metric	Simulation (+ sparse high-fid.)
Almeida 2025 [29]; Davami 2025 [30]	Tensegrity-inspired structures	Additive manufacturing	None reported	n/a	Experiment (high-rate/dynamic)
Wang et al. 2026 [31]	Tensegrity-inspired rigid-flexible metamat.	Integrated dual-material	None reported	n/a	Physical validation
This work	Tensegrity-inspired T_3-prism cell (PLA/TPU)	Multi-material FDM (PLA + TPU)	Experiment-driven BO (SAASBO/qNEHVI)	t_{180}; provisional E_{reb}	Physical experiment

Working prototype and search-space evolution. The first instance of this family used to validate the fabrication and test pipeline is a three-strut, T_3-prism-inspired cell scaled to a ~50 mm bounding box. In batches 1 and 2 the BO harness exposes five continuous design variables (base radius R, cell height H, twist angle θ, a single strut diameter d_s, and a single cable (tendon) diameter d_t) over the ranges listed in Table 2; the cable diameter d_t is treated as a *continuous* variable on $[3.0, 5.5]$ mm rather than a discrete set. From batch 3 the space grows to include the print process: two per-article sparse-infill densities (strut and tendon, each 12 to 35%) chosen by the acquisition for every article, and four filament settings (PLA and TPU nozzle temperature and maximum volumetric speed) that are physically one value per print job, so they are drawn as one quasi-random point per batch and are acknowledged as confounded with batch until a round varies them within a plate (Section 3.4). Under the prism's D_3 symmetry all struts share one diameter and all cables share one diameter, so the parameterization uses a single strut-diameter axis and a single cable-diameter axis (two member-diameter axes), leaving room to relax to per-orbit (saddle, top, bottom) or fully per-member diameters once the individual orbits have been characterized. The joint diameter d_j is held fixed at 7.0 mm rather than optimized: it sets the printed strut-end cage that houses the internal cable anchors (Section 3.2), so it is constrained primarily by the TPU-tendon outlet count and the dual-nozzle clearance rather than by energy-absorption performance, and fixing it keeps the anchor geometry constant across specimens so that the optimized variables are not confounded by joint-strength changes; relaxing d_j is deferred to a follow-on joint-design study. Figure 2 shows the parametric CAD model alongside an as-printed prototype of this working T_3 prism.

Constant-mass projection and printability screens. Because cell mass varies severalfold across the raw design box, an unconstrained search would partly reward designs for carrying more material rather than for their architecture. Every candidate is therefore projected onto a constant material budget before printing: the design is uniformly rescaled (all dimensions except the twist angle) until its mass target is met, converged to within 0.15 g on rendered geometry. The target evolved with the campaign. Batches 1 and 2 held *solid* CAD mass $\rho_{\text{PLA}} V_{\text{PLA}} + \rho_{\text{TPU}} V_{\text{TPU}}$ at $m^\star = 30.95$ g, the solid mass of the reference prism. That budget does not hold printed grams constant, because PLA struts print at partial infill while thin TPU cables print near solid. As-printed masses spanned 18.50 to 22.04 g across the tested seed articles, a coefficient of variation (CV, the standard deviation divided by the mean) of 5.5%, and 17.91 to 23.47 g (CV 8.7%) across batch 2. The abstract's "common mass" is therefore approximate for those batches, and the surrogate carries each article's weighed mass explicitly (Section 3.4). From batch 3 the projection instead holds *printed* mass at 20.23 g, the weight of the printed reference article. A calibrated model predicts each design's printed mass from its geometry, and the design is scaled until that prediction equals the target (Supplementary Information). The printed batches came in slightly light. Their mean masses were 0.2 to 0.6 g (1 to 3%) below the target, and the CV within a batch was 1.7% for batch 3 and 2.3% for batch 4.

We also checked each projected design against two printability limits. Both were recorded as warnings, and neither was used to reject or change a design. The first compares $\pi R^2 H$ with 250 cm^3, where R is the radius of the circle through the joint centers and H is the height between joint centers. The 250 cm^3 value is a placeholder size limit carried over from an earlier simulation study. It is not the printer's build volume, and because it is measured to the joint centers it undercounts the printed part. Seven printed articles (five designs) exceeded it. The second limit is a 3.0 mm minimum on the printed TPU cable diameter, adopted after the thin, unsupported top cables of early PETG test prints failed. Because the projection rescales the whole cell, a design at the 3.0 mm lower bound of the cable variable can print thinner. Nine articles printed with cables of 2.51 to 2.78 mm, including all four batch-4 articles that reduced the peak shock (Section 4.2). With hand-painted tendon supports (Section 3.2), all nine printed. One had stringing, one had a slight tendon indent, and seven had no logged defect. The most common tendon defect was a TPU strand that did not fuse to the tendon and came away from it. It was logged on five articles, all with cables of 3.28 to 4.23 mm. The 3.0 mm value is therefore a conservative rule for this workflow. Our prints do not show that thinner cables cause more defects.

As-built resolution of the continuous variables. Although d_s and d_t are treated as continuous, the as-built cross-sections are discretized by the nozzle diameter, the slicer line width, and support interaction, so the effective search granularity is coarser than the nominal continuous box. The realized member diameter therefore changes in steps set by the slicer line width, and these slicer limits set the smallest CAD change that gives a distinguishable as-built member. The 3.0 mm lower bound on the TPU cable diameter is likewise a limit of this workflow rather than of the geometry. It is the printability minimum described above, set by printing unsupported TPU cables and by the slicer's auto-support detection on this H2D printer. The as-built quantity measured for every article is its mass, weighed on a 0.01 g scale; dimensional metrology of the printed members has not yet been performed, so the geometry attached to the surrogate is the commanded post-projection geometry. Two print-to-print measurements bound the fabrication scatter: one seed design printed in triplicate has a mass standard deviation of 0.457 g, and the full reprint of the batch-3 plate produced nine design-replicate mass pairs whose second print weighed 0.27 g heavier article for article on average, a per-session flow offset rather than random scatter. Both feed the observation noise model (Section 3.4).

Table 2 Design variables for the T_3-prism campaign, as implemented in the BO harness. The seed batch is an $n = 9$ Sobol draw (fixed seed) over the five geometry variables, with each design then projected onto the constant-mass budget of the text. The process variables joined the space in batch 3: the two infill densities are acquisition-chosen per article, while the four filament settings admit one value per print job and are therefore drawn as a single quasi-random point per batch (confounded with batch until varied within a plate). The joint diameter is held fixed. All specimens print upright on a Bambu Lab H2D, with the prism axis normal to the build plate and the base triangle on the bed (Fig. 3, slicing panel). The seed batch used one specimen per named build plate, and each later batch used one nine-article plate.

Variable	Symbol	Range	Units	Active
Base radius	R	25-40	mm	batch 1 on
Cell height	H	60-110	mm	batch 1 on
Twist angle	θ	40-80	deg	batch 1 on
Strut (PLA) diameter	d_s	6.0-12.0	mm	batch 1 on
Cable (TPU) diameter	d_t	3.0-5.5	mm	batch 1 on
Strut infill density	-	12-35	%	batch 3 on
Tendon infill density	-	12-35	%	batch 3 on
PLA nozzle temperature	-	212-228	°C	batch 3 on[a]
PLA volumetric speed	-	20-30	mm^3/s	batch 3 on[a]
TPU nozzle temperature	-	235-245	°C	batch 3 on[a]
TPU volumetric speed	-	2.2-3.6	mm^3/s	batch 3 on[a]
Joint diameter (fixed)	d_j	7.0	mm	-

[a]One value per print job (a plate carries a single filament configuration), so per-batch rather than per-article.




Fig. 2 Working T_3-prism prototype. *(a)* Parametric OpenSCAD model whose base radius R, cell height H, twist angle θ, strut diameter d_s, and cable diameter d_t are the design variables of Table 2. *(b)* A representative dual-material prototype print (rigid PLA struts in white, tendon members in orange), with callouts marking the strut diameter d_s, a tendon (cable) diameter d_t, and the cell height H. The inter-plate twist θ is the relative rotation of the top and bottom node triangles, and the base radius R sets their circumradius. The photograph's wooden background was digitally replaced with a plain light backdrop. The specimen itself is unedited.

3.2 Multi-Material Fabrication.

Specimens are fabricated on a multi-material FDM printer using PLA for the rigid struts and TPU for the soft tension elements. Figure 3 summarizes the end-to-end fabrication and characterization workflow, from parametric CAD through multi-material slicing, dual-extrusion printing, post-processing, and mechanical testing. Rather than wrapping the struts in a continuous TPU skin, the current design anchors the TPU tension elements *inside* the ends of each PLA strut: the cables converging at a given strut end are joined within the strut, which acts as a rigid cage housing the junction, and the individual tendons then exit through discrete outlets. This keeps the soft-rigid interface in internal, compression-dominated pockets rather than at an exposed overmolded surface. This construction effectively inverts the material roles of Ye et al.'s soft-skin-over-rigid-core wrapping [12]: here a soft TPU core is captured within a rigid PLA shell, so we cite that work only as a multi-material co-printing precedent rather than as validation of the present junction.

Print platform and joint geometry. The working platform is a Bambu Lab H2D printer, which permits a single rigid-soft build without filament swaps. Strut endpoints are tied to cables through parametric joint geometries developed and ranked through a five-design OpenSCAD study (anchor-bulb, dovetail, TPU-sleeve overmold, eyelet-loop, and TPU-rebar variants); the working prototype uses a dovetail joint (Design B) with an anchor-bulb backup (Design A) for sensitivity studies, with a captive TPU core routed inside the PLA shell to keep the soft tendon protected from layer-line failure at the strut-to-cable transition. The full five-design comparison and the selected junction are detailed in the Supplementary Information.

Supports for soft members. Because near-vertical TPU tendons are otherwise unsupported during printing, automatic support generation is disabled and supports are painted manually in the slicer: PLA edge supports run along each tendon, with the support-to-object clearance tightened from 0.35 mm to 0.2 mm during tuning on the reference prism. Support removal left two recurring defects in the seed batch, both logged per article in the print key (Supplementary Information). One is surface stringing. The other, on two articles, is a TPU strand that did not fuse to a bottom tendon and came away during support removal. An automated alternative (a lowered support-threshold angle plus mesh-ray-cast narrowing pillars) was developed in parallel and is documented in the Supplementary Information.

Moisture and nozzle management. TPU is hygroscopic, so the soft filament is fed from a heated dry box held near 8 % relative humidity, logged per print. Midway through the seed batch the TPU extruder developed a progressive flow taper (a partial clog, compounded by a stray PLA fragment found inside the extruder); it was resolved by a cold pull and by moving the TPU to a dedicated high-flow 0.6 mm nozzle, after which print quality was restored. The affected and post-fix articles are identified in the print key so that any nozzle-related covariate can be checked against the measured objectives.

3.3 Experimental Characterization.

Drop-tower fixture. The primary characterization is repeated drop-weight impact on a Lansmont Model 23 shock test system. The printed specimen rides upright on the carriage plate, which is raised 60 in (1.524 m) along guide rails and released; the plate lands on a single 0.5 in Shore 60 OO polyurethane cushioning sheet, which shapes the landing into a single sharp base pulse of roughly 1.6 ms duration. This impact-surface configuration was selected by a blinded crossover experiment over three candidate mat arrangements, and unlike a felt stack it does not measurably compact over hundred-drop sessions. Rig health is monitored continuously through the impact velocity change Δv recovered from the base accelerometer: over an uninterrupted 100-drop characterization session the Δv coefficient of variation was 0.54% with no drift, and every campaign session is checked against the healthy tower baseline (details, including the within-session mat warm-up and recovery pattern, in the Supplementary Information). One drop takes roughly 42 s, so a seed-batch characterization completes in about ninety minutes per article and a later-batch session in about fifteen.




Fig. 3 Fabrication and characterization workflow for the multi-material tensegrity-inspired unit cells: design parameters drive parametric CAD, slicing with manually generated TPU supports, a single multi-material print on the Bambu Lab H2D, post-processing and inspection, and mechanical testing. Node photographs are representative artifacts drawn from the project's build history: the OpenSCAD T_3-prism render (CAD), the dual-nozzle Bambu Studio slice with PLA on the left extruder and TPU on the right (slicing), an in-progress H2D print of the prism batch (FDM), an as-printed specimen (post-processing), and the bungee-assisted drop-tower base plate with accelerometer (testing).

Table 3 Multi-material print parameters on the Bambu Lab H2D, transcribed from the archived as-printed Bambu Studio project (`t3-prism-bo-batch.H2D-MM-PLAstruts-TPUcables.as-printed.3mf`, Bambu Studio 2.7.1). Filaments are Bambu Lab PLA Basic (struts, support material) and Bambu Lab TPU 85A (tendons); the print profile is "0.30 mm Standard @BBL H2D 0.6 nozzle." The reporting structure follows the methods section of Ye et al. [12].

Parameter	PLA (struts)	TPU 85A (tendons)
Nozzle	0.6 mm	0.4 then 0.6 mm HF[a]
Nozzle temperature (°C)	220	220
Bed temperature, profile (°C)	55	35
Layer height / line width (mm)	0.30 / 0.62	
Infill	15% grid, 2 walls	near-solid
Outer / inner wall speed (mm/s)	200 / 300 (profile)	
Filament drying	n/a	dry box, ~8% RH
Build-plate type	Textured PEI	
Build orientation	Upright (Fig. 3)	
Supports	Manual painted tree supports, PLA	

[a]The TPU side ran a standard 0.4 mm nozzle until the mid-batch clog, then a dedicated high-flow (HF) 0.6 mm nozzle; affected articles are flagged in the print key.

Instrumentation and signal processing. A single-axis piezoelectric accelerometer on the carriage plate records the base input and triggers the acquisition; a triaxial accelerometer (Dytran 3133A4) seated in a printed pocket at the specimen's top vertex records the transmitted response. The two base-capable channels were cross-calibrated in place over fifteen co-located drops (ratio 0.953±0.001 at matched filtering), and the transducer settings are archived with the data. Signals are captured at 1.25 MHz over a 100 ms record with a 2 ms pre-trigger. All channels are low-pass filtered with the SAE J211/1 channel-frequency-class (CFC) filters [19], implemented from the standard's published coefficients with the two-pass corner frequency handled explicitly (a common implementation shortcut narrows the passband by roughly 20%, which we identified and corrected before the campaign; all reported numbers use the corrected filter). CFC-180 is the reporting class for peak metrics, with CFC-1000 retained as a higher-bandwidth diagnostic.

Per-article objectives and session protocol. Session length evolved with the campaign's understanding of its own noise, and the per-batch counts are stated here because they differ. Seed sessions recorded 103 drops per article and contribute 101 stabilized captures each (103 for one article, autv5r) after the first two drops of each session are discarded as seating warm-up. A pre-campaign variance study on the commissioning datasets put the statistical minimum at five stabilized drops after two warm-ups, and the seed sessions confirmed that the stabilized mean is insensitive to session length: within-session per-drop CVs of 0.17 to 0.48% with flat post-warm-up trends, and a replay of the seed sessions truncated to twenty drops leaves the transmissibility ranking of all eight tested articles unchanged, with a worst-case mean shift of +0.008 against design-to-design gaps of 0.007 to 0.087 and a per-drop standard error still an order of magnitude below those gaps. Later sessions were therefore shortened to about twenty drops per article: the committed record lists 21 to 22 valid captures per batch-2 article and 20 recorded drops per article in batches 3 and 4, against 101 valid captures per seed article, with the first two drops of every session discarded as before (exact per-session counts are in the archived per-drop records). The shortening cuts tower time per article from about ninety minutes to about fifteen while retaining roughly four times the minimum stabilized-drop budget; a shorter session simply enters the surrogate with a proportionally larger standard error, which the model downweights. The second print-and-test pass of batch 3 (Section 4.2) subsequently confirmed that

seating and print variation, not session length, limit what a session can claim, so the freed tower time goes to re-seats. Each session yields two objectives, each reported as a stabilized mean with the per-drop scatter quoted as one standard deviation; the standard error of the mean is what enters the surrogate's noise model (Section 3.4):

$$
\begin{aligned}
t_{180} &= \frac{\max_t \|\mathbf{a}_{\text{top}}(t)\|_{\text{CFC180}}}{\max_t |a_{\text{base}}(t)|_{\text{CFC180}}}, \\
\text{VLI} &= 1 - e_{\text{reb}}, \qquad e_{\text{reb}} = \frac{g\, t_{\text{second}}}{2\,\Delta v}, \\
E_{\text{reb}} &= (1 - \text{VLI})\, m\, g\, h,
\end{aligned}
\tag{1}
$$

where t_{180} is the CFC-180 filtered peak-acceleration ratio, which we name once here and then call the *transmissibility* throughout: the peak magnitude of the triaxial top-vertex response over the peak base input within the impact window. The term is used in the shock-testing sense standard for cushioning and packaging drop tests, a ratio of filtered peak accelerations across the article under a single transient, not the steady-state frequency-response function of vibration isolation: the two peaks need not be simultaneous, the filter class is part of the definition, and SAE J211/1 is cited only for the impact-channel filtering. Values above unity indicate the structure amplifies the peak shock reaching its top vertex; values below unity indicate attenuation. The second objective is built on the *velocity loss index* (VLI), the fraction of the impact velocity change that the structure does not give back at its top vertex. Its complement is the rebound fraction e_{reb}, the speed at which the top vertex hops after impact divided by the measured base velocity change Δv. We estimate the hop speed from the time to the second contact, t_{second}, assuming the hop is ballistic [50]. The index is dimensionless, and higher is better, the opposite of the transmissibility. Across the 44 tested articles it ranges from 0.937 to 0.986. In all four batches the optimizer minimized a mass-weighted form of the index, E_{reb}, which multiplies $1 - \text{VLI}$ by the article's weighed mass m, the gravitational acceleration g, and the drop height h to give millijoules per drop. The tables and figures report E_{reb}, since it is the quantity the optimizer used. Weighting by mass keeps grams in the objective, because equal indices on articles of different mass are not equivalent outcomes for a payload. The weighting matters most where printed mass varied. In batches 3 and 4, which held printed mass constant, ranking the articles by E_{reb} and by the index gives nearly the same order (Spearman rank correlation $\rho = 0.995$ over 27 articles). In batches 1 and 2 the two orders agree less well ($\rho = 0.855$ over 17). Two caveats apply. First, we have not yet checked the hop timing against synchronized video, and Δv is the base plate's velocity change, which may differ from the relative velocity at impact. The index is therefore a timing-based measure, and $1 - \text{VLI}$ should not be read as a coefficient of restitution. Second, returned kinetic energy would scale with the *square* of a velocity ratio, so E_{reb} is a ranking score that penalizes designs, and grams, that send more motion back to the payload. It is not a measured energy. Once the hop timing is validated, the index could become a constraint rather than an objective (Section 5). Ringdown descriptors (the fitted natural frequency f_n, 260 to 470 Hz for every article but one batch-4 design that rings at 764 Hz, and, where the exponential fit passes an $r^2 \geq 0.85$ gate, a damping ratio ζ) are recorded per drop as print-health and prestress diagnostics [51] but are not campaign objectives. The within-session per-drop CV of t_{180} spans 0.06 to 2.0% across the campaign's 35 articles (0.17 to 0.48% in the seed batch). These values describe repeated drops of the same physical article in one seating and do not estimate print-to-print or seating-to-seating repeatability; serial dependence among drops may also make $s/\sqrt{n_{\text{drops}}}$ optimistic. Two replication measurements bound what a single session can claim: the seed attenuator re-measured across a day and an independent re-seat agreed to 0.13%, while a full second print-and-test pass of the batch-3 plate showed same-design shifts with a median of +1.2% and heavy tails (Section 4.2). The campaign therefore adopted a between-seat replication rule: a single-seating value that would drive a decision (a batch extreme, a claimed attenuator, a front membership) requires confirmation on an independent re-seat before it is treated as a design property. A mechanism-oriented trace figure (processed deceleration response with event markers keyed to synchronized video frames) will be generated from archived campaign captures once the event labels can be supported by synchronized measurements; no such figure is shown here because none of the required event synchronization has yet been performed.

Planned quasi-static extension. The drop test loads the specimens in their elastic regime (the crush lasts 1 to 3 ms and the article recovers), so crush-energy metrics such as specific energy absorption (SEA) and compaction efficiency are not recoverable from these captures by any reprocessing. A quasi-static compression campaign on a benchtop load frame (BYU CB 123 Instron, with a low-range load cell appropriate to the expected cell stiffness) is planned to supply the complementary crush metrics

$$
\text{SEA} = \frac{1}{m}\int_0^{\delta_d} F(\delta)\,\mathrm{d}\delta, \qquad \eta_c = \frac{\int_0^{\delta_d} F(\delta)\,\mathrm{d}\delta}{F_{\max}\,\delta_d},
\tag{2}
$$

with the densification displacement δ_d taken at the maximum of the energy-absorption efficiency curve and $F_{\max}$ the peak force within $[0, \delta_d]$, following the canonical cellular-solid treatments [52–55] and mirroring the quasi-static protocol of Pajunen et al. [11]. These metrics are reported as a complementary characterization of selected designs rather than as objectives of the drop-tower campaign. Slip resistance and traction at the specimen-to-floor interface, governed by the tip geometry rather than the internal architecture, follow ISO 11334-4 [56] for walking-aid tips and are out of scope for the present axial-impact study.

Complementary data streams. High-speed video (959 fps, three clips per specimen) supplements the accelerometer data. The camera cannot resolve the millisecond-scale impact pulse (one to two frames), so the division of labor is explicit: the accelerometer channels produce the objectives, and video documents the post-impact rebound and recovery. Synchronized laser-Doppler vibrometry is reserved for follow-up characterization of selected designs.

3.4 Experiment-Driven Bayesian Optimization Loop. The optimization loop maintains a Gaussian-process (GP) surrogate over the design space defined in Section 3.1. After each round of physical experiments, the surrogate is refit and an acquisition function is maximized to recommend the next batch of designs to fabricate. The campaign is posed as a two-objective minimization: simultaneously minimize the transmissibility t_{180} and the mass-weighted velocity-loss objective E_{reb} of Eq. (1) (equivalently, favor a high velocity loss index on a light article). Both objectives serve the same payload: t_{180} bounds the peak shock it feels during the impact, and E_{reb} penalizes the motion thrown back into it afterward. The seed data showed an apparent trade-off driven substantially by the single strongest attenuator, not statistically resolved at seven mapped articles (Spearman $\rho = -0.39$, $p = 0.38$; Section 5); the measured front after four batches is nondegenerate (its members span both axes), and the velocity loss index remains a candidate to become a constraint once its ballistic reading is validated. Implementation uses the Ax platform [21] over BoTorch [20], with noisy expected hypervolume improvement (qNEHVI) [44] as the multi-objective acquisition. The T_3-prism search space is fully continuous, including the process variables added in batch 3 (Table 2), so no categorical encoding is required; the mixed-search-space constructions of [48] and the BOCS combinatorial baseline [47] remain the route for the future connectivity-topology categorical

rather than part of the current loop. The input-noise-robust acquisition of Daulton et al. [45] and the evolution-guided constrained variant of Low et al. [46] are held in reserve as contingencies.

Surrogate and noise model. The surrogate is the fully Bayesian sparse axis-aligned subspace model (SAASBO) [22]: a Matérn-5/2 kernel with automatic relevance determination whose length scales carry strong sparsity-inducing priors and are marginalized by Markov-chain Monte Carlo (NUTS) rather than point-estimated; every refit in the campaign, through the batch-4 ingestion, uses this model with qNEHVI on top (Ax 0.4 for the early rounds, Ax 0.5.0 from the batch-3 refit). We retain SAASBO even though the dimensionality is modest because marginalizing the hyperparameters tends to improve uncertainty quantification at the very small sample sizes of physical campaigns; the fitted model is audited each round with cross-validation (leave-one-out, and leave-one-design-out once replicates entered the record) and length-scale-based sensitivity diagnostics (Section 4). Inputs are normalized to the unit cube and outputs standardized. Observation noise is supplied per observation as a fixed variance: for t_{180} the squared standard error of the stabilized mean, $\sigma_t^2 = s_{\text{drop}}^2/n_{\text{drops}}$, and for E_{reb} the drop-scatter term plus the propagated print-to-print mass scatter, $\sigma_E^2 = \sigma_{E,\text{drops}}^2 + (\partial E_{\text{reb}}/\partial m)^2\sigma_m^2$ with $\sigma_m = 0.457\,\text{g}$ measured from the one design printed in triplicate; a shorter session enters with a proportionally larger standard error. The estimand this noise model implies is the response of the tested article in its seating, not of a freshly printed article at the same design: an independent adversarial review (Section 5) argued the decision-relevant target is the latter, and the campaign's response is the measured replication evidence of Section 4.2 (a full second print-and-test pass of one batch) together with the between-seat replication rule, rather than an inflated per-article noise term. Once the lab confirmed that second pass as article-level re-prints of the same designs, its nine articles were ingested as distinct completed trials at identical design coordinates, each with its own weighed mass and per-session standard error and with no pre-pooling, so refits from that point observe measured design-level replicates directly. Because per-session variances are supplied as known, replicate disagreement is not absorbed by a separately inferred noise parameter; it widens the posterior through the fit itself. SAASBO is the prespecified surrogate; we make no claim that it outperforms a standard single-task GP at this dimensionality and sample size, and the planned head-to-head calibration comparison against a point-estimated GP with the same kernel remains future work.

Mass treatment. Because the constant *solid*-mass projection of batches 1 and 2 does not hold printed grams constant (Section 3.1), printed mass correlates with the shape variables in the seed batch ($r = 0.83$, $n = 7$, dominated by the lightest article, against t_{180}). The loop therefore keeps mass explicit. The second objective, E_{reb}, is in absolute millijoules computed with each article's weighed mass, so added grams are penalized through the motion they send back to the payload. The transmissibility t_{180} stays a ratio on purpose, because payload peak acceleration is a damage criterion that does not scale with specimen mass. The objective surrogates take the design coordinates of Table 2 as their inputs; printed mass is attached as a separately modeled *tracking metric*, so the model learns as-printed mass as a function of the design coordinates and every recommendation reports a predicted printed mass (the diagnostic refit behind Fig. 8 additionally includes printed mass as an input, precisely to probe this confound). The calibrated printed-mass model (Supplementary Information) then let batches 3 and 4 hold *printed* grams constant. Across all 44 tested articles, printed mass explains about 1% of the variance in transmissibility ($r = 0.12$), so the seed batch's mass confound was removed by the experimental design rather than adjusted away in the analysis (Section 4.3).

Budget and seeding. The seed batch is an $n = 9$ Sobol draw with a recorded seed over the five-variable box, printed together with the fixed reference prism (S0). Optimization proceeds in sequential batches of $q = 9$ prints, sized to one build-plate generation cycle. Three model-recommended batches are reported here (Ax trials 10 to 18, 28 to 36, and 37 to 45; the numbering gap records a superseded draft batch that was regenerated, before printing, when the batch-level filament handling was simplified). From batch 3 the four filament settings take one quasi-random point per batch, formally the settings of that batch's best-predicted article, so those axes are confounded with batch and are reported as unidentified rather than learned. All random seeds, the full experiment state, and the recommendation tables are recorded per round; full computational reproducibility (the exact processing pipeline and model settings) is carried by the campaign code, whose archival release is a declared submission gate rather than a solved item. Escalation to trust-region BO (TuRBO) [57] is planned only if per-member-diameter extensions push the design space well beyond the present regime; a single-objective log-Expected-Improvement run [43] on t_{180} is retained as a baseline for quantifying the benefit of the multi-objective formulation. The campaign code and recommended batches will be archived at a Zenodo-minted DOI mirroring the GitHub repository.

3.5 Replicate Rank-Stability Study. The batch-3 second pass (Section 4.2) showed that a single article's measurement can move between seatings and prints by more than the design signal separating neighboring articles, which bounds any claim that one design outranks another. A planned replicate study formalizes that bound by re-printing a deliberately spread subset of the already-measured designs. Among the campaign's in-sample designs, ranked by the current posterior's predictions, we will select the best-predicted design, the worst-predicted design, and one mid-pack ("run-of-the-mill") design, then print a nominal three fresh articles of each (the repeat count, provisionally three, will be fixed when the print is scheduled) and drop-test every article under the standard protocol of Section 3.3, including the between-seat replication rule. The question is whether the predicted ordering survives fabrication and seating variation. With three designs the exact permutation floor for a Spearman rank correlation is $p = 1/6$, so no significance claim is available at this size; the primary readout is instead the separation of the three designs' repeat clusters relative to the within-design (print-to-print plus seat-to-seat) scatter, reported alongside ρ_s between the predicted and measured orderings of each repeat. Clean separation would support treating the campaign's rankings as design properties; overlapping clusters would localize the ranking noise floor that the batch-3 second pass could only bound. The reporting format is specified in Table 4; entries and design IDs will be added once the repeat articles are printed and tested.

Table 4 ***Placeholder (data pending).*** **Planned replicate rank-stability study: the best-, mid-, and worst-predicted in-sample designs, each re-printed as a nominal three fresh articles and drop-tested under the standard protocol. Entries will record each repeat's stabilized t_{180}, the within-design scatter, and the measured rank of each design's repeat cluster against its predicted rank.**

Tier	Design	Pred. t_{180}	t_{180} (repeats 1 / 2 / 3)	
Best	*TBD*	-	- -	-
Mid	*TBD*	-	- -	-
Worst	*TBD*	-	- -	-

3.6 Metal-Analog Validation. In the future we plan a validation campaign that tests whether the rankings learned on the printed PLA/TPU specimens generalize beyond the as-printed polymer system, by reproducing a subset of the T_3-prism designs as *metal*

analogs built from hollow aluminum rods (compression members) and stainless-steel threaded cables (tension members), using the same R, H, θ, and member-diameter parameterization. Rather than fabricating only the top-ranked geometries, we deliberately span the predicted performance range: a few designs the surrogate predicts to be *worst*-performing, a few *mediocre*, and a few *best*-performing are each built in both material systems. Comparing the measured ordering of the PLA/TPU specimens against their hollow-aluminum/stainless-steel counterparts probes whether both systems preserve the same rank ordering of impact performance. We treat this as a *planned, exploratory* comparison rather than a preregistered validation: the deformation modes, joint compliance, friction, pretension behavior, and strain-rate sensitivity all differ between the PLA/TPU and aluminum/steel systems, so agreement is not expected a priori, and the protocol details that would let the comparison distinguish geometric rank transfer from material-system and mass confounds (aluminum alloy and temper, tube wall thickness, cable construction, joint hardware and torque, article and payload masses, replicate count, and tie-handling rules) remain to be fixed and will be tabulated before any metal article is built. The intended rank statistic is the Spearman rank-correlation coefficient ρ_s between the two material systems' orderings of the primary campaign metric (t_{180} under the identical drop protocol), reported with an exact permutation test, with the velocity loss index and, once the quasi-static extension runs, SEA reported as secondary rankings. Rank agreement would be preliminary evidence consistent with transfer; disagreement would not isolate which material or joint difference caused the change. The planned reporting format is specified in Table 5; the table entries and the specimen photographs of Fig. 4 will be added after fabrication and testing.

Table 5 ***Placeholder (data pending).*** **Planned rank-ordering validation: representative T_3-prism designs predicted to be worst-, mid-, and best-performing, each fabricated as a printed PLA/TPU specimen and as a hollow-aluminum-rod / stainless-steel-cable metal analog. Entries record the measured performance metric (t_{180} under the identical drop protocol, with the velocity loss index secondary) and the resulting rank within each material system; rank agreement would be preliminary evidence consistent with transfer, while disagreement would not isolate which material or joint difference caused the change.**

Predicted tier	Design ID	PLA/TPU (rank)	Al/SS (rank)
Worst	*D-w1*	-	-
Worst	*D-w2*	-	-
Mediocre	*D-m1*	-	-
Mediocre	*D-m2*	-	-
Best	*D-b1*	-	-
Best	*D-b2*	-	-

4 Results

4.1 Seed-Batch Measurements. All nine Sobol specimens and the reference prism were printed and declared acceptable to test. Nine articles (seven mapped Sobol designs, the reference prism, and one article whose design mapping is unconfirmed) completed seed characterization sessions, totaling over 900 clean captures within a project-wide history of more than 4,000 instrumented drops; the two remaining seed designs (specs 03 and 06) were printed, but their drop sessions are absent from the campaign record and they do not enter any fit or figure. Table 6 reports the stabilized objectives. Three findings frame the batch. First, the measured t_{180} spans 0.893 to 1.062: six of nine tested articles *amplify* the peak shock reaching the top vertex (means above unity), two sit marginally below unity (0.997 and 0.980), and one tested article (the print of Sobol spec 01, the thick-strut, thin-cable, high-twist corner of the batch) had a mean t_{180} of 0.893, indicating peak attenuation under the tested condition. This article's attenuation later reproduced across an independent re-seat to 0.13%, the campaign's positive control for the replication rule of Section 3.3. Across the tested articles, t_{180} spans 0.169 (18.9% of the observed minimum). This between-article range far exceeds the 0.17 to 0.48% within-session per-drop CV, but one mechanically tested article per geometry does not permit separation of geometry effects from print-to-print variation or other fabrication covariates. Second, the objectives show an apparent trade-off in this sample. The best attenuator has the lowest velocity loss index of the batch (0.950, and the largest E_{reb}, 13.9 mJ per drop), so the observed front is nondegenerate. The trade-off rests largely on that single article, though, and is not statistically resolved at this sample size (Section 5). Third, among the eight mapped articles with weighed masses, printed mass and t_{180} showed a large sample correlation ($r = 0.82$, $n = 8$). The association is confounded with the design coordinates and is highly sensitive to the lightest article ($r = 0.26$ when 6lhxfy is omitted); it is not evidence of a causal mass effect. It nonetheless motivated the mass-aware objective formulation of Section 3.4, and the constant-printed-mass batches later broke the confound outright (Section 4.3). Figure 5 renders the seed geometries to a common scale, showing how widely the constant-mass box spans aspect ratio, member sizing, and twist.

Figure placeholder: Assembled validation specimens for each predicted performance tier (worst / mediocre / best), shown as printed PLA/TPU builds alongside their hollow-aluminum-rod and stainless-steel-threaded-cable metal analogs, with callouts marking the aluminum compression members, the threaded steel tension cables, and the strut-end cable anchors. Photographs to be added once the specimens are fabricated.

Fig. 4 ***Placeholder.*** **Assembled validation specimens for each predicted performance tier (worst / mediocre / best), shown as printed PLA/TPU builds alongside their hollow-aluminum-rod and stainless-steel-threaded-cable metal analogs, with callouts marking the aluminum compression members, the threaded steel tension cables, and the strut-end cable anchors. Photographs to be added once the specimens are fabricated.**




Fig. 5 The nine seed geometries rendered to a common millimeter scale (rigid PLA struts in black, TPU tendons in orange). Every rendering corresponds to a physically printed article in the seed campaign.

4.2 Model-Recommended Batches and Replication. Table 8 reports the stabilized objectives for the three model-recommended batches, and Fig. 6 overlays every measured article with the non-dominated front after each batch (Pareto membership is evaluated over articles with both objectives; the unmapped seed article amdjwm is omitted because its missing weighed mass

Table 6 Seed-batch drop-tower results: 101 stabilized captures per article (103 for autv5r) at 60 in onto the standardized polyurethane surface, CFC-180 filtering, counted after the first two warm-up drops of each session were discarded. Means ± one standard deviation over the stabilized drops; rows are ordered by t_{180}. E_{reb} uses each article's weighed mass per Eq. (1). The ringdown frequency f_n is a print-health descriptor, not an objective. A dash denotes a quantity that cannot be computed from the available record: article *amdjwm* lacks a weighed mass and a confirmed design mapping (it is excluded from the surrogate fit and from all mass-dependent quantities), and no accepted f_n estimate is available for *bag26v* or *ajhby6*. Specs 03 and 06 were printed but have no drop sessions in the campaign record.

Design	Article	Mass (g)	t_{180}	E_{reb} (mJ)	f_n (Hz)
Spec 01	6lhxfy	18.50	0.8931 ± 0.0042	13.9	368
(unmapped)	amdjwm	-	0.9805 ± 0.0025	-	455
Spec 05	6nheas	21.73	0.9970 ± 0.0032	13.1	322
S0 ref.	bpx68c	20.23	1.0111 ± 0.0024	6.2	468
Spec 07	ajhby6	20.53	1.0127 ± 0.0038	6.1	-
Spec 00	9hhbkp	21.62	1.0183 ± 0.0017	6.9	364
Spec 04	nvxsrv	20.66	1.0275 ± 0.0044	8.2	294
Spec 02	autv5r	22.04	1.0404 ± 0.0035	8.8	386
Spec 08	bag26v	21.42	1.0616 ± 0.0051	7.7	-

prevents computing E_{reb}). Dominated hypervolume, evaluated at the fixed reference point $(t_{180}, E_{reb}) = (1.35, 15\,\text{mJ})$, grew from 3.155 after the seed batch to 3.969 after batch 2 (+25.8%), 4.007 after batch 3 (+0.9%), and 5.195 after batch 4 (+29.7%): a 65% total gain over the seed front. No budget-matched quasi-random physical baseline has been run, so the comparison the data support is against the campaign's own Sobol seed: after batch 4, every member of the combined front (corny7, corny6, drran5, drran3, r2d2c6) is a model-recommended design, and the last seed article left the front when the batch-4 record dominated it outright. These fronts score every article as measured, repeated designs at their first prints. Collapsing the batch-3 repeat pairs to their design means (Table 7) removes drran5 and drran3 from the final front, whose design-mean membership becomes corny7, corny6, r2d2c2, corny4, and r2d2c6, still entirely model-recommended, with r2d2c2's membership provisional on its drift flag; batch 3's +0.9% should accordingly be read as an upper bound on a gain that was partly print luck.

Batch 2 (Ax trials 10 to 18). The first recommended batch was generated from the seed fit and printed under the constant-solid-mass projection, so its printed masses still spread widely (17.91 to 23.47 g; a regenerated constant-printed-mass recommendation set is archived alongside the as-printed one, and the two must not be conflated). The batch grew the front almost entirely on the velocity-loss axis, and four batch-2 articles joined the front. Article r2d2c6 still holds the lowest E_{reb} on record, 4.1 mJ per drop, and its velocity loss index of 0.986 ties two later articles (drran3 and corny4) for the highest. On the transmissibility axis the batch humbled its own forecasts: the archived posterior predictions sat below the measurements for nine of nine articles (mean absolute percentage error 14.4%; worst case r2d2c3, predicted 0.910, measured 1.334, the strongest amplifier in the campaign record). That nine-of-nine optimism widened the refit posterior for every batch that followed.

Batch 3 (Ax trials 28 to 36). The first batch at constant *printed* mass (19.24 to 20.06 g, CV 1.7%) and the first with the infill and filament axes active (Section 3.1). It filled the knee of the front rather than growing the box (+0.9% hypervolume; three articles joined), and the recalibrated posterior held: eight of nine articles measured within 0.3 posterior standard deviations of their predictions (MAPE 3.8%). The batch also delivered the campaign's sharpest single surprise in both directions: the best-predicted design (trial 32, predicted 1.020) measured 1.251, the strongest amplification then on record, while the batch's only attenuator (drran8, 0.980, drift-flagged, provisional) was its only twisted design.

Batch 4 (Ax trials 37 to 45). The acquisition split the batch between the wide, high-twist, thin-cable family it had been steering toward since batch 2 and a previously unvisited tall, low-twist corner. The wide family delivered: four of nine articles attenuate, and corny7, the batch's best-predicted design (trial 37, predicted 0.934 ± 0.13), measured $t_{180} = 0.8031 \pm 0.0025$, the strongest attenuation in the program, 10% below the best seed article and 21% below the reference prism. Its velocity loss index, 0.968 (E_{reb} = 9.4 mJ per drop), is mid-pack, and it dominates the seed attenuator on both objectives (Fig. 7). Within the attenuating family the frozen predictions ranked the four measurements perfectly (Spearman $\rho = +1.0$; 0.82 across all nine, where the five amplifier predictions span only 0.9% and so carry no ordering signal), batch MAPE was 6.0%, and no article left its predictive band by more than one standard deviation (the record itself beat its band by 1.0 standard deviation in the good direction). Per the between-seat replication rule, the batch-4 attenuation values, including the record, are single-seating measurements whose re-seat confirmations are scheduled; one session (corny5) carries a drift flag and its mean is provisional, and another (corny6) was erratic (per-drop CV 2.0%) but attenuates under any reading of its record.

Replication: a second pass of batch 3. The batch-3 plate was printed a second time and the second set was drop-tested under the identical protocol, 360 drops across the two passes. The lab record confirms the second set as design-level re-prints of the first, article for article (2dran*N* re-prints drran*N* at the same Ax trial, per the round-3 print key), so the nine pairs of Table 7 compare directly, the reprint weighing 0.27 g heavier on average. Neither extreme of the first pass recurred: the design that measured 1.2513 (drran7, then the strongest amplification on record) re-measured 1.0286, a 17.8% drop, and the 0.9804 attenuator (drran8) re-measured 1.0109, so batch 3 contains no reproducibly attenuating design. Eight of the nine same-design transmissibility shifts are upward, with median +2.2%, and three of nine fall inside the previously characterized ±2.2% re-seat envelope. E_{reb} repeats far less well between prints than transmissibility does. Same-design E_{reb} pairs span ratios of 0.38 to 2.9 (5.2 mJ against 15.1 mJ at trial 30), although one pair repeats to 0.2%. The reprint sessions ran on a settled seat at slightly lower arrest velocity, so session state and print variation are confounded in the systematic upward shift; after removing it, the residual print-to-print standard deviation in t_{180} is about 0.013 per article, an order of magnitude above the within-session standard errors near 0.001 that the fit ingests, and the E_{reb} pairs order their nine designs with rank correlation −0.18. The two passes cannot separate seating effects from print-to-print differences, but the methodological conclusion does not depend on that split: the 1.2513 session had passed every within-session stability check (per-drop CV 0.77%, no drift), so *within-session*

stability does not certify a measurement as a design property. The between-seat replication rule of Section 3.3 was adopted in response, the seed attenuator's 0.13% agreement across an independent re-seat shows that genuine attenuation does reproduce, and a broadband seat gauge (the ratio of CFC-1000 to CFC-180 transmissibility; healthy sessions read 1.00 to 1.07) now accompanies the rule as an advisory: every large same-design shift observed so far carried a gauge reading of at least 1.15 in one of its seatings, and all four batch-4 attenuators gauge healthy (0.98 to 1.06). With the pairing confirmed, the nine reprint articles also join the surrogate's training set as distinct observations at identical design coordinates (Section 3.4), so later refits observe measured design-level replicates directly rather than carrying the replication evidence only as an interpretation bound.

Table 7 Batch-3 print-pair repeatability: each design's first print (drran) against its confirmed re-print (2dran), stabilized values under the protocol of Table 6. Δ is the reprint's relative t_{180} shift, and E_{reb} pairs are given as first → reprint. Two sessions carry the transmissibility-drift flag: the first print of trial 35 (drran8, flagged in Table 8) and the re-print of trial 34 (2dran6); their means are provisional.

Trial	Pair	t_{180} 1st	t_{180} 2nd	Δ (%)	E_{reb} (mJ)
28	drran5/2dran5	1.0373	1.0604	2.2	5.0 → 5.0
29	drran4/2dran4	1.0344	1.0433	0.9	9.1 → 11.2
30	drran9/2dran9	1.0425	1.0451	0.3	5.2 → 15.1
31	drran3/2dran3	1.0389	1.0533	1.4	4.2 → 9.4
32	drran7/2dran7	1.2513	1.0286	−17.8	8.2 → 11.6
33	drran2/2dran2	1.0345	1.0900	5.4	11.8 → 4.5
34	drran6/2dran6	1.0471	1.0859	3.7	4.8 → 7.7
35	drran8/2dran8	0.9804	1.0109	3.1	11.2 → 9.9
36	drran1/2dran1	1.0326	1.0791	4.5	18.1 → 7.3

4.3 Surrogate Audits Across the Campaign. Each refit is audited with leave-one-out cross-validation (LOOCV; one full NUTS refit per held-out article) and length-scale diagnostics. Figure 8 reports the seed-state SAASBO feature importances (normalized inverse length scales, median over the Monte Carlo draws with interquartile whiskers, over the five design variables plus printed mass). At seven observations for six correlated inputs these are prior-sensitive model diagnostics only: no input separates decisively from the equal-share line, and none supports a claim of variable relevance or ranking.

The honest headline of the cross-validation trajectory is that held-out point accuracy *declined* as the campaign grew: t_{180} LOOCV MAPE was 2.9% with rank correlation +0.76 on the seed state (8 articles, 6 model inputs), 5.4% and +0.60 after batch 2 (17 articles), and 6.2% and +0.19 after batch 3 (26 articles, 12 inputs); the E_{reb} channel reads 29.3%, 23.6%, and 32.2% MAPE at the same states (the fold-level records are archived with the campaign data). Three changes landed together and are confounded: the input space doubled from 6 to 12 while the data grew only from 17 to 26, four of the six added axes carry a single value per batch and are therefore perfectly confounded with batch, and batch 3 itself added the campaign's largest outliers. The held-out posterior shrinks predictions toward the pooled mean, so the campaign's defining extremes are exactly what it misses. The practical stance this trajectory dictates, and the one the campaign took, is to treat predicted columns as exploration bookkeeping rather than forecasts: batch 4's value was the design family it selected and the record it found, not its point accuracy, and its best-predicted article was the record.

Plain LOOCV also leaks once replicates exist: hold out one print of a repeated design and its twin remains in training at nearly identical coordinates, so the fold tests interpolation rather than prediction. Re-auditing the full record with leave-one-design-out folds (35 folds over 44 articles, each drran/2dran pair held out together, one full NUTS refit per fold) gives the campaign's most honest held-out numbers (Fig. 9): t_{180} MAPE 5.0% with rank correlation +0.08, the held-out posterior hugging the pooled mean while the measurements span 0.80 to 1.33, and E_{reb} MAPE 39.4% with rank correlation −0.38. Held-out design-level t_{180} skill is therefore near zero, and the apparent E_{reb} skill of the earlier states was partly the model predicting print luck, the model-side counterpart of the 0.38 to 2.9 pair ratios of Table 7. The comparison to the LOOCV trajectory is descriptive rather than a controlled ablation: the states differ in article count, fold structure, and the presence of the repeat data itself.

Two further audit facts round out the picture. The correlation between printed mass and transmissibility fell from $r = 0.82$ over the eight seed articles to 0.12 over all 44 tested articles ($r^2 = 0.01$), so the constant-printed-mass projection removed the seed batch's main confound. Within batch 4 alone the two correlate strongly ($r = 0.85$). There, however, the wide, high-twist family printed at 19.45 to 19.64 g and the tall, low-twist family at 20.15 to 20.58 g, so printed mass follows the design family. The correlation within the batch therefore cannot be read as a mass effect. And the planned head-to-head calibration comparison against a point-estimated single-task GP with the same kernel has not yet been run, so no claim is made that SAASBO outperforms it here.

Studies pending. The re-seat confirmations of the batch-4 attenuators (the record article first), any batches beyond the fourth (a fifth batch is generated, regenerated once the reprint pass entered the fit, and staged for printing, but nothing from it appears here), the replicate rank-stability study of Section 3.5 (best-, mid-, and worst-predicted in-sample designs re-printed in nominal triplicate), the quasi-static crush campaign, and the metal-analog comparison (Table 5) remain future work; none of their values appear in this section.

5 Discussion

What the campaign establishes. The four measured batches settle four questions the planned-methods stage could only pose. The end-to-end loop runs and closes, repeatedly: printed articles, instrumented characterizations, a fitted fully Bayesian surrogate, and three successive model-recommended batches whose own measurements fed the next refit. The measurement distinguishes the tested articles: the campaign t_{180} means span 0.803 to 1.334, far beyond within-session drop scatter, though the batch-3 second pass shows that seating and print variation, not drop scatter, set the resolution floor for any single article. The physics is more adversarial than the cushioning intuition suggests: at this scale and rate, most printed prisms *amplify* the peak shock reaching their top vertex (26 of 35 articles measured above unity), which sharpened the campaign question from "how much does the architecture cushion" to "which corner of the design space crosses into attenuation, and at what cost to the velocity loss index." And the batches answered that sharpened question, though not on the first try: batch 2's forecasts were optimistic on nine of nine articles, batch 3's best-predicted design was its worst amplifier, and batch 4 then delivered four attenuators from the wide, high-twist, thin-cable family, led by its best-predicted design at $t_{180} = 0.803$. The strongest attenuators still tend to have low velocity loss indices (0.938 and 0.940 for corny9 and corny8), and the record article is mid-pack at 0.968. The tall batch-4 family reaches an index as high as 0.986 at a transmissibility near unity, so the front remains two-dimensional.

Honest accounting of the objective stack. We pre-registered an adversarial, data-first review of the objective choices with an external AI referee that was required to commit to its own objective set from the raw campaign files before reading ours. Its findings temper the round-1 formulation and set the round-3 revision: the rebound fraction e_{reb} rests on a ballistic interpretation of the second contact event that has not yet been validated against synchronized

Table 8 Model-recommended batch results under the protocol and reporting conventions of Table 6 (CFC-180, stabilized means ± one standard deviation; about twenty drops per article against the seed batch's 101, with exact per-session counts in the archived per-drop records; rows ordered by t_{180} within each batch). E_{reb} uses each article's weighed mass per Eq. (1). "Pred." is the posterior-mean t_{180} archived when the batch was recommended, before any of its articles were tested. Batch-2 articles were projected to constant solid mass; batches 3 and 4 to constant printed mass (20.23 g). Flags follow the session record: † marks a transmissibility-drift-flagged session whose mean is provisional, and ‡ marks the erratic corny6 session (per-drop CV 2.0%).

Batch	Article	Trial	Mass (g)	t_{180}	E_{reb} (mJ)	Pred. t_{180}
2	r2d2c7	15	18.51	0.9484 ± 0.0008	12.2	0.905
2	r2d2c1	13	19.38	0.9942 ± 0.0021	6.0	0.948
2	r2d2c2†	12	17.96	1.0411 ± 0.0154	5.6	0.926
2	r2d2c9	10	17.91	1.0530 ± 0.0035	5.8	0.873
2	r2d2c6	14	19.11	1.0548 ± 0.0042	4.1	0.953
2	r2d2c8	17	19.98	1.0704 ± 0.0116	7.9	0.955
2	r2d2c5	18	23.47	1.1516 ± 0.0040	6.7	0.987
2	r2d2c4	11	19.33	1.1847 ± 0.0076	6.4	0.885
2	r2d2c3	16	18.63	1.3337 ± 0.0117	5.6	0.910
3	drran8†	35	19.32	0.9804 ± 0.0051	11.2	1.039
3	drran1	36	19.31	1.0326 ± 0.0016	18.1	1.051
3	drran4	29	19.92	1.0344 ± 0.0017	9.1	1.032
3	drran2	33	19.33	1.0345 ± 0.0006	11.8	1.056
3	drran5	28	19.88	1.0373 ± 0.0024	5.0	1.059
3	drran3	31	19.92	1.0389 ± 0.0012	4.2	1.043
3	drran9	30	19.34	1.0425 ± 0.0009	5.2	1.058
3	drran6	34	19.24	1.0471 ± 0.0040	4.8	1.065
3	drran7	32	20.06	1.2513 ± 0.0096	8.2	1.020
4	corny7	37	19.62	0.8031 ± 0.0025	9.4	0.934
4	corny9	43	19.46	0.8766 ± 0.0036	18.1	0.942
4	corny6‡	41	19.45	0.9106 ± 0.0181	5.7	0.943
4	corny8	39	19.64	0.9535 ± 0.0025	17.5	0.954
4	corny1	42	20.20	1.0459 ± 0.0029	8.7	1.010
4	corny4	44	20.56	1.0475 ± 0.0025	4.3	1.013
4	corny3	45	20.15	1.0705 ± 0.0013	8.8	1.004
4	corny2	38	20.21	1.0846 ± 0.0030	9.2	1.008
4	corny5†	40	20.58	1.0876 ± 0.0099	8.5	1.012

video (a restrained-versus-unrestrained check is scheduled); the apparent t_{180}-versus-E_{reb} trade-off is driven substantially by the single strongest attenuator (Spearman $\rho = -0.39$, $p = 0.38$ across the reliable articles); and per-drop standard errors are substantially smaller than the between-article variation, and therefore understate design-level uncertainty. The campaign's responses were physical rather than statistical: the batch-3 plate was printed and tested twice, which measured the same-design shift distribution directly (median +2.2% under the confirmed pairing, with a −17.8% tail; Section 4.2) and confirmed the understatement at an order of magnitude in t_{180}; the between-seat replication rule now gates every extreme; the velocity loss index stays a candidate constraint pending its ballistic validation; and the constant-printed-mass projection removed the mass channel the review flagged. We report this trajectory rather than presenting the seed-state choices as final because the loop is the contribution and revising objectives mid-campaign, with the revision criteria stated in advance, is how such loops behave in practice.

Mass as a confound and as a design variable. Holding solid CAD mass constant did not hold printed grams constant: PLA prints at partial infill while thin TPU cables print near solid, so the seed articles span 18.50 to 22.29 g, and among the mapped seed articles mass and t_{180} are correlated ($r = 0.82$). Printed mass is itself induced by the geometry and is strongly collinear with member dimensions (light articles *are* the thick-strut, thin-cable corner by construction), so the seed observations cannot identify separate geometry and mass effects; a post hoc mass-adjusted regression would be unstable and would estimate a different, direct-effect quantity. The campaign's answer was experimental design rather than adjustment: the calibrated printed-mass model (Supplementary Information) let batches 3 and 4 compare geometries at fixed printed grams (batch mass CVs of 1.7 and 2.3%). Over all 44 tested articles, mass and transmissibility are nearly uncorrelated ($r = 0.12$). The confound was broken by construction, and E_{reb} keeps grams penalized where they matter physically, in the motion returned to the payload.

Relation to prior art, and why simulation sits outside the loop. Relative to Pajunen et al. [11], the present work varies the geometry under an optimization loop rather than characterizing a single fabrication condition; relative to Mo et al. [17], the loop's ground truth is physical measurement, and no simulated number enters the objectives, the acquisition, or candidate priority. That exclusion is a measured decision, not an omission: an exploratory multi-engine simulation study conducted alongside the campaign (rigid-body through finite-element fidelities, archived in the project repository) could not reproduce the amplification that dominates the measured record (rigid-strut models cap the transmissibility near unity while most printed articles exceed it), predicted design-invariant rebound where the measurement discriminates strongly, and correlated only weakly with the measured transmissibility. Its constant-mass fairness constraints and its diagnosis of the seed batch's mass confound did shape the campaign design, which is the screening role we consider simulation to have earned here; anything more must first demonstrate prospective predictive skill on articles it has not seen. The measured near-unity transmission of most seed articles also cautions against reading the printed-tensegrity literature's attenuation results as generic: the as-printed cells here are not pretensioned, and activating genuine pretension in additively manufactured tensegrity (for example through shrink-on-treatment routes) is an open direction we deliberately scope out of the present campaign.




Fig. 6 Measured objective space and front evolution across the four batches; the vertical axis is the mass-weighted velocity-loss objective $E_{\mathrm{reb}} = (1 - \mathrm{VLI})\, mgh$ of Eq. (1). Gray circles are all measured articles at their stabilized means; the blue lines are the non-dominated fronts after each batch, with the dominated hypervolume at the (1.35, 15 mJ) reference in the legend. Batch 2 grew the front on the velocity-loss axis, batch 3 filled the knee, and batch 4 broke the transmissibility floor. Repeated batch-3 designs are drawn at their first-print values; the design-mean front is given in the text. Both axes improve downward.

Practical considerations and path forward. TPU-PLA interface durability under repeated impact remains open: no joint failed during the repeated-drop measurement sessions (more than 1,400 stabilized captures across 35 articles plus the batch-3 second pass), but because those sessions were not designed as controlled fatigue tests, the observation does not establish interface durability, and pull-out and fatigue characterization of the internal-anchor joint is an area of planned follow-on work. Sensitivity to print-process covariates (the print key logs defects, humidity, and the mid-batch nozzle change for exactly this purpose) and transfer to other material pairs likewise remain open. In the future we plan the re-seat confirmations of the batch-4 attenuators, the replicate rank-stability study of Section 3.5, the metal-analog rank-transfer comparison of Section 3.6, quasi-static testing as an extension of the characterization (Section 3.3), pretension activation, tiled multi-cell absorbers and lattices [34], and miniaturization to crutch-tip envelopes: long-term crutch use is associated with substantial upper-extremity overuse injury and ground-reaction-force impulses [58–62]; existing spring-loaded [63, 64] and polymer-damped [65] tip designs reduce loading rate but not peak transmitted force, and recent tensegrity crutch concepts [66] and open-source 3D-printed crutch work [67] suggest a plausible translation path, with adjacent footwear and orthotic lattice studies [68–70] providing transferable design heuristics.

Limitations. The measured evidence base is 44 articles: 35 across the four batches plus the nine confirmed re-prints of the batch-3 designs, which are the only designs carrying more than one mechanical-response article in the fit. That replication is what exposed the seating and print sensitivity, so every single-article extreme, including the batch-4 record, is provisional until its re-seat. The drop protocol probes one height, one impact surface, and axial loading only; the specimens never leave the elastic regime, so crush-energy metrics await the quasi-static campaign; per-specimen energy absorption in joules is not recoverable from the current rig (the falling-mass and displacement channels required for a force integral are not instrumented); the four filament axes carry one value per batch and are unidentified; the held-out prediction skill of the surrogate declined as the input space grew (Section 4.3); one tested seed article lacks a design mapping, one seed design's official article assignment carries a recorded discrepancy, and two seed designs have no session record; and all results are from a single printer, material pair, and cell topology. The replication rule, the planned re-seat confirmations, the replicate rank-stability study (Section 3.5), and the metal-analog protocol (Section 3.6) are the designed responses to these limits.

6 Conclusions

We have presented an experiment-driven Bayesian-optimization framework for designing multi-material 3D-printed tensegrity-inspired energy absorbers, with TPU used in place of the traditional tension elements and PLA members carrying compression most of the time, and we have run it through the recommend, fabricate, measure, and update cycle three times on physical hardware. The framework parameterizes a T_3-prism family (five geometry variables, joined in batch 3 by infill and filament process variables) under a constant-mass fairness projection, fabricates each candidate in a single multi-material FDM build with TPU tendons anchored inside the PLA strut ends, characterizes every article with repeated instrumented drops (101 stabilized captures in the seed batch, about twenty thereafter), and updates a fully Bayesian Gaussian-process surrogate [20, 22] that recommends the next batch. Across the four measured batches (35 articles), the transmissibility spanned 0.803 to 1.334, most articles amplified the peak shock, and the model-recommended batches grew the dominated hypervolume 65% over the Sobol seed front, ending with a front whose five members are all model-chosen; the batch-4 best-predicted design set the program record at $t_{180} = 0.803$, ten percent below the best seed article, and awaits its re-seat confirmation under the campaign's




Fig. 7 Batch-4 predictions against outcomes. Orange diamonds with bars are the archived posterior predictions (mean ± one standard deviation) for trials 37 to 45 at recommendation time; arrows connect each prediction to its article's measured value (black circles; all previously measured articles shown for context). The vertical axis is E_{reb}, as in Fig. 6. The record attenuator corny7 (measured 0.803) is the left-most measured point. Both axes improve downward.




Fig. 8 Seed-state SAASBO length-scale diagnostics per objective (normalized inverse length scales; median over MCMC draws, interquartile whiskers; inputs are the five design variables plus printed mass; the horizontal axis, labeled "share of model sensitivity" in the plot, is this normalized inverse-length-scale diagnostic). No input separates decisively from the equal-share line (dashed) at seven mapped articles, and these are prior-sensitive model diagnostics, not evidence of variable relevance.

replication rule. Reprinting one batch's nine designs showed that a design's result can shift between prints by more than the scatter between drops, so a single-print extreme needs a replicate before it counts. [Placeholder: what the third print of the batch-3 designs and the replicate study show about seating and print variation.] The workflow is a candidate for other experimentally evaluated architected structures whose constitutive response is difficult to calibrate from first principles, but transfer beyond this printer, material pair, topology, and axial impact condition remains untested.

Acknowledgment

This work was supported by the Brigham Young University Mentored Research Grant program. The authors thank the undergraduate researchers who carried out the multi-material printing and impact testing, and the graduate co-mentor who supported day-to-day operations.

Funding Data

- Brigham Young University Mentored Research Grant.

Conflict of Interest

The authors declare no conflict of interest.

References

[1] Skelton, R. E. and de Oliveira, M. C., 2009, *Tensegrity Systems*, Springer, New York.

[2] Sultan, C., 2009, "Tensegrity: 60 Years of Art, Science, and Engineering," Advances in Applied Mechanics, **43**, pp. 69–145.

[3] Amendola, A., Carpentieri, G., de Oliveira, M. C., Skelton, R. E., and Fraternali, F., 2014, "Experimental Investigation of the Softening–Stiffening Response of Tensegrity Prisms under Compressive Loading," Composite Structures, **117**, pp. 234–243.

[4] Zhang, Q., Zhang, D., Dobah, Y., Scarpa, F., Fraternali, F., and Skelton, R. E., 2018, "Tensegrity Cell Mechanical Metamaterial with Metal Rubber," Applied Physics Letters, **113**(3), p. 031906.

[5] Fraternali, F., Carpentieri, G., and Amendola, A., 2015, "Tensegrity Ring Structures for Impact Protection," International Journal of Solids and Structures, **65–66**, pp. 232–243.

[6] Agogino, A. K., SunSpiral, V., and Atkinson, D., 2018, "Super Ball Bot — Structures for Planetary Landing and Exploration," NASA Ames Research Center, https://www.nasa.gov/general/super-ball-bot/

[7] Caluwaerts, K., Agogino, A. M., and SunSpiral, V., 2014, "SUPERball: Exploring Tensegrities for Planetary Probes," *Proceedings of the 12th International Symposium on Artificial Intelligence, Robotics and Automation in Space (i-SAIRAS)*.




Fig. 9 Leave-one-design-out cross-validation of the SAASBO surrogate over the full 44-article record (35 design folds; each batch-3 reprint pair is held out together so neither print leaks into the other's prediction; one full NUTS refit per fold). Vertical bars are one posterior standard deviation of the held-out prediction; horizontal bars are the ingested standard error; the dashed line is parity. The held-out t_{180} posterior hugs the pooled mean (MAPE 5.0%, rank correlation +0.08) and the E_{reb} ordering is anti-correlated (−0.38): design-level held-out skill is near zero on transmissibility and absent on the mass-weighted velocity-loss objective.

[8] Sabelhaus, A. P., Bruce, J., Caluwaerts, K., Manovi, P., Firoozi, R. F., Dobi, S., Agogino, A. M., and SunSpiral, V., 2015, "System Design and Locomotion of SUPERball, an Untethered Tensegrity Robot," *2015 IEEE International Conference on Robotics and Automation (ICRA)*, pp. 2867–2873, doi: 10.1109/ICRA.2015.7139590.

[9] Vespignani, M., Friesen, J. M., SunSpiral, V., and Bruce, J., 2018, "Design of SUPERball v2, a Compliant Tensegrity Robot for Absorbing Large Impacts," *2018 IEEE/RSJ International Conference on Intelligent Robots and Systems (IROS)*, pp. 2865–2871, doi: 10.1109/IROS.2018.8594374.

[10] Deitrich, N., Baldonado, K. M., Khan, A., Cook, J., and Rizzo, L., 2022, "A Rideshare Tensegrity Rover Concept to Explore Titan's Lands and Oceans," *AIAA SciTech Forum*, NASA Langley Research Center / Ames Research Center.

[11] Pajunen, K., Johanns, P., Pal, R. K., Rimoli, J. J., and Daraio, C., 2019, "Design and Impact Response of 3D-Printable Tensegrity-Inspired Structures," Materials & Design, **182**, p. 107966.

[12] Ye, H., Liu, Q., Cheng, J., Li, H., Jian, B., Wang, R., Sun, Z., Lu, Y., and Ge, Q., 2023, "Multimaterial 3D Printed Self-Locking Thick-Panel Origami Metamaterials," Nature Communications, **14**, p. 1607.

[13] Khatri, N. R. and Egan, P. F., 2024, "Energy Absorption of 3D Printed ABS and TPU Multimaterial Honeycomb Structures," 3D Printing and Additive Manufacturing, **11**, pp. e840–e850.

[14] Chen, Y., Huang, A., Wang, Z., Antonoglou, I., Schrittwieser, J., Silver, D., and de Freitas, N., 2018, "Bayesian Optimization in AlphaGo," arXiv preprint arXiv:1812.06855.

[15] Ament, S., Witte, A., Garg, N., and Kusuma, J., 2023, "Sustainable Concrete via Bayesian Optimization," arXiv preprint arXiv:2310.18288, NeurIPS 2023 Workshop on Adaptive Experimental Design and Active Learning in the Real World.

[16] Strieth-Kalthoff, F., Hao, H., Rathore, V., Derasp, J., Gaudin, T., Angello, N. H., Seifrid, M., Trushina, E., Guy, M., Liu, J., et al., 2024, "Delocalized, Asynchronous, Closed-Loop Discovery of Organic Laser Emitters," Science, **384**(6697), p. eadk9227.

[17] Mo, C., Perdikaris, P., and Raney, J. R., 2023, "Accelerated Design of Architected Materials with Multifidelity Bayesian Optimization," Journal of Engineering Mechanics, **149**(6), p. 04023028.

[18] Zhang, M., Parnell, A., Brabazon, A., and Benavoli, A., 2021, "Bayesian Optimisation for Sequential Experimental Design with Applications in Additive Manufacturing," arXiv preprint arXiv:2107.12809.

[19] SAE International, 2022, "Instrumentation for Impact Test—Part 1: Electronic Instrumentation," Surface Vehicle Recommended Practice J211/1_202208, doi: 10.4271/J211/1_202208.

[20] Balandat, M., Karrer, B., Jiang, D. R., Daulton, S., Letham, B., Wilson, A. G., and Bakshy, E., 2020, "BoTorch: A Framework for Efficient Monte-Carlo Bayesian Optimization," *Advances in Neural Information Processing Systems 33 (NeurIPS 2020)*, https://arxiv.org/abs/1910.06403

[21] Olson, M., Santorella, E., Tiao, L. C., Cakmak, S., Garrard, M., Daulton, S., Lin, Z. J., Ament, S., Beckerman, B., Onofrey, E., Igusti, P., Lara, C., Letham, B., Cardoso, C., Shen, S. S., Lin, A. C., Grange, M., Kashtelyan, E., Eriksson, D., Balandat, M., and Bakshy, E., 2025, "Ax: A Platform for Adaptive Experimentation," *Proceedings of the Fourth International Conference on Automated Machine Learning*, L. Akoglu, C. Doerr, J. N. van Rijn, R. Garnett, and J. R. Gardner, eds., Proceedings of Machine Learning Research, Vol. 293, PMLR, pp. 21/1–25, https://proceedings.mlr.press/v293/olson25a.html

[22] Eriksson, D. and Jankowiak, M., 2021, "High-Dimensional Bayesian Optimization with Sparse Axis-Aligned Subspaces," *Proceedings of the Thirty-Seventh Conference on Uncertainty in Artificial Intelligence (UAI)*, Proceedings of Machine Learning Research, Vol. 161, pp. 493–503, https://proceedings.mlr.press/v161/eriksson21a.html

[23] Santos, F. A., 2023, "Toward a novel energy-dissipation metamaterial with tensegrity architecture," Advanced Materials, May 2023.

[24] Cloutier, G. J., 1966, "Landing Impact Energy Absorption Using Anisotropic Crushable Materials," Journal of Spacecraft and Rockets, **3**(12), pp. 1755–1761.

[25] Adams, D. S., 2004, "Mars Exploration Rover Airbag Landing Loads Testing and Analysis," *45th AIAA/ASME/ASCE/AHS/ASC Structures, Structural Dynamics and Materials Conference*, doi: 10.2514/6.2004-1795.

[26] Jackson, K. E., Fasanella, E. L., and Polanco, M. A., 2014, "Simulating the Response of a Composite Honeycomb Energy Absorber: I. Dynamic Crushing of Components and Multiterrain Impacts," Journal of Aerospace Engineering, **27**(3), pp. 424–436.

[27] Davami, K., Mohsenizadeh, M., Munther, M., Palma, T., Beheshti, A., and Momeni, K., 2019, "Dynamic energy absorption characteristics of additively-manufactured shape-recovering lattice structures," Materials Research Express, **6**(4), p. 045302.

[28] Intrigila, C., Micheletti, A., Nodargi, N. A., Artioli, E., and Bisegna, P., 2022, "Fabrication and experimental characterisation of a bistable tensegrity-like unit for lattice metamaterials," Additive Manufacturing, **57**, p. 102946.

[29] Almeida, N., Gulledge, B., Park, J., Momeni, K., Tajyar, A., Davami, K., and Beck, S., 2025, "High strain rate response of 3D-printable tensegrity-inspired structures," International Journal of Solids and Structures, **322**, p. 113590.

[30] Davami, K., Rowe, R., Gulledge, B., Park, J., Beheshti, A., Palazotto, A., Tavangarian, F., and Beck, S., 2025, "Dynamic analysis of additively manufactured tensegrity structures," International Journal of Impact Engineering, **198**, p. 105208.

[31] Wang, Z., Zhang, M., Sun, J., Wen, Q., and Chu, J., 2026, "Integrated fabrication and validation of tensegrity-inspired rigid-flexible mechanical metamaterials," Additive Manufacturing, **118**, p. 105107.

[32] Bauer, J., Kraus, J. A., Crook, C., Rimoli, J. J., and Valdevit, L., 2021, "Tensegrity Metamaterials: Toward Failure-Resistant Engineering Systems through Delocalized Deformation," Advanced Materials, **33**(10), p. 2005647.

[33] Pajunen, K., Celli, P., and Daraio, C., 2021, "Prestrain-induced bandgap tuning in 3D-printed tensegrity-inspired lattice structures," Extreme Mechanics Letters, **44**, p. 101236.

[34] Sabouni-Zawadzka, A. A., Gilewski, W., and Zawadzki, A., 2024, "Experimental investigations on mechanical properties of 3D-printed tensegrity-inspired metamaterials based on 4-strut simplex module," Archives of Civil Engineering, **70**(2), pp. 343–357.

[35] Arifvianto, B., Satiti, B. E., Salim, U. A., Suyitno, Nuryanti, A., and Mahardika, M., 2022, "Mechanical properties of the fff sandwich-structured parts made of pla/tpu multi-material," Progress in Additive Manufacturing, 7:1213-1223, Apr 2022.

[36] Ezeh, O. H. and Susmel, L., 2018, "On the fatigue strength of 3d-printed polylactide (pla)," Procedia structural integrity, 9:29-36, Jan 2018.

[37] Vanaei, H. R., Shirinbayan, M., Vanaei, S., Fitoussi, J., Khelladi, S., and Tcharkhtchi, A., 2021, "Multi-scale damage analysis and fatigue behavior of pla manufactured by fused deposition modeling (fdm)," Rapid Prototyping Journal, 27:371-378, Jan 2021.

[38] Yavas, D., Liu, Q., Zhang, Z., and Wu, D., 2022, "Design and fabrication of architected multi-material lattices with tunable stiffness, strength, and energy absorption," Materials & Design, 217:110613, May 2022.

[39] Bustihan, A. and Botiz, I., 2026, "Recent advances in additively manufactured polymeric structures for mechanical energy absorption," Polymers, 18:1019, Apr 2026.

[40] Liu, J., Seidu, R., Hu, L., Cheng, C., Yan, S., Yang, L., and xiang Jiang, S., 2026, "Three-dimensional printed lattice structures for next generation of wearable technology," Fashion and Textiles, Mar 2026.

[41] Shahriari, B., Swersky, K., Wang, Z., Adams, R. P., and de Freitas, N., 2016, "Taking the Human Out of the Loop: A Review of Bayesian Optimization," Proceedings of the IEEE, **104**(1), pp. 148–175.

[42] Frazier, P. I., 2018, "A Tutorial on Bayesian Optimization," arXiv preprint arXiv:1807.02811.

[43] Ament, S., Daulton, S., Eriksson, D., Balandat, M., and Bakshy, E., 2023, "Unexpected Improvements to Expected Improvement for Bayesian Optimization," *Advances in Neural Information Processing Systems*, Vol. 36, doi: 10.52202/075280-0904.

[44] Daulton, S., Balandat, M., and Bakshy, E., 2021, "Parallel Bayesian Optimization of Multiple Noisy Objectives with Expected Hypervolume Improvement," *Advances in Neural Information Processing Systems*, Vol. 34, pp. 2187–2200, https://arxiv.org/abs/2105.08195

[45] Daulton, S., Cakmak, S., Balandat, M., Osborne, M. A., Zhou, E., and Bakshy, E., 2022, "Robust Multi-Objective Bayesian Optimization Under Input Noise," *Proceedings of the 39th International Conference on Machine Learning*, Proceedings of Machine Learning Research, Vol. 162, pp. 4831–4866, https://arxiv.org/abs/2202.07549

[46] Low, A. K. Y., Mekki-Berrada, F., Ostudin, A., Xie, J., Vissol-Gaudin, E., Lim, Y.-F., Gupta, A., Li, Q., Ong, Y. S., Khan, S. A., and Hippalgaonkar, K., 2024, "Evolution-guided Bayesian Optimization for Constrained Multi-Objective Optimization in Self-Driving Labs," npj Computational Materials, **10**, pp. 1–11.

[47] Baptista, R. and Poloczek, M., 2018, "Bayesian Optimization of Combinatorial Structures," *Proceedings of the 35th International Conference on Machine Learning (ICML)*, pp. 462–471, https://proceedings.mlr.press/v80/baptista18a.html

[48] Garrido-Merchán, E. C. and Hernández-Lobato, D., 2020, "Dealing with Categorical and Integer-Valued Variables in Bayesian Optimization with Gaussian Processes," Neurocomputing, **380**, pp. 20–35.

[49] Perdikaris, P., Raissi, M., Damianou, A., Lawrence, N. D., and Karniadakis, G. E., 2017, "Nonlinear Information Fusion Algorithms for Data-Efficient Multi-Fidelity Modelling," Proceedings of the Royal Society A, **473**(2198), p. 20160751.

[50] Bernstein, A. D., 1977, "Listening to the coefficient of restitution," American Journal of Physics, **45**(1), pp. 41–44.

[51] Ashwear, N. and Eriksson, A., 2014, "Natural frequencies describe the pre-stress in tensegrity structures," Computers & Structures, **138**, pp. 162–171.

[52] Gibson, L. J. and Ashby, M. F., 1997, *Cellular Solids: Structure and Properties*, 2nd ed., Cambridge Solid State Science Series, Cambridge University Press.

[53] Avalle, M., Belingardi, G., and Montanini, R., 2001, "Characterization of polymeric structural foams under compressive impact loading by means of energy-absorption diagram," International Journal of Impact Engineering, **25**(5), pp. 455–472.

[54] Tan, P. J., Reid, S. R., Harrigan, J. J., Zou, Z., and Li, S., 2005, "Dynamic compressive strength properties of aluminium foams. Part I—experimental data and observations," Journal of the Mechanics and Physics of Solids, **53**(10), pp. 2174–2205.

[55] Michailidis, N., Stergioudi, F., Tsouknidas, A., and Pavlidou, E., 2011, "Establishment of process parameter optimization for the manufacturing of aluminium foams and the determination of their mechanical properties," Materials Science and Engineering: B, **176**(1), pp. 19–25.

[56] International Organization for Standardization, 1999, "ISO 11334-4:1999 Assistive products for walking manipulated by one arm — Requirements and test methods — Part 4: Walking sticks with three or more legs," Standard, International Organization for Standardization, https://www.iso.org/standard/27298.html

[57] Eriksson, D., Pearce, M., Gardner, J. R., Turner, R. D., and Poloczek, M., 2019, "Scalable Global Optimization via Local Bayesian Optimization," *Advances in Neural Information Processing Systems 32 (NeurIPS 2019)*, pp. 5496–5507, https://arxiv.org/abs/1910.01739

[58] Requejo, P. S., Wahl, D. P., Bontrager, E. L., Newsam, C. J., Gronley, J. K., Mulroy, S. J., and Perry, J., 2005, "Upper extremity kinetics during lofstrand crutch-assisted gait," Medical engineering & physics, 27 1:19-29, Jan 2005.

[59] Rasouli, F. and Reed, K. B., 2020, "Walking assistance using crutches: a state of the art review," Journal of Biomechanics, 98:109489, Jan 2020.

[60] Manocha, R. H. K., MacGillivray, M. K., Eshraghi, M., and Sawatzky, B. J., 2021, "Injuries associated with crutch use: a narrative review," PM&R, 13:1176-1192, Dec 2021.

[61] da Silva, D. B.-B. and Fachin-Martins, E., 2022, "Pain mapping and health-related conditions in relation to forearm crutch usage: a cross-sectional study," Assistive Technology, 34:334-340, Oct 2022.

[62] Dozono, K., Hachisuka, A., Wada, F., and Hachisuka, K., 2015, "Peripheral neuropathies in nonparetic upper extremities of stroke patients induced by excessive use of a walking device," Journal of stroke and cerebrovascular diseases : the official journal of National Stroke Association, 24 8:1841-7, Aug 2015.

[63] Segura, A. and Piazza, S. J., 2007, "Mechanics of ambulation with standard and spring-loaded crutches," Archives of physical medicine and rehabilitation, 88 9:1159-63, Sep 2007.

[64] Zhang, Y., Liu, G., Xie, S., and Liger, A., 2011, "Biomechanical evaluation of an innovative spring-loaded axillary crutch design," Assistive Technology, 23:225-231, Dec 2011.

[65] MacGillivray, M. K., Manocha, R. H., and Sawatzky, B., 2016, "The influence of a polymer damper on swing-through crutch gait biomechanics," Medical engineering & physics, 38 3:275-9, Mar 2016.

[66] Gu, J., Spyra, J., Walski, A., Elsaesser, L., Bierner, S., and Dotov, D., 2026, "Tensegrity crutches with compliance from a pre-stressed self-tensile module improve ground reaction force profiles, speed, effort, comfort, and perceived stability," arXiv preprint arXiv:2605.02710, Preprint.

[67] Mottaghi, M., Woods, M. C., Danier, L., So, A., Reeves, J. M., and Pearce, J. M., 2025, "Open-source 3d printable forearm crutch," PLOS ONE, Nov 2025.

[68] Wang, H.-Y., Wu, L., Qi, J., Ding, J.-T., and Wang, Y., 2025, "Porous lattice structure optimization in 3d printed insole design," Journal of Fiber Bioengineering and Informatics, **18**, pp. 29–39.

[69] Zhang, J., Lu, S., Lin, Y., Wang, Y., Yi, X., and Fang, W., 2024, "Pressure-reducing design of 3d-printed diabetic shoe midsole utilizing auxetic lattice structure," Applied Sciences, 14:5291, Jun 2024.

[70] Janarthanan, A. K. K. and Vaidhyanathan, B., 2024, "Additive manufacturing of smart footwear components for healthcare applications," Micromachines, 16:30, Dec 2024.

List of Figures

1 Closed-loop, experiment-driven design framework. Parameterized PLA/TPU tensegrity-inspired unit cells are printed, characterized by repeated instrumented drop-weight impacts, and the resulting performance data drive a Gaussian-process surrogate that recommends the next batch of designs to fabricate. . . . 3

2 Working T_3-prism prototype. *(a)* Parametric OpenSCAD model whose base radius R, cell height H, twist angle θ, strut diameter d_s, and cable diameter d_t are the design variables of Table 2. *(b)* A representative dual-material prototype print (rigid PLA struts in white, tendon members in orange), with callouts marking the strut diameter d_s, a tendon (cable) diameter d_t, and the cell height H. The inter-plate twist θ is the relative rotation of the top and bottom node triangles, and the base radius R sets their circumradius. The photograph's wooden background was digitally replaced with a plain light backdrop. The specimen itself is unedited. . . . 5

3 Fabrication and characterization workflow for the multi-material tensegrity-inspired unit cells: design parameters drive parametric CAD, slicing with manually generated TPU supports, a single multi-material print on the Bambu Lab H2D, post-processing and inspection, and mechanical testing. Node photographs are representative artifacts drawn from the project's build history: the OpenSCAD T_3-prism render (CAD), the dual-nozzle Bambu Studio slice with PLA on the left extruder and TPU on the right (slicing), an in-progress H2D print of the prism batch (FDM), an as-printed specimen (post-processing), and the bungee-assisted drop-tower base plate with accelerometer (testing). . . . 6

4 *Placeholder.* Assembled validation specimens for each predicted performance tier (worst / mediocre / best), shown as printed PLA/TPU builds alongside their hollow-aluminum-rod and stainless-steel-threaded-cable metal analogs, with callouts marking the aluminum compression members, the threaded steel tension cables, and the strut-end cable anchors. Photographs to be added once the specimens are fabricated. . . . 9

5 The nine seed geometries rendered to a common millimeter scale (rigid PLA struts in black, TPU tendons in orange). Every rendering corresponds to a physically printed article in the seed campaign. . . . 9

6 Measured objective space and front evolution across the four batches; the vertical axis is the mass-weighted velocity-loss objective $E_{\mathrm{reb}} = (1 - \mathrm{VLI})\, mgh$ of Eq. (1). Gray circles are all measured articles at their stabilized means; the blue lines are the non-dominated fronts after each batch, with the dominated hypervolume at the $(1.35, 15\,\mathrm{mJ})$ reference in the legend. Batch 2 grew the front on the velocity-loss axis, batch 3 filled the knee, and batch 4 broke the transmissibility floor. Repeated batch-3 designs are drawn at their first-print values; the design-mean front is given in the text. Both axes improve downward. . . . 13

7 Batch-4 predictions against outcomes. Orange diamonds with bars are the archived posterior predictions (mean ± one standard deviation) for trials 37 to 45 at recommendation time; arrows connect each prediction to its article's measured value (black circles; all previously measured articles shown for context). The vertical axis is E_{reb}, as in Fig. 6. The record attenuator corny7 (measured 0.803) is the left-most measured point. Both axes improve downward. . . . 14

8 Seed-state SAASBO length-scale diagnostics per objective (normalized inverse length scales; median over MCMC draws, interquartile whiskers; inputs are the five design variables plus printed mass; the horizontal axis, labeled "share of model sensitivity" in the plot, is this normalized inverse-length-scale diagnostic). No input separates decisively from the equal-share line (dashed) at seven mapped articles, and these are prior-sensitive model diagnostics, not evidence of variable relevance. . . . 14

9 Leave-one-design-out cross-validation of the SAASBO surrogate over the full 44-article record (35 design folds; each batch-3 reprint pair is held out together so neither print leaks into the other's prediction; one full NUTS refit per fold). Vertical bars are one posterior standard deviation of the held-out prediction; horizontal bars are the ingested standard error; the dashed line is parity. The held-out t_{180} posterior hugs the pooled mean (MAPE 5.0%, rank correlation +0.08) and the E_{reb} ordering is anti-correlated (−0.38): design-level held-out skill is near zero on transmissibility and absent on the mass-weighted velocity-loss objective. . . . 15

List of Tables

1 Positioning of this work against selected prior efforts spanning the elements combined here. The present campaign uses physical drop measurements of the transmissibility (t_{180}) and a mass-weighted form of the velocity loss index (E_{reb}, Eq. (1)) as its BO responses; it does not optimize specific energy absorption or crush energy. . . . 4

2 Design variables for the T_3-prism campaign, as implemented in the BO harness. The seed batch is an $n = 9$ Sobol draw (fixed seed) over the five geometry variables, with each design then projected onto the constant-mass budget of the text. The process variables joined the space in batch 3: the two infill densities are acquisition-chosen per article, while the four filament settings admit one value per print job and are therefore drawn as a single quasi-random point per batch (confounded with batch until varied within a plate). The joint diameter is held fixed. All specimens print upright on a Bambu Lab H2D, with the prism axis normal to the build plate and the base triangle on the bed (Fig. 3, slicing panel). The seed batch used one specimen per named build plate, and each later batch used one nine-article plate. . . . 5

3 Multi-material print parameters on the Bambu Lab H2D, transcribed from the archived as-printed Bambu Studio project (`t3-prism-bo-batch.H2D-MM-PLAstruts-TPUcables.as-printed.3mf`, Bambu Studio 2.7.1). Filaments are Bambu Lab PLA Basic (struts, support material) and Bambu Lab TPU 85A (tendons); the print profile is "0.30 mm Standard @BBL H2D 0.6 nozzle." The reporting structure follows the methods section of Ye et al. [12]. . . . 6

4 *Placeholder (data pending).* Planned replicate rank-stability study: the best-, mid-, and worst-predicted in-sample designs, each re-printed as a nominal three fresh articles and drop-tested under the standard protocol. Entries will record each repeat's stabilized t_{180}, the within-design scatter, and the measured rank of each design's repeat cluster against its predicted rank. . . . 8

5 *Placeholder (data pending).* Planned rank-ordering validation: representative T_3-prism designs predicted to be worst-, mid-, and best-performing, each fabricated as a printed PLA/TPU specimen and as a hollow-aluminum-rod / stainless-steel-cable metal analog. Entries record the measured performance metric (t_{180} under the identical drop protocol, with the velocity loss index secondary) and the resulting rank within each material system; rank agreement would be preliminary evidence consistent with transfer, while disagreement would not isolate which material or joint difference caused the change. . . . 9

6 Seed-batch drop-tower results: 101 stabilized captures per article (103 for autv5r) at 60 in onto the standardized polyurethane surface, CFC-180 filtering, counted after the first two warm-up drops of each session were discarded. Means ± one standard deviation over the stabilized drops; rows are ordered by t_{180}. E_{reb} uses each article's weighed mass per Eq. (1). The ringdown frequency f_n is a print-health descriptor, not an objective. A dash denotes a quantity that cannot be computed from the available record: article *amdjwm* lacks a weighed mass and a confirmed design mapping