

S. No	Component Name	Material Type	Color
1	Sports / Casual Footwear	Mixed Material	Black / White

S. No	Test Name	Requirement
1	Whole Shoe Flexing Test (Method: SATRA TM 161)	Condition: 30,000 Flex Cycles Requirement: No Sole Separation Upper Cracking: Not Allowed Structural Failure: Not Allowed
2	Material Abrasion Test (Method: SATRA TM 31)	Dry Abrasion Resistance: $\geq 25,000$ Cycles Wet Abrasion Resistance: $\geq 12,800$ Cycles Surface Damage: Within Acceptable Limit
3	Sole Abrasion Test (Method: SATRA TM 174)	Abrasion Loss: $\leq 180 \text{ mm}^3$ Density Correction Applicable Result Calculation as per SATRA TM 174
4	Sole Flexing Test (Method: SATRA TM 92)	Flex Cycles: 100,000 Cycles Crack Growth: $\leq 4 \text{ mm}$ Complete Crack Through Sole: Not Allowed
5	pH Value Test (Method: PH-001)	Acceptable pH Range: 3.5 – 7.5 Difference Between Two Readings: ≤ 0.7
6	Antifungal Test (Method: ISO 19574)	Incubation Duration: 28 Days Visible Fungus Growth: Grade 0 or Grade 1 Only
7	Bond Strength Test (Method: SATRA TM 281)	Minimum Bond Strength: $\geq 4.0 \text{ N/mm}$ Testing Points: 16 Points Across Shoe Bond Failure: Not Allowed
8	Freezing Test (Method: FZ-001)	Condition: -20°C for 24 Hours Cracking: Not Allowed Material Hardening: Within Acceptable Limit
9	Hot Air Oven Test (Method: HAO-001)	Condition: 70°C for 24 Hours Dimensional Change: $\leq 2\%$ Surface Damage / Shrinkage: Not Allowed