
Sodium-ion batteries for stationary storage: chemistry, costs, and commercial status

A cited research report

Date	2026-08-06
Engine	assisted
API spend	USD 0.0567
Run id	b2aea99978f7

Contents

- Overview 3
- What are the key chemical components and reaction mechanisms in 3
- How do the energy density and cycle life of sodium-ion batteries 4
- What are the challenges in scaling up sodium-ion battery production 5
- What are the current market trends and growth projections for 6
- What are the regulatory and policy frameworks supporting sodium-ion 6
- What are the safety considerations for sodium-ion batteries in 7
- What are the challenges in sourcing raw materials for sodium-ion 8
- What are the future prospects and potential of sodium-ion batteries 8
- Conclusions 9
- Run Charts 10
- References 12
- Run Facts 13

Overview

Overview

Sodium-ion batteries (SIBs) are emerging as a viable alternative to lithium-ion batteries for stationary storage applications, offering advantages in cost, resource availability, and environmental impact. They utilize sodium ions (Na^+) as charge carriers, similar to lithium-ion batteries, but with cathode materials such as layered transition oxides, Prussian blue analogues, and polyanionic compounds like phosphates and fluorosulfates [1] [2]. Sodium ions shuttle between the positive and negative electrodes during charge and discharge cycles [3].

SIB production involves key cost factors including cathode, anode, current collectors, electrolyte, separator, packaging, and manufacturing overhead [7][8]. While SIBs have lower energy density compared to lithium-ion batteries, especially in aqueous versions [11][13], they offer superior cycle life and lower upfront costs in low-cycle or seasonal operating conditions [12]. Their performance is also notable for low-temperature operation [12]. However, they are unsuitable for high-cycle stationary storage due to the limitations of LFP cathodes [16].

Commercial applications of SIBs are expanding, with the Datang Hubei Sodium-Ion BESS in China demonstrating over 95% capacity retention after 18 months [16]. The market is projected to capture 20-30% of the stationary storage market by 2030, up from less than 5% in 2026 [9][10]. Key players in SIB development include CATL, BYD, Northvolt, Natron, and Reliance [12][15].

Technological advancements in SIBs include improvements in electrode materials, electrolyte stability, and full-cell design strategies [5], with recent progress in hard carbon materials significantly enhancing performance and scalability [4][20]. Environmental impacts are lower compared to lithium-ion batteries due to sodium's abundance and widespread distribution [14], and recycling remains an area of active research [18].

Challenges in scaling up production include achieving higher energy density, ensuring long cycle life, and maintaining cost competitiveness with lithium-ion technologies [5][10]. Raw material sourcing for sodium, iron, and cobalt also presents challenges, although SIBs reduce reliance on geopolitically concentrated materials like lithium, cobalt, or nickel [1][12]. Regulatory and policy frameworks support SIB adoption by prioritizing supply chain security and cost-effectiveness [9][12].

Compared to other stationary storage technologies such as lead-acid or flow batteries, SIBs offer lower upfront costs, better safety characteristics, and improved supply chain security [11][13]. Safety considerations include ensuring electrolyte compatibility with all cell components to achieve high safety standards [25].

Overall, SIBs show significant future potential in the stationary storage market, driven by their viability in daily cycling applications and growing adoption in Asia [16].

What are the key chemical components and reaction mechanisms in

What are the key chemical components and reaction mechanisms in sodium-ion batteries used for stationary storage?

Sodium-ion batteries for stationary storage rely on several key chemical components and specific reaction mechanisms. The primary components include cathode materials, anode materials, electrolytes, separators, and current collectors. Cathode materials are classified into layered transition oxides, organic compounds, Prussian blue analogues (PBAs), and polyanionic compounds such as phosphates, fluorosulfates, pyrophosphates, and oxychlorides [2]. These materials facilitate the shuttling of sodium ions between the positive and negative electrodes during charge and discharge cycles [3].

The anode materials in SIBs primarily consist of hard carbon, titanium-based materials, alloy-based materials, and other carbon-based materials. Hard carbon is particularly significant due to its ability to intercalate sodium ions, a critical reaction mechanism for energy storage [4]. The reaction mechanism involves sodium ion intercalation into the anode material during charging and extraction during discharging. Alloy-based anodes undergo a conversion reaction, where sodium reacts with the metal to form alloys capable of storing substantial amounts of sodium [5].

The electrolyte in SIBs typically consists of a liquid or solid medium that enables sodium ion movement between the electrodes. The electrolyte plays a crucial role in maintaining the stability of the solid electrolyte interphase (SEI) and ensuring efficient ion transport [5]. The separator prevents direct electrode contact while allowing ion passage, contributing to the battery's safety and performance [5].

Aluminum current collectors in SIBs are a notable feature, as they eliminate the need for expensive copper, thereby reducing material costs [10]. The abundance of sodium in the Earth's crust further enhances the cost-effectiveness of SIBs [10].

What are the primary cost factors in the production of sodium-ion batteries for stationary storage?

The primary cost factors in SIB production for stationary storage include cathode material, anode material, current collectors, electrolyte, separator and packaging, and manufacturing overhead. The cost comparison between sodium-ion and lithium iron phosphate (LFP) batteries reveals significant savings across multiple components [7].

Cathode materials for SIBs are generally less expensive than those for LFP batteries, with a cost range of \$18-22 per kWh compared to \$25-30 per kWh for LFP [7]. The use of aluminum current collectors, which are cheaper than copper, provides an additional savings of \$10 per kWh [7].

Anode materials, particularly hard carbon, are relatively inexpensive at \$8-10 per kWh, though slightly more costly than graphite used in LFP batteries [7]. Electrolyte and separator-packaging components also contribute to cost reductions of \$2 per kWh each [7].

Manufacturing overhead represents a significant cost advantage, with SIBs having lower overhead costs of \$15-20 per kWh compared to \$35-40 per kWh for LFP batteries [7]. These component savings result in a total cell cost reduction of \$36 per kWh, representing a 38% decrease compared to LFP batteries [7].

Sodium's abundance in the Earth's crust and the use of aluminum current collectors are key factors contributing to lower SIB production costs [10]. Combined with the potential for scale-up and increased production volumes, these factors are expected to further reduce costs and enhance SIB competitiveness in stationary storage applications [7].

How do the energy density and cycle life of sodium-ion batteries

How do the energy density and cycle life of sodium-ion batteries compare to lithium-ion batteries in stationary storage applications?

Sodium-ion batteries exhibit lower gravimetric energy density compared to lithium-ion batteries in stationary storage applications. SIBs have a gravimetric energy density of 150-175 Wh/kg, while LFP lithium-ion batteries achieve 170-185 Wh/kg, and NMC 811 lithium-ion batteries reach 250-280 Wh/kg [11]. Additionally, SIBs have a specific energy range of 75-200 W·h/kg, lower than the lithium-ion battery energy density of 250-375 W·h/L [1]. Energy density is notably lower in aqueous SIB versions compared to lithium-ion batteries [13].

Regarding cycle life, SIBs demonstrate superior performance compared to LFP lithium-ion batteries under specific conditions. SIBs achieve 3,000-5,000 cycles at 80% depth of discharge (DoD), while LFP lithium-ion batteries provide 4,000-8,000 cycles [11]. For applications with low-cycle requirements (<200 cycles/year), SIBs offer significant advantages through lower upfront cost and longer cycle life [11]. SIBs also outperform NMC 811 lithium-ion batteries, which typically achieve only 1,500-2,500 cycles [11].

What are the current commercial applications of sodium-ion batteries in stationary storage?

SIBs are increasingly used in stationary storage applications, particularly for grid storage and low-cycle or seasonal storage. The Datang Hubei Sodium-Ion BESS in China exemplifies commercial deployment, demonstrating capacity retention exceeding 95% after 18 months of operation [16]. SIB adoption in stationary storage is driven by lower costs and sodium's abundance compared to lithium [10]. Their lower upfront cost makes them particularly attractive for applications prioritizing cost and supply security over energy density [11].

SIB adoption in stationary storage is further accelerated by their cost-effectiveness in price-sensitive markets. SIBs are also increasingly used in electric two-wheelers across Asia, with an estimated 50+ million units sold annually [16]. The combination of lower costs and superior cycle life for low-cycle applications positions SIBs as a viable option for stationary storage [11].

What are the challenges in scaling up sodium-ion battery production

What are the challenges in scaling up sodium-ion battery production for stationary storage?

Scaling up SIB production for stationary storage faces several significant challenges. Core obstacles include achieving higher energy density, ensuring long cycle life, and maintaining safety [5]. These factors are essential for reliable battery performance in stationary storage applications. Additionally, maintaining cost competitiveness with established lithium-ion technologies while meeting growing demand presents a substantial challenge [10].

Manufacturing scale-up speed is another critical factor influencing SIB adoption. Delays in production scaling can impede market demand fulfillment and competition with established lithium-ion technologies [9]. The trajectory of lithium prices and Western policy support for non-Chinese supply chains also influence the feasibility of scaling up SIB production [9].

Regarding specific applications, SIBs are unsuitable for high-cycle stationary storage due to inferior cycle life compared to lithium iron phosphate (LFP) batteries [16]. This limitation restricts their applicability in scenarios requiring extensive daily cycling, a common requirement for stationary storage systems.

What are the environmental impacts of sodium-ion battery production and disposal?

SIB production has environmental impacts best assessed through a full life-cycle perspective [19]. The environmental competitiveness of SIBs is influenced by raw material availability, manufacturing processes, and end-of-life disposal [19].

A key advantage of SIBs is their use of more abundant and widely distributed sodium, which reduces environmental impact compared to lithium-ion batteries through lower mining requirements [14]. Sodium is over 1000 times more abundant than lithium and more evenly distributed globally, contributing to lower environmental impact [14].

SIB recycling represents an active research area with recent advances in recycling methodologies [18]. This indicates ongoing efforts to develop sustainable disposal and recycling practices that minimize environmental impact.

However, the complete environmental impacts of SIB production and disposal are still under investigation, and their full extent remains not entirely understood. While SIBs offer certain environmental advantages, challenges persist in comprehensively assessing and mitigating their overall environmental impact [19].

What are the current market trends and growth projections for

What are the current market trends and growth projections for sodium-ion batteries in stationary storage?

The SIB market is experiencing significant growth, driven by cost-effectiveness, supply chain security, and suitability for stationary storage applications. As of 2026, SIBs are projected to capture **20-30% of the stationary storage market by 2030**, up from less than 5% in 2026 [9]. Additionally, they are expected to capture **15-25% of the sub-\$25,000 EV segment by 2028** [10]. These projections are supported by increasing SIB adoption in grid storage and urban electric vehicles, particularly in price-sensitive markets such as India and Southeast Asia [11].

Market expansion in capacity is also anticipated. By 2030, the SIB market is projected to reach **200+ GWh capacity with 60%+ market share by 2028** [16]. This growth is attributed to first-mover advantages in manufacturing learning curves, the scalability of layered oxide technologies, and rising demand for low-cost, low-maintenance storage solutions [16].

Leading companies such as **CATL** and **BYD** spearhead the sector, with CATL achieving **30 GWh annual capacity** in 2026 [10]. **Northvolt** and **Natron** focus on **Prussian Blue technology** for stationary storage, though they encounter challenges with manufacturing costs and scalability [9]. The **Indian market**, supported by companies like **Faradion** and **Reliance**, shows strong potential for SIB adoption, particularly in e-rickshaws and storage applications [16].

What are the key technological advancements in sodium-ion batteries for stationary storage in recent years?

Recent technological advancements have significantly improved SIB performance and scalability for stationary storage. A notable development is the advancement in **positive and negative electrode materials**. For positive electrodes, researchers have focused on **layered oxides, polyanion compounds, Prussian blue analogs, and organic materials**, optimizing their structure-performance relationships and modification strategies [5]. For negative electrodes, **hard carbon** and other carbon-based materials have been extensively studied, with progress in sodium storage mechanisms and optimization approaches [4].

Development of **solid and liquid electrolytes** has enhanced SIB stability and efficiency. The formation of the **solid electrolyte interphase (SEI)** has been analyzed, and strategies for optimal full-cell design, including **pre-sodiation**, have been refined [5]. These advancements have contributed to improved **cycle life** and **energy density** in SIBs, increasing their competitiveness in stationary storage applications [11].

Additional research has addressed **NASICON-type electrode materials**, which have been tailored to enhance sodium ion transport. These materials show promise in improving **ion transport efficiency** and **electrochemical performance** in SIBs [21].

These technological advancements position SIBs as a viable alternative to lithium-ion batteries in stationary storage, with potential to significantly reduce costs and improve supply chain security [10].

What are the regulatory and policy frameworks supporting sodium-ion

Regulatory and policy frameworks supporting SIB adoption in stationary storage are primarily driven by supply chain independence, cost reduction, and energy security needs. These frameworks are particularly relevant in regions such as the European Union (EU) and China, where governments actively promote sodium-ion technology to reduce reliance on geopolitically sensitive materials including lithium, cobalt, and nickel. The EU's emphasis on supply chain independence serves as a key driver, with the European supply chain independence narrative attracting substantial EU policy support [9]. This is reinforced by SIBs' elimination of dependence on geopolitically concentrated materials, making them a strategic choice for countries diversifying their energy storage supply chains [12].

In China, the government has proactively supported SIB development through initiatives establishing a domestic manufacturing base. Companies like CATL and BYD are expanding SIB production capacities, with CATL already operating at 30 GWh annual capacity [10]. These efforts reflect a broader strategy to reduce reliance on imported materials and position China as a global battery technology leader. Government support for SIBs is evident in market share projections, with SIBs expected to capture 20-30% of the stationary storage market by 2030 [9].

In the United States, the regulatory landscape remains nascent, with some initiatives facing challenges. However, growth potential exists as policies and markets evolve. The U.S. Department of Energy has demonstrated interest in SIBs due to their potential to reduce costs and improve energy security. Private sector initiatives, such as those by Reliance in India, also support SIB development by leveraging market access and manufacturing capabilities [12].

When comparing SIBs to other stationary storage technologies such as lead-acid and flow batteries, SIBs offer notable advantages. They feature lower upfront costs and superior supply chain security compared to lead-acid and flow batteries [11]. For stationary applications, SIBs' lower upfront cost and superior cycle life create compelling total cost of ownership (TCO) advantages. For example, SIB initial costs are significantly lower than lead-acid batteries, with cycle life comparable to lithium iron phosphate (LFP) batteries [11].

Regarding safety, SIBs demonstrate better safety characteristics compared to lead-acid batteries, particularly in aqueous versions [13]. This advantage stems from their lower energy density and use of abundant materials, which reduce thermal runaway risk. Additionally, SIBs offer lower environmental impact than lithium-ion batteries, as they eliminate extraction of cobalt, copper, or nickel, materials associated with significant environmental and social costs [1].

SIBs do have certain limitations. They exhibit lower energy density than lithium-ion batteries, making them less suitable for applications requiring high energy density, such as long-range electric vehicles. Furthermore, SIB development remains in early commercial stages, with challenges related to manufacturing scale-up and cost reduction [9]. Despite these limitations, regulatory and policy frameworks supporting SIBs are robust, and adoption in stationary storage is expected to grow significantly in coming years.

What are the safety considerations for sodium-ion batteries in

What are the safety considerations for sodium-ion batteries in stationary storage applications?

SIBs present several safety considerations essential for ensuring their reliability and performance in stationary storage applications. A critical aspect is electrolyte compatibility with all cell components, including current collectors, cell casing, the separator, and binders. This compatibility is crucial for achieving long cycle life and high safety standards, as the electrolyte must prevent continuous decomposition at high or low potentials and establish stable interphases at electrode/electrolyte interfaces [25].

High-temperature stability represents another important safety consideration. SIBs demonstrate excellent high-temperature stability at 60°C, contributing to their safety in stationary storage applications [12]. This stability

is essential for maintaining performance and preventing thermal runaway in environments with temperature fluctuations.

Core safety challenges requiring attention include ensuring long cycle life and enhancing energy density, both critical for long-term SIB reliability [5]. Additionally, safety strategies addressing thermal stability and meeting regulatory requirements are discussed in the literature, highlighting the importance of developing robust safety protocols and adhering to regulatory standards [3].

What are the key players and companies involved in the development of sodium-ion batteries for stationary storage?

Several companies are actively developing SIBs for stationary storage. These include CATL, BYD, Northvolt, Natron, and Reliance. CATL and BYD are key players developing SIBs using layered oxide chemistry, optimized for applications including stationary storage and urban EVs [16]. Northvolt and Natron are notable for their work on Prussian Blue cathode chemistry, targeting stationary storage with high cycle life and ultra-low cost [8].

Faradion, part of Reliance, is also active in SIB development for stationary storage, particularly for applications such as e-rickshaws and storage [16]. Companies including HiNa Battery, Natron Energy, and Tiamat contribute to SIB development using various cathode materials such as Prussian White and vanadium phosphate [15].

Competitive dynamics in the SIB market are crystallizing around three strategic positions: scale-first layered oxide manufacturers (CATL, BYD), niche Prussian Blue specialists (Northvolt, Natron), and vertically integrated Indian entrants (Faradion/Reliance) [16]. These companies play crucial roles in advancing the technology and commercializing SIBs for stationary storage applications.

What are the challenges in sourcing raw materials for sodium-ion

Raw material sourcing for SIBs presents multifaceted challenges involving availability, cost, and processing. While sodium is abundant and cost-effective, other critical materials such as iron, cobalt, and hard carbon present significant sourcing difficulties. Hard carbon sourcing, a key raw material for SIB anodes, remains particularly challenging due to limited availability and high production costs [4]. Additionally, cost and resource analyses of SIBs highlight challenges in sourcing raw materials, including limited availability and higher processing costs compared to lithium-ion batteries [26]. These factors collectively impact the scalability and economic viability of SIB production.

Regarding performance benchmarks for SIBs in stationary storage under varying operating conditions, SIBs exhibit a specific energy range of 0.27–0.72 MJ/kg (75–200 W·h/kg) and an energy density of 250–375 W·h/L [1]. For cycle life, SIBs achieve thousands of cycles with a nominal cell voltage of 3.0–3.1 V. In stationary storage applications, SIBs deliver 3,000–5,000 cycles at 80% depth of discharge (DoD), lower than the 6,000–8,000 cycles achieved by LFP lithium-ion batteries [11]. However, SIBs offer lower upfront costs, delivering 20–30% total cost of ownership (TCO) savings for seasonal storage or low-cycle applications (<200 cycles/year) [11]. Additionally, SIBs demonstrate excellent low-temperature performance, retaining 85–90% capacity at –20°C, making them suitable for diverse stationary storage conditions [12].

What are the future prospects and potential of sodium-ion batteries

What are the future prospects and potential of sodium-ion batteries in stationary storage?

SIBs demonstrate strong future prospects in the stationary storage market, driven by cost-effectiveness, supply chain security, and proven performance in extended-duration cycling applications. By 2028, SIBs are projected to capture 20-30% of the stationary storage market [10], with projections rising to 20-30% by 2030 [9]. These outlooks are supported by expanding SIB adoption in Asia, where over 50 million electric two-wheelers are sold annually, with 30-40% of new e-scooters in China and India expected to use SIBs by 2027 [12].

Cost advantages of SIBs are substantial, with cell costs ranging from \$55-70/kWh in 2026—35-40% lower than lithium iron phosphate (LFP) batteries [10]. This cost reduction results from sodium's abundance, the use of aluminum current collectors, and elimination of cobalt and nickel supply chains [10]. These factors enable lower total cost of ownership (TCO) in seasonal storage or low-cycle applications, where SIBs can deliver 20-30% TCO savings compared to LFP batteries [11].

Despite these advantages, SIBs remain unsuitable for high-cycle stationary storage applications, where LFP batteries offer superior cycle life (6,000-8,000 cycles) [12]. For grid storage with daily cycling, LFP maintains a slight TCO advantage through its longer cycle life [11]. However, SIBs are well-suited for applications where cost and supply security take priority over energy density, such as urban EVs, e-rickshaws, and stationary storage [12].

The SIB market remains in its commercial infancy, though competitive dynamics are already crystallizing around three strategic positions: scale-first layered oxide manufacturers (CATL, BYD), niche Prussian Blue specialists (Northvolt, Natron), and vertically integrated Indian entrants (Faradion/Reliance) [16]. CATL and BYD are projected to hold over 70% combined market share by 2030, while Western entrants face a 3-5 year manufacturing cost gap relative to Chinese scale leaders [9].

SIB market prospects in stationary storage are also influenced by manufacturing scale-up speed, lithium price trajectory, and Western policy support for non-Chinese supply chains [9]. While substantial market growth is expected, SIBs' capacity to capture a significant stationary storage market share depends on these factors and continued technology development.

Conclusions

Conclusions

Sodium-ion batteries (SIBs) are emerging as a viable alternative to lithium-ion batteries for stationary storage applications, driven by lower costs, abundant raw materials, and environmental benefits. The key chemical components of SIBs include sodium ions (Na⁺) as charge carriers, with cathode materials such as layered transition oxides, Prussian blue analogues, and polyanionic compounds including phosphates and fluorosulfates [1][2]. Sodium ions shuttle between positive and negative electrodes during charge and discharge cycles [3].

The primary cost factors in SIB production include cathode, anode, current collectors, electrolyte, separator and packaging, and manufacturing overhead [7][8]. While SIBs are projected to capture 20-30% of the stationary storage market by 2030 [9][10], challenges in scaling up production persist, including achieving higher energy density, ensuring long cycle life, and maintaining cost competitiveness with lithium-ion technologies [5][10]. Manufacturing scale-up speed, lithium price trajectory, and Western policy support for non-Chinese supply chains also present challenges [9].

Regarding performance, SIBs have lower energy density compared to lithium-ion batteries, particularly in aqueous versions [11][13]. However, they offer superior cycle life and lower upfront costs, making them suitable for low-cycle or seasonal operating conditions [12][14]. SIBs are unsuitable for high-cycle stationary storage due to LFP (lithium iron phosphate) cathode limitations [16].

Current commercial applications of SIBs include stationary electrical grid storage, exemplified by the Datang Hubei Sodium-Ion BESS in China, which demonstrated over 95% capacity retention after 18 months of operation

[15][16]. SIB production has lower environmental impact than lithium-ion batteries due to sodium’s greater abundance and wider distribution [14][17].

Technological advancements in SIBs include improvements in electrode materials, electrolyte stability, and full-cell design strategies [5]. Recent progress in hard carbon materials has significantly enhanced SIB performance and scalability for stationary energy storage [4][20].


Regulatory and policy frameworks supporting SIB adoption emphasize supply chain security and cost-effectiveness, with European policies prioritizing supply chain independence [12][16]. Key players in SIB development include CATL, BYD, Northvolt, Natron, and Reliance [15][16].




SIBs compare favorably to other stationary storage technologies including lead-acid and flow batteries, offering lower costs, better safety, and improved supply chain security [10][11][13]. Some sources project 20-30% market share by 2028 [10], while others project this by 2030 [9][15].


Safety considerations for SIBs include ensuring electrolyte compatibility with all cell components to achieve long cycle life and high safety standards [25]. Raw material sourcing challenges for sodium, iron, and cobalt also influence SIB viability [1][12][20].

Overall, while SIBs demonstrate significant potential in the stationary storage market, further research and development are necessary to address production scaling challenges and improve energy density. The evidence broadly supports SIB benefits, though certain discrepancies exist in market projections and specific performance benchmarks that warrant further clarification.

Run Charts







References

-
- [1] Sodium-ion battery - Wikipedia - https://en.wikipedia.org/wiki/Sodium-ion_battery (chunk e2bf31e5d96fe6f0, chars 0-1738)
 - [2] Recent Progress in Sodium-Ion Batteries: Advanced Materials, Reaction Mechanisms and Energy Applications - Electrochemical Energy Reviews - <https://link.springer.com/article/10.1007/s41918-024-00215-y> (chunk 749a56ae240eb99e, chars 3129-5143)
 - [3] Sodium-Ion Batteries - https://link.springer.com/chapter/10.1007/978-3-031-88550-1_6 (chunk 305f6c412fe3ad96, chars 0-786)
 - [4] Sodium-Ion Batteries - https://link.springer.com/chapter/10.1007/978-3-031-88550-1_6 (chunk 33c46459fe73e7e1, chars 4086-6116)
 - [5] Sodium-ion Batteries: A comprehensive review of materials chemistry, interfacial challenges, and industrialization progress - Ionics - <https://link.springer.com/article/10.1007/s11581-026-07080-3> (chunk 6123e134e481403b, chars 0-1484)
 - [6] Chemistry - Nadion Energy - <https://nadionenergy.com/chemistry/> (chunk 22df59f08fb8bcd0, chars 1532-2246)
 - [7] Sodium-Ion Batteries 2026: Complete Technical & Economic Analysis | \$60/kWh Revolution - <https://energy-solutions.co/articles/sub/sodium-ion-batteries-cheaper-lithium-alternative> (chunk 6961b8ae4b9acee5, chars 4776-6357)
 - [8] Sodium-Ion Batteries 2026: Complete Technical & Economic Analysis | \$60/kWh Revolution - <https://energy-solutions.co/articles/sub/sodium-ion-batteries-cheaper-lithium-alternative> (chunk 49105b5bf33baeab, chars 3986-5601)
 - [9] Sodium-Ion Batteries 2026: Complete Technical & Economic Analysis | \$60/kWh Revolution - <https://energy-solutions.co/articles/sub/sodium-ion-batteries-cheaper-lithium-alternative> (chunk cd6f4bd75e1dea7f, chars 9610-11648)
 - [10] Sodium-Ion Batteries 2026: Complete Technical & Economic Analysis | \$60/kWh Revolution - <https://energy-solutions.co/articles/sub/sodium-ion-batteries-cheaper-lithium-alternative> (chunk 4ebdb90f5d0c2f41, chars 0-2047)
 - [11] Sodium-Ion Batteries 2026: Complete Technical & Economic Analysis | \$60/kWh Revolution - <https://energy-solutions.co/articles/sub/sodium-ion-batteries-cheaper-lithium-alternative> (chunk 0d0d2018a6535761, chars 5601-7959)
 - [12] Sodium-Ion Batteries 2026: Complete Technical & Economic Analysis | \$60/kWh Revolution - <https://energy-solutions.co/articles/sub/sodium-ion-batteries-cheaper-lithium-alternative> (chunk d15050bea5bd4660, chars 6357-8309)

- [13] Sodium-ion battery - Wikipedia - https://en.wikipedia.org/wiki/Sodium-ion_battery (chunk d4fec59575af5f9b, chars 21196-23355)
- [14] Sodium-Ion Battery - Battery Design - <https://www.batterydesign.net/chemistry/sodium-ion-battery/> (chunk eb1e8f33793fd6d9, chars 0-1295)
- [15] Sodium-ion battery - Wikipedia - https://en.wikipedia.org/wiki/Sodium-ion_battery (chunk b486eb6a6907dbe0, chars 1456-2333)
- [16] Sodium-Ion Batteries 2026: Complete Technical & Economic Analysis | \$60/kWh Revolution - <https://energy-solutions.co/articles/sub/sodium-ion-batteries-cheaper-lithium-alternative> (chunk 8cfe7a6873b0d506, chars 7959-9938)
- [17] Chemistry - Nadion Energy - <https://nadionenergy.com/chemistry/> (chunk 3e8f724aa9b88cbf, chars 2248-2539)
- [18] Sodium-ion Batteries: A comprehensive review of materials chemistry, interfacial challenges, and industrialization progress - Ionics - <https://link.springer.com/article/10.1007/s11581-026-07080-3> (chunk ac52ccae947a083b, chars 100710-102534)
- [19] Sodium-ion Batteries: A comprehensive review of materials chemistry, interfacial challenges, and industrialization progress - Ionics - <https://link.springer.com/article/10.1007/s11581-026-07080-3> (chunk b9f015f20a7a0f22, chars 6242-8275)
- [20] Sodium-Ion Batteries - https://link.springer.com/chapter/10.1007/978-3-031-88550-1_6 (chunk b14ec3c728dd534d, chars 2538-4489)
- [21] Sodium-ion Batteries: A comprehensive review of materials chemistry, interfacial challenges, and industrialization progress - Ionics - <https://link.springer.com/article/10.1007/s11581-026-07080-3> (chunk 323dde4b87709f5e, chars 4647-6664)
- [22] Sodium-Ion Batteries: What They Are, Pros & Outlook - <https://udpwr.com/blogs/portable-power-station-knowledge/sodium-ion-battery> (chunk 9b129040f676db9f, chars 6131-6813)
- [23] Sodium-Ion Batteries: What They Are, Pros & Outlook - <https://udpwr.com/blogs/portable-power-station-knowledge/sodium-ion-battery> (chunk bb0ca112da71b2ab, chars 3920-4617)
- [24] Sodium-ion battery - Wikipedia - https://en.wikipedia.org/wiki/Sodium-ion_battery (chunk 7f32bcde5a836b32, chars 21114-21196)
- [25] Working principle sodium-ion battery | E-Lyte | - <https://e-lyte.de/electrolyte-knowledge/working-principle-sodium-ion-battery/> (chunk e7e15ab71e61801d, chars 0-1042)
- [26] Recent Progress in Sodium-Ion Batteries: Advanced Materials, Reaction Mechanisms and Energy Applications - Electrochemical Energy Reviews - <https://link.springer.com/article/10.1007/s41918-024-00215-y> (chunk 0f98fa76b44799bb, chars 138782-140722)
- [27] Chemistry - Nadion Energy - <https://nadionenergy.com/chemistry/> (chunk 701fdf379ebc0af1, chars 375-675)
- [28] Sodium-ion battery - Wikipedia - https://en.wikipedia.org/wiki/Sodium-ion_battery (chunk 875e6d0b217188c5, chars 36241-38291)

Run Facts

Run id	b2aea99978f7
Engine	assisted

Iterations	2
Sources fetched	19
Chunks	354
After dedup	354
Evidence chunks	100
Claims checked	125
Claims rewritten / dropped	0 / 1
API spend	USD 0.0567
Spend: polish	USD 0.0383
Spend: gap	USD 0.0184