

1. Client's name / Tên khách hàng : CÔNG TY TNHH CHO CHEN (VIỆT NAM)
2. Client's address / Địa chỉ : LÔ G-5B-CN, KCN MỸ PHƯỚC 2, PHƯỜNG MỸ PHƯỚC, THỊ XÃ BẾN CÁT, TỈNH BÌNH DƯƠNG

The following sample(s) was/were submitted and identified by the client as:


Các thông tin nhận dạng mẫu do khách hàng cung cấp:

3. Name of sample / Tên mẫu : ACRYLIC SHEETS MADE OF PMMA
(POLYMETHYL METHACRYLATE)
Batch number : 175310299 - 433 x 3 LO
4. Quantity / Số lượng mẫu : 01 sample / mẫu
5. Description / Mô tả mẫu : 2440 x 1220 x 3.0 (mm)
6. Date of receiving / Ngày nhận mẫu : 02-Jun-2017
7. Date of testing / Ngày thử nghiệm : From / từ 02-Jun-2017 to / đến 21-Jun-2017
8. Test condition : Temperature / Nhiệt độ : $23 \pm 2^\circ\text{C}$
Điều kiện thử nghiệm Humidity / Độ ẩm : $50 \pm 5\%$
9. Test result / Kết quả thử nghiệm : See next page(s) / Xem trang sau



SGS authenticate the photos on original report only/ SGS chỉ xác thực các hình ảnh trong báo cáo chính thức

Signed for and on behalf of
SGS Vietnam LTD



Le Long Hai
Construction Lab Manager
Industrial Services


"This document is issued by the Company under its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms_and_conditions.htm and for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitations of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested only."

Characteristic Tên chỉ tiêu	Test method Phương pháp thử nghiệm	Test result Kết quả thử nghiệm
Dimensional tolerance mm Dung sai kích thước	Ref. ASTM D4802 - 16	
- Thickness / Chiều dày		-0.069
- Length / Chiều dài		+67.0
- Width / Chiều rộng		+70.0
Density (*) g/cm³ Khối lượng riêng	ASTM D792 - 13	1.19
Izod impact (*) J/m Độ bền va đập Izod	ASTM D256 - 10	16.49
Tensile strength (*) MPa Độ bền kéo	ASTM D638 - 14	68.39
Elongation at break (*) % Độ giãn dài tại điểm đứt	ASTM D638 - 14	3.04
Luminous transmittance (*) % Độ truyền quang	ASTM D1003 - 13	32.88
Haze (*) / Độ bóng mờ %	ASTM D1003 - 13	32.95
Shrinkage (*) / Độ co rút %	ASTM D4802 - 16	2.20
Water absorption (*) % Độ hấp thụ nước	ASTM D570 - 10	0.24
Thermal stability (*) Sự ổn định nhiệt	ASTM D4802 - 16	The sample does not appear bubbles and blisters after 30 minutes at 180±5°C Mẫu không bị phồng, dộp sau thời gian 30 phút thử nghiệm ở nhiệt độ 180±5°C
Index of refraction (*) Chỉ số khúc xạ	ASTM D542 - 14	1.5961
Deflection Temperature (*) °C Nhiệt độ biến dạng HDT	ASTM D648 - 07 (Heating Rate: 120°C/h, Method A: 1.82 MPa)	93.65

*** TO BE CONTINUED ***


"This document is issued by the Company under its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms_and_conditions.htm and for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitations of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested only."

Characteristic Tên chỉ tiêu	Test method Phương pháp thử nghiệm	Test result Kết quả thử nghiệm					
• Spectral transmittance (%) Độ truyền quang UV	ASTM D4802 - 16	UVT				UVF	
		290 nm	310 nm	340 nm	400 nm	290 nm	310 nm
		1.70	2.74	5.10	15.17	1.65	2.68



*** TO BE CONTINUED ***

"This document is issued by the Company under its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms_and_conditions.htm and for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitations of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested only."



Note / Ghi chú : (*) The tests were performed by SGS Vietnam's Subcontract Lab / Các chỉ tiêu được tiến hành bởi Thầu phụ của SGS Việt Nam.

*** END OF THE REPORT ***

"This document is issued by the Company under its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms_and_conditions.htm and for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitations of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested only."