(a) bending: through-thickness electrodes



(b) extensional: end electrodes



$L = 200$ μm, thickness h; window half-widths $a_1 \times a_2$, $M_{ii} = a_i^2/3$ (cuboid), $a_i^2/4$ (ellipse)