

Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 1 of 24

Applicant: Wenzhou qiaohouer playground Equipment Co., Ltd.
Address: Xiaojingao village, Qiaoxia town, Yongjia country, Wenzhou City, Zhejiang province.

The following sample was submitted and identified by/on behalf of the client as:

Product Name: Dome Climber Swings/10ft Dome Climber Hammocks
Model No.: PXXZIP073BU/ PXXZIP074BU/QH073
Labeled Age Grading: 3+
Requested Age Grading: 3+
Age Group Applied in Testing: Over 3 years
Manufacturer: YANGZHOU JIUXIN SPORTS TECHNOLOGY CO., LTD.
Address: No. 6, Xinji Industrial Park, Yizheng City, Yangzhou City, Jiangsu Province
Country of origin: Yangzhou China
Sample Received Date: 2026.4.10
Testing Period: 2026.4.10—2026.4.20
Test Requested: Please refer to the following page(s).
Test Method: Please refer to the following page(s).
Test Result(s): Please refer to the following page(s).
Summary of Test Results: Please refer to the Next page(s).

Signed for and on behalf of
Shenzhen Element Testing Co., Ltd.



Noel Yin
Technical Manager



Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 2 of 24

Test Requested**Result**

1. ASTM F963-23 Standard Consumer Safety Specification for Toy Safety
 - 1.1 Mechanical and Physical test Pass
 - 1.2 Flammability test Pass
 - 1.3 Heavy metal content
 - 1.3.1 Clause 4.3.5.2 Heavy elements –Toy substrate materials Pass
 - 1.3.2 Clause 4.3.5.1 Heavy elements –Toy Paint/Similar Surface Coating materials Pass
 - 1.4 Clause 4.3.5 Heavy elements – Migration of certain elements Pass
 - 1.5 Clause 4.3.8 Phthalates Pass
2. USA Consumer Product Safety Improvement Act (CPSIA) Sec.101 Children's products containing Lead; Lead paint rule Pass
3. USA Consumer Product Safety Improvement Act (CPSIA) Sec.108 Prohibition on sale of certain products containing specified phthalates USA 16 CFR Part 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates Pass
4. USA 16 CFR Part 1303 Ban of Lead Containing Paint and Certain Consumer Products Bearing Lead- Containing Paint Pass
5. CPSIA Section 103 Tracking Labels for Children's Products Pass
6. As specified in title 16, code of federal regulations, chapter II- consumer products Safety commission of U.S.A
 - 6.1 Physical and Mechanical Tests Pass
 - 6.2 Flammability Tests Pass
7. As specified by client, according to 15 U.S.C. § 1278a Children's products containing lead; lead paint rule (a) General lead ban, to determine the content of Lead (Pb) in the submitted sample. Pass

Note: N/A=Not Applicable

Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 3 of 24

Test Results:

1. ASTM F963-23 Standard Consumer Safety Specification for Toy Safety

1.1 Mechanical and Physical test

Clause	Description	Result
4	Safety Requirements	
4.1	Material Quality (Visual Examination)	Pass
4.2	Flammability	Pass (See Result Page)
4.3	Toxicology	
4.3.1	Hazardous substance	N/A
4.3.2	Manufacturing and Packaging of Food	N/A
4.3.3	Indirect Food Additives	N/A
4.3.4	Cosmetics	N/A
4.3.5	Heavy Elements	Pass (See Result Page)
4.3.5.1	Paint and Simllar Surface-coating Materials	Pass (See Result Page)
4.3.5.2	Toy substance Materials	Pass (See Result Page)
4.3.6	Cosmetics, Liquid, Pastes, Putties, Gels and Powders	N/A
4.3.7	Stuffing Materials	N/A
4.3.8	Phthalates	Pass (See Result Page)
4.4	Electrical / Thermal Energy	N/A
4.5	Sound-producing Toys	N/A
4.6	Small Objects	
4.6.1	Toys that are intended for children under 36 months of age	N/A
4.6.2	Mouth-Actuated Toys	N/A
4.6.3	Toys and games that are intended for use by children who at least three years old but less than six years old	N/A
4.7	Accessible Edges	Pass
4.8	Projections	N/A
4.9	Accessible Points	Pass
4.10	Wires or Rods	N/A
4.11	Nails and Fasteners	Pass
4.12	Plastic Film	Pass
4.13	Folding Mechanisms and Hinges	N/A
4.14	Cords, Straps, and Elastics	N/A

Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 4 of 24

Clause	Description	Result
4.15	Stability and Over-Load Requirements	Pass
4.16	Confined Spaces	N/A
4.17	Wheels, Tires and Axles	N/A
4.18	Holes, Clearance, and Accessibility of Mechanisms	Pass
4.19	Simulated Protective Devices	N/A
4.20	Pacifiers	N/A
4.21	Projectile Toys	N/A
4.22	Teethers and Teething Toys	N/A
4.23	Rattles	N/A
4.24	Squeeze Toys	N/A
4.25	Battery-Operated Toys	N/A
4.26	Toys Intended to be Attached to a Crib or Playpen	N/A
4.27	Stuffed & Beanbag-Type Toy	N/A
4.28	Stroller and Carriage Toys	N/A
4.29	Art Materials	N/A
4.30	Toy Gun Marking	N/A
4.31	Balloons	N/A
4.32	Certain Toys with Nearly Spherical Ends	N/A
4.33	Marbles	N/A
4.34	Balls	N/A
4.35	Pompoms	N/A
4.36	Hemispheric-Shaped Objects	N/A
4.37	Yo Yo Elastic Tether Toys	N/A
4.38	Magnets	N/A
4.39	Jaw Entrapment in Handles and Steering Wheels	N/A
4.40	Expanding Materials	N/A
4.41	Toy Chests	N/A
5	Labeling Requirements	
5.1	Federal Government Requirements	Pass
5.2	Age Grading Labeling	Pass
5.3	Safety Labeling Requirements	N/A
5.4	Aquatic Toys	N/A
5.5	Crib and Playpen Toys	N/A
5.6	Mobiles	N/A
5.7	Stroller and Carrier Toys	N/A
5.8	Toys Intended to be Assembled by an Adult	N/A
5.9	Stimulated Protective Devices	N/A

Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 5 of 24

Clause	Description	Result
5.10	Toys with Functional Sharp Edges or Points	N/A
5.11	Small Objects, Small Balls, Marbles, and Balloons	N/A
5.12	Art Materials	N/A
5.13	Electric Toys	N/A
5.14	Battery-Operated Toys	N/A
5.15	Promotional Materials	Pass
5.16	Magnets	N/A
6	Instructional Literature	
6.1	Definition and description	Pass
6.2	Crib and Playpen Toys	N/A
6.3	Mobiles	N/A
6.4	Toys Intended to be Assembled by an Adult	N/A
6.5	Battery-Operated Toys	N/A
6.6	Battery-powered Ride-on Toys	N/A
6.7	Toys in contact with Food	N/A
6.8	Toy chests	N/A
6.9	Toys which require a manufacturer-supplied specialty or custom tool to access the battery(ies)	N/A
7	Producers Markings	
7.1	Producers Markings	Pass
7.2	Battery-Powered Ride-on Toys	N/A
7.3	Toy chests	N/A
8	Test Methods	
8.5	Normal Use Testing	Pass
8.5.1	Washable Test	N/A
8.7	Impact Test	Pass
8.8	Torque Test	Pass
8.9	Tension Test	Pass
8.10	Compression Test	Pass
8.11	Test for Tire Removal and snap-in wheel and axle assembly removal	N/A
8.12	Flexure Test	N/A
8.14	Projectiles	N/A
8.16	Tension Test for Pompoms	N/A
8.17	Stalled Motor Test for Battery-operated Toys	N/A
8.18	Tests for Battery-Powered Ride-on Toys	N/A
8.19	Tests for Toys that Contain Secondary Cells or Batteries	N/A

Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 6 of 24

Clause	Description	Result
8.20	Tests for Toys Which Produce Noise	N/A
8.21	Dynamic Strength Test for Wheeled Ride-on Toys	N/A

Note: N/A=Not Applicable

1.2 Flammability test (Clause 4.2)

Flammability Test on Solid

Requirement	Test Sample	Burning Rate (inch/sec)	Limit (inch/sec)	Result
Method for determining extremely flammable and flammable solids	Solid (Dome Climber Swings/Dome Climber Hammocks)	DNI	≤0.1	Pass

Note: DNI = Did Not Ignite IBE = Ignite But Self-Extinguished

Flammability Test on Fabrics

Requirement	Fabric Type	Location	Average(sec)	Limit(sec)	Result
Standard for the flammability of fabric	Plain	Gloves	DNI	≥3.5	Pass

1.3 Heavy elements test - Total Lead content

As specified in ASTM F963-23 standard consumer safety specification for toy safety clause 4.3.5, acid digestion methods specified in clause 8.3 were used and total Lead content was determined by ICP-OES

1.3.1 Toy substrate materials:

Tested Item	MDL (mg/kg)	Limit(mg/kg)	Result (mg/kg)				
			1+4+5	6+8+9	10+15+16	11+13+14	12+21+22
Total Lead (Pb)	10	100	ND	ND	ND	ND	ND

Tested Item	MDL (mg/kg)	Limit(mg/kg)	Result (mg/kg)				
			17+19	20+32	23+25	24+26+27	28+29+30
Total Lead (Pb)	10	100	ND	ND	ND	ND	ND

Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 7 of 24

Tested Item	MDL (mg/kg)	Limit(mg/kg)	Result (mg/kg)		
			18+31	7	33
Total Lead (Pb)	10	100	ND	ND	ND

1.3.2 Toy Paint/Similar Surface Coating materials:

Tested Item	MDL (mg/kg)	Limit(mg/kg)	Result (mg/kg)
			2+3
Total Lead (Pb)	10	90	ND

1.4 Heavy elements test - Migration of certain elements

As specified in ASTM F963-23 standard consumer safety specification for toy safety clause 4.3.5, acid extraction methods specified in clause 8.3 were used and Migration of certain elements content were determined by ICP-OES

Tested Item	Unit	MDL	Limit (Modeling Clay)	Limit (Other than Modeling Clay)	Result	
					2	3
Soluble Lead (Pb)	mg/kg	5	90	90	ND	ND
Soluble Barium (Ba)	mg/kg	10	250	1000	ND	ND
Soluble Cadmium (Cd)	mg/kg	5	50	75	ND	ND
Soluble Chromium (Cr)	mg/kg	5	25	60	ND	ND
Soluble Mercury (Hg)	mg/kg	5	25	60	ND	ND
Soluble Antimony (Sb)	mg/kg	5	60	60	ND	ND
Soluble Selenium (Se)	mg/kg	5	500	500	ND	ND
Soluble Arsenic (As)	mg/kg	2.5	25	25	ND	ND

Tested Item	Unit	MDL	Limit (Modeling Clay)	Limit (Other than Modeling Clay)	Result		
					7	8	9
Soluble Lead (Pb)	mg/kg	5	90	90	ND	ND	ND
Soluble Barium (Ba)	mg/kg	10	250	1000	ND	ND	ND
Soluble Cadmium (Cd)	mg/kg	5	50	75	ND	ND	ND
Soluble Chromium (Cr)	mg/kg	5	25	60	ND	ND	ND
Soluble Mercury (Hg)	mg/kg	5	25	60	ND	ND	ND
Soluble Antimony (Sb)	mg/kg	5	60	60	ND	ND	ND
Soluble Selenium (Se)	mg/kg	5	500	500	ND	ND	ND
Soluble Arsenic (As)	mg/kg	2.5	25	25	ND	ND	ND

Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 8 of 24

Tested Item	Unit	MDL	Limit (Modeling Clay)	Limit (Other than Modeling Clay)	Result		
					10	11	12
Soluble Lead (Pb)	mg/kg	5	90	90	ND	ND	ND
Soluble Barium (Ba)	mg/kg	10	250	1000	ND	ND	ND
Soluble Cadmium (Cd)	mg/kg	5	50	75	ND	ND	ND
Soluble Chromium (Cr)	mg/kg	5	25	60	ND	ND	ND
Soluble Mercury (Hg)	mg/kg	5	25	60	ND	ND	ND
Soluble Antimony (Sb)	mg/kg	5	60	60	ND	ND	ND
Soluble Selenium (Se)	mg/kg	5	500	500	ND	ND	ND
Soluble Arsenic (As)	mg/kg	2.5	25	25	ND	ND	ND

Tested Item	Unit	MDL	Limit (Modeling Clay)	Limit (Other than Modeling Clay)	Result		
					13	14	15
Soluble Lead (Pb)	mg/kg	5	90	90	ND	ND	ND
Soluble Barium (Ba)	mg/kg	10	250	1000	ND	ND	ND
Soluble Cadmium (Cd)	mg/kg	5	50	75	ND	ND	ND
Soluble Chromium (Cr)	mg/kg	5	25	60	ND	ND	ND
Soluble Mercury (Hg)	mg/kg	5	25	60	ND	ND	ND
Soluble Antimony (Sb)	mg/kg	5	60	60	ND	ND	ND
Soluble Selenium (Se)	mg/kg	5	500	500	ND	ND	ND
Soluble Arsenic (As)	mg/kg	2.5	25	25	ND	ND	ND

Tested Item	Unit	MDL	Limit (Modeling Clay)	Limit (Other than Modeling Clay)	Result		
					16	17	18
Soluble Lead (Pb)	mg/kg	5	90	90	ND	ND	ND
Soluble Barium (Ba)	mg/kg	10	250	1000	ND	ND	ND
Soluble Cadmium (Cd)	mg/kg	5	50	75	ND	ND	ND
Soluble Chromium (Cr)	mg/kg	5	25	60	ND	ND	ND
Soluble Mercury (Hg)	mg/kg	5	25	60	ND	ND	ND
Soluble Antimony (Sb)	mg/kg	5	60	60	ND	ND	ND
Soluble Selenium (Se)	mg/kg	5	500	500	ND	ND	ND
Soluble Arsenic (As)	mg/kg	2.5	25	25	ND	ND	ND

Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 9 of 24

Tested Item	Unit	MDL	Limit (Modeling Clay)	Limit (Other than Modeling Clay)	Result		
					19	20	21
Soluble Lead (Pb)	mg/kg	5	90	90	ND	ND	ND
Soluble Barium (Ba)	mg/kg	10	250	1000	ND	ND	ND
Soluble Cadmium (Cd)	mg/kg	5	50	75	ND	ND	ND
Soluble Chromium (Cr)	mg/kg	5	25	60	ND	ND	ND
Soluble Mercury (Hg)	mg/kg	5	25	60	ND	ND	ND
Soluble Antimony (Sb)	mg/kg	5	60	60	ND	ND	ND
Soluble Selenium (Se)	mg/kg	5	500	500	ND	ND	ND
Soluble Arsenic (As)	mg/kg	2.5	25	25	ND	ND	ND

Tested Item	Unit	MDL	Limit (Modeling Clay)	Limit (Other than Modeling Clay)	Result		
					22	23	24
Soluble Lead (Pb)	mg/kg	5	90	90	ND	ND	ND
Soluble Barium (Ba)	mg/kg	10	250	1000	ND	ND	ND
Soluble Cadmium (Cd)	mg/kg	5	50	75	ND	ND	ND
Soluble Chromium (Cr)	mg/kg	5	25	60	ND	ND	ND
Soluble Mercury (Hg)	mg/kg	5	25	60	ND	ND	ND
Soluble Antimony (Sb)	mg/kg	5	60	60	ND	ND	ND
Soluble Selenium (Se)	mg/kg	5	500	500	ND	ND	ND
Soluble Arsenic (As)	mg/kg	2.5	25	25	ND	ND	ND

Tested Item	Unit	MDL	Limit (Modeling Clay)	Limit (Other than Modeling Clay)	Result		
					25	26	27
Soluble Lead (Pb)	mg/kg	5	90	90	ND	ND	ND
Soluble Barium (Ba)	mg/kg	10	250	1000	ND	ND	ND
Soluble Cadmium (Cd)	mg/kg	5	50	75	ND	ND	ND
Soluble Chromium (Cr)	mg/kg	5	25	60	ND	ND	ND
Soluble Mercury (Hg)	mg/kg	5	25	60	ND	ND	ND
Soluble Antimony (Sb)	mg/kg	5	60	60	ND	ND	ND
Soluble Selenium (Se)	mg/kg	5	500	500	ND	ND	ND
Soluble Arsenic (As)	mg/kg	2.5	25	25	ND	ND	ND

Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 10 of 24

Tested Item	Unit	MDL	Limit (Modeling Clay)	Limit (Other than Modeling Clay)	Result		
					28	29	30
Soluble Lead (Pb)	mg/kg	5	90	90	ND	ND	ND
Soluble Barium (Ba)	mg/kg	10	250	1000	ND	ND	ND
Soluble Cadmium (Cd)	mg/kg	5	50	75	ND	ND	ND
Soluble Chromium (Cr)	mg/kg	5	25	60	ND	ND	ND
Soluble Mercury (Hg)	mg/kg	5	25	60	ND	ND	ND
Soluble Antimony (Sb)	mg/kg	5	60	60	ND	ND	ND
Soluble Selenium (Se)	mg/kg	5	500	500	ND	ND	ND
Soluble Arsenic (As)	mg/kg	2.5	25	25	ND	ND	ND

Tested Item	Unit	MDL	Limit (Modeling Clay)	Limit (Other than Modeling Clay)	Result	
					31	33
Soluble Lead (Pb)	mg/kg	5	90	90	ND	ND
Soluble Barium (Ba)	mg/kg	10	250	1000	ND	ND
Soluble Cadmium (Cd)	mg/kg	5	50	75	ND	ND
Soluble Chromium (Cr)	mg/kg	5	25	60	ND	ND
Soluble Mercury (Hg)	mg/kg	5	25	60	ND	ND
Soluble Antimony (Sb)	mg/kg	5	60	60	ND	ND
Soluble Selenium (Se)	mg/kg	5	500	500	ND	ND
Soluble Arsenic (As)	mg/kg	2.5	25	25	ND	ND

Note: - Results shown of soluble elements are of adjusted analytical results by subtracting analytical correction factor.

Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 11 of 24

1.5 ASTM – Phthalates Content

As specified in ASTM F963-23 standard consumer safety specification for toy safety clause 4.3.8, with reference to CPSC-CH-C1001-09.4, and Phthalates content were determined by GC-MS

Test Item(s)	CAS No.	Unit	MDL	Limit	Result (s)	
					17+19+25	26+27+31
Dibutyl Phthalate (DBP)	84-74-2	mg/kg	30	1000	ND	ND
Benzylbutyl Phthalate (BBP)	85-68-7	mg/kg	30	1000	ND	ND
Di-(2-ethyl hexyl) phthalate (DEHP)	117-81-7	mg/kg	30	1000	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	mg/kg	100	1000	ND	ND
Di-n-Hexyl phthalate (DHP/DnHP/DHEXP)	84-75-3	mg/kg	30	1000	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	mg/kg	30	1000	ND	ND
Di-n-pentylphthalate (DPEP/DPENP)	131-18-0	mg/kg	30	1000	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	mg/kg	30	1000	ND	ND

Test Item(s)	CAS No.	Unit	MDL	Limit	Result (s)	
					28+29+30	33
Dibutyl Phthalate (DBP)	84-74-2	mg/kg	30	1000	ND	ND
Benzylbutyl Phthalate (BBP)	85-68-7	mg/kg	30	1000	ND	ND
Di-(2-ethyl hexyl) phthalate (DEHP)	117-81-7	mg/kg	30	1000	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	mg/kg	100	1000	ND	ND
Di-n-Hexyl phthalate (DHP/DnHP/DHEXP)	84-75-3	mg/kg	30	1000	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	mg/kg	30	1000	ND	ND
Di-n-pentylphthalate (DPEP/DPENP)	131-18-0	mg/kg	30	1000	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	mg/kg	30	1000	ND	ND

Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 12 of 24

Test Item(s)	CAS No.	Unit	MDL	Limit	Result (s)	
					15+18+24	2+3
Dibutyl Phthalate (DBP)	84-74-2	mg/kg	30	1000	ND	ND
Benzylbutyl Phthalate (BBP)	85-68-7	mg/kg	30	1000	ND	ND
Di-(2-ethyl hexyl) phthalate (DEHP)	117-81-7	mg/kg	30	1000	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	mg/kg	100	1000	ND	ND
Di-n-Hexyl phthalate (DHP/DnHP/DHEXP)	84-75-3	mg/kg	30	1000	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	mg/kg	30	1000	ND	ND
Di-n-pentylphthalate (DPEP/DPENP)	131-18-0	mg/kg	30	1000	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	mg/kg	30	1000	ND	ND

Test Item(s)	CAS No.	Unit	MDL	Limit	Result (s)	
					10+16+23	11+13+14
Dibutyl Phthalate (DBP)	84-74-2	mg/kg	30	1000	ND	ND
Benzylbutyl Phthalate (BBP)	85-68-7	mg/kg	30	1000	ND	ND
Di-(2-ethyl hexyl) phthalate (DEHP)	117-81-7	mg/kg	30	1000	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	mg/kg	100	1000	ND	ND
Di-n-Hexyl phthalate (DHP/DnHP/DHEXP)	84-75-3	mg/kg	30	1000	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	mg/kg	30	1000	ND	ND
Di-n-pentylphthalate (DPEP/DPENP)	131-18-0	mg/kg	30	1000	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	mg/kg	30	1000	ND	ND

Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 13 of 24

Test Item(s)	CAS No.	Unit	MDL	Limit	Result (s)
					12+21+22
Dibutyl Phthalate (DBP)	84-74-2	mg/kg	30	1000	ND
Benzylbutyl Phthalate (BBP)	85-68-7	mg/kg	30	1000	ND
Di-(2-ethyl hexyl) phthalate (DEHP)	117-81-7	mg/kg	30	1000	ND
Diisononyl phthalate (DINP)	28553-12-0	mg/kg	100	1000	ND
Di-n-Hexyl phthalate (DHP/DnHP/DHEXP)	84-75-3	mg/kg	30	1000	ND
Diisobutyl phthalate (DIBP)	84-69-5	mg/kg	30	1000	ND
Di-n-pentylphthalate (DPEP/DPENP)	131-18-0	mg/kg	30	1000	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	mg/kg	30	1000	ND

2. Lead Content

2.1 CPSIA - Lead in Paint/Similar Surface Coating Materials

Test Method: With reference to CPSC-CH-E1003-09.1 - Standard Operating Procedure for Determining Lead (Pb) in Paint and Other Similar Surface Coatings

Analysis was performed by ICP-OES

Tested Item	MDL (mg/kg)	Limit(mg/kg)	Result (mg/kg)
			2+3
Total Lead (Pb)	10	90	ND

2.2 CPSIA - Lead in Accessible Substrate Materials

Test Method: With reference to CPSC-CH-E1002-08.3 - Standard Operation Procedure for Determining Total Lead (Pb) in Non-Metal Children Product ;

With reference to CPSC-CH-E1001-08.3 - Standard Operating Procedure for Determining Total Lead (Pb) in Children's Metal Products (Including Children's Metal Jewelry)

Analysis was performed by ICP-OES

Tested Item	MDL (mg/kg)	Limit(mg/kg)	Result (mg/kg)				
			1+4+5	6+8+9	10+15+16	11+13+14	12+21+22
Total Lead (Pb)	10	100	ND	ND	ND	ND	ND

Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 14 of 24

Tested Item	MDL (mg/kg)	Limit(mg/kg)	Result (mg/kg)				
			17+19	20+32	23+25	24+26+27	28+29+30
Total Lead (Pb)	10	100	ND	ND	ND	ND	ND

Tested Item	MDL (mg/kg)	Limit(mg/kg)	Result (mg/kg)		
			18+31	7	33
Total Lead (Pb)	10	100	ND	ND	ND

3. CPSIA – Phthalates Content

Test Method: With reference to CPSC-CH-C1001-09.4

Analysis was performed by Gas Chromatography Mass Spectrometer (GC-MS)

Test Item(s)	CAS No.	Unit	MDL	Limit	Result (s)	
					17+19+25	26+27+31
Dibutyl Phthalate (DBP)	84-74-2	mg/kg	30	1000	ND	ND
Benzylbutyl Phthalate (BBP)	85-68-7	mg/kg	30	1000	ND	ND
Di-(2-ethyl hexyl) phthalate (DEHP)	117-81-7	mg/kg	30	1000	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	mg/kg	100	1000	ND	ND
Di-n-Hexyl phthalate (DHP/DnHP/DHEXP)	84-75-3	mg/kg	30	1000	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	mg/kg	30	1000	ND	ND
Di-n-pentylphthalate (DPEP/DPENP)	131-18-0	mg/kg	30	1000	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	mg/kg	30	1000	ND	ND

Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 15 of 24

Test Item(s)	CAS No.	Unit	MDL	Limit	Result (s)	
					28+29+30	33
Dibutyl Phthalate (DBP)	84-74-2	mg/kg	30	1000	ND	ND
Benzylbutyl Phthalate (BBP)	85-68-7	mg/kg	30	1000	ND	ND
Di-(2-ethyl hexyl) phthalate (DEHP)	117-81-7	mg/kg	30	1000	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	mg/kg	100	1000	ND	ND
Di-n-Hexyl phthalate (DHP/DnHP/DHEXP)	84-75-3	mg/kg	30	1000	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	mg/kg	30	1000	ND	ND
Di-n-pentylphthalate (DPEP/DPENP)	131-18-0	mg/kg	30	1000	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	mg/kg	30	1000	ND	ND

Test Item(s)	CAS No.	Unit	MDL	Limit	Result (s)	
					15+18+24	2+3
Dibutyl Phthalate (DBP)	84-74-2	mg/kg	30	1000	ND	ND
Benzylbutyl Phthalate (BBP)	85-68-7	mg/kg	30	1000	ND	ND
Di-(2-ethyl hexyl) phthalate (DEHP)	117-81-7	mg/kg	30	1000	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	mg/kg	100	1000	ND	ND
Di-n-Hexyl phthalate (DHP/DnHP/DHEXP)	84-75-3	mg/kg	30	1000	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	mg/kg	30	1000	ND	ND
Di-n-pentylphthalate (DPEP/DPENP)	131-18-0	mg/kg	30	1000	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	mg/kg	30	1000	ND	ND

Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 16 of 24

Test Item(s)	CAS No.	Unit	MDL	Limit	Result (s)	
					10+16+23	11+13+14
Dibutyl Phthalate (DBP)	84-74-2	mg/kg	30	1000	ND	ND
Benzylbutyl Phthalate (BBP)	85-68-7	mg/kg	30	1000	ND	ND
Di-(2-ethyl hexyl) phthalate (DEHP)	117-81-7	mg/kg	30	1000	ND	ND
Diisononyl phthalate (DINP)	28553-12-0	mg/kg	100	1000	ND	ND
Di-n-Hexyl phthalate (DHP/DnHP/DHEXP)	84-75-3	mg/kg	30	1000	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	mg/kg	30	1000	ND	ND
Di-n-pentylphthalate (DPEP/DPENP)	131-18-0	mg/kg	30	1000	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	mg/kg	30	1000	ND	ND

Test Item(s)	CAS No.	Unit	MDL	Limit	Result (s)	
					12+21+22	
Dibutyl Phthalate (DBP)	84-74-2	mg/kg	30	1000	ND	
Benzylbutyl Phthalate (BBP)	85-68-7	mg/kg	30	1000	ND	
Di-(2-ethyl hexyl) phthalate (DEHP)	117-81-7	mg/kg	30	1000	ND	
Diisononyl phthalate (DINP)	28553-12-0	mg/kg	100	1000	ND	
Di-n-Hexyl phthalate (DHP/DnHP/DHEXP)	84-75-3	mg/kg	30	1000	ND	
Diisobutyl phthalate (DIBP)	84-69-5	mg/kg	30	1000	ND	
Di-n-pentylphthalate (DPEP/DPENP)	131-18-0	mg/kg	30	1000	ND	
Dicyclohexyl phthalate (DCHP)	84-61-7	mg/kg	30	1000	ND	

4. USA 16 CFR Part 1303 Ban of Lead Containing Paint and Certain Consumer Products Bearing Lead- Containing Paint

Test Method: With reference to CPSC-CH-E1003-09.1 - Standard Operating Procedure for Determining Lead (Pb) in Paint and Other Similar Surface Coatings

Analysis was performed by ICP-OES

Test Item(s)	Unit	MDL	Limit	Result	
				2+3	
Lead (Pb)	mg/kg	10	90	ND	

Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 17 of 24

5. CPSIA Section 103 Tracking Labels for Children's Products

Test Sample	Requirement	Result
Dome Climber Swings/Dome Climber Hammocks	Tracking Labels for Children's Products, CPSIA Section 103	PASS

6. As specified in title 16, code of federal regulations, chapter II- consumer products Safety commission of U.S.A

6.1 Physical and Mechanical Tests

USE AND ABUSE TEST	NO. OF SAMPLE TESTED	SHARP POINT	SHARP EDGE	SMALL PART
		(1500.48)	(1500.49)	(1501)
As Received	2	Pass	Pass	N/A
Impact Test (Sec. 1500. 51b)	2	Pass	Pass	N/A
Bite Test (Sec. 1500. 53c)	2	N/A	N/A	N/A
Torque Test (Sec. 1500. 53e)	2	Pass	Pass	N/A
Tension Test (Sec. 1500. 53f)	2	Pass	Pass	N/A

Note: N/A=Not Applicable

6.2 Flammability Tests

Flammability Test on Solid (Sec.1500.44)

AS SPECIFIED IN TITLE 16 PART 1500.44 CODE OF FEDERAL REGULATIONS U.S.A.

Requirement	Test Sample	Burning Rate (inch/sec)	Limit (inch/sec)	Result
Method for determining extremely flammable and flammable solids	Solid (Dome Climber Swings/Dome Climber Hammocks)	DNI	≤0.1	Pass

Note: DNI=Did Not Ignite

Flammability Test on Fabrics

Requirement	Fabric Type	Location	Average(sec)	Limit(sec)	Result
Standard for the flammability of fabric	Plain	Gloves	DNI	≥3.5	Pass

Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 18 of 24

7. Lead Content

7.1 15 U.S.C. § 1278a - Lead in Accessible Substrate Materials

Test Method: With reference to CPSC-CH-E1002-08.3 - Standard Operation Procedure for Determining Total Lead (Pb) in Non-Metal Children Product ;

With reference to CPSC-CH-E1001-08.3 - Standard Operating Procedure for Determining Total Lead (Pb) in Children's Metal Products (Including Children's Metal Jewelry)

Analysis was performed by ICP-OES

Tested Item	MDL (mg/kg)	Limit(mg/kg)	Result (mg/kg)				
			1+4+5	6+8+9	10+15+16	11+13+14	12+21+22
Total Lead (Pb)	10	100	ND	ND	ND	ND	ND

Tested Item	MDL (mg/kg)	Limit(mg/kg)	Result (mg/kg)				
			17+19	20+32	23+25	24+26+27	28+29+30
Total Lead (Pb)	10	100	ND	ND	ND	ND	ND

Tested Item	MDL (mg/kg)	Limit(mg/kg)	Result (mg/kg)		
			18+31	7	33
Total Lead (Pb)	10	100	ND	ND	ND

Specimen Description:

1. Silvery metal
2. Blue coating
3. Yellow coating
4. Silvery metal
5. Silvery metal
6. Silvery metal
7. Silvery metal screw
8. Silvery metal
9. Silvery metal nut
10. Black plastic
11. Black textile belt
12. Blue textile thread
13. Black textile belt
14. Black textile belt
15. Black soft plastic

Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 19 of 24

16. Black plastic
17. Blue plastic
18. LT.brown soft plastic
19. Red plastic
20. Silvery metal
21. Orange textile thread
22. White textile thread
23. Black plastic
24. Black soft plastic
25. White plastic
26. Orange soft plastic
27. Red soft plastic
28. Purple soft plastic
29. Deep skyblue soft plastic
30. Greenyellow soft plastic
31. Yellow soft plastic
32. Silvery metal
33. White foam

Note:

- MDL = Method Detection Limit
- ND = Not Detected(<MDL)
- N/A=Not Applicable
- 1mg/kg=1ppm=0.0001%
- “+” =Composite test has been performed as per client’s request and the result(s) is (are) calculated using the minimum specimen weight.


Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 20 of 24

Photo(s) of the sample(s)






Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 21 of 24

Photo(s) of the sample(s)






Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 22 of 24

Photo(s) of the sample(s)






Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 23 of 24

Photo(s) of the sample(s)



Test Report

Report No.: ELE2604C06519

Date: Apr. 20, 2026

Page No.: 24 of 24

Photo(s) of the sample(s)



***** End of Report *****

Remark: This report is considered invalidated without the Special Seal of Shenzhen Element Testing Co., Ltd.. This report shall not be altered, increased, or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of Shenzhen Element Testing Co., Ltd., this test report shall not be copied except in full and published as advertisement.