

DIEKAN 1640



Insulating oil

TOTAL

Mineral insulating pure oil not inhibited.

EMPLOYMENTS

Insulating oil

- **DIEKAN 1640** is a dielectric mineral based oil, not inhibited.
- **DIEKAN 1640** is specially used as dielectric, in transformers, switches and electric equipments.

SPECIFICATIONS

National and international specifications

- C.E.I 10.1 classes I
- I.E.C 296 classes I

ADVANTAGES

- High insulating power.
- Low viscosity to guarantee an effective cooling.
- Excellent resistance to the oxidation to allow long operative periods.
- Low pour point
- Pure product without gases, water and solid substances in suspension.

CHARACTERISTICS	METHODS	UNIT	C.E.I 10.1 Specific	DIEKAN 1640
			Class I	Class I
Aspect	Visual	--	Limpid	limpid
Density at 20°C	ASTM D 1298	kg/l	0,895 Max	0,853
Viscosity at 40 °C	ASTM D 445	mm ² /s	16,5 Max	12,80
Pour Point	ASTM D 97	°C	-30 Max	-33
Flash Point P.M.	ASTM D 93	°C	140 Min	174
Neutralization No	CEI 10.1	mg KOH/g	0,03 Max	0,01
Corrosive sulphur	ASTM D 1275		Not corrosive	Not corrosive
Breakdown voltage: Untreated	IEC 156	KV	30 Min	48
Treated		KV	50 Min	>65
Dissipation factor (tg Δ) at 90°C	IEC 247	--	0,005 Max	0,001
Oxidation stability: sludge	CEI 74	%p	0,10 Max	0,05
neutralization value		mg KOH/g	0,40 Max	0,12

The above mentioned information does not constitute a specification but is an indication based on current production and can be affected by allowable production.