


Supplementary material for
Mother-pebble-resolved fracture sequences in random Li_4SiO_4
ceramic breeder beds by bonded-template DEM

Jian Wang et al.



Supplementary Fig. S1 — Three-dimensional single-pebble fragment morphology. Final morphology of the x-normal 0.05 m s^{-1} single-pebble rerun at 0.30 mm displacement, rendered from the particle and intact-bond dumps. The 500 subparticles are coloured by final intact-bond connected component: largest fragment, second-largest fragment and smaller fragments. Semi-transparent tubes show the remaining intact internal bonds. The final graph contains 5335 intact bonds and 40 fragments, with the two largest fragments containing 236 and 226 subparticles. The split-type morphology is used as qualitative calibration evidence against published Li_4SiO_4 single-pebble fracture observations.