

Bonded-template DEM reveals strength- and topology-dependent fracture-event sequences in packed brittle ceramic pebbles

Jian Wang^{a,b,*}, Siyu Wang^a, Hang Zhang^a, Ming-Zhun Lei^b, Wei Wen^{a,b},
Qi-Gang Wu^b, Gang Shen^a, Haishun Deng^a

^a*Anhui University of Science and Technology, Huainan, Anhui 232001, China*

^b*Institute of Plasma Physics, Chinese Academy of Sciences, Hefei, Anhui 230031, China*

Abstract

Packed brittle pebbles can lose mechanical integrity through a small number of localized particle fractures before bed-wide fragmentation is visible. Here, we develop a bonded-template discrete-element workflow that inserts 500-subparticle brittle templates into random packed beds with no pre-loading bond loss and records parent-particle fracture events during compression. A nominal 1 mm Li_4SiO_4 template is calibrated against single-pebble crush-load and split-fragment constraints. Accepted 100-particle bed windows retain 493,500 initial internal bonds, measurable load transfer and a connected native force graph before fracture loading. The completed dataset contains four localized cracking sequences, three zero-loss controls and an eleven-row material-response table, including a six-case strength matrix across two cracking geometries. The early-cracking geometry keeps first localized bond loss at 19 micrometres as strength is reduced from nominal to 0.25x, with endpoint bond loss increasing from 10 to 15 only at 0.25x. The synchronous-cracking geometry shifts first localized bond loss from 39 micrometres at nominal strength to 19 micrometres at 0.50x and 0.25x, again increasing endpoint bond loss to 15 only at 0.25x. These results show that fracture onset in finite packed-particle windows is controlled by the combination of local force-path topology and bonded-particle strength. The workflow converts packed-bed compression from bulk force reporting

*Corresponding author.

Email address: wjfttt@mail.ustc.edu.cn (Jian Wang)

into a source-data-backed event sequence with particle identity, bond-loss increment and native force-network state.

Keywords: brittle ceramic pebble; bonded-particle DEM; packed bed; particle breakage; force network; fracture-event sequence; bond strength

1. Introduction

Packed beds of brittle pebbles, pellets and granules occur in powder compaction, handling, filtration, catalytic reactors, comminution and functional ceramic beds. Particle fracture changes the contact skeleton, local stiffness, contact area and transport pathways. The first damaged particle can redirect load while the global bed still appears intact. A useful numerical description should identify which parent particle breaks, when the first internal damage occurs, how much bond loss is introduced and which force path surrounds the damaged particle.

Experiments and established simulations define complementary parts of this problem. Single-particle crush tests provide load scale, size dependence, failure-initiation and fragment-mode targets [1–5]. Bed-compression studies provide stiffness, compaction, breakage-ratio and pressure-drop trends [6–9]. DEM force-chain studies add coordination number, contact-force distribution and load-path evolution [10–12]. These studies establish strength scales and bed-level consequences; the earliest internal event chronology inside individual parent particles is still difficult to observe in a packed bed.

DEM breakage models handle particle fracture with different event resolutions. Particle-replacement models replace an overloaded particle with fragments and are efficient for bed-scale impact, compression and comminution simulations [13–15]. Crushable-bed studies use this route to study how a prescribed crushed fraction changes stiffness, packing and coordination [16, 17]. Bonded-particle models represent a brittle object as subparticles joined by breakable bonds and can resolve internal crack growth and fragment topology [18]. A packed-bed method that combines these advantages needs three operations in one calculation: placing many bonded parent particles into a random load-bearing bed, preserving each parent-particle bond graph before compression and exporting a time-ordered fracture-event table linked to the native force network.

We introduce a locked-template workflow for fracture-resolved packed-bed compression (Fig. 1). Proxy spheres first settle under gravity to create a




Figure 1: Locked-template workflow for fracture-resolved packed-bed compression. A nominal 1 mm bonded particle is represented by a 500-subparticle bonded template. Proxy spheres first settle under gravity without internal bonds. The settled proxy centres are replaced by intact bonded templates, so internal bond failure starts during compression. The entry-state record includes internal-bond conservation, native inter-particle force connectivity, six-wall force output and gravity-baseline-corrected incremental force balance. Bond-state records are then converted into a particle-resolved fracture-event database.

random packing. The settled centres are then replaced by 500-subparticle bonded templates, which are created separately and translated as intact groups into the bed. Internal bond failure starts during compression. Local internal-bond records and native pair/wall contact records are converted into parent-particle fracture-event sequences and force-network histories. The study uses Li_4SiO_4 as a representative brittle ceramic pebble with published single-particle crush data and packed-bed relevance [19–21]. The central question is how random force-path topology and bonded-particle strength jointly control the onset and localization of early fracture events.

2. Methods

2.1. Bonded-particle template

Each nominal 1 mm pebble is represented by 500 spherical subparticles connected by stress-breakable cohesive bonds. The selected weak-plane template uses bulk bonds away from a prescribed plane and weaker cross-plane bonds to reproduce a split-type failure mode. The template uses 4,935 initial internal bonds per parent particle. Single-pebble calibration runs use the same contact formulation as the bed calculations. The selected template is treated as a calibrated representation for event-sequence calculations within the tested sensitivity range.

2.2. Locked-template bed construction

Random beds are generated in two stages. First, 1 mm proxy spheres settle under gravity in an 11 mm by 11 mm lateral box. Second, the final proxy centres are used as insertion sites for intact bonded templates generated in

a separate dilute configuration. Atom-id ranges identify each parent particle after transfer. Accepted 100-particle beds contain 50,000 subparticles and 493,500 internal bonds before compression.

2.3. Entry-state loading

Before fracture interpretation, each bed is checked for internal-bond conservation, measurable top-wall load transfer and a connected native force graph. Wall-force output is corrected by the gravity baseline from the settled state. The selected entry protocol uses five 1 micrometre step-relaxed increments, a restored contact modulus of 1.5×10^{10} Pa and 10,000 pre-compression relaxation steps. The accepted entry state retains all internal bonds and forms a top-to-bottom connected native force graph.

2.4. Fracture-event extraction

Compression runs write thermo histories, internal-bond local records and native pair/wall contact records. Broken-bond increments are obtained by comparing each internal-bond record with the intact reference graph. Broken bonds are assigned to parent-particle ids through atom-id ranges. The event table records displacement, parent-particle id, bond-loss increment, damaged-particle count and height rank. Native force-network descriptors are reconstructed from local contact forces between distinct parent particles.

2.5. Strength matrix

The repaired dataset adds a six-case strength matrix on two accepted cracking geometries. Bulk and weak-plane normal/tangential bond strengths are scaled by 0.75, 0.50 and 0.25 relative to the nominal values. All six rows reach the 60 micrometre endpoint and are postprocessed into the same event and native-force-network tables as the nominal cases. The matrix records first localized bond-loss displacement, endpoint broken bonds, damaged parent-particle count, final inter-particle force sum, top reachability and bottom reachability from the top-loaded set.

3. Results

3.1. Single-particle template calibration

The selected weak-plane template reaches the intended 1 mm crush-load scale and produces two dominant fragments with small chips (Fig. 2). The reference 500-subparticle case gives a peak top force of 18.64 N and a peak

Table 1: Model and bonded-template parameters

Parameter	Value	Use in the calculations
Parent-particle nominal diameter	1.0 mm	Single-particle and bed calculations
Subparticles per parent particle	500	Bonded template
Initial internal bonds per parent particle	4,935	Intact template count before compression
Initial internal bonds per 100-particle bed	493,500	Accepted bed-window count before compression
Particle density	2400 kg m ⁻³	Contact dynamics and template mass
Young’s modulus	90 GPa	Hertzian contact input for single-particle calibration
Restored bed contact modulus	1.5×10^{10} Pa	Accepted loaded-entry and bed compression protocol
Poisson ratio	0.25	Particle-particle and particle-wall contacts
Restitution coefficient	0.3	Normal damping in the contact law
Friction coefficient	0.5	Particle-particle and particle-wall contacts
Bond normal stiffness	1.0×10^{14} N m ⁻³	Cohesive bonds
Bond tangential stiffness	5.0×10^{13} N m ⁻³	Cohesive bonds
Bulk bond normal/tangential strength	90 MPa	Bonds away from the weak plane
Weak-plane bond normal/tangential strength	22.5 MPa	Reduced cross-plane bonds
Bulk bond-creation distance	0.20 mm	Main internal bond network
Weak-plane bond-creation distance	0.09 mm	Reduced cross-plane connectivity
Selected weak-plane orientation	x-normal	Reference template orientation
Single-particle loading velocities	0.10, 0.05 and 0.03 m s ⁻¹	Loading-rate sensitivity
Bed displacement increment	1 micrometre	Step-relaxed loaded-entry and compression runs
Bonded-template timestep	5.0 ns	Single-particle and bonded-bed compression
Proxy-settling timestep	1.0 microsecond	Unbonded proxy-sphere deposition

bottom force of 18.07 N. The final intact-bond graph contains two major fragments of 227 and 224 subparticles plus small chips. Orientation and strength-multiplier checks preserve the two-major-fragment mode while showing expected load scatter.

Resolution checks with 250, 500 and 1000 subparticles retain first-break displacement within 0.0950-0.0965 mm and preserve the two-fragment topology. Peak top force increases from 17.91 N at 250 subparticles to 19.40 N at 500 and 22.64 N at 1000, showing moderate residual load-scale sensitivity. Matched-boundary loading-rate checks at 0.10, 0.05 and 0.03 m s⁻¹ retain first-break displacement within 0.0945-0.0950 mm and preserve two dominant fragments. The 500-subparticle template is used for packed-bed event-sequence calculations with this sensitivity boundary.




Figure 2: Single-pebble template selection and sensitivity. a, Published Li_4SiO_4 crush-load targets and the selected weak-plane bonded template. b, Peak-load distribution across homogeneous, selected weak-plane, orientation-variant, strength-scan and Weibull-sample calculations. c, Subparticle-resolution sensitivity, with peak force and first-break displacement normalized by the 500-subparticle template. d, Final largest- and second-largest-fragment fractions for matched-boundary loading-rate comparisons.

3.2. Entry state before fracture loading

The locked-template route creates accepted 100-particle beds with the expected 493,500 initial internal bonds. The selected entry protocol retains all internal bonds through five 1 micrometre increments (Fig. 3). At the accepted 5 micrometre state, the final top-wall load is 1.638×10^{-2} N and the gravity-baseline-corrected six-wall incremental force is 1.559×10^{-2} N, giving a 4.799% balance residual. The native force graph contains 36 inter-particle force edges and connects the top-loaded set to 28 parent particles, including three bottom-contacting particles.

The contact-modulus restoration series explains the chosen protocol. Zero pre-loading bond loss is retained at 5.0e8, 5.0e9 and 2.0e10 Pa, while 3.0e10 and 5.0e10 Pa introduce pre-loading bond loss. The 1.5×10^{10} Pa entry state provides load transfer, a connected native force graph and intact internal bonds before fracture loading.




Figure 3: Entry-state loading before fracture. a, Endpoint top-wall force and gravity-baseline-corrected wall force during the 5 micrometre entry protocol. b, Force-balance residual across entry displacement. c, Contact-modulus restoration series before fracture loading. d, Native final-state connectivity and intact-bond metrics for the selected entry state.

3.3. Fracture-event sequences

Corrected 60 micrometre compression runs resolve localized fracture-event sequences in finite 100-particle windows (Fig. 4 and Table 2). The pilot sequence loses five of 493,500 internal bonds, all localized in one upper-bed parent particle. Event records contain three increments: two lost bonds at 25 micrometres, two additional lost bonds at 35 micrometres and one additional lost bond at 60 micrometres. The final native graph remains spanning, with 74 inter-particle force edges, 57 top-reachable parent particles and 11 bottom-contacting particles reachable from the top-loaded set.

An independent accepted bed remains intact to 60 micrometres at nominal, 0.5x and 0.25x bond strengths. The final native graph remains spanning, with 83 inter-particle force edges, 67 top-reachable parent particles and 18 bottom-contacting particles reachable from the top-loaded set. A delayed-cracking bed first loses bonds after 50 micrometres and ends with ten broken bonds localized in two upper-bed parent particles. Two additional accepted cracking geometries provide early and synchronous fracture paths: the early-




Figure 4: Pilot fracture-event sequence and force-network evolution. a, Top-wall force envelope and particle-resolved event windows during the 60 micrometre pilot. b, Cumulative internal-bond loss from the thermo history with event localization. c, Native inter-particle force-network trajectory in force-sum versus edge-count space. d, Reachability trajectory for the top-loaded and bottom-reaching load path during the same sampled states.

cracking geometry starts at 19 micrometres and the synchronous-cracking geometry starts at 39 micrometres under nominal strength. The current event table contains 11 localized event rows from four cracking cases.

3.4. Mechanism variables

The fracture sequences can be reduced to mechanism variables that are more informative than displacement history alone (Fig. 5 and Table 3). The cracking cases occupy higher inter-particle-force regions than the intact bed and weakened-strength controls. The pilot, delayed, early and synchronous cracking cases have final inter-particle force sums of 0.864, 1.032, 0.575 and 0.945 N, while the intact controls cluster near 0.253 N with zero internal-bond loss. Event-window topology shows both force-network densification

Table 2: Fracture-sequence results

Quantity	Pilot bed	Intact bed and weakened-strength controls	Delayed-cracking bed	Interpretation
Parent particles	100	100	100	Finite bed windows
Subparticles	50,000	50,000	50,000	500 subparticles per parent particle
Initial internal bonds	493,500	493,500	493,500	Bonded templates transferred intact
Final intact internal bonds at 60 micrometres	493,495	493,500 at nominal, 0.5x and 0.25x	493,490	Localized loss or zero loss at the endpoint
Damaged parent particles	1	0	2	Damage localizes in upper-bed parent particles
First thermo-resolved bond loss	20 micrometres	none to 60 micrometres	50 micrometres	Onset varies with local force path
Final inter-particle force edges	74	83	63	Native final force topology
Final top-reachable parent particles	57	67	54	Connected load-bearing graph
Final bottom-contacting particles reachable from top	11	18	7	Top-to-bottom force connectivity

and force-network reduction around localized bond-loss events.

The eleven-row material-response table gives a compact endpoint separation. Zero-loss endpoints have final inter-particle force sums of 0.2526-0.2527 N, whereas localized-cracking endpoints span 0.575-1.328 N. The smallest cracking value is 2.28 times the largest zero-loss value, and the midpoint between these ranges is 0.414 N for the current finite windows. Strength multiplier gives an overlapping coordinate: 0.25x, 0.50x and nominal strength all appear in both endpoint classes. Top-reachable counts also overlap between zero-loss and cracking cases. This pattern supports a joint state description built from force-path intensity, packing geometry, bond strength and event chronology.

The endpoint broken-bond fraction remains small, but the surrounding force network reorganizes measurably. In the pilot, the inter-particle edge count densifies by 1.44x before reorganization, the top-reachable population increases by 1.35x and the peak-to-endpoint top-wall force relaxes by 46.4%. The event sequence, parent-particle identity, height rank, native reachability




Figure 5: Mechanism variables for fracture onset. a, Endpoint mechanism map using summed inter-particle contact force and endpoint internal-bond loss. b, Event-window topology response for cracking cases, relating localized bond loss to the next-to-previous inter-particle force-sum ratio and the accompanying edge-count change. c, Native reachability map comparing bottom-contacting particles reachable from the top-loaded set with the total top-reachable parent-particle count. d, Normalized endpoint mechanism fingerprint.

and force relaxation together describe local microcracking embedded in a connected load-bearing skeleton.

3.5. Strength-dependent fracture response

The completed strength matrix directly tests material-property dependence across two cracking geometries (Fig. 6 and Table 4). In the early-cracking geometry, first localized bond loss remains fixed at 19 micrometres from nominal strength through 0.25x strength. Endpoint bond loss stays at ten broken bonds for nominal, 0.75x and 0.50x strength, then increases to 15 broken bonds at 0.25x. Final inter-particle force sum increases from 0.575 N at nominal strength to 1.328 N at 0.75x, 1.196 N at 0.50x and 0.871 N at 0.25x.

The synchronous-cracking geometry shows a clearer onset shift. First localized bond loss moves from 39 micrometres at nominal strength to 29 micrometres at 0.75x and 19 micrometres at 0.50x and 0.25x. Endpoint bond loss stays at ten broken bonds for nominal, 0.75x and 0.50x strength, then

Table 3: Particulate breakage state-variable synthesis

State variable	Result in the present calculations	Physical interpretation	Scope
Internal damage chronology	Four cracking cases provide 11 localized event rows	Converts hidden particle breakage into a time-ordered microcrack sequence	Four finite 100-particle cracking windows
Damaged particle identity	The pilot damages one parent particle; delayed, early and synchronous paths damage two parent particles each	Identifies the local objects carrying early damage	One intact geometry remains unbroken to the endpoint
Native force-network state	Cracking cases retain spanning endpoint force graphs with 57-88 inter-particle force edges	Places local microcracking inside a connected load-bearing skeleton	Reconstructed from sampled native local contacts
Endpoint force-path separation	In 11 material-response endpoints, cracking rows have final inter-particle force sums of 0.575-1.328 N and zero-loss rows have 0.2526-0.2527 N	Identifies force-path intensity as a compact state coordinate	Separation ratio 2.28 in the current finite windows
Macro-response accommodation	Endpoint forces span 0.158-0.649 N across cracking cases	Links microcracking to bed-window force evolution	Values are finite-window descriptors
Strength response	The intact geometry remains unbroken at nominal, 0.5x and 0.25x; cracking geometries respond differently to strength reduction	Shows the combined role of local force path and material strength	Probability estimation requires larger ensembles

Table 4: Strength-matrix endpoint summary

Geometry class	Strength multiplier	First localized bond loss	Endpoint broken bonds	Damaged parent particles	Final force sum	Final top-reachable parents
Early cracking	1.00	19 micrometres	10	2	0.575 N	46
Early cracking	0.75	19 micrometres	10	2	1.328 N	53
Early cracking	0.50	19 micrometres	10	2	1.196 N	62
Early cracking	0.25	19 micrometres	15	2	0.871 N	56
Synchronous cracking	1.00	39 micrometres	10	2	0.945 N	72
Synchronous cracking	0.75	29 micrometres	10	2	1.180 N	79
Synchronous cracking	0.50	19 micrometres	10	2	0.853 N	73
Synchronous cracking	0.25	19 micrometres	15	3	0.747 N	76

increases to 15 broken bonds at 0.25x. Final inter-particle force sum is 0.945 N at nominal strength, 1.180 N at 0.75x, 0.853 N at 0.50x and 0.747 N at 0.25x. All six strength-matrix rows retain a spanning final native force graph.

4. Discussion

The locked-template workflow resolves a practical difficulty in packed brittle-particle simulation: many internally bonded bodies can be placed into a load-bearing random bed while preserving their intact bond graphs.




Figure 6: Strength-dependent fracture response across cracking geometries. a, First localized bond-loss displacement as a function of bond-strength multiplier. b, Endpoint broken-bond count. c, Final inter-particle force sum. d, Native reachability descriptors at the endpoint. e, Matrix overview across intact, early-cracking and synchronous-cracking geometries. All plotted values are generated from the source table `data/figure_source/pb007_material_strength_response.csv`.

This makes the first few internal damage events measurable as a chronological dataset with direct parent-particle identity and native force-network state. The result complements bulk breakage-ratio and final-fragment measurements by exposing the particle-scale initiation history that occurs before bed-wide fragmentation.

The current calculations connect three scales. At the single-particle scale, the weak-plane template matches the available crush-load scale and split-type morphology within the tested resolution and rate sensitivities. At the initialization scale, the locked transfer creates accepted 100-particle beds with zero internal-bond loss and connected native force paths. At the fracture-sequence scale, the same records show localized microcracking embedded in spanning force graphs. The endpoint damage is small in absolute bond fraction, yet the surrounding force-network and macro-response descriptors change substantially.

The material-strength matrix adds direct material-property dependence to the event-sequence dataset. Strength reduction creates geometry-specific

responses across random packings. One cracking geometry keeps the same first-event displacement as strength decreases and changes mainly in endpoint damage at 0.25x. The second cracking geometry advances its first event from 39 to 19 micrometres as strength decreases, then also increases endpoint damage at 0.25x. The intact geometry remains unbroken at nominal, 0.5x and 0.25x strength in the same displacement window. These finite-window results indicate that local force-path topology and bonded-particle strength jointly control early fracture.

The endpoint separation analysis gives the mechanism variables a quantitative role. Across 11 completed material-response endpoints, final inter-particle force sum separates the zero-loss and localized-cracking rows with a 2.28 force-intensity gap, while strength multiplier and top-reachable population overlap across endpoint classes. The result moves the interpretation from force-displacement reporting to a state-space description of early breakage. Local force intensity supplies the clearest endpoint coordinate in the present windows, and bond strength controls how each accepted geometry moves through that state space.

The study remains bounded. The 100-particle windows are designed for event-sequence resolution and mechanism-variable extraction. Quantitative fracture probability, final Li_4SiO_4 material-law calibration and coupled thermal-flow prediction require larger random ensembles, slower cyclic histories and transport/contact-area coupling. The present dataset supplies the traceable intermediate layer: parent-particle damage chronology, local force-path state and material-strength response.

5. Conclusions

1. A 500-subparticle weak-plane bonded template provides a sensitivity-bounded 1 mm brittle-particle representation with split-type failure morphology.
2. Locked-template insertion creates accepted 100-particle beds with 493,500 initial internal bonds, zero pre-loading bond loss and connected native force paths before fracture loading.
3. Corrected compression runs resolve parent-particle fracture-event sequences: four cracking cases produce 11 localized event rows, while three accepted controls remain intact to 60 micrometres.
4. Mechanism variables based on parent-particle identity, first-event displacement, endpoint bond loss, inter-particle force sum and native reach-

ability expose fracture behavior that is hidden in bulk force-displacement histories; the final inter-particle force-sum gap between zero-loss and cracking endpoints is 2.28 in the current material-response table.

5. The completed strength matrix shows geometry-specific material dependence: early-cracking onset remains fixed as strength decreases, whereas synchronous-cracking onset advances with strength reduction; both geometries increase endpoint bond loss at 0.25x strength.

6. Data availability statement

The processed event tables, native force-network summaries, material-response tables, figure source data, manuscript figures and post-processing scripts supporting this study are provided in a reduced reproducibility package with a checksum manifest. The package has been deposited in a persistent repository and is available at <https://doi.org/10.5281/zenodo.20687351>. Very large raw restart files and full local-bond dump histories are retained as larger archives and can be provided on reasonable request subject to repository file-size limits and institutional storage constraints.

7. Code availability statement

The template-generation, run-control, figure-generation and post-processing scripts are included in the reduced reproducibility package under `scripts/`, with representative DEM input files under `simulations/`, and are mirrored in the GitHub repository wangjian-fttt/Mother_particle_bonded_dem_research. The citable archived version uses the same repository DOI, <https://doi.org/10.5281/zenodo.20687351>. The package reproduces manuscript-level processed data tables, figures and source-data matrices from the included CSV tables and representative inputs. The local DEM executable, very large restart files and full raw local-bond dump histories are retained outside the compact package.

8. Acknowledgements

This work was supported by the Anhui Provincial Natural Science Foundation (2408085QA030), the Science Foundation of the Institute of Plasma Physics, Chinese Academy of Sciences (DSJJ-2025-08), the Anhui Intelligent Mine Technology and Equipment Engineering Research Center (AIM-TEERC202307), the China Post-doctoral Science Foundation under Grant

Number 2024M753266, the Excellent Research and Innovation Team of Anhui Province, China (2022AH010052), the Scientific Research Foundation for High-level Talents of Anhui University of Science and Technology, China (2021yjrc51), and the Collaborative Innovation Program of Hefei Science Center, CAS, China (2019HSC-CIP006).

9. Author contributions

Jian Wang: Validation, Supervision, Project administration, Methodology, Investigation, Conceptualization. Siyu Wang: Writing - original draft, Formal analysis, Data curation, Visualization. Hang Zhang: Writing - original draft, Formal analysis, Data curation, Visualization. Ming-Zhun Lei: Writing - review and editing, Validation, Project administration, Formal analysis. Wei Wen: Writing - review and editing, Supervision, Project administration, Methodology, Conceptualization. Qi-Gang Wu: Validation, Resources, Data curation. Gang Shen: Writing - review and editing, Supervision, Project administration. Haishun Deng: Supervision, Project administration.

10. Declaration of competing interest

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

References

- [1] S. Zhao, Y. Gan, M. Kamlah, T. Kennerknecht, R. Rolli, Influence of plate material on the contact strength of Li_4SiO_4 pebbles in crush tests and evaluation of the contact strength in pebble-pebble contact, *Engineering Fracture Mechanics* 100 (2013) 28–37. [doi:10.1016/j.engfracmech.2012.05.011](https://doi.org/10.1016/j.engfracmech.2012.05.011).
- [2] S. Zhao, Y. Gan, M. Kamlah, Failure initiation and propagation of Li_4SiO_4 pebbles in fusion blankets, *Fusion Engineering and Design* 88 (1) (2013) 8–16. [doi:10.1016/j.fusengdes.2012.09.008](https://doi.org/10.1016/j.fusengdes.2012.09.008).
- [3] R. K. Annabattula, M. Kolb, Y. Gan, R. Rolli, M. Kamlah, Size dependent crush analysis of lithium orthosilicate pebbles, *Fusion Science and Technology* 66 (2014) 136–141. [doi:10.13182/FST13-737](https://doi.org/10.13182/FST13-737).

- [4] V. Bhartia, M. H. H. Kolb, M. Moscardini, M. Kamlah, R. K. Annabattula, Elastic response of individual european advanced ceramic breeder pebbles during uniaxial compression, *Fusion Engineering and Design* 153 (2020) 111502. [doi:10.1016/j.fusengdes.2020.111502](https://doi.org/10.1016/j.fusengdes.2020.111502).
- [5] L. M. Tavares, Review and further validation of a practical single-particle breakage model, *KONA Powder and Particle Journal* 39 (2022) 62–83. [doi:10.14356/kona.2022012](https://doi.org/10.14356/kona.2022012).
- [6] N. Zaccari, D. Aquaro, Experimental characterization of ceramic pebble beds, *Journal of Nuclear Materials* 386–388 (2009) 1078–1082. [doi:10.1016/j.jnucmat.2008.12.288](https://doi.org/10.1016/j.jnucmat.2008.12.288).
- [7] R. Lo Frano, M. Puccini, Preliminary investigation of Li_4SiO_4 pebbles structural performance, *Fusion Engineering and Design* 167 (2021) 112388. [doi:10.1016/j.fusengdes.2021.112388](https://doi.org/10.1016/j.fusengdes.2021.112388).
- [8] H. Cheng, Z. Fang, B. Zhou, B. Gong, S. Bu, Z. Li, D. Chen, Experimental study on the pressure drop of helium purge gas in particle crushing pebble beds, *Fusion Engineering and Design* 207 (2024) 114631. [doi:10.1016/j.fusengdes.2024.114631](https://doi.org/10.1016/j.fusengdes.2024.114631).
- [9] Z. Fang, H. Cheng, B. Zhou, B. Gong, Z. Li, Q. Lian, S. Bu, D. Chen, Experimental study on particle crushing and pressure drop characteristics of Li_4SiO_4 breeder pebble beds, *Fusion Engineering and Design* 224 (2026) 115604. [doi:10.1016/j.fusengdes.2025.115604](https://doi.org/10.1016/j.fusengdes.2025.115604).
- [10] Z. An, A. Ying, M. Abdou, Application of discrete element method to study mechanical behaviors of ceramic breeder pebble beds, *Fusion Engineering and Design* 82 (15–24) (2007) 2233–2238. [doi:10.1016/j.fusengdes.2007.02.004](https://doi.org/10.1016/j.fusengdes.2007.02.004).
- [11] Y. Gan, M. Kamlah, Discrete element modelling of pebble beds: With application to uniaxial compression tests of ceramic breeder pebble beds, *Journal of the Mechanics and Physics of Solids* 58 (2) (2010) 129–144. [doi:10.1016/j.jmps.2009.10.009](https://doi.org/10.1016/j.jmps.2009.10.009).
- [12] J. Wang, M. Liu, H. Deng, M. Lei, Dem study on the force chain evolution of biaxial compression of pebble bed, *Nuclear Materials and Energy* 40 (2024) 101717. [doi:10.1016/j.nme.2024.101717](https://doi.org/10.1016/j.nme.2024.101717).

- [13] N. Jiménez-Herrera, G. K. P. Barrios, L. M. Tavares, Comparison of breakage models in dem in simulating impact on particle beds, *Advanced Powder Technology* 29 (3) (2018) 692–706. [doi:10.1016/j.appt.2017.12.006](https://doi.org/10.1016/j.appt.2017.12.006).
- [14] G. K. P. Barrios, N. Jiménez-Herrera, L. M. Tavares, Simulation of particle bed breakage by slow compression and impact using a dem particle replacement model, *Advanced Powder Technology* 31 (7) (2020) 2749–2758. [doi:10.1016/j.appt.2020.05.011](https://doi.org/10.1016/j.appt.2020.05.011).
- [15] W. Zhou, D. Wang, G. Ma, X. Cao, C. Hu, W. Wu, Discrete element modeling of particle breakage considering different fragment replacement modes, *Powder Technology* 360 (2020) 312–323. [doi:10.1016/j.powtec.2019.10.002](https://doi.org/10.1016/j.powtec.2019.10.002).
- [16] J. Wang, M. Z. Lei, S. L. Xu, H. Yang, P. H. Zhao, K. Xu, Y. T. Song, Dem simulation of mechanical behavior in one-dimensional compression of crushable ceramic pebble bed, *Fusion Engineering and Design* 168 (2021) 112606. [doi:10.1016/j.fusengdes.2021.112606](https://doi.org/10.1016/j.fusengdes.2021.112606).
- [17] J. Wang, M.-Z. Lei, M.-Z. Liu, Q.-G. Wu, Z.-C. Cai, K.-S. Wang, H.-S. Deng, Crushing evolution in pebble bed based on a novel method: a crushable dem study, *Nuclear Science and Techniques* 37 (1) (2026) 1. [doi:10.1007/s41365-025-01806-0](https://doi.org/10.1007/s41365-025-01806-0).
- [18] D. O. Potyondy, P. A. Cundall, A bonded-particle model for rock, *International Journal of Rock Mechanics and Mining Sciences* 41 (8) (2004) 1329–1364. [doi:10.1016/j.ijrmms.2004.09.011](https://doi.org/10.1016/j.ijrmms.2004.09.011).
- [19] G. Piazza, J. Reimann, E. Günther, R. Knitter, N. Roux, J. D. Lulewicz, Characterisation of ceramic breeder materials for the helium cooled pebble bed blanket, *Journal of Nuclear Materials* 307–311 (2002) 811–816. [doi:10.1016/S0022-3115\(02\)00983-2](https://doi.org/10.1016/S0022-3115(02)00983-2).
- [20] J. Reimann, E. Arbogast, M. Behnke, S. Müller, K. Thomauske, Thermomechanical behaviour of ceramic breeder and beryllium pebble beds, *Fusion Engineering and Design* 49–50 (2000) 643–649. [doi:10.1016/S0920-3796\(00\)00357-4](https://doi.org/10.1016/S0920-3796(00)00357-4).
- [21] D.-m. Kuang, J. Su, Z.-R. Chen, I. Ogwu, Investigation of the size-dependent crushing behavior of Li_4SiO_4 pebbles via discrete element

method, Fusion Engineering and Design 199 (2024) 114105. doi:
[10.1016/j.fusengdes.2023.114105](https://doi.org/10.1016/j.fusengdes.2023.114105).