

BOM

Component	Layer	Thickness m	Porosity	Density kg/m3	Areal mass kg/m2	Included mass kg	Notes
Positive electrode	active	9.828e-05	0.35	3262	0.208383084	0.0214009427268	Active layer
Negative electrode	active	0.00011076	0.27	1657	0.1339764036	0.01375937664972	Active layer
Positive CC	current collector	1e-05	0	2700	0.027	0.0027729	Aluminum
Negative CC	current collector	8e-06	0	8960	0.07168	0.007361535999900002	Copper
Separator	separator	8e-06	0.47	210.41	0.00168328	0.000172872856	Default porosity assumed
Electrolyte	electrolyte						Excluded due to missing c