

bom

Sheet: BOM

Component	Mass (g/cell)	Mass (kg/kWh)	Source
Positive active material (LNMO)	22.71781512	0.8579605229750238	calc-energy layer_kg_m2.positive_electrode x area
Positive conductive additive (carbon black, 3wt%)	0.7250366527659575	0.02738171881835182	literature default (no parameter), annotated
Positive binder (PVDF, 3wt%)	0.7250366527659575	0.02738171881835182	literature default (no parameter), annotated
Negative active material (graphite)	13.7840859	0.5205694951309495	calc-energy layer_kg_m2.negative_electrode x area
Negative conductive additive (carbon black, 1wt%)	0.143584228125	0.005422598907614058	literature default (no parameter), annotated
Negative binder (CMC/SBR, 3wt%)	0.430752684375	0.01626779672284217	literature default (no parameter), annotated
Separator	0.151263749	0.005712623529757942	calc-energy layer_kg_m2.separator x area
Electrolyte	6.85411584	0.2588523931353216	pore volume x 1.2 g/cm3 (literature density, annotated)
Positive current collector (Al)	2.21832	0.08377702597158714	calc-energy layer_kg_m2.positive_cc x area
Negative current collector (Cu)	5.521152000000001	0.2085117090848391	calc-energy layer_kg_m2.negative_cc x area
Enclosure / tabs	Not modeled		Not provided
Total (incl. electrolyte, excl. casing)	53.27116282703192	2.011837603094639	sum
Total (contract-caliber, electrolyte/casing excluded)	44.39263676900001	1.676531376692158	calc-energy mass_kg
Cell energy (kWh)	0.02647885830600313		calc-energy energy_wh