

Bill of Materials - Design L (Case T2R1NOCEILING)

Changes vs Chen2020 baseline: Al CC 16->10 um, Cu CC 12->8 um, anode porosity 0.25->0.35, nominal 4.9506 Ah.

Layer	Thickness um	Porosity	Areal mass kg/m2	Mass g
Positive electrode (NMC811)	75.6	0.335	0.163994	16.84
Negative electrode (graphite)	85.2	0.35	0.091765	9.42
Positive current collector (Al)	10.0	n/a	0.027000	2.77
Negative current collector (Cu)	8.0	n/a	0.071680	7.36
Separator	12.0	0.47	0.002525	0.26
Total (electrolyte excluded)	190.8	-	0.356964	36.66