

DVP&R - VBF-T5R2-DVPR-01

Case t5_r2 - acceptance criteria from log.jsonl entry 0 (frozen contract). Method = bda simulator chain.

ID	Requirement	Method	Target	Result	Verdict	Evidence
---	---	---	---	---	---	---
DVP-01	Delivers contract capacity (nominal 6.5 Ah class)	simulated 1C CC discharge (DFN)	>= 6.5 Ah (design nominal)	7.171 Ah	PASS	cell/r7_final_f2_energy_dfn.json capacity_ah
DVP-02	Energy density >= 500.94 Wh/kg	calc-energy on 1C DFN discharge	>= 500.94	666.3 Wh/kg	PASS	cell/r7_final_f2_energy_dfn.json (log-evaluate round 7)
DVP-03	4C charge without lithium plating	4C_charge_45C (1C disc + 4C CC to 4.2 V, 45 C) anode potential	min > 0 V	min +0.0506 V	PASS	cell/r7_final_f2_4c45.json anode_potential_v
DVP-04	Max temperature <= 60 C at 4C	lumped thermal in 4C_charge_45C	<= 333.15 K	330.984 K = 57.83 C	PASS	cell/r7_final_f2_4c45.json T_max_K
DVP-05	Voltage window integrity	parameter-set bounds	2.5 - 4.2 V	as designed	PASS	Chen2020 parameter set
DVP-06	Mid-voltage / polarity	midpoint of 1C discharge	positive, stable	3.78 V	PASS	cell/r7_final_f2_energy_dfn.json

N/A rows (criteria not in contract OR simulator out of scope - honestly not simulated):

ID	Requirement	Reason not run
---	---	---
DVP-07	Nail penetration / internal-short thermal runaway	no such simulator in the protocol funnel; N/A (physical test required)
DVP-08	Overcharge to thermal runaway (+0.5 V protocol)	overcharge protocol exists but is outside the frozen criteria; NOT run to avoid unrequested scope
DVP-09	Crush / drop / vibration	mechanical abuse out of simulator scope
DVP-10	Cycle life (rated)	not in acceptance criteria; informational aging run exists but its per-cycle capacity series is protocol-artifact-flagged - a rated cycle-life figure is NOT claimed
DVP-11	Rate-pulse internal resistance spec	DCR reported informationally (2.538 mohm); no target registered in contract