

Bill of Materials — VBF-T7R1NOFORCE-BOM-01

Case t7_r1_noforce — 2026-08-25. Dual caliber g/cell and kg/kWh (cell energy 17.804 Wh). Additive/binder split uses literature weight fractions (parameter set has no additive/binder parameters).

Component	g/cell	kg/kWh	Formula note
Positive AM (NMC811)	16.168	0.908	coating x 0.96 wt (lit default 96/2/2)
Positive CB	0.337	0.019	coating x 0.02 wt (lit default)
Positive binder PVDF	0.337	0.019	coating x 0.02 wt (lit default)
Negative AM (graphite)	10.417	0.585	coating x 0.958 wt (lit default 95.8/1.2/3.0)
Negative CB	0.130	0.007	coating x 0.012 wt (lit default)
Negative binder CMC/SBR	0.326	0.018	coating x 0.03 wt (lit default)
Separator	0.216	0.012	thickness x area x (1-eps) x 397 kg/m3 (tool caliber)
Electrolyte	6.326	0.355	pore vol 5.27 cm3 x 1.2 g/cm3 (lit)
Al current collector	2.773	0.156	10 um x area x 2700 kg/m3
Cu current collector	5.521	0.310	6 um x area x 8960 kg/m3
Enclosure / tabs	Not modeled	—	—
TOTAL	42.552	2.390	36.226 g contract (no electrolyte) + 6.326 g est.