

THERMAL CONDUCTIVITY MATERIAL TESTING REPORT

QC Lab, Dte. SW

Received from: NDC Site#ADP/3C

Received on: 24/02/2022

Nature of Sample #: Silica Phenolic Ablative

Reporting Date: 18/03/2022

Lot # Si (820)-10A/1120-221~333 Lot Size: 7922 RM

Sample ID	Lab Ref.#	Temperature (°C)	Thermal Conductivity (W/m.K)
PP-Si-10A/1120-TC-01	QC/2022/016-R	150 °C	0.336
PP-Si-10A/1120-TC-02	QC/2022/017-R	150 °C	0.315
PP-Si-10A/1120-TC-03	QC/2022/018-R	150 °C	0.276
PP-Si-10A/1120-TC-04	QC/2022/019-R	150 °C	0.295
PP-Si-10A/1120-TC-05	QC/2022/020-R	150 °C	0.290

Analyzed By: 

Verified By: 

Approved By: 
(AM/MGR/HOD/GM)

Form Number	Issue No.	Approved By:
QC/FM/30	02	PD