



Confidential

NATIONAL DEVELOPMENT COMPLEX
Deputy Directorate General of Quality Control
Mechanical Testing Laboratory; S#3A
TEST REPORT

Test Report No: TR (497)/MTL/22
Job Card No: JC (1104)/MTL/22

Date: 07-07-2022

INDENTER'S DATA		
Name: <i>Usama Masood</i>	Designation: <i>GM(T)</i>	
Group: <i>Prefom/QM</i>	Directorate/Sr.Dte/DDG: <i>3DC-P/CPS</i>	
Organization: <i>NDC</i>	Site: <i>3-1</i>	Contact No: <i>9314439-441 Ext:228</i>

GENERAL DATA			
Sample Name: <i>3D Carbon Composite</i>	Sample ID: <i>RD-20C/TS-01~03</i> <i>Lot#: 3D/CCC/Jun 21/L-09</i>		
Project ID: <i>Misc</i>	Sample Material: <i>3D Carbon Composite</i>		
Chemical Composition (If any): <i>Carbon</i>	Geometrical Shape: <i>Bar</i>		
Receiving Date: <i>05-07-2022</i>	Quantity: <i>03 samples</i>	Lot Size: <i>Nil</i> (If any)	Test Date: <i>05-07-2022</i>

TEST DATA			
Test : <i>Tension</i>	Test Type: <i>General</i>	Temp & Humidity: <i>21°C & 43%</i>	Test Speed: <i>2 mm/min.</i>
Gauge Length: <i>Nil</i>	Gauge Height: <i>NA</i>	Span: <i>NA</i>	Scale: <i>NA</i>
Instrument Used: <i>Universal Testing Machine 100 KN</i>			
Extensometer Used: <i>Not used</i>		Load Cell Used: <i>100 KN</i>	
Test Method: <i>MTL/SOP/03 & MTL/WI/02</i>		Qualification Standard: <i>MDE-MP-SQC (Rev 01)</i>	
RESULTS:			
		Sample No	*UTS (MPa)
		01	102.5
		02	110.9
		03	86.3
Status: <i>Samples are Qualified</i>			
Remarks (if any): 1. These results relate to the samples mentioned and tested above. 2. This Test Report shall not be reproduced except in full, without written approval of laboratory. 3. *With Ref to NCR decision (Ref: 3DC-P/NC/IOA-20/01 dated 20-02-2020), samples were made as per approved QAS having bar shape and speed is recommended as 2 mm/min. 4. Qualification Criteria: U.T.S. $\geq$ 76 MPa.			

Test Performed By: <i>Abid Butt; RA</i>	Contact No. <i>3247</i>
---	-------------------------

Verified By: <i>for Mubasher Hassan Khan; PD (MT)</i>	Approved By: <i>Khalid Ata; Dir. (STE)</i>
---	--

MTL/FM/02, Issue 10 (03-04-17)

End of Report

Page 1 of 1

Prepared by: <i>GM</i>	Reviewed by: <i>GM/HOD</i>	Approved by: <i>GMR/DD</i>
------------------------	----------------------------	----------------------------