

AE-252: Synthesis of $[\text{Ru}(\text{CO})(\text{OH})_2(\text{PNPtBu})]$ using Ag_2O , 5 h


Date: 2024-04-04

Tags: Dihydroxo Ag₂O PNP
P(tBu)N(py)P(tBu) $[\text{Ru}(\text{CO})(\text{OH})_2(\text{PNP})]$
NMR AE Future reference analytics ¹H
³¹P stability test

Status: Done

Created by: Alexander Eith

Reaction scheme/sample structure



Literature/reference experiments

Literature	https://doi.org/10.1039/D1EE01053K
Reproduction	/
Related experiments	Experiment - AE-KRA-204: Synthesis of $[\text{Ru}(\text{CO})(\text{OH})_2(\text{PNPtBu})]$ using Ag_2O , 5 h Experiment - AE-238: Synthesis of $[\text{Ru}(\text{CO})(\text{OH})_2(\text{PNPtBu})]$ using Ag_2O , 5 h

Reagents

Name	CAS-Number/Experiment-Number	Amount [mmol]	Equivalents	Mass _{theo} [mg]	Mass _{exp} [mg]	Molar mass [g/mol]	Volume _{theo} [ml]	Volume _{exp} [ml]	Density [g/mL]
$[\text{RuCl}_2(\text{CO})(\text{PNP}\{\text{tBu}\})]$	Experiment - AE-232: Synthesis of $[\text{RuCl}_2(\text{CO})(\text{PNP})]$ with 2,6-Bis((tert-butyl)phosphinomethyl)pyridine via $[\text{RuCl}_2(\text{CO})(\text{p-cymene})]$ -2	0.232	1.00	138.24	138.24	595.53	/	/	/
Ag_2O	20667-12-3	1.425	6.14	330.29	329.81	231.74	/	/	/
H_2O	Experiment - KRA-104: Degassing of Milli-Q water	54.32	234	978.8	/	18.02	0.981	0.98	0.998
THF	Experiment - KRA-080: Degassing of THF	/	/	/	/	/	6.9	7 + 11	/
n-Heptane	Experiment - AE-121: Degassing of n-Heptane	/	/	/	/	/	/	13	/

Procedure/observations

All steps, unless mentioned otherwise, were carried out under argon using standard Schlenk technique or in an argon

filled glovebox. (see Protocol [Protocol - Schlenk Technique](#))

Due to the instability of Ag_2O and Dihydroxo to the light, the procedure was done mostly in the dark. The precise measures, which were taken, are listed in "**Steps**".

Date	Time	Step	Observations
04.04	13:00	A 25mL-brown glas Schlenk flask was prepared, by heating under vacuum	
	13:15	$[\text{RuCl}_2(\text{CO})(\text{PNP})]$ (138.24 mg) was weighted in air into the reaction schlenk flask and the flask was set under argon.	
		The substance was stored under argon ar rt	
05.04	8:20	Ag_2O (329.81 mg) was weighted under air into the reaction schlenk flask and the flask was set under argon.	
		The light in the fumehood was turned out	
	8:45 - 8:46	THF (7.0 mL) and water (0.98 mL) were added to the reaction schlenk flask.	
	8:46 - 13:54	The reaction mixture was stirred for 5 h at 750 rpm. After approx. 3 h the flask was covered in aluminium foil and the light in the fumehood was turned on	
		The light was turned off and the aluminium foil was removed	
	13:54 - 13:58	The reaction mixture was allowed to settle	after-reaction.jpg
	13:58	The reaction mixture was filtrated through a PTFE-syringe-filter (0.20 μm) into a separate 25 mL-Schlenk flask, equipped with a stirring bar.	after-1st-filt.jpg
	14:08 - 14:23	The solvents of the first flask was removed under reduced pressure.	wet-raw-product.jpg
	- 14:48	The obtained solid was dried under reduced pressure	
	15:25	To the solid THF (11 mL) was added und the obtained mixture was stirred and shaken strongly for approx. 5 min	Some solids remained in-THF.jpg
	15:36	n-heptane (10 mL) was added to the mixture	More solids formed, after addition of hept.jpg , after addition of hept settled.jpg

	16:00 - 16:55	The mixture was filtered through a pore 5 frit according to Protocol - Filtration with frit technique into a 100 mL-Schlenk	Slow filtration, first filt was colouress likely due to strong vacuum, whcih leads to evaporation of THF. After approx. 1.5 mL start of typical purple colour. after-approx-1-mL-during-filt.jpg after-approx-2-mL-of-filt.jpg
	16:55 - 17:05	The solid was washed with n-heptane (3 * 1 mL)	after-filt.jpg
	17:06 - 17:08	The solid was dried under reduced pressure	prod-A.jpg
09.04	11:23 - 15:35	The solid was dried under reduced pressure	
	15:50	The solid was transffered into a vial in a 10 mL Schlenk flask	AE-252-1, final prod.jpg
	16:00	A sample (3.2 mg) was transferred into another 10 mL Schlenk flask	
	16:16	To the sample Milli-Q water (1 mL) was added	
		The mixture was stirred for apporx. 2 min	NMR sample in water.jpg
	16:18	A NMR sample was preapred according to Protocol - Preparation of NMR Sample , during the trasnfer the mixture was filtered through a PA syringe filter (pore diamter = 0.22 µm)	AE-252-1, NMR sample after filt.jpg
		The remaining solid of AE-252-1 was stored on the frit at -20 °C in the dark under argon	
22.04		The same NMR tube, which was used for AE-252-1 was submitted again as AE-252-2	NMR-2.jpg
17.05		Two 10 mL-Schlenk flasks were prepared	
	12:50	To each flask AE-252-1 (approx. 4 mg) was added and the flask were set under argon again	
	13:10	To one flask THF-d8 (0.7 mL) was added (AE-252-3) and the obtained suspension was stirred	in THF.jpg
		To the other flask toluene-d8 (0.7 mL) was added (AE-252-4) and the obtained suspension was stirred	in tol.jpg
	13:25	Both, AE-252-3 and -4 , were transffered in separate Yound type NMR tubes according to Protocol - Preparation of NMR Sample	NMR in tol.jpg NMR in THF.jpg
		From both, AE-252-3 and -4 NMR spectra were masured	
08.07	15:00	The sample AE-280-2 was used to prepare an NMR in DMF-d7 accoring to Protocol - Preparation of NMR Sample	

Analysis

Date	Time	Sample name	Analysis method	Used device	Solvent	Raw Data	Processed Data	Comparative Data	Interpretation
10.04	10:14	AE-252-1	NMR 1H, 31P{1H}quant, 1Hzgespg	IAAC 400 MHz I	H2O	AE-252-1_10.zip	AE-252-1_10.nmrium	Experiment - AE-246: Radiation of [Ru(CO)(OH)2(PNP{tBu})] (AE-238, 97 % pure) 365 nm and white -1	Desired product. In 31P no impurities are observed. In 1H some small impurities are observed (mainly some residual solvents)
22.04	17:56	AE-252-2	NMR 1H, 31P{1H}quant, 1Hzgespg	IAAC 400 MHz I	H2O	AE-252-2_10.zip	AE-252-2_10.nmrium	AE-252-1	No relevant change observed. Slight decrease in intensity. 90 % of the main species is still present. Other 10 % are not observed, but also no solid formation is observed --> maybe formation of [Ru(III)]? but no greenish colour is observed
17.05	20:36	AE-252-3	NMR 1H, 31P{1H}quant, 1Hzgespg	IAAC 400 MHz I	THF-d8	AE-252-3-10.zip	AE-252-3_10.nmrium	Experiment - AE-105: Synthesis of [Ru(CO)(OH)2(PNP)] with 2,6-bis(P,P-di(tertbutyl)phosphinomethyl) using Ag2O (AE-105-6) Experiment - AE-KRA-204: Synthesis of [Ru(CO)(OH)2(PNPtBu)] using Ag2O, 5 h (AE-204-1)	Significantly lower concentration than in MeCN-d3 and DMSO-d6. But still signals are good observable. Significantly more impurities are observed in 1H and some impurities are observed in 31P. This increase can be likely explained by the low solubility of the desired complex, since most of the material remained undissolved and so leading to a higher proportion of the impurities in the solution. A signal for the residualwater/-OH group is observed, as well as the other expected signals. The Methylene-bridge proton signal is partially overlapped by a solvent peak of the THF
17.05	18:46	AE-252-4	NMR 1H, 31P{1H}quant, 1Hzgespg	IAAC 400 MHz I	toluene-d8	AE-252-4-10.zip	AE-252-3_10.nmrium	Experiment - AE-105: Synthesis of [Ru(CO)(OH)2(PNP)] with 2,6-bis(P,P-di(tertbutyl)phosphinomethyl) using Ag2O (AE-105-6) Experiment - AE-KRA-204: Synthesis of [Ru(CO)(OH)2(PNPtBu)] using Ag2O, 5 h (AE-204-1) AE-252-3	Very low intensity. Signals in the 1H can not be attributed due to the low concentration. In 31P a weak signal can be observed at 68 ppm. Height approx. 2 to 3 times the base line noise.
08.07	17:00	AE-252-5	NMR 1H, 31P{1H}quant	IAAC 400 MHz I	DMF-d7	AE-252-5.zip	AE-252-5_10.nmrium	/	Good intensity --> good solubility, but slower dissolved than in MeCN Quite large water peak, besides drying over molecular sieve of DMF-d7 Other signals can clearly be seen and fit to what was seen in other solvents. Shift in 31 P: 68 ppm Baseline bit wired: in area were signals are (8 to 1 ppm) generally slightly higher than in other area's. No idea why.

Product characterization and results

Sample	Mass [mg]	Purity	Mass _{pure} [mg]	Amount [μmol]	Yield [%]	Description
AE-252-1	40.17	>97 %	40.17	71.9	31	final prod.jpg

The product is stable in the dark in water at rt for at least 12 d, with only minor degradation of approx. 10 %
Poorly soluble in THF, very poorly soluble in toluene

No material left

Future recommendations

Old procedure	Problem	Suggested new procedure
Direct after reaction: filtration with PTFE syringe filter	filter gets blocked with larger quantities of Ag ₂ O, high pressure was needed towards the end of the filtration	filtration via a filter paper or a filter frit

Linked experiments

- [AEI-010: Synthesis of \[Ru\(CO\)\(OH\)₂\(PNN\)\] using Ag₂O](#)
- [JSC-KS-04: Degassing of n-Heptane](#)
- [AEI-024: Synthesis of \[Ru\(CO\)\(OH\)₂\(NNN\)\] with 2,6-bis\(N,N-diethylaminomethyl\) using Ag₂O](#)
- [AEI-026: Capillary production](#)
- [AEI-048: Synthesis of \[Ru\(CO\)\(OH\)₂\(NNN\)\] with 2,6-bis\(N,N-diisopropylaminomethyl\) using Ag₂O](#)
- [AEI-064: Synthesis of \[Ru\(CO\)\(OH\)₂\(PNP\)\] with 2,6-bis\(P,P-di\(tertbutyl\)phosphinomethyl\) using Ag₂O](#)
- [AEI-073: Synthesis of \[Ru\(CO\)\(OH\)₂\(PNP\)\] with 2,6-bis\(P,P-di\(tertbutyl\)phosphinomethyl\) using Ag₂O](#)
- [AE-101: Synthesis of \[RuCl₂\(CO\)\(PNP\)\] with 2,6-Bis\(\(tert-butyl\)phosphinomethyl\)pyridine via \[RuCl₂\(CO\)\(p-cymene\)\]](#)
- [AE-102: Degassing of THF](#)
- [AE-105: Synthesis of \[Ru\(CO\)\(OH\)₂\(PNP\)\] with 2,6-bis\(P,P-di\(tertbutyl\)phosphinomethyl\) using Ag₂O](#)
- [AE-108: Synthesis of \[RuCl₂\(CO\)\(PNP\)\] with 2,6-Bis\(\(tert-butyl\)phosphinomethyl\)pyridine via \[RuCl₂\(CO\)\(p-cymene\)\]](#)
- [AE-114: Synthesis of \[Ru\(CO\)\(OH\)₂\(PNP\)\] with 2,6-bis\(P,P-di\(tertbutyl\)phosphinomethyl\) using Ag₂O](#)
- [AE-121: Degassing of n-Heptane](#)
- [AE-145: Synthesis of \[Ru\(CO\)\(OH\)₂\(PNP\)\] with 2,6-bis\(P,P-di\(tertbutyl\)phosphinomethyl\) using Ag₂O](#)
- [AE-157: Synthesis of \[RuCl₂\(CO\)\(PNP\)\] with 2,6-Bis\(\(tert-butyl\)phosphinomethyl\)pyridine via \[RuCl₂\(CO\)\(p-cymene\)\]](#)
- [AE-167: Irradiation of PhPDA \(365 nm + white LED, gas phase measurement\), AE-151, 1.5 mg/mg SDS, 2 mg/mL PhPDA](#)

- AE-198: Synthesis of $[\text{Ru}(\text{CO})(\text{OH})_2(\text{PNP}\{\text{tBu}\})]$ with Ag_2O with different reaction times (1, 2, 5, 24 h)
- AE-KRA-204: Synthesis of $[\text{Ru}(\text{CO})(\text{OH})_2(\text{PNPtBu})]$ using Ag_2O , 5 h
- AE-208: Degassing of Milli-Q water
- KRA-080: Degassing of THF
- KRA-104: Degassing of Milli-Q water
- AE-230: Synthesis of $[\text{RuCl}_2(\text{CO})(\text{PNP})]$ with 2,6-Bis((tert-butyl)phosphinomethyl)pyridine via $[\text{RuCl}_2(\text{CO})(\text{p-cymene})]$
- AE-232: Synthesis of $[\text{RuCl}_2(\text{CO})(\text{PNP})]$ with 2,6-Bis((tert-butyl)phosphinomethyl)pyridine via $[\text{RuCl}_2(\text{CO})(\text{p-cymene})]$
- AE-238: Synthesis of $[\text{Ru}(\text{CO})(\text{OH})_2(\text{PNPtBu})]$ using Ag_2O , 5 h
- AE-246: Radiation of $[\text{Ru}(\text{CO})(\text{OH})_2(\text{PNP}\{\text{tBu}\})]$ (AE-238, 97 % pure) 365 nm and white

Linked resources

Protocol - [Preparation of NMR Sample](#)

Protocol - [Filtration with frit technique](#)

Protocol - [Schlenk Technique](#)

Protocol - [Preparation of capillary for H₂O-NMR](#)

Attached files

AE-252-5_10.nmrium

sha256: 869db83c23f61e22a1483c95583266cd983960baabc6b4d457a748a3a8fa5f14

AE-252-5.zip

sha256: 30e96961f7a4f75e3e676f41ba07e306a630c68a11b726d9260cea229d6358e7

AE-252-3_10.nmrium

sha256: 655db7982cab3b6d7a171348e2ca7561b0bb51a3e04244afbf075f9362ffe2b

AE-252-4-10.zip

sha256: 640bc6b561e92e6b0a2b5b215f4dd6a0faa058b30a4f63e961286308ca3c9b6e

AE-252-3-10.zip

sha256: e08b968ed60abf9c8a59649a23b3cc5cca21493ba111f3525e1fa4f9d0269b8a

NMR-in-THF.jpg

sha256: 4d23615c91f055b7b59098c1acb11e4a527e43f97234ee26e7cdea2177ee4c2d



in-THF.jpg

sha256: 960f63444a633d3e09f6d4fa92796627535336c0dbeefdadcc85e7d2e941f3cb



in-tol.jpg

sha256: 038bb16a146d0542ecd3c249faebcd2accae07cd4aa7d62a0b8d0b986d8116de



NMR-in-tol.jpg

sha256: d24b6b50d2d92c5132eafc4bd5861730b253ac4d551a9a9be784e63930d5fa6a



AE-252_Yield_Determination.xlsx

sha256: 1f721f67a8c6286ccf69d6d504db6ed24995d0e5c5bdf1143b5a0726e9e869f4

AE-252-2_10.zip

sha256: a7b692823defa13439c9619ec56e72072636fb250df45e5a3dd99eeb11ab894a

AE-252-2_10.nmrium

sha256: b964aa5db9b7545d0f2d5628b5628a3ae959d9574b47152281b8ab50187a9b71

NMR-2.jpg

sha256: 0b0abd1c4d7736c7dfa40d260d1b82efb9aadfafa29d49397fcb71f1c68411d9



AE-252-1_10.nmrium

sha256: c8dde33ca010673df1728b8355e6c6fbd74432977f4996a9f156f067e8a518a1

AE-252-1_10.zip

sha256: 46a55685061c963d20ecbb68b7e4139c51ebc33926464047da8e345c36a413d6


final-prod.jpg

sha256: 9b68f2fca588ebb62399593b13ec6b007c1d9a326e1ac4a515ed886c654d6c04




NMR-sample-after-filt.jpg

sha256: da1f0c96770729d99ad161aa1e22d05b3a6194ffac31604b3bf100160f02e815



NMR-sample-in-water.jpg

sha256: 4326371a06d9e28d216ac8879ca90bfc979ec24527c5df4dee86d52759bdf773



prod-A.jpg

sha256: d5a7807409dd893cc80627f09a63c97afb5c758123aa40e6a695cebf9657b0a7




after-approx-2-mL-of-filt.jpg

sha256: 273c5c7f646f77e67b3221aeb5b024c891f5f50fff6cc9455a29371eed3b174f




in-THF.jpg

sha256: 2ea5df34d44c6c9915edbcbcf49d61754ae2be0897fef2f70e499964e21c0d65



wet-raw-product.jpg

sha256: c8a8a507de3dd738022827b69f44dacb9fcc534d3e07a7aaa9abde5e930d9328



after-1st-filt.jpg

sha256: 50b7883d7220d35570075171a0b660ea62e74277077bdaca52c38fdae9cbbf4



after-reaction.jpg

sha256: 49fdc52231ac7ec76143347ced8f77e44ce2a4b035a1cd8efa53c2026f8bdaff



after-filt.jpg

sha256: 466dfe5c330d0ee4db20c871a86ed2841d89145801faea07bad2a7caaaa6e3a8



after-approx-1-mL-during-filt.jpg

sha256: 2db6cf790ea356f91d913fc3c05c1dbfb4a257578d9bf3bf5e43ff76690d2f7d



after-addition-of-hept-settled.jpg

sha256: 5b6df678fa335208dc4f1cc88a5954a14cb1a6880ff04f9d8508206a1a253069



after-addition-of-hept.jpg

sha256: f4040776e5d475bcae69ab34f8b718a4f2e6ced7ed595e0d1599fa814d9ca3d2



AE-2042.cdxml

sha256: 70d2a67f6ae7477a3c31ec8e776e001181c617b18e0d276cd2995bdbdfdb2ca2



Unique eLabID: 20240404-33635a49cec7282ce4628c7f5476a2157a80517f
Link: <https://elab.water-splitting.org/experiments.php?mode=view&id=928>