
A Concise Review of Scientific Research at EQ-SANS: Advancing Nanoscale Science Across Diverse Disciplines

Anonymous Author(s)

Affiliation

Address

email

Abstract

1 The Extended Q-range Small-Angle Neutron Scattering (EQ-SANS) instrument at
2 the Spallation Neutron Source (SNS), Oak Ridge National Laboratory (ORNL), has
3 enabled investigations of nanoscale structures across diverse scientific disciplines.
4 This review highlights key research advancements using EQ-SANS, spanning
5 polymer science, biological and biomimetic systems, nanomaterials and colloids,
6 energy materials, and environmental applications. We also discuss methodological
7 developments and data analysis, including the integration of machine learning
8 and artificial intelligence. Leveraging its unique capabilities, EQ-SANS has pro-
9 vided unprecedented insights into complex material behaviors, advancing both
10 fundamental science and technological innovation.

11 1 Introduction: The EQ-SANS Instrument and Scope of this Review

12 The Extended Q-range Small-Angle Neutron Scattering (EQ-SANS) diffractometer at the Spallation
13 Neutron Source (SNS) in Oak Ridge National Laboratory (ORNL) stands as a premier instrument for
14 probing structural details across length scales ranging from approximately 0.5 nm to over hundreds
15 of nm [1]. It offers wide neutron momentum transfer (Q) coverage, high intensity, and excellent
16 wavelength resolution via time-of-flight and frame-skipping modes [2, 3]. Its ability to provide
17 real-time, in-situ measurements, particularly for time-dependent phenomena and complex processes,
18 distinguishes it as a powerful tool in materials science and beyond. The instrument features neutron
19 optics optimized for transport and background minimization, and a two-dimensional ^3He tube detector
20 featuring high counting rates and efficiency [2]. Initial operations confirmed its design goals, marking
21 a significant advancement in SANS instrumentation at pulsed spallation sources [3].

22 This review overviews diverse research at EQ-SANS, illustrating its impact on nanoscale science..
23 We aim to synthesize the key findings from a broad range of publications, organize them into thematic
24 areas to showcase the instrument's versatility and the breadth of its scientific contributions. This
25 review will cover advancements in polymer science and engineering, insights into biological and
26 biomimetic systems, studies on nanomaterials and colloidal systems, research in energy materials and
27 environmental applications, and significant methodological developments in data analysis, including
28 the emerging role of artificial intelligence. By highlighting these achievements, we underscore
29 EQ-SANS's crucial role in deciphering complex material structures and their relationship to material
30 properties, paving the way for future scientific discoveries and technological innovations.

31 2 Advancements in Polymer Science and Engineering

32 EQ-SANS has significantly contributed to understanding the intricate structures and behaviors of
33 polymers, ranging from their self-assembly in solutions to their mechanical properties in bulk. The

34 unique capabilities of SANS, particularly with deuterium labeling, allow for detailed insights into
35 polymer conformation, phase behavior, and interactions with other components.

36 2.1 Polymer Conformation and Self-Assembly

37 Studies on bottlebrush polymers have clarified their structural evolution and scaling laws. Ahn
38 et al. tracked PLA bottlebrushes during ROMP and observed elongated \rightarrow globular \rightarrow elongated
39 transitions driven by excluded-volume effects [4]. Alaboalirat et al. established scaling relations
40 linking structural parameters to backbone and side-chain degrees of polymerization [5]. Atomistic
41 side-chain conformations have also been resolved with combined SANS and MD [6].

42 Block-copolymer self-assembly in water has been mapped extensively. Do et al. combined mesoscale
43 simulations and SANS to identify spherical micellar, lamellar, and reverse-micellar phases of Pluronic
44 L62 [7]. Jang et al. showed Pluronic blends form temperature-sensitive unilamellar vesicles with
45 tunable size and bilayer thickness [8]. Additives modulate micellization: nucleoside analogues reduce
46 L62 micelle size and enhance core hydration [9], while ionic liquids depress transition temperatures
47 and favor larger aggregates [10].

48 Guest–host architecture and hydration have been probed by contrast variation. In PAMAM den-
49 drimers, surfactants localize to the periphery, inducing steric crowding and reduced hydration [11].
50 Amphiphilic invertible polymers form cylindrical core–shell micelles that invert in toluene [12].
51 Isotopic-label SANS further shows star-polymer branches fold inward via solvation effects [13, 14].

52 2.2 Polymer Mechanics and Dynamics

53 The mechanical properties and dynamics of polymers and polymer composites have been extensively
54 studied. The impact of backbone rigidity on the thermomechanical properties of semiconducting
55 polymers with conjugation break spacers was quantified, revealing that increased spacer length en-
56 hances flexibility and reduces elastic modulus [15]. The chain stiffness of donor-acceptor conjugated
57 polymers in solution was measured by SANS, showing that side-chain size and branching signif-
58 icantly influence persistence lengths, correlating with charge-carrier mobility [16]. Investigations
59 into poly(3-alkylthiophenes) (P3ATs) have demonstrated that side chain isomerism influences their
60 rigidity, with branched side chains promoting greater flexibility [17, 18, 19].

61 The impact of polydispersity on microphase separation in thin films of lamellar-forming diblock
62 copolymers has been explored, demonstrating that increasing polydispersity reduces the number of
63 lamellar strata and induces conformational asymmetry [20]. The phenomenon of structural anisotropy
64 relaxation in deformed polymers has been quantitatively investigated, revealing a scaling law where
65 the relaxation rate is proportional to Q at high Q and short times, challenging classical Rouse and tube
66 models [21, 22]. Furthermore, a generalized Zimm plot approach has been introduced to quantify
67 molecular deformation in polymer melts using SANS, providing a model-independent analysis of
68 spatially dependent molecular deformation [23].

69 Structural information from SANS is often used to complement other experimental techniques, such
70 as neutron spin-echo (NSE) or rheometry, for a more complete understanding of polymer dynamics.
71 Studies on associative polymer networks have shown that sticker clustering increases relaxation
72 times, attributed to cooperative dissociation of multiple bonds, while also surprisingly accelerating
73 diffusion due to loop defects [24]. Hindered segmental dynamics in associative protein hydrogels
74 due to transient binding have also been quantified using NSE [25]. The dynamics of Li^+ transport in
75 poly(ethylene oxide) (PEO) based electrolytes have been investigated using neutron spin-echo (NSE),
76 dielectric spectroscopy, and MD simulations, revealing a strong coupling between dc conductivity
77 and dielectric α relaxation time [26].

78 2.3 Responsive Polymer Systems

79 Temperature-responsive polymer systems have been a key area of research. Hyatt et al. investigated
80 poly(*N*-isopropylacrylamide) (pNIPAM) microgels, observing mass segregation at the particle pe-
81 riphery and a decrease in the polymer network length scale at high temperatures, linked to charge
82 segregation [27, 28, 29]. The self-assembly of thermo-reversible block copolymers coating single-
83 walled carbon nanotubes has been characterized, showing tunable encapsulation structures [30, 31].
84 The phase behavior of Pluronic P65 blended with 5-methylsalicylic acid (5mS) exhibited a closed

85 loop-like phase behavior, transitioning from isotropic to ordered and back to isotropic with increasing
86 temperature [32]. Additionally, temperature-responsive polymersomes composed of poly(3- methy-n-
87 vinylcaprolactam)-block-(poly(n-vinylpyrrolidone) diblock copolymers have been synthesized for
88 reduced doxorubicin-induced cardiotoxicity [33].

89 The study of water-soluble polymers across multiple concentration regimes has quantified the number
90 of hydration water molecules associated with different polymers using contrast-variation SANS,
91 leading to improved understanding of water-polymer interactions [34, 35, 36, 37]. The self-assembly
92 of a multifunctional ionic block copolymer in selective solvents has been elucidated, forming
93 ellipsoidal core-shell micelles with varying sizes and aggregation numbers depending on concentration
94 [38]. The dynamic implications of noncovalent interactions in amphiphilic single-chain polymer
95 nanoparticles (SCNPs) have also been explored, demonstrating how these interactions restrict internal
96 relaxations and guide the design of biomimetic materials [39].

97 **3 Insights into Biological and Biomimetic Systems**

98 EQ-SANS has been instrumental in unraveling the complex structures and dynamics of biological
99 and biomimetic systems, providing a deeper understanding of fundamental biological processes and
100 informing the design of advanced biomaterials.

101 **3.1 Protein Structure and Dynamics**

102 The molecular conformation and binding activity of crucial proteins, such as the tumor suppressor
103 NF2/Merlin, have been investigated, revealing a rheostat model of function where conformation and
104 binding are not simply open or closed states [40]. The dynamic structure of the scaffolding protein
105 NHERF1, and how disease-associated point mutations alter its flexibility and signaling complex
106 assembly, has been characterized using NMR and SANS [41]. The structural information of a-Catenin
107 obtained from EQ-SANS helped understanding nanoscale dynamics too, both in solution and in
108 complex with F-actin, suggesting its dynamic conformations enable mechanosensing [42]. Phospho-
109 mimetic mutation of the multi-domain scaffolding protein NHERF1 and buffer salt concentration
110 was show to influence the protein’s nanoscale dynamics and binding kinetics [43].

111 The conformational behavior of intrinsically disordered proteins (IDPs) under macromolecular
112 crowding conditions has been explored, revealing a biphasic response of compaction followed by
113 expansion for FlgM [44]. The folding propensity of IDPs by osmotic stress has been investigated,
114 highlighting the importance of hydration changes in IDP folding [45]. The solution structures of
115 NADPH-dependent assimilatory Sulfite Reductase (SiR) have been modeled, providing insights into
116 electron transfer mechanisms and conformational changes upon subunit binding and changes in redox
117 state [46, 47, 48]. Furthermore, the structural ensemble of an IDP complex (NCBD/ACTR complex,
118 that is associated with breast and ovarian cancers) has been characterized using an integrated approach
119 combining residue-specific deuterium labeling SANS, MD simulations, and deep learning algorithms
120 [49].

121 **3.2 Membrane Biophysics**

122 EQ-SANS has clarified the structure and dynamics of lipid bilayers, often in the presence of peptides
123 and other biomolecules. PIP2 clusters the cell-adhesion molecule CD44 and mediates assembly of
124 CD44–Ezrin heterocomplexes, while the conformation of Ezrin bound to PIP2 and F-actin illuminates
125 the membrane–cytoskeleton interface [50, 51].

126 Cholesterol may promote protein binding by altering membrane electrostatics and solvation [52].
127 Joint SANS/SAXS resolved the molecular structure of sphingomyelin in fluid bilayers, informing
128 lipid packing and reconciling differences between NMR- and scattering-derived parameters [53].

129 Peptide–membrane interactions strongly remodel bilayer structure. An HIV-1 gp41 fusion-peptide
130 derivative undergoes a helix-to-sheet transition that induces localized negative curvature and increased
131 rigidity, changes consistent with fusion promotion [54, 55, 56]. Alamethicin disrupts cholesterol
132 distribution and homogenizes laterally heterogeneous phases [57], while melittin causes concentration-
133 dependent thickening or thinning linked to lipid redistribution [58].

134 Lipid transport is sensitive to environment and architecture: methanol accelerates DMPC flip-flop
135 and intervesicle transfer [59]; bicelles exhibit faster transfer than vesicles, attributed to interfacial
136 defects from hydrophobic mismatch [60, 61].

137 Lipid domains (rafts) have been probed at nanoscopic scales. The bending modulus of domains
138 was isolated, showing modulus mismatch drives lateral heterogeneity [62]. In vivo evidence for
139 domains in *Bacillus subtilis* membranes was obtained using isotopic labeling [63, 64, 65]. Rafts
140 appear to buffer membrane physical properties, stabilizing diffusion and bending modulus with tem-
141 perature changes [66]. Ergosterol shows nonstereotypical distributions and concentration-dependent
142 rigidifying/softening effects, and promotes jump diffusion [67].

143 3.3 Biomaterials, Bio-Inspired Systems, and Drug Delivery

144 EQ-SANS studies have advanced the design of biomaterials for drug delivery and other applica-
145 tions. Lignin-graft-poly(lactic-co-glycolic acid) biopolymers have been synthesized for polymeric
146 nanoparticle synthesis, exhibiting a core-shell structure and showing potential as a delivery system
147 [68]. Recombinant globular fusion proteins have been engineered to self-assemble into vesicles
148 with tunable size and membrane structure, with EQ-SANS measurements quantifying membrane
149 thickness and confirming temperature-dependent transitions critical for designing protein-based deliv-
150 ery systems. [69]. PEGylation site-dependent structural heterogeneity of monoPEGylated human
151 parathyroid hormone fragment hPTH(1-34) has been investigated, showing core-shell cylindrical
152 structures with size variations potentially impacting pharmacokinetics [70]. The spontaneous nanos-
153 tructures of bicellar mixtures and the effects of temperature, salinity, concentration, and PEGylated
154 lipids on nanodisc-to-vesicle transitions have been characterized, revealing nanodisc stabilization by
155 PEGylation [71, 72]. Nucleopore-inspired polymer hydrogels for selective biomolecular transport
156 have been developed, demonstrating selective permeability based on binding interactions between
157 biomolecules and the hydrogel [73].

158 The structural and dynamic heterogeneity in associative networks formed by artificial coiled-coil
159 proteins has been explored, revealing various static length scales and superdiffusive regimes [74, 75].
160 Alginate/PEO-PPO-PEO composite hydrogels with thermally-active plasticity have been developed,
161 demonstrating increased elastic modulus and fracture stress above the lower gelation temperature
162 [76]. The enhancement of polymer thermoresponsiveness and drug delivery across biological barriers
163 by adding small molecules to poloxamer has also been demonstrated [77]. The assembly of lipid-
164 hyaluronan complexes in osteoarthritic conditions, and the influence of HA concentration and
165 molecular weight on their structure, has been investigated, with implications for cartilage lubrication
166 [78].

167 3.4 Plant Biology

168 Research at EQ-SANS has also contributed to plant biology and bio-inspired materials. The structural
169 changes of the CESA1 catalytic domain of Arabidopsis cellulose synthesis complex provided evidence
170 for CESA trimers, supporting the "hexamer of trimers" model for cellulose synthesis [79]. Dynamic
171 in vivo monitoring of granum structural changes in *Ctenanthe setosa* during drought stress and
172 recovery has revealed rapid recovery of granum structure upon rewatering, preceding functional and
173 biochemical recovery [80]. The functional in vitro diversity of an intrinsically disordered plant protein
174 (COR15A) during freeze-thawing, encoded by its structural plasticity, has been investigated [81].
175 Evidence for lignin-carbohydrate complexes from studies of transgenic and wild type switchgrass
176 and a model lignin-pectin composite has been provided, suggesting their role in biomass recalcitrance
177 [82].

178 4 Nanomaterials and Colloidal Systems

179 EQ-SANS has been a crucial tool for characterizing the structure and behavior of diverse nanomateri-
180 als and colloidal systems, from metal nanoparticles to complex hierarchical assemblies.

4.1 Nanoparticle Synthesis and Characterization

Gold nanoparticle (AuNP) architectures span from 2D superlattices formed within polymer vesicle layers via hydrophobic interactions—useful for traceable nanoreactors and electron-exchange platforms [83]—to binary AuNP/Brij 58/water superlattices whose structures are AuNP-size dependent and thermally responsive [84]. Charge-tunable surfactant capping also yields water-redispersible, highly stable AuNPs suitable for biomedical processing [85].

Pluronic triblock copolymers markedly improve BNNT dispersibility in water [86]. BNNTs further self-assemble into 2D hexagonal arrays in block-copolymer matrices (with piezoelectric potential) [87] and into highly ordered 2D binary superlattices with cationic surfactant vesicles via electrostatics [88].

Silica-conjugated polymer hybrid fluorescent nanoparticles prepared by surface-initiated polymerization exhibit tunable optical responses [89]. Core-shell nanospheres with smectic hydrophobic cores and PEG shells show concentration-dependent structures relevant to drug release [90].

4.2 Colloidal Interactions and Dynamics

The densification of ionic liquid molecules within hierarchical nanoporous carbon structures has been revealed, showing significantly higher room temperature ionic liquid (RTIL) densities compared to the bulk fluid due to strong affinity between the RTIL cation and the carbon surface [91]. A dense microemulsion system formed with an ionic liquid has been studied, revealing a two-phase system of water-in-oil and bicontinuous microemulsions [92]. The internal structure of polyelectrolyte complex coacervates has been comprehensively evaluated, determining chain dimensions, validating sticky reptation theory, and quantifying salt doping effects on dynamics [93].

The multiscale structure of asphaltenes in various solvents has been investigated, showing that asphaltene clusters persist to dilute concentrations and follow a fractal scaling law [94]. The aggregation behavior of high-purity vanadyl petroporphyrins (VOPPs) and their impact on asphaltene aggregation have been explored, with VOPPs forming small nanoaggregates and influencing asphaltene self-assembly [95]. The interfacial behavior of purified VOPPs and their influence on asphaltene film formation at the water-oil interface has also been studied, revealing that VOPPs can form monolayers with low tension but do not prevent thick asphaltene films [96].

The effect of magnetization on the gel structure and protein electrophoresis in polyacrylamide hydrogel nanocomposites has been investigated, showing morphological changes and reduced pore size correlating with protein separation performance [97]. An interface-driven stiffening mechanism in polymer nanocomposites has been identified, where chains desorb from nanoparticle surfaces and entangle with free chains during resting periods, leading to interfacial hardening [98]. The synergistic role of temperature and salinity in the aggregation of nonionic surfactant-coated silica nanoparticles has been demonstrated, promoting surfactant adsorption and silica aggregation [99].

4.3 Advanced Nanostructure Fabrication

The formation of uniformly aligned chiral photonic films from cellulose nanocrystals (CNCs) within a thin capillary has been demonstrated, accelerating the ordering process and leading to highly oriented films [100]. Multicompartmental microcapsules from star copolymer micelles have been fabricated using layer-by-layer assembly, possessing nanoporous shells capable of storing different components [101]. The structural study of star polyelectrolytes and their porous multilayer assembly in solution revealed contraction of cationic star polyelectrolyte arms and disruption of spatial ordering upon salt addition [102].

A novel bio-templating method for synthesizing chiral metal-organic frameworks (MOFs) from achiral precursors using chiral nematic nanocelluloses has been developed, resulting in chiral zeolitic imidazolate frameworks (ZIFs) with enantioselective sensing abilities [103]. The kinetically controlled assembly of conjugated polymer (CP) nanostructures has been investigated, yielding hierarchically organized CP systems with distinct optoelectronic properties through in situ polymerization [104]. The control of molecular ordering in water-soluble conjugated polymers through thermally-controlled and surfactant-guided assembly has also been shown to influence electronic interaction and optical function [105]. The discovery of iridescence in nematic liquid crystals composed of

nanoplates, even without long-range periodicity, has opened new possibilities for photonic materials [106].

5 Energy Materials and Environmental Applications

EQ-SANS has been a valuable tool for understanding the structure and dynamics of materials relevant to energy storage, conversion, and environmental remediation.

5.1 Battery and Energy Storage Materials

In-situ observation of solid electrolyte interphase (SEI) formation in ordered mesoporous hard carbon has provided real-time information on the composition and microstructure of electrodes in lithium half-cells [107]. The framework expansion of ordered mesoporous hard carbon anodes with ionic-liquid electrolytes has been observed, highlighting the importance of framework expansion and SEI formation for stable cycling [108]. Insight into SEI formation in bis(fluorosulfonyl)imide based ionic liquid electrolytes has been gained, confirming the protective role of the bis(fluorosulfonyl)imide (FSI-) anion against 1-ethyl-3-methylimidazolium (EMIm) cation co-intercalation [109].

Structural investigation using EQ-SANS has contributed to the understanding of the solution dynamics and binding of polyvinylidene fluoride (PVDF) binder with silicon, graphite, and Nickel Manganese Cobalt (NMC) materials have been investigated, revealing incomplete binder adsorption on silicon, disrupting percolation pathways and leading to poor cycling performance [110]. The origin of rate limitations in solid-state polymer batteries from constrained segmental dynamics within the cathode has been identified, where PEO chains adsorb onto lithium iron phosphase (LFP) particles, reducing Li⁺ mobility [111]. The structural properties of quaternary ammonium-based ionic liquids have been studied, characterizing short- and long-range liquid structure indicative of alternating polarity, charge, and neighboring domains [112].

The effect of metal ion intercalation on the structure of MXene and water dynamics on its internal surfaces has been explored, showing that K⁺ intercalation enhances structural homogeneity and water stability in MXenes [113]. The structure-performance relationships of lithium-ion battery cathodes have been revealed by contrast-variation SANS, deconvoluting carbon and binder phases and correlating solvent-accessible carbon black surface area with diminished capacity retention [114].

5.2 Catalysis and Adsorption

The linking of CO₂ sorption performance to polymer morphology in aminopolymer/silica composites has been achieved through neutron scattering, revealing that poly(ethylenimine) (PEI) forms a thin conformal coating on pore walls, with additional polymer aggregating into plugs [115]. The interactions of an imine polymer with nanoporous silica and carbon in hybrid adsorbents for carbon capture have been investigated, showing strong densification of PEI in carbon nanopores and its impact on capture capacity [116]. The distribution and mobility of PEI within mesoporous silica after multiple CO₂ sorption-regeneration cycles have been probed, highlighting the crucial role of water in maintaining PEI distribution and mobility [117]. The underlying roles of polyol additives in promoting CO₂ capture in PEI/silica adsorbents have been elucidated, showing that poly(ethylene glycol) (PEG) displaces wall-bound PEI, making amines more accessible for CO₂ sorption [118].

The adsorption and catalytic activity of gold nanoparticles in mesoporous silica have been studied, demonstrating that confined gold nanoparticles (AuNPs) can withstand aggregation under high salinity, retaining catalytic activity [119]. Characterization of nano-assemblies inside mesopores using neutron scattering has extended a method to include interparticle correlations, enabling qualitative characterization of surfactants and nanoparticles adsorbed in cylindrical pores [120].

5.3 Environmental Remediation and Sustainable Materials

Research into solvent extraction systems for heavy metal ions has utilized SANS. The microscopic structures of tri-n-butyl phosphate (TBP)/n-octane mixtures have been investigated, revealing that TBP self-associates into ellipsoidal assemblies [121]. EQ-SANS data have provided complementary information to the neutron polarization analysis to accurately determine coherent scattering intensity from biphasic solvent extraction systems, crucial for structural analysis of extracted complexes [122].

281 A telescoping view of solute architectures in a complex fluid system involved in metal refining and
282 purification has elucidated the hierarchical aggregation of metal-ligand complexes [123]. Proton
283 chelating ligands have been shown to drive improved chemical separations for rhodium, with SANS
284 characterizing the outer-sphere assembly of the Rh(III) complex [124].

285 The nanoscopic structure of borosilicate glass with additives for nuclear waste vitrification has
286 been investigated, revealing the impact of additives on microphase separation and void formation
287 [125]. The structure and water-binding in Alkali-Silica Reaction (ASR) sol and gel have been
288 studied, showing how alkali cation type influences agglomerate structures and water binding ability,
289 with implications for concrete durability [126]. The impact of fuel on surfactant microstructure of
290 firefighting foam has been investigated, providing insights into the factors controlling firefighting
291 performance and aiding in the development of environmentally friendly foams [127].

292 **5.4 Organic Photovoltaics and Flexible Electronics**

293 The role of additives in improving the performance of bulk heterojunction organic solar cells has
294 been investigated, revealing that additives induce a shift in morphology from solution to film, leading
295 to hierarchical structures with optimum crystallinity [128, 129]. The morphology of active layers in
296 all-polymer photovoltaic cells has been characterized, showing P3HT crystallites dispersed within an
297 amorphous matrix, with graphene addition affecting electronic properties but not film structure [130].
298 The critical role of electron-donating thiophene groups on the mechanical and thermal properties
299 of donor-acceptor semiconducting polymers has been elucidated, showing their anti-plasticizing
300 effect and providing design rules for stretchable electronics [131]. The concept of disorder-tolerant
301 semiconducting polymers has been approached through computer-aided molecular design, identifying
302 pyrazine and difluorothiophene combinations for high torsional barrier and planarity, leading to
303 efficient n-doping and high electrical conductivities [132].

304 **6 Methodological Developments and Data Analysis at EQ-SANS**

305 Beyond its direct scientific applications, EQ-SANS has been a hub for significant advancements in
306 neutron scattering methodologies and data analysis, particularly integrating computational techniques
307 and machine learning.

308 **6.1 Advancements in AI and Machine Learning for SANS Data Analysis**

309 The application of deep learning-based super-resolution techniques has been explored to accelerate
310 SANS data collection. Chang et al. demonstrated the feasibility of reconstructing high-resolution
311 scattering data from low-resolution inputs using a deep convolutional neural network, potentially
312 speeding up experimental workflows [133]. A machine learning (ML) inversion scheme has been
313 introduced for determining the effective interaction in colloids directly from scattering data, offering
314 superior accuracy and efficiency compared to traditional parametric methods [134, 135].

315 Deep learning has also been leveraged to decipher the scattering of mechanically driven polymers.
316 Ding et al. presented a Variational Autoencoder (VAE) approach to analyze two-dimensional
317 scattering data of semiflexible polymers under external forces, enabling significantly faster extraction
318 of polymer parameters compared to traditional fitting procedures [136]. An integration of machine
319 learning with Monte Carlo simulations has been developed to model kinked CANAL ladder polymer
320 structures, uncovering features conventional methods fail to capture [137].

321 Model-free approaches for profiling polydisperse soft matter using small angle scattering have been
322 developed. Huang et al. introduced a strategy that uses moment expansion to extract central moments
323 and reconstruct the size distribution function without bias, validating the approach on L64 Pluronic
324 micelles [138]. A novel method for reconstructing the neutron scattering length density profile from
325 SANS intensity profiles has been presented, utilizing a universal operator and PhaseLift framework
326 to eliminate the need for predefined models and mitigate error propagation [139]. Bayesian statistical
327 inference using Gaussian Process Regression (GPR) has also been explored to reconstruct high-
328 fidelity scattering data from sparse SANS measurements, maximizing experimental efficiency and
329 enabling high-throughput studies [140].

6.2 Probing Deformed Systems: Understanding Structure under Flow and Stress

EQ-SANS has facilitated the study of materials under various mechanical stresses, providing insights into their structural response. A portable hydro-thermo-mechanical loading cell has been developed for in-situ SANS studies of proton exchange membranes, allowing for tensile loading of samples immersed in liquid environments at controlled temperatures [141]. This cell has been used to investigate the mechanical properties and microstructure changes of Nafion membranes under immersed conditions, revealing a disorder-order transition with increasing temperature and water uptake [142].

The influence of elongation-induced concentration fluctuations on segmental friction in polymer blends has been investigated using rheology and SANS, demonstrating that viscoelastic asymmetry leads to demixing and apparent friction enhancement [143]. The local elasticity in nonlinear rheology of interacting colloidal glasses has been revealed by in-situ SANS and rheological measurements, identifying a transient elasticity zone (TEZ) at the particle level that governs shear-thinning behavior [144, 145]. An exact inversion method for extracting orientation ordering from small-angle scattering has been introduced, accurately determining the orientation distribution function (ODF) of sheared interacting rods [146, 147]. Furthermore, the potentials of SANS for understanding the structure-property relation of 3D-printed materials have been explored, correlating microstructure of carbon fiber-embedded composites with mechanical strength and highlighting the impact of carbon fiber on polymer chain conformation and interfacial structure [148].

6.3 Other Instrument Performance and Enhancements

Significant efforts have been made to improve the accuracy and efficiency of SANS data acquisition and processing at ORNL. Corrections for the geometric distortion of the tube detectors on SANS instruments have been developed, improving data quality [149, 150]. The data processing scheme for the EQ-SANS diffractometer has been refined to be fast, versatile, and highly automated, directly converting event files into scattering intensity data and enabling time-slicing for time-resolved experiments [151].

The phenomenon of inelastically scattered neutrons from water on a time-of-flight SANS instrument has been investigated, revealing a significant inelastic process where scattered neutrons exhibit energies consistent with room-temperature thermal energies, emphasizing the need for careful data processing for hydrogenous materials [152].

A unified user-friendly instrument control and data acquisition system (IC-DAS) has been developed for the ORNL SANS instrument suite, improving ease of use and efficiency for researchers conducting SANS experiments [153]. Furthermore, the EQ-SANS Assisting Chatbot (ESAC) has been introduced, leveraging Large Language Models (LLM) and Retrieval-Augmented Generation (RAG) to enhance user experience by providing an interactive reference and automating script generation [154].

7 Conclusion and Future Perspectives

The extensive research conducted using the EQ-SANS instrument has significantly impacted various scientific fields. In polymer science, it has provided key insights into polymer structures and properties, while in biology, it has helped to clarify complex protein and membrane dynamics. EQ-SANS has also been crucial for advancing the understanding of nanomaterials and colloids and has played a vital role in research on energy materials, such as batteries, and sustainable technologies. The instrument's versatility is highlighted by the more than 300 publications it has contributed to, underscoring its central role in the global scientific community.

The future of EQ-SANS is promising, with planned upgrades to the accelerator and the consequent increased neutron flux expected to enhance its capabilities significantly. These improvements will allow scientists to conduct more complex experiments on smaller samples, observe faster changes in materials, and resolve even finer structural details. This will continue to push the frontiers of nanoscale science and drive innovation in crucial areas. The ongoing collaboration between advanced instrumentation and interdisciplinary research will ensure that EQ-SANS remains a leading facility for scientific discovery for many years.

References

- [1] William T. Heller, Matthew Cuneo, Lisa Debeer-Schmitt, Changwoo Do, Lilin He, Luke Heroux, Kenneth Littrell, Sai Venkatesh Pingali, Shuo Qian, Christopher Stanley, Volker S. Urban, Bin Wu, and Wim Bras. The suite of small-angle neutron scattering instruments at oak ridge national laboratory. *J. Appl. Cryst.*, 51:242–248, 2018.
- [2] J. K. Zhao, C. Y. Gao, and D. Liu. The extended q-range small-angle neutron scattering diffractometer at the sns. *Journal of Applied Crystallography*, 43:1068–1077, 2010.
- [3] Dazhi Liu, Kunlun Hong, Carrie Y. Gao, Yuri Melnichenko, Ken Littrell, Greg Smith, and Jinkui Zhao. First data acquired on the extended q-range small-angle neutron scattering (eq-sans) diffractometer at the spallation neutron source. *Journal of Applied Crystallography*, 44:1120–1122, 2011.
- [4] Suk-kyun Ahn, Jan-Michael Y. Carrillo, Youngkyu Han, Tae-Hwan Kim, David Uhrig, Deanna L. Pickel, Kunlun Hong, S. Michael Kilbey, Bobby G. Sumpter, Gregory S. Smith, and Changwoo Do. Structural evolution of polylactide molecular bottlebrushes: Kinetics study by size exclusion chromatography, small angle neutron scattering, and simulations. *ACS Macro Letters*, 3(9):862–866, 2014.
- [5] Mohammed Alaboalirat, Samantha J. Scannelli, Hadi Rahmaninejad, Jan-Michael Carrillo, Changwoo Do, John B. Matson, and Rana Ashkar. Solution structure and scaling laws of cylindrical and tapered bottlebrush polymers. *Macromolecules*, 56(23):9264–9276, 2023.
- [6] Zhe Zhang, Jan-Michael Y. Carrillo, Suk-kyun Ahn, Bin Wu, Kunlun Hong, Gregory S. Smith, and Changwoo Do. Atomistic structure of bottlebrush polymers: Simulations and neutron scattering studies. *Macromolecules*, 47(16):5808–5814, 2014.
- [7] Changwoo Do, Wei-Ren Chen, Kunlun Hong, and Gregory S. Smith. Equilibrium structure of a triblock copolymer system revealed by mesoscale simulation and neutron scattering. *Physica B: Condensed Matter*, 430:87–94, 2013.
- [8] Jong Dae Jang, Changwoo Do, Joona Bang, Young Soo Han, and Tae-Hwan Kim. Self-assembly of temperature sensitive unilamellar vesicles by a blend of block copolymers in aqueous solution. *Polymers*, 11(1):63, 2019.
- [9] Youngkyu Han, Zhe Zhang, Gregory S. Smith, and Changwoo Do. Effect of nucleoside analogue antimetabolites on the structure of peo–ppo–peo micelles investigated by sans. *Physical Chemistry Chemical Physics*, 19(24):15686–15692, 2017.
- [10] William T. Heller and Changwoo Do. Impact of two water-miscible ionic liquids on the temperature-dependent self-assembly of the (eo) 6(po) 34(eo) 6 block copolymer. *ACS Omega*, 7(22):19474–19483, 2022.
- [11] Chih-Ying Liu, Hsin-Lung Chen, Changwoo Do, and Kunlun Hong. Spatial distributions of guest molecule and hydration level in dendrimer-based guest host complex. *ACS Macro Letters*, 5(9):1004–1008, 2016.
- [12] Olena Kudina, Ananiy Kohut, Ihor Tarnavchyk, Ivan Hevus, and Andriy Voronov. Solvent-responsive self-assembly of amphiphilic invertible polymers determined with sans. *Langmuir*, 30(12):3310–3318, 2014.
- [13] Xin Li, Lionel Porcar, Luis E. Sánchez-Díaz, Changwoo Do, Yun Liu, Tae-Hwan Kim, Gregory S. Smith, William A. Hamilton, Kunlun Hong, and Wei-Ren Chen. Influence of molecular solvation on the conformation of star polymers. *Macromolecules*, 47(1):2–5, 2014.
- [14] Xin Li, Changwoo Do, Yun Liu, Luis E. Sánchez-Díaz, Kunlun Hong, Gregory S. Smith, and Wei-Ren Chen. Scattering from star polymers including excluded volume effects. *arXiv preprint arXiv:1404.6269*, 2014.
- [15] Luke A. Galuska, William W. McNutt, Zhiyuan Qian, Song Zhang, Daniel W. Weller, Sujata Dhakal, Eric R. King, Sarah E. Morgan, Jason D. Azoulay, Jianguo Mei, and Xiaodan Gu. Impact of backbone rigidity on the thermomechanical properties of semiconducting polymers with conjugation break spacers. *Macromolecules*, 53(14):6032–6042, 2020.

- 429 [16] Scott P. O. Danielsen, Colin R. Bridges, and Rachel A. Segalman. Chain stiffness of donor
430 acceptor conjugated polymers in solution. *Macromolecules*, 55(2):437–449, 2022.
- 431 [17] William D. Hong, Christopher N. Lam, Yangyang Wang, Dongsook Chang, Youjun He, Luis E.
432 Sánchez-Díaz, Changwoo Do, and Wei-Ren Chen. Influence of side chain isomerism on
433 the rigidity of poly(3-alkylthiophenes) in solutions revealed by neutron scattering. *Physical
434 Chemistry Chemical Physics*, 21(15):7745–7749, 2019.
- 435 [18] Bryan McCulloch, Victor Ho, Megan Hoarfrost, Chris Stanley, Changwoo Do, William T.
436 Heller, and Rachel A. Segalman. Polymer chain shape of poly(3-alkylthiophenes) in solution
437 using small-angle neutron scattering. *Macromolecules*, 46(6):1899–1907, 2013.
- 438 [19] Pengfei Zhan, Wenlin Zhang, Ian E Jacobs, David M Nisson, Renxuan Xie, Albree R Weissen,
439 Ralph H Colby, Adam J Moulé, Scott T Milner, Janna K Maranas, and Enrique D Gomez.
440 Side chain length affects backbone dynamics in poly(3-alkylthiophene)s. *Journal of Polymer
441 Science Part B Polymer Physics*, 56(17):1181–1187, 2018.
- 442 [20] Rajeev Kumar, Bradley S Lokitz, Scott W Sides, Jihua Chen, William T Heller, John F Ankner,
443 James F Browning, S Michael Kilbey II, and Bobby G Sumpter. Microphase separation in
444 thin films of lamellar forming polydisperse di-block copolymers. *RSC Advances*, 5(27):21336–
445 21348, 2015.
- 446 [21] Christopher N. Lam, Wen-Sheng Xu, Wei-Ren Chen, Zhe Wang, Christopher B. Stanley,
447 Jan-Michael Y. Carrillo, David Uhrig, Weiyu Wang, Kunlun Hong, Yun Liu, Lionel Porcar,
448 Changwoo Do, Gregory S. Smith, Bobby G. Sumpter, and Yangyang Wang. Scaling behavior
449 of anisotropy relaxation in deformed polymers. *Phys. Rev. Lett.*, 121(11):117801, 2018.
- 450 [22] Zhe Wang, Christopher N. Lam, Wei-Ren Chen, Weiyu Wang, Jianning Liu, Yun Liu, Li-
451 onel Porcar, Christopher B. Stanley, Zhichen Zhao, Kunlun Hong, and Yangyang Wang.
452 Fingerprinting molecular relaxation in deformed polymers. *Physical Review X*, 7:031003,
453 2017.
- 454 [23] Christopher N. Lam, Lilin He, Changwoo Do, Wei-Ren Chen, Weiyu Wang, Kunlun Hong,
455 and Yangyang Wang. Quantifying molecular deformation in polymer melts by a generalized
456 zimm plot approach. *J. Appl. Cryst.*, 56:1168–1179, 2023.
- 457 [24] Irina Mahmad Rasid, Changwoo Do, Niels Holten-Andersen, and Bradley D. Olsen. Effect of
458 sticker clustering on the dynamics of associative networks. *Soft Matter*, 17(39):8960–8972,
459 2021.
- 460 [25] Ameya Rao, Brian R. Carrick, Helen Yao, and Bradley D. Olsen. Hindered segmental dynamics
461 in associative protein hydrogels studied by neutron spin-echo spectroscopy. *Physical Review
462 Materials*, 7(7):075602, 2023.
- 463 [26] Changwoo Do, Peter Lunkenheimer, Diddo Diddens, Marion Götz, Matthias Weiß, Alois
464 Loidl, Xiao-Guang Sun, Jürgen Allgaier, and Michael Ohl. Li⁺ transport in poly(ethylene
465 oxide) based electrolytes: Neutron scattering, dielectric spectroscopy, and molecular dynamics
466 simulations. *Physical Review Letters*, 111(1):018301, 2013.
- 467 [27] John S. Hyatt, Changwoo Do, Xiaobo Hu, Hong Sung Choi, Jin Woong Kim, L. Andrew Lyon,
468 and Alberto Fernandez-Nieves. Segregation of mass at the periphery of n-isopropylacrylamide-
469 co-acrylic-acid microgels at high temperatures. *Phys. Rev. E*, 92(3):030302, 2015.
- 470 [28] John S. Hyatt, Alison M. Douglas, Chris Stanley, Changwoo Do, Thomas H. Barker, and
471 Alberto Fernández-Nieves. Charge segregation in weakly ionized microgels. *Phys. Rev. E*,
472 95(1):012608, 2017.
- 473 [29] Michael Tennenbaum, Caleb Anderson, John S. Hyatt, Changwoo Do, and Alberto Fernandez-
474 Nieves. Internal structure of ultralow-crosslinked microgels: From uniform deswelling to
475 phase separation. *Physical Review E*, 103(2):022614, 2021.
- 476 [30] Youngkyu Han, Suk-kyun Ahn, Zhe Zhang, Gregory S. Smith, and Changwoo Do. Tunable
477 encapsulation structure of block copolymer coated single-walled carbon nanotubes in aqueous
478 solution. *Macromolecules*, 48(11):3475–3480, 2015.

- 479 [31] Youngkyu Han, Suk-kyun Ahn, Zhe Zhang, Gregory S. Smith, and Changwoo Do. Function-
480 alization of single-walled carbon nanotubes with thermo-reversible block copolymers and
481 characterization by small-angle neutron scattering. *J. Vis. Exp.*, 112:e53969, 2016.
- 482 [32] Tae-Hwan Kim, Eunhye Kim, Changwoo Do, Hyungju Ahn, Hoyeon Lee, and Young-Soo
483 Han. Anomalous self-assembled phase behavior of block copolymer blended with organic
484 derivative depending on temperature. *Macromolecules*, 49(17):6541–6548, 2016.
- 485 [33] Veronika Kozlovskaya, Fei Liu, Yiming Yang, Kevin Ingle, Shuo Qian, Ganesh Halade,
486 Volker Urban, and Eugenia Kharlampieva. Temperature-responsive polymersomes of poly(3-
487 methy-n-vinylcaprolactam)-block-(poly(n-vinylpyrrolidone) to decrease doxorubicin-induced
488 cardiotoxicity. *Biomacromolecules*, 2019.
- 489 [34] Bin Wu, Xin Li, Changwoo Do, Tae-Hwan Kim, Chwen-Yang Shew, Yun Liu, Jun Yang,
490 Kunlun Hong, Lionel Porcar, Chun-Yu Chen, Emily L. Liu, Gregory S. Smith, Kenneth W.
491 Herwig, and Wei-Ren Chen. Spatial distribution of intra-molecular water and polymeric
492 components in polyelectrolyte dendrimers revealed by small angle scattering investigations.
493 *The Journal of Chemical Physics*, 135(14):144903, 2011.
- 494 [35] Bin Wu, Wei-Ren Chen, Takeshi Egami, Xin Li, Yun Liu, Yongmei Wang, Changwoo Do, Li-
495 onel Porcar, Kunlun Hong, Li Liu, Gregory S. Smith, and Sean C. Smith. Molecular dynamics
496 and neutron scattering study of the dependence of polyelectrolyte dendrimer conformation on
497 counterion behavior. *J. Chem. Phys.*, 137(6):064902, 2012.
- 498 [36] Xin Li, Luis E. Sánchez-Díaz, Bin Wu, William A. Hamilton, Péter Falus, Lionel Porcar, Yun
499 Liu, Changwoo Do, Antonio Faraone, Gregory S. Smith, Takeshi Egami, and Wei-Ren Chen.
500 Dynamical threshold of diluteness of soft colloids. *ACS Macro Letters*, 3(12):1271–1275,
501 2014.
- 502 [37] Helen Yao and Bradley D. Olsen. Sans quantification of bound water in water-soluble polymers
503 across multiple concentration regimes. *Soft Matter*, 17(21):5303–5318, 2021.
- 504 [38] Thusitha N. Etampawala, Dipak Aryal, Naresh C. Osti, Lilin He, William T. Heller, Carl Willis,
505 Gary S. Grest, and Dvora Perahia. Association of a multifunctional ionic block copolymer in a
506 selective solvent. *The Journal of chemical physics*, 145(18), 2016.
- 507 [39] Peter A. Dykeman-Birmingham, Laura R. Stingaciu, Changwoo Do, and Abigail S. Knight.
508 Dynamic implications of noncovalent interactions in amphiphilic single-chain polymer
509 nanoparticles. *ACS Macro Letters*, 13(5):889–895, 2024.
- 510 [40] Jahan Ali Khajeh, Jeong Ho Ju, Moussoubaou Atchiba, Marc Allaire, Christopher Stanley,
511 William T. Heller, David J.E. Callaway, and Zimei Bu. Molecular conformation of the full-
512 length tumor suppressor nf2/merlin—a small angle neutron scattering study. *J Mol Biol*,
513 426(15):2755–2768, 2014.
- 514 [41] Shibani Bhattacharya, Christopher B. Stanley, William T. Heller, Peter A. Friedman, and
515 Zimei Bu. Dynamic structure of the full-length scaffolding protein nherf1 influences signaling
516 complex assembly. *Journal of Biological Chemistry*, 294(29):11297–11310, 2019.
- 517 [42] Iain D. Nicholl, Tsutomu Matsui, Thomas M. Weiss, Christopher B. Stanley, William T. Heller,
518 Anne Martel, Bela Farago, David J. E. Callaway, and Zimei Bu. α -catenin structure and
519 nanoscale dynamics in solution and in complex with f-actin. *Biophysical Journal*, 115(3):642–
520 654, 2018.
- 521 [43] David J.E. Callaway, Tsutomu Matsui, Thomas Weiss, Laura R. Stingaciu, Christopher B.
522 Stanley, William T. Heller, and Zimei Bu. Controllable activation of nanoscale dynamics in a
523 disordered protein alters binding kinetics. *J Mol Biol*, 429(7):987–998, 2017.
- 524 [44] Anthony Banks, Sanbo Qin, Kevin L. Weiss, Christopher B. Stanley, and Huan-Xiang Zhou.
525 Intrinsically disordered protein exhibits both compaction and expansion under macromolecular
526 crowding. *Biophysical Journal*, 114(6):1067–1079, 2018.

- 527 [45] Amanda L. Mansouri, Laura N. Grese, Erica L. Rowe, James C. Pino, S. Chakra Chennubhotla,
528 Arvind Ramanathan, Hugh M. O'Neill, Valerie Berthelie, and Christopher B. Stanley. Folding
529 propensity of intrinsically disordered proteins by osmotic stress. *Mol Biosyst*, 12(12):3695–
530 3701, 2016.
- 531 [46] Daniel T. Murray, Kevin L. Weiss, Christopher B. Stanley, Gergely Nagy, and M. Eliza-
532 beth Stroupe. Small-angle neutron scattering solution structures of nadph-dependent sulfite
533 reductase. *Journal of Structural Biology*, 2021.
- 534 [47] D.T. Murray, N. Walia, K.L. Weiss, P.S. Randolph, C.B. Stanley, G. Nagy, and M.E. Stroupe.
535 Neutron scattering maps the higher-order assembly of nadph-dependent assimilatory sulfite
536 reductase. *Biophysical journal*, 121(10):1799–1812, 2022.
- 537 [48] Nidhi Walia, Daniel T. Murray, Yashika Garg, Huan He, Kevin L. Weiss, Gergely Nagy,
538 and M. Elizabeth Stroupe. Domain crossover in the reductase subunit of nadph-dependent
539 assimilatory sulfite reductase. *Journal of Structural Biology*, 215(4):108028, 2023.
- 540 [49] Serena H. Chen, Kevin L. Weiss, Christopher Stanley, and Debsindhu Bhowmik. Structural
541 characterization of an intrinsically disordered protein complex using integrated small-angle
542 neutron scattering and computing. *Protein Science*, 32(10):e4772, 2023.
- 543 [50] Xiaodong Chen, Jahan Ali Khajeh, Jeong Ho Ju, Yogesh K. Gupta, Christopher B. Stanley,
544 Changwoo Do, William T. Heller, Aneel K. Aggarwal, David J. E. Callaway, and Zimei Bu.
545 Phosphatidylinositol 4,5-bisphosphate clusters the cell adhesion molecule cd44 and assembles
546 a specific cd44-ezrin heterocomplex, as revealed by small angle neutron scattering. *Journal of*
547 *Biological Chemistry*, 290(10):6639–6652, 2015.
- 548 [51] Jayant James Jayasundar, Jeong Ho Ju, Lilin He, Dazhi Liu, Flora Meilleur, Jinkui Zhao, David
549 J. E. Callaway, and Zimei Bu. Open conformation of ezrin bound to phosphatidylinositol
550 4,5-bisphosphate and to f-actin revealed by neutron scattering. *The Journal of Biological*
551 *Chemistry*, 287(44):37119–37133, 2012.
- 552 [52] Milka Doktorova, Frederick A. Heberle, Richard L. Kingston, George Khelashvili, Michel A.
553 Cuendet, Yi Wen, John Katsaras, Gerald W. Feigenson, Volker M. Vogt, and Robert A. Dick.
554 Cholesterol promotes protein binding by affecting membrane electrostatics and solvation
555 properties. *Biophysical Journal*, 113(9):2004–2015, 2017.
- 556 [53] Milka Doktorova, Norbert Kučerka, Jacob J. Kinnun, Jianjun Pan, Drew Marquardt, Haden L.
557 Scott, Richard M. Venable, Richard W. Pastor, Stephen R. Wassall, John Katsaras, and
558 Frederick A. Heberle. The molecular structure of sphingomyelin in fluid phase bilayers
559 determined by the joint analysis of small-angle neutron and x-ray scattering data. *J Phys Chem*
560 *B*, 124(25):5186–5200, 2020.
- 561 [54] William T. Heller and Durgesh K. Rai. Changes in lipid bilayer structure caused by the helix
562 -to-sheet transition of an hiv -1 gp41 fusion peptide derivative. *Chemistry and Physics of*
563 *Lipids*, 203:46–53, 2017.
- 564 [55] William T. Heller and Piotr A. Zolnierczuk. The helix-to-sheet transition of an HIV-1 fusion
565 peptide derivative changes the mechanical properties of lipid bilayer membranes. *Biochimica*
566 *et Biophysica Acta Biomembranes*, 1861(3):565–572, 2019.
- 567 [56] William T. Heller. A small-angle neutron scattering study of the physical mechanism that
568 drives the action of a viral fusion peptide. *Chemistry and Physics of Lipids*, 234:105022, 2021.
- 569 [57] Shuo Qian, Durgesh Rai, and William T. Heller. Alamethicin disrupts the cholesterol distribu-
570 tion in dimyristoyl phosphatidylcholine cholesterol lipid bilayers. *The Journal of Physical*
571 *Chemistry B*, 118(37):11200–11208, 2014.
- 572 [58] Durgesh K. Rai, Shuo Qian, and William T. Heller. The interaction of melittin with dimyristoyl
573 phosphatidylcholine-dimyristoyl phosphatidylserine lipid bilayer membranes. *Biochimica et*
574 *Biophysica Acta (BBA) - Biomembranes*, 1858(11):2788–2794, 2016.

- 575 [59] Michael H. L. Nguyen, Mitchell DiPasquale, Brett W. Rikeard, Christopher B. Stanley,
576 Elizabeth G. Kelley, and Drew Marquardt. Methanol accelerates dmpe flip-flop and transfer:
577 A sans study on lipid dynamics. *Biophysical Journal*, 116(5):755–759, 2019.
- 578 [60] Yan Xia, Ming Li, Kamil Charubin, Ying Liu, Frederick A. Heberle, John Katsaras, Benxin
579 Jing, Yingxi Zhu, and Mu-Ping Nieh. The effects of nanoparticle morphology and acyl chain
580 length on spontaneous lipid transfer rates. *Langmuir*, 31(47):13065–13071, 2015.
- 581 [61] Yan Xia, Kamil Charubin, Drew Marquardt, Frederick A. Heberle, John Katsaras, Jianhui
582 Tian, Xiaolin Cheng, Ying Liu, and Mu-Ping Nieh. Morphology-induced defects enhance lipid
583 transfer rates. *Langmuir*, 32(38):9757–9764, 2016.
- 584 [62] Jonathan D. Nickels, Xiaolin Cheng, Barmak Mostofian, Christopher Stanley, Benjamin
585 Lindner, Frederick A. Heberle, Stefania Perticaroli, Mikhail Feygenson, Takeshi Egami,
586 Robert F. Standaert, Jeremy C. Smith, Dean A. A. Myles, Michael Ohl, and John Katsaras.
587 Mechanical properties of nanoscopic lipid domains. *Journal of the American Chemical Society*,
588 137(50):15772–15780, 2015.
- 589 [63] Jonathan D. Nickels, Sneha Chatterjee, Christopher B. Stanley, Shuo Qian, Xiaolin Cheng,
590 Dean A. A. Myles, Robert F. Standaert, James G. Elkins, and John Katsaras. The in vivo struc-
591 ture of biological membranes and evidence for lipid domains. *PLOS Biology*, 15(5):e2002214,
592 2017.
- 593 [64] Leo Williams. Neutrons provide the first nanoscale look at a living cell membrane. *Neutron*
594 *News*, 29(1):21–22, 2018.
- 595 [65] Jonathan D. Nickels, Kyle S. Bonifer, Rachel R. Tindall, Ahmad Yahya, Luoxi Tan, Changwoo
596 Do, Brian H. Davison, and James G. Elkins. Improved chemical and isotopic labeling of
597 biomembranes in *bacillus subtilis* by leveraging crispr inhibition of beta-ketoacyl-*acp* synthase
598 (fabf). *Frontiers in Molecular Biosciences*, 9:1011981, 2022.
- 599 [66] Jonathan D. Nickels, Micholas Dean Smith, Richard J. Alsop, Sebastian Himbert, Ahmad
600 Yahya, Destini Cordner, Piotr Zolnierczuk, Christopher B. Stanley, John Katsaras, Xiaolin
601 Cheng, and Maikel C. Rheinstädter. Lipid rafts: Buffers of cell membrane physical properties.
602 *The Journal of Physical Chemistry B*, 123(2):405–413, 2019.
- 603 [67] Shuo Qian, Gergely Nagy, Piotr Zolnierczuk, Eugene Mamontov, and Robert Standaert.
604 Nonstereotypical distribution and effect of ergosterol in lipid membranes. *J. Phys. Chem. Lett.*,
605 15(15):4745–4752, 2024.
- 606 [68] Carlos E. Astete, Judith U. De Mel, Sudipta Gupta, YeRim Noh, Markus Bleuel, Gerald J.
607 Schneider, and Cristina M. Sabliov. Lignin-graft-poly(lactic- co-glycolic) acid biopolymers
608 for polymeric nanoparticle synthesis. *ACS Omega*, 5(16):9892–9902, 2020.
- 609 [69] Yeongseon Jang, Won Tae Choi, William T. Heller, Zunlong Ke, Elizabeth R. Wright, and
610 Julie A. Champion. Engineering globular protein vesicles through tunable self-assembly of
611 recombinant fusion proteins. *Small*, 13(36), 2017.
- 612 [70] Chih-Ying Liu, Xin Li, Wen-Yih Chen, Li-Chiao Chang, Yi-Fan Chen, Hsin-Lung Chen,
613 Ya-Sen Sun, Hsiu-Yun Lai, and E-Wen Huang. Pegylation site-dependent structural hetero-
614 geneity study of monopegylated human parathyroid hormone fragment hpth(1–34). *Langmuir*,
615 30(38):11421–11427, 2014.
- 616 [71] Ying Liu, Ming Li, Yongkun Yang, Yan Xia, and Mu-Ping Nieh. The effects of temperature,
617 salinity, concentration and pegylated lipid on the spontaneous nanostructures of bicellar
618 mixtures. *Biochimica et Biophysica Acta (BBA) - Biomembranes*, 1838(7):1871–1880, 2014.
- 619 [72] Ming Li, William T. Heller, Chung-Hao Liu, Carrie Y. Gao, Yutian Cai, Yiming Hou, and
620 Mu-Ping Nieh. Effects of fluidity and charge density on the morphology of a bicellar mixture
621 –a sans study. *BBA - Biomembranes*, 1862(7):183315, 2020.
- 622 [73] Yun Jung Yang, Danielle J. Mai, Thomas J. Dursch, and Bradley D. Olsen. Nucleopore-inspired
623 polymer hydrogels for selective biomolecular transport. *Biomacromolecules*, 19(10):3905–
624 3916, 2018.

- [74] Ameya Rao and Bradley D. Olsen. Structural and dynamic heterogeneity in associative networks formed by artificially engineered protein polymers. *Soft Matter*, 19(29):6314–6328, 2023.
- [75] Ameya Rao, Helen Yao, and Bradley D. Olsen. Bridging dynamic regimes of segmental relaxation and center-of-mass diffusion in associative protein hydrogels. *Physical Review Research*, 2(4):043369, 2020.
- [76] Joseph C. White, Erika M. Saffer, and Surita R. Bhatia. Alginate/peo-ppo-peo composite hydrogels with thermally-active plasticity. *Biomacromolecules*, 14(12):4456–4464, 2013.
- [77] Zipei Zhang, Xiyu Li, Changwoo Do, and Daniel S. Kohane. Enhancement of polymer thermoresponsiveness and drug delivery across biological barriers by addition of small molecules. *Heliyon*, 9:e16923, 2023.
- [78] Kangdi Sun, Tooba Shoaib, Mark W. Rutland, Joesph Beller, Changwoo Do, and Rosa M. Espinosa-Marzal. Insight into the assembly of lipid-hyaluronan complexes in osteoarthritic conditions. *Biointerphases*, 18(2):021005, 2023.
- [79] Venu Gopal Vandavasi, Daniel K. Putnam, Qiu Zhang, Loukas Petridis, William T. Heller, B. Tracy Nixon, Candace H. Haigler, Udaya Kalluri, Leighton Coates, Paul Langan, Jeremy C. Smith, Jens Meiler, and Hugh O’Neill. A structural study of cesa1 catalytic domain of arabidopsis cellulose synthesis complex: Evidence for cesa trimers. *Plant Physiology*, 170(1):123–135, 2016.
- [80] Richard Hembrom, Renáta Ünnepe, Éva Sárvári, Gergely Nagy, and Katalin Solymosi. Dynamic in vivo monitoring of granum structural changes of *ctenanthe setosa* (roscoe) eichler during drought stress and subsequent recovery. *Physiologia Plantarum*, 177(e14621), 2025.
- [81] Itzell Hernández-Sánchez, Tobias Rindfleisch, Jessica Alpers, Martin Dulle, Christopher J. Garvey, Patrick Knox-Brown, Markus S. Miettinen, Gergely Nagy, Julio M. Pusterla, Agata Rekas, Keyun Shou, Andreas M. Stadler, Dirk Walther, Martin Wolff, Ellen Zuther, and Anja Thalhammer. Functional in vitro diversity of an intrinsically disordered plant protein during freeze–thawing is encoded by its structural plasticity. *Protein Science*, 33(e4989), 2024.
- [82] Riddhi S. Shah, Manjula Senanayake, Hong-Hai Zhang, Yunqiao Pu, Ajaya K. Biswal, Sai Venkatesh Pingali, Brian Davison, and Hugh O’Neill. Evidence for lignincarbohydrate complexes from studies of transgenic switchgrass and a model ligninpectin composite. *ACS Sustainable Chemistry Engineering*, 11(45):15941–15950, 2023.
- [83] Jong Dae Jang, Moongi Bae, Changwoo Do, Soo-Hyung Choi, Joona Bang, Young Soo Han, and Tae-Hwan Kim. Self-assembly of 2d gold nanoparticle superlattice in a polymer vesicle layer driven by hydrophobic interaction. *The Journal of Physical Chemistry Letters*, 12(28):6736–6743, 2021.
- [84] Young-Jin Yoon, Jae-Min Ha, Hyuk-Jin Seo, Jong Dae Jang, Changwoo Do, and Tae-Hwan Kim. Temperature-responsive binary superlattices prepared by the selective solvent evaporation of o/w microemulsion composed of gold nanoparticles and surfactants. *Nanoscale*, 15(30):12481–12491, 2023.
- [85] Young-Jin Yoon, Shin-Hyun Kang, Changwoo Do, Se Youn Moon, and Tae-Hwan Kim. Water-redispersible and highly stable gold nanoparticles permanently capped by charge-controllable surfactants for potential medical applications. *ACS Applied Nano Materials*, 2(12):7924–7932, 2019.
- [86] Sang-Woo Jeon, Shin-Hyun Kang, Jung Chul Choi, and Tae-Hwan Kim. Dispersion of boron nitride nanotubes by pluronic triblock copolymer in aqueous solution. *Polymers*, 11(4):582, 2019.
- [87] Sang-Woo Jeon, HeeIl Yoo, Se Youn Moon, and Tae-Hwan Kim. Two-dimensional hexagonal structure of boron nitride nanotubes and bnnt-induced phase transition of blockcopolymer in bnnt/block copolymer complex forenergy harvesting. *International Journal of Energy Research*, 2023:1–13, 2023.

- [88] Sang-Woo Jeon, Changwoo Do, Se Youn Moon, and Tae-Hwan Kim. Two-dimensional binary superlattice of bnnt-surfactant vesicle complex induced by electrostatic interaction. *ACS Central Science*, 11(9):950–959, 2025.
- [89] Sourav Chatterjee, Tony E. Karam, Cornelia Rosu, Chun-Han Wang, Sang Gil Youm, Xin Li, Changwoo Do, Yaroslav Losovyj, Paul S. Russo, Louis H. Haber, and Evgueni E. Nesterov. Silica – conjugated polymer hybrid fluorescent nanoparticles: Preparation by surface-initiated polymerization and spectroscopic studies. *Unknown*, 2018.
- [90] N. Sanjeeva Murthy, Zheng Zhang, Siddharth Borsadia, and Joachim Kohn. Nanospheres with a smectic hydrophobic core and an amorphous peg hydrophilic shell: Structural changes and implications for drug delivery. *Soft Matter*, 14(8):1327–1335, 2018.
- [91] José Leobardo Bañuelos, Guang Feng, Pasquale F. Fulvio, Song Li, Gernot Rother, Sheng Dai, Peter T. Cummings, and David J. Wesolowski. Densification of ionic liquid molecules within a hierarchical nanoporous carbon structure revealed by small-angle scattering and molecular dynamics simulation. *Chemistry of Materials*, 26(3):1144–1153, 2014.
- [92] T. Kang, S. Qian, G. S. Smith, C. Do, and W. T. Heller. Small-angle neutron scattering study of a dense microemulsion system formed with an ionic liquid. *Soft Matter*, 13(4):846–854, 2017.
- [93] Khalil Akkaoui, Zachary A. Digby, Changwoo Do, and Joseph B. Schlenoff. Comprehensive dynamics in a polyelectrolyte complex coacervate. *Macromolecules*, 57:1169–1181, 2024.
- [94] Michael P. Hoepfner and H. Scott Fogler. Multiscale scattering investigations of asphaltene cluster breakup, nanoaggregate dissociation, and molecular ordering. *Langmuir*, 29(51):15423–15432, 2013.
- [95] B. McKay Rytting, Michael R. Harper, Kazem V. Edmond, Yunlong Zhang, and Peter K. Kilpatrick. High-purity vanadyl petroporphyrins: Their aggregation and effect on the aggregation of asphaltenes. *Energy & Fuels*, 34(1):164–178, 2020.
- [96] B. McKay Rytting, Michael R. Harper, Kazem V. Edmond, Shamel Merchant, Yunlong Zhang, and Peter K. Kilpatrick. Interfacial phenomena of purified petroporphyrins and their impact on asphaltene interfacial film formation. *Energy & Fuels*, 34(5):5444–5456, 2020.
- [97] Jeffery W. Thompson, Holly A. Stretz, Pedro E. Arce, Hongsheng Gao, Harry J. Ploehn, and Jibao He. Effect of magnetization on the gel structure and protein electrophoresis in polyacrylamide hydrogel nanocomposites. *Journal of Applied Polymer Science*, 126(5):1600–1612, 2012.
- [98] Erkan Senses and Pinar Akcora. An interface-driven stiffening mechanism in polymer nanocomposites. *Macromolecules*, 46(6):1868–1874, 2013.
- [99] Yingzhen Ma, Christian Heil, Gergely Nagy, William T. Heller, Yaxin An, Arthi Jayaraman, and Bhuvnesh Bharti. Synergistic role of temperature and salinity in aggregation of nonionic surfactant-coated silica nanoparticles. *Langmuir*, 39(17):5917–5928, 2023.
- [100] V. Cherpak, V.F. Korolovych, R. Geryak, T. Turiv, D. Nepal, J. Kelly, T.J. Bunning, O.D. Lavrentovich, W.T. Heller, and V.V. Tsukruk. Robust chiral organization of cellulose nanocrystals in capillary confinement. *N/A*, 2018.
- [101] Ikjun Choi, Sidney T. Malak, Weinan Xu, William T. Heller, Constantinos Tsitsilianis, and Vladimir V. Tsukruk. Multicompartmental microcapsules from star copolymer micelles. *Macromolecules*, 46(4):1425–1436, 2013.
- [102] Weinan Xu, Sidney T. Malak, Felix A. Plamper, Christopher V. Synatschke, Axel H. E. Müller, William T. Heller, Yuri B. Melnichenko, and Vladimir V. Tsukruk. Structural study of star polyelectrolytes and their porous multilayer assembly in solution. *Springer Proceedings in Physics*, 171:299–309, 2015.

- [103] Minkyu Kim, Moon Jong Han, Hansol Lee, Paraskevi Flouda, Daria Bukharina, Kellina J. Pierce, Katarina M. Adstedt, Madeline L. Buxton, Young Hee Yoon, William T. Heller, Srikanth Singamaneni, and Vladimir V. Tsukruk. Bio-templated chiral zeolitic imidazolate framework for enantioselective chemoresistive sensing. *Angewandte Chemie International Edition*, 62(30):e202305646, 2023.
- [104] Peter Kei, Carlos A. Chavez, Joseph C. Mai, Changwoo Do, Kunlun Hong, and Evgueni E. Nesterov. Kinetically controlled assembly of conjugated polymer nanostructures. *Macromolecules*, 54(5):2162–2177, 2021.
- [105] J. Zhu, Y. Han, R. Kumar, Y. He, K. Hong, P. V. Bonnesen, B. G. Sumpter, S. C. Smith, G. S. Smith, I. N. Ivanov, and C. Do. Controlling molecular ordering in solution-state conjugated polymers. *Nanoscale*, 7(37):15134–15141, 2015.
- [106] Minxiang Zeng, Daniel King, Dali Huang, Changwoo Do, Ling Wang, Mingfeng Chen, Shijun Lei, Pengcheng Lin, Ying Chen, and Zhengdong Cheng. Iridescence in nematics: Photonic liquid crystals of nanoplates in absence of long-range periodicity. *Proceedings of the National Academy of Sciences*, 116(37):18322–18327, 2019.
- [107] Craig A. Bridges, Xiao-Guang Sun, Jinkui Zhao, M. Parans Paranthaman, and Sheng Dai. In situ observation of solid electrolyte interphase formation in ordered mesoporous hard carbon by small-angle neutron scattering. *The Journal of Physical Chemistry C*, 116(14):7701–7711, 2012.
- [108] Craig A. Bridges, Xiao-Guang Sun, Bingkun Guo, William T. Heller, Lilin He, Mariappan Parans Paranthaman, and Sheng Dai. Observing framework expansion of ordered mesoporous hard carbon anodes with ionic-liquid electrolytes via in situ small-angle neutron scattering. *ACS Energy Letters*, 2(8):1698–1704, 2017.
- [109] Charl J. Jafta, Xiao-Guang Sun, Hailong Lyu, Hao Chen, Bishnu P. Thapaliya, William T. Heller, Matthew J. Cunneo, Richard T. Mayes, M. Parans Paranthaman, Sheng Dai, and Craig A. Bridges. Insight into the solid electrolyte interphase (sei) formation in bis(fluorosulfonyl)imide based ionic liquid electrolytes. *Advanced Functional Materials*, 31(23), 2021.
- [110] Mary K. Burdette-Trofimov, Beth L. Armstrong, Rachel J. Korkosz, J. Landon Tyler, Rebecca D. McAuliffe, Luke Heroux, Mathieu Doucet, David T. Hoelzer, Nihal Kanbargi, Amit K. Naskar, and Gabriel M. Veith. Understanding the solution dynamics and binding of pvdf binder with silicon, graphite, and nmc materials and the influence on cycling performance. *ACS Applied Materials & Interfaces*, 14(20):23322–23331, 2022.
- [111] X. Chelsea Chen, Charles Soulen, Mary K. Burdette-Trofimov, Xiaomin Tang, Changhao Liu, Luke Heroux, Mathieu Doucet, Madhusudan Tyagi, and Gabriel M. Veith. Origin of rate limitations in solid-state polymer batteries from constrained segmental dynamics within the cathode. *Cell Reports Physical Science*, 4(8):101538, 2023.
- [112] Shehan M. Parmar, William Dean, Changwoo Do, James F. Browning, Jeffrey M. Klein, Burcu E. Gurkan, and Jesse G. McDaniel. Structural properties of [n1888][tfsi] ionic liquid: A small-angle neutron scattering and polarizable molecular dynamics study. *J. Phys. Chem. B*, 128(48):11313–11327, 2024.
- [113] Naresh C. Osti, Michael Naguib, Alireza Ostadhossein, Yu Xie, Paul R. C. Kent, Boris Dyatkin, Gernot Rother, William T. Heller, Adri C. T. van Duin, Yury Gogotsi, and Eugene Mamontov. Effect of metal ion intercalation on the structure of mxene and water dynamics on its internal surfaces. *ACS Applied Materials & Interfaces*, 8(16):10648–10654, 2016.
- [114] Qingsong Liu, Willa Brenneis, Gergely Nagy, Mathieu Doucet, Jeffrey Lopez, and Jeffrey J. Richards. Structure –performance relationships of lithium-ion battery cathodes revealed by contrast-variation small-angle neutron scattering. *J. Mater. Chem. A*, 12(33114):33114–33124, 2024.
- [115] Adam Holewinski, Miles A. Sakwa-Novak, and Christopher W. Jones. Linking co₂ sorption performance to polymer morphology in aminopolymer/silica composites through neutron scattering. *J. Am. Chem. Soc.*, 137(36):11749–11759, 2015.

- [116] Gernot Rother, Uma Tumuluri, Kuan Huang, William T. Heller, Sheng Dai, Jan-Michael Carrillo, and Bobby G. Sumpter. Interactions of an imine polymer with nanoporous silica and carbon in hybrid adsorbents for carbon capture. *Langmuir*, 37(15):4622–4631, 2021.
- [117] Hyun June Moon, William T. Heller, Naresh C. Osti, Min Gyu Song, Laura Proano, Ida Vaghefi, and Christopher W. Jones. Probing the distribution and mobility of aminopolymers after multiple sorption-regeneration cycles: Neutron scattering studies. *Industrial & Engineering Chemistry Research*, 63(15):15100–15112, 2024.
- [118] Hyun June Moon, Jan-Michael Y. Carrillo, Min Gyu Song, Guanhe Rim, William T. Heller, Johannes Leisen, Laura Proaño, Gabriel N. Short, Sayan Banerjee, Bobby G. Sumpter, and Christopher W. Jones. Underlying roles of polyol additives in promoting co₂ capture in pei/silica adsorbents. *ChemSusChem*, 17(22):e202400967, 2024.
- [119] Yingzhen Ma, Gergely Nagy, Miriam Siebenbürger, Ravneet Kaur, Kerry M. Dooley, and Bhuvnesh Bharti. Adsorption and catalytic activity of gold nanoparticles in mesoporous silica: Effect of pore size and dispersion salinity. *J. Phys. Chem. C*, 126(4):2531–2541, 2022.
- [120] Yingzhen Ma, William Heller, Lilin He, William Shelton, Gernot Rother, and Bhuvnesh Bharti. Characterization of nano-assemblies inside mesopores using neutron scattering. *Molecular Physics*, 119(15-16):e1905190, 2021.
- [121] Ryuhei Motokawa, Shinichi Suzuki, Hiroki Ogawa, Mark R. Antonio, and Tsuyoshi Yaita. Microscopic structures of tri-n-butyl phosphate/n-octane mixtures by x-ray and neutron scattering in a wide q range. *The Journal of Physical Chemistry B*, 116(3):1319–1327, 2012.
- [122] Ryuhei Motokawa, Hitoshi Endo, Michihiro Nagao, and William T. Heller. Neutron polarization analysis for biphasic solvent extraction systems. *Solvent Extraction and Ion Exchange*, 35(2):109–116, 2016.
- [123] Ryuhei Motokawa, Tohru Kobayashi, Hitoshi Endo, Junju Mu, Christopher D. Williams, Andrew J. Masters, Mark R. Antonio, William T. Heller, and Michihiro Nagao. A telescoping view of solute architectures in a complex fluid system. *ACS Central Science*, 5(1):85–96, 2019.
- [124] Hirokazu Narita, Rebecca M. Nicolson, Ryuhei Motokawa, Fumiyuki Ito, Kazuko Morisaku, Midori Goto, Mikiya Tanaka, William T. Heller, Hideaki Shiwaku, Tsuyoshi Yaita, Ross J. Gordon, Jason B. Love, Peter A. Tasker, Emma R. Schofield, Mark R. Antonio, and Carole A. Morrison. Proton chelating ligands drive improved chemical separations for rhodium. *Inorganic Chemistry*, 58(13):8720–8734, 2019.
- [125] Ryuhei Motokawa, Koji Kaneko, Yojiro Oba, Takayuki Nagai, Yoshihiro Okamoto, Taishi Kobayashi, Takayuki Kumada, and William T. Heller. Nanoscopic structure of borosilicate glass with additives for nuclear waste vitrification. *Journal of Non-Crystalline Solids*, 578:121352, 2022.
- [126] Mehdi Rashidi, Alvaro Paul, Changwoo Do, and Kimberly Kurtis. The role of composition in the structure and water-binding in alkali-silica reaction sol and gel. *Cement and Concrete Research*, 124:105814, 2019.
- [127] Rezawana Islam and Brian Y. Lattimer. Understanding the impact of fuel on surfactant microstructure of firefighting foam. *Fire Technology*, 60:3413–3441, 2024.
- [128] Wei Chen and Seth B. Darling. Understanding the role of additives in improving the performance of bulk heterojunction organic solar cells. *Microscopy and Microanalysis*, 21(Suppl 3):2439–2440, 2015.
- [129] Ming Shao, Jong Kahk Keum, Rajeev Kumar, Jihua Chen, James F. Browning, Sanjib Das, Wei Chen, Jianhui Hou, Changwoo Do, Kenneth C. Littrell, Adam Rondinone, David B. Geohegan, Bobby G. Sumpter, and Kai Xiao. Understanding how processing additives tune the nanoscale morphology of high efficiency organic photovoltaic blends: From casting solution to spun-cast thin film. *Advanced Functional Materials*, 24(42):6647–6657, 2014.

- [130] Andrew J. Mulderig, Yan Jin, Fei Yu, Jong Keum, Kunlun Hong, James F. Browning, Gregory Beaucage, Gregory S. Smith, and Vikram K. Kupp. Determination of active layer morphology in all-polymer photovoltaic cells. *J. Appl. Cryst.*, 50:1–10, 2017.
- [131] Song Zhang, Michael U Ocheje, Lifeng Huang, Luke Galuska, Zhiqiang Cao, Shaochuan Luo, Dakota Ehlenberg, Renée Goodman, Dongshan Zhou, Yi Liu, Yu-Cheng Chiu, Jason D Azoulay, Simon Rondeau-Gagné, and Xiaodan Gu. The critical role of electron-donating thiophene groups on the mechanical and thermal properties of donor–acceptor semiconducting polymers. *Advanced Electronic Materials*, 5(5):1–11, 2019.
- [132] Xinwen Yan, Miao Xiong, Xin-Yu Deng, Kai-Kai Liu, Jia-Tong Li, Xue-Qing Wang, Song Zhang, Nathaniel Prine, Zhuoqiong Zhang, Wanying Huang, Yishan Wang, Jie-Yu Wang, Xiaodan Gu, Shu Kong So, Jia Zhu, and Ting Lei. Approaching disorder-tolerant semiconducting polymers. *Nature Communications*, 12(1):5723, 2021.
- [133] Ming-Ching Chang, Yi Wei, Wei-Ren Chen, and Changwoo Do. Deep learning based super-resolution for small-angle neutron scattering data: Attempt to accelerate experimental workflow. *MRS Communications*, 10(1):11–17, 2020.
- [134] Ming-Ching Chang, Chi-Huan Tung, Shou-Yi Chang, Jan Michael Carrillo, Yangyang Wang, Bobby G. Sumpter, Guan-Rong Huang, Changwoo Do, and Wei-Ren Chen. A machine learning inversion scheme for determining interaction from scattering. *Communications Physics*, 5(46), 2022.
- [135] Chi-Huan Tung, Shou-Yi Chang, Hsin-Lung Chen, Yangyang Wang, Kunlun Hong, Jan Michael Carrillo, Bobby G. Sumpter, Yuya Shinohara, Changwoo Do, and Wei-Ren Chen. Small angle scattering of diblock copolymers profiled by machine learning. *J. Chem. Phys.*, 156(13):131101, 2022.
- [136] Lijie Ding, Chi-Huan Tung, Bobby G. Sumpter, Wei-Ren Chen, and Changwoo Do. Deciphering the scattering of mechanically driven polymers using deep learning. *J. Chem. Theory Comput.*, 21(11):4176–4182, 2025.
- [137] Lijie Ding, Chi-Huan Tung, Zhiqiang Cao, Zekun Ye, Xiaodan Gu, Yan Xia, Wei-Ren Chen, and Changwoo Do. Machine learning-assisted pro filing of a kinked ladder polymer structure using scattering. *Digital Discovery*, 4:1570–1577, 2025.
- [138] Guan-Rong Huang, Chi-Huan Tung, Lionel Porcar, Yangyang Wang, Yuya Shinohara, Changwoo Do, and Wei-Ren Chen. Model-free approach for profiling of polydisperse soft matter using small angle scattering. *Macromolecules*, 56(17):6436–6443, 2023.
- [139] Guan-Rong Huang, Chi-Huan Tung, Lionel Porcar, Yuya Shinohara, Changwoo Do, Wei-Ren Chen, and Pengwen Chen. Scattering-based structural reconstruction by dimensional elevation. *J. Chem. Phys.*, 162(17):174102, 2025.
- [140] Chi-Huan Tung, Sidney Yip, Guan-Rong Huang, Lionel Porcar, Yuya Shinohara, Bobby G. Sumpter, Lijie Ding, Changwoo Do, and Wei-Ren Chen. Unlocking hidden information in sparse small-angle neutron scattering measurements. *Journal of Colloid And Interface Science*, 692:137554, 2025.
- [141] Dunji Yu, Ke An, Carrie Y. Gao, William T. Heller, and Xu Chen. A portable hydro-thermo-mechanical loading cell for in situ small angle neutron scattering studies of proton exchange membranes. *Review of Scientific Instruments*, 84(10):105115, 2013.
- [142] Shouwen Shi, Dan Liu, Dazhi Liu, Patrick Tae, Carrie Y. Gao, Lei Yan, Ke An, and Xu Chen. Mechanical properties and microstructure changes of proton exchange membrane under immersed conditions. *Polymer Engineering & Science*, 54(10):2215–2221, 2014.
- [143] Yangyang Wang, Shalin Patil, Shiwang Cheng, and Changwoo Do. The influence of elongation-induced concentration fluctuations on segmental friction in polymer blends. *Soft Matter*, 20(20):4257–4269, 2024.

- [144] Zhe Wang, Takuya Iwashita, Lionel Porcar, Yangyang Wang, Yun Liu, Luis E. Sánchez-Díaz, Bin Wu, Guan-Rong Huang, Takeshi Egami, and Wei-Ren Chen. Local elasticity in nonlinear rheology of interacting colloidal glasses revealed by neutron scattering and rheometry. *Physical Chemistry Chemical Physics*, 21(1):38–45, 2019.
- [145] Dejie Kong, Wei-Ren Chen, Ke-Qi Zeng, Lionel Porcar, and Zhe Wang. Localized elasticity governs the nonlinear rheology of colloidal supercooled liquids. *Physical Review X*, 12(4):041006, 2022.
- [146] Guan-Rong Huang, Jan Michael Carrillo, Yangyang Wang, Changwoo Do, Lionel Porcar, Bobby Sumpter, and Wei-Ren Chen. An exact inversion method for extracting orientation ordering from small-angle scattering. *Phys. Chem. Chem. Phys.*, 0(0):1–5, 2021.
- [147] Guan-Rong Huang, Yangyang Wang, Changwoo Do, Yuya Shinohara, Takeshi Egami, and Wei-Ren Chen. Orientational distribution function of aligned elongated molecules and particulates determined from their scattering signature. *ACS Macro Letters*, 8(10):1257–1262, 2019.
- [148] Tae Hui Kang, Brett G. Compton, William T. Heller, Shuo Qian, Gregory S. Smith, Volker S. Urban, Chad E. Duty, and Changwoo Do. Potentials with small-angle neutron scattering technique for understanding structure-property relation of 3d-printed materials. *Unspecified Journal*, 2019.
- [149] Lilin He, Changwoo Do, Shuo Qian, George D. Wignall, William T. Heller, Kenneth C. Littrell, and Gregory S. Smith. Corrections for the geometric distortion of the tube detectors on sans instruments at ornl. *Nuclear Instruments and Methods in Physics Research Section A: Accelerators, Spectrometers, Detectors and Associated Equipment*, 775:63–70, 2015.
- [150] Changwoo Do, Gergely Nagy, William Heller, Carrie Gao, Timothy M. Carroll, and Matt Kyte. Eq-sans detector distance measurement with laser alignment method. Technical Report ORNL/TM-2021/1982, Oak Ridge National Laboratory, 2021.
- [151] Jinkui Zhao. Data processing for the SNS EQ-SANS diffractometer. *Nuclear Instruments and Methods in Physics Research A*, 647:107–111, 2011.
- [152] Changwoo Do, William T. Heller, Christopher Stanley, Franz Xb. Gallmeier, Mathieu Doucet, and Gregory S. Smith. Understanding inelastically scattered neutrons from water on a time-of-flight small-angle neutron scattering (sans) instrument. *Nuclear Instruments and Methods in Physics Research Section A: Accelerators, Spectrometers, Detectors and Associated Equipment*, 737:42–46, 2014.
- [153] Xingxing Yao, Blake Avery, Miljko Bobrek, Lisa Debeer-Schmitt, Xiaosong Geng, Ray Gregory, Greg Guyotte, Mike Harrington, Steven Hartman, Lilin He, Luke Heroux, Kay Kasemir, Rob Knudson, James Kohl, Carl Lionberger, Kenneth Littrell, Matthew Pearson, Sai Venkatesh Pingali, Cody Pratt, Shuo Qian, Mariano Ruiz-Rodriguez, Vladislav Sedov, Gary Taufer, Volker Urban, and Klemen Vodopivec. A unified user-friendly instrument control and data acquisition system for the ornl sans instrument suite. *Applied Sciences*, 11(3):1216, 2021.
- [154] Changwoo Do, Gergely Nagy, and William T. Heller. Esac (eq-sans assisting chatbot): Application of large language models and retrieval-augmented generation for enhanced user experience at eq-sans. *SoftwareX*, 31:102191, 2025.

A Technical Appendices and Supplementary Material

Technical appendices with additional results, figures, graphs and proofs may be submitted with the paper submission before the full submission deadline, or as a separate PDF in the ZIP file below before the supplementary material deadline. There is no page limit for the technical appendices.

Agents4Science AI Involvement Checklist

1. **Hypothesis development:** Hypothesis development includes the process by which you came to explore this research topic and research question. This can involve the background research performed by either researchers or by AI. This can also involve whether the idea was proposed by researchers or by AI.

Answer: [\[A\]](#)

Explanation: The idea was proposed by researchers. The publication list was provided by human. Extended summary of all the publication list was prepared by AI.

2. **Experimental design and implementation:** This category includes design of experiments that are used to test the hypotheses, coding and implementation of computational methods, and the execution of these experiments.

Answer: [\[C\]](#)

Explanation: AI proposed the article's first outline as directed by human and drafted the complete review, including the bibliography.

3. **Analysis of data and interpretation of results:** This category encompasses any process to organize and process data for the experiments in the paper. It also includes interpretations of the results of the study.

Answer: [\[C\]](#)

Explanation: The first organization of the sections and subsections was proposed by the AI based on the summaries of all the publications. Minor revision to the outline was done by the human. Appropriate references were indexed and cited by the AI, which were reviewed by humans later.

4. **Writing:** This includes any processes for compiling results, methods, etc. into the final paper form. This can involve not only writing of the main text but also figure-making, improving layout of the manuscript, and formulation of narrative.

Answer: [\[D\]](#)

Explanation: Most of the writing was done by the AI including the selection of references. Humans reviewed them and provided minor corrections such as missing page numbers or journal names.

5. **Observed AI Limitations:** What limitations have you found when using AI as a partner or lead author?

Description: AI made a few mistakes understanding subtle details of the scientific article. Among the list of publications we provided, there were several publications where the contribution of the small-angle scattering technique, which is the main topic of this review, is rather small compared to the other techniques that were used in those studies. However, AI chose to highlight those publication.

Agents4Science Paper Checklist

1. Claims

Question: Do the main claims made in the abstract and introduction accurately reflect the paper's contributions and scope?

Answer: [Yes]

Justification: The coauthors agree the abstract and introduction effectively capture the article's goal of highlighting EQ-SANS's broad scientific impact and future prospects.

Guidelines:

- The answer NA means that the abstract and introduction do not include the claims made in the paper.
- The abstract and/or introduction should clearly state the claims made, including the contributions made in the paper and important assumptions and limitations. A No or NA answer to this question will not be perceived well by the reviewers.
- The claims made should match theoretical and experimental results, and reflect how much the results can be expected to generalize to other settings.
- It is fine to include aspirational goals as motivation as long as it is clear that these goals are not attained by the paper.

2. Limitations

Question: Does the paper discuss the limitations of the work performed by the authors?

Answer: [NA]

Justification: As this is a review paper, the primary goal is to provide a comprehensive overview and synthesis of existing literature. It does not introduce novel experimental work or original data that would typically have inherent limitations.

Guidelines:

- The answer NA means that the paper has no limitation while the answer No means that the paper has limitations, but those are not discussed in the paper.
- The authors are encouraged to create a separate "Limitations" section in their paper.
- The paper should point out any strong assumptions and how robust the results are to violations of these assumptions (e.g., independence assumptions, noiseless settings, model well-specification, asymptotic approximations only holding locally). The authors should reflect on how these assumptions might be violated in practice and what the implications would be.
- The authors should reflect on the scope of the claims made, e.g., if the approach was only tested on a few datasets or with a few runs. In general, empirical results often depend on implicit assumptions, which should be articulated.
- The authors should reflect on the factors that influence the performance of the approach. For example, a facial recognition algorithm may perform poorly when image resolution is low or images are taken in low lighting.
- The authors should discuss the computational efficiency of the proposed algorithms and how they scale with dataset size.
- If applicable, the authors should discuss possible limitations of their approach to address problems of privacy and fairness.
- While the authors might fear that complete honesty about limitations might be used by reviewers as grounds for rejection, a worse outcome might be that reviewers discover limitations that aren't acknowledged in the paper. Reviewers will be specifically instructed to not penalize honesty concerning limitations.

3. Theory assumptions and proofs

Question: For each theoretical result, does the paper provide the full set of assumptions and a complete (and correct) proof?

Answer: [NA]

Justification: Since this is a review article, no assumptions were made and no proofs were required.

1002 Guidelines:

1003 • The answer NA means that the paper does not include theoretical results.

1004 • All the theorems, formulas, and proofs in the paper should be numbered and cross-

1005 referenced.

1006 • All assumptions should be clearly stated or referenced in the statement of any theorems.

1007 • The proofs can either appear in the main paper or the supplemental material, but if

1008 they appear in the supplemental material, the authors are encouraged to provide a short

1009 proof sketch to provide intuition.

1010 **4. Experimental result reproducibility**

1011 Question: Does the paper fully disclose all the information needed to reproduce the main ex-

1012 perimental results of the paper to the extent that it affects the main claims and/or conclusions

1013 of the paper (regardless of whether the code and data are provided or not)?

1014 Answer: [\[Yes\]](#)

1015 Justification: While a review article cannot discuss experimental results or their reproducibil-

1016 ity, the AI has successfully cited appropriate and relevant references, which is a critical

1017 aspect of a well-written review.

1018 Guidelines:

1019 • The answer NA means that the paper does not include experiments.

1020 • If the paper includes experiments, a No answer to this question will not be perceived

1021 well by the reviewers: Making the paper reproducible is important.

1022 • If the contribution is a dataset and/or model, the authors should describe the steps taken

1023 to make their results reproducible or verifiable.

1024 • We recognize that reproducibility may be tricky in some cases, in which case authors

1025 are welcome to describe the particular way they provide for reproducibility. In the case

1026 of closed-source models, it may be that access to the model is limited in some way

1027 (e.g., to registered users), but it should be possible for other researchers to have some

1028 path to reproducing or verifying the results.

1029 **5. Open access to data and code**

1030 Question: Does the paper provide open access to the data and code, with sufficient instruc-

1031 tions to faithfully reproduce the main experimental results, as described in supplemental

1032 material?

1033 Answer: [\[NA\]](#)

1034 Justification: The full list of publications used in our review is available at the EQ-SANS

1035 homepage. (neutrons.ornl.gov/eqsans)

1036 Guidelines:

1037 • The answer NA means that paper does not include experiments requiring code.

1038 • Please see the Agents4Science code and data submission guidelines on the conference

1039 website for more details.

1040 • While we encourage the release of code and data, we understand that this might not be

1041 possible, so “No” is an acceptable answer. Papers cannot be rejected simply for not

1042 including code, unless this is central to the contribution (e.g., for a new open-source

1043 benchmark).

1044 • The instructions should contain the exact command and environment needed to run to

1045 reproduce the results.

1046 • At submission time, to preserve anonymity, the authors should release anonymized

1047 versions (if applicable).

1048 **6. Experimental setting/details**

1049 Question: Does the paper specify all the training and test details (e.g., data splits, hyper-

1050 parameters, how they were chosen, type of optimizer, etc.) necessary to understand the

1051 results?

1052 Answer: [\[NA\]](#)

1053 Justification: As experiments were not presented in this article, this question cannot be
1054 answered.

1055 Guidelines:

- 1056 • The answer NA means that the paper does not include experiments.
- 1057 • The experimental setting should be presented in the core of the paper to a level of detail
1058 that is necessary to appreciate the results and make sense of them.
- 1059 • The full details can be provided either with the code, in appendix, or as supplemental
1060 material.

1061 7. Experiment statistical significance

1062 Question: Does the paper report error bars suitably and correctly defined or other appropriate
1063 information about the statistical significance of the experiments?

1064 Answer: [NA]

1065 Justification: As this article does not contain experiments, this question cannot be answered.

1066 Guidelines:

- 1067 • The answer NA means that the paper does not include experiments.
- 1068 • The authors should answer "Yes" if the results are accompanied by error bars, confi-
1069 dence intervals, or statistical significance tests, at least for the experiments that support
1070 the main claims of the paper.
- 1071 • The factors of variability that the error bars are capturing should be clearly stated
1072 (for example, train/test split, initialization, or overall run with given experimental
1073 conditions).

1074 8. Experiments compute resources

1075 Question: For each experiment, does the paper provide sufficient information on the com-
1076 puter resources (type of compute workers, memory, time of execution) needed to reproduce
1077 the experiments?

1078 Answer: [NA]

1079 Justification: As this article does not contain experiments, this question cannot be answered.

1080 Guidelines:

- 1081 • The answer NA means that the paper does not include experiments.
- 1082 • The paper should indicate the type of compute workers CPU or GPU, internal cluster,
1083 or cloud provider, including relevant memory and storage.
- 1084 • The paper should provide the amount of compute required for each of the individual
1085 experimental runs as well as estimate the total compute.

1086 9. Code of ethics

1087 Question: Does the research conducted in the paper conform, in every respect, with the
1088 Agents4Science Code of Ethics (see conference website)?

1089 Answer: [Yes]

1090 Justification: This research was conducted in full compliance with the NeurIPS Code of
1091 Ethics. We have carefully considered all aspects of the code, including potential harms,
1092 societal impact, and mitigation strategies.

1093 Guidelines:

- 1094 • The answer NA means that the authors have not reviewed the Agents4Science Code of
1095 Ethics.
- 1096 • If the authors answer No, they should explain the special circumstances that require a
1097 deviation from the Code of Ethics.

1098 10. Broader impacts

1099 Question: Does the paper discuss both potential positive societal impacts and negative
1100 societal impacts of the work performed?

1101 Answer: [Yes]

1102 Justification: This work serves as a practical guide for potential users of the EQ-SANS
1103 instrument, demonstrating the diverse research possibilities it offers. By showcasing a
1104 variety of experiments, it aims to attract a broader community of scientists and expand
1105 the instrument's user base. Additionally, this study highlights the effectiveness of AI
1106 in generating review articles, which can help researchers quickly gain a comprehensive
1107 understanding of specific topics.

1108 Guidelines:

- 1109 • The answer NA means that there is no societal impact of the work performed.
- 1110 • If the authors answer NA or No, they should explain why their work has no societal
1111 impact or why the paper does not address societal impact.
- 1112 • Examples of negative societal impacts include potential malicious or unintended uses
1113 (e.g., disinformation, generating fake profiles, surveillance), fairness considerations,
1114 privacy considerations, and security considerations.
- 1115 • If there are negative societal impacts, the authors could also discuss possible mitigation
1116 strategies.