



1,3-Propanesultone (PS)

ELECTROLYTE ADDITIVE

PRODUCT OVERVIEW

1,3-Propanesultone (PS) is an electrolyte additive supplied for battery-electrolyte formulation, additive screening, and electrochemical research. This sheet summarizes specification limits and representative quality-control results.

PRODUCT INFORMATION

CAS No. 1120-71-4 | Formula $C_3H_6O_3S$ | Abbreviation PS

TECHNICAL SPECIFICATIONS

PROPERTY	SPECIFICATION	REPRESENTATIVE QC RESULT	UNIT
Appearance	Colorless transparent liquid or crystalline material, with no mechanical impurities, insoluble matter, or flocculent material	Conforms	—
Color	≤20	5.2	Hazen
Water	≤50	32.4	ppm
Assay	≥99.95	99.997	wt%
Free acid, as HF	≤20	5.4	ppm
Chloride	≤2	<2.0	ppm
Sulfate	≤5	<5.0	ppm
Trace metals: Na / Ca / K / Pb / Fe / Cu / Zn	≤2 each	0.22 / 0.25 / ND / 0.30 / ND / ND / 0.01	ppm
Trace metals: Mg / Cr / Ni / Mn / Ba / Cd / Al	≤2 each	0.03 / ND / 0.32 / ND / ND / ND / 0.31	ppm

REPRESENTATIVE QC HIGHLIGHTS

99.997 wt% assay

32.4 ppm water

5.4 ppm free acid

RESEARCH APPLICATIONS

Electrolyte formulation development; additive screening; cell-material compatibility studies; and electrochemical research. Suitability should be confirmed in the intended system.

STORAGE / SHELF LIFE

60 days

QUALITY / DOCUMENTATION

Specification limits and representative quality-control results are provided for technical reference. Lot-specific Certificate of Analysis is available upon request.

Supplied and technically supported by Winigen Materials.

www.winigenmaterials.com | contact@winigenmaterials.com

PS-TDS-001

Specification limits and representative quality-control results are provided for technical reference. Representative results are lot-specific and are not guaranteed values. The applicable lot-specific Certificate of Analysis governs material supplied.