



Mo₂CT_x MXene — Single-/Few-Layer Powder

Research-grade two-dimensional transition-metal carbide powder

This delaminated Mo₂CT_x MXene powder is prepared from Mo₂Ga₂C by HF etching followed by intercalation and delamination. The material has a single-/few-layer structure of no more than five layers and nanoscale lateral dimensions. Surface terminations include –O, –OH, and –F.

KEY FEATURES

- Delaminated single-/few-layer morphology (≤ 5 layers)
- Nanoscale nominal lateral size
- Typical conductivity of 1000 ± 500 S/cm
- Mixed –O/–OH/–F surface terminations

POTENTIAL RESEARCH APPLICATIONS

- Electrochemical energy-storage and metal–sulfur battery research
- Electrocatalysis and conductive-composite studies
- Two-dimensional materials and interface research

STORAGE & HANDLING

Keep dry in a tightly closed container. Vacuum or inert-atmosphere storage is recommended. Minimize exposure to moisture and air; use appropriate controls for fine powders.

QUALITY / DOCUMENTATION


Surface termination distributions vary with synthesis and lot. Quantitative surface composition can be discussed when required.

TECHNICAL SPECIFICATIONS

PROPERTY	TYPICAL / REPRESENTATIVE VALUE
Material	Mo ₂ CT _x MXene
Precursor	Mo ₂ Ga ₂ C
Product form	Delaminated single-/few-layer powder
Preparation	HF etching followed by intercalation / delamination
Layer structure / count	≤ 5 layers
Nominal lateral size	200–1000 nm
Typical conductivity	1000 ± 500 S/cm
Surface terminations	–O, –OH, and –F
Appearance	Dark powder (descriptive only)
Recommended storage	Dry; vacuum or inert atmosphere

Conductivity values are representative technical values. Measurement results can vary with sample preparation, packing, film preparation and measurement geometry.

REPRESENTATIVE CHARACTERIZATION



Product positioning: Supplied and technically supported by WiniGen Materials for research and development use.

WINIGEN MATERIALS
www.winigenmaterials.com | contact@winigenmaterials.com

MO2CTX-SFL-TDS-001

Representative technical values. Properties can vary with synthesis and lot. Lot-specific documentation and additional analytical details are available subject to review.