

Service Number
#BR-Aug-11-2014

Date
11-11-2014

Client

MEK Clay Sintered Bricks Production Line
Industrial Experiment Report

Notice

1. Test report is invalid without the stamp of test department on it.
2. Duplication of test report is invalid without the stamp of test department on it.
3. Test report is invalid without the signatures of writer, verification and approval.
4. Test report is invalid if altered.
5. The test results are only responsible for the delivered samples.

Xi'an Brictec Engineering Co.,LTD
info@brictec.com
WhatsApp: +86 181 8262 2677

Raw Material Test Report

Physical Property Report

No. of Report: (2014) 029

Raw material type	Clay			Source of material	Delivery		
Client	MEK			Delivery date	Jul 28, 2014		
Delivery unit	MEK			Testing item	Physical test		
Analysis result							
Item Type	Pfefferkom shaping moisture(%)	Plasticity			Critical moisture(%)	Drying sensitivity modulus(%)	Drying shrinkage(%)
		Liquid limit(%)	Plastic limit(%)	Plasticity index			
Clay	22.17	31.30	18.54	12.76	10.98	1.02	5.42
Partical composition Type	Bore diameter (mm)	Sieving method					
		> 0.5	0.5 ~ 0.25		0.25 ~ 0.1		< 0.1
	Percentage (%)						
Remark							
Date of report	Aug 11, 2014	Date of issue					

Accounts Manager

Mazharul Basu

Company

Website: www.brictec.com E-mail: info@brictec.com Xi'an Brictec Engineering Co.,LTD

Service Number
#BR-Aug-11-2014Date
11-11-2014

Client

MEK Clay Sintered Bricks Production Line
Industrial Experiment Report

Notice

1. Test report is invalid without the stamp of test department on it.
2. Duplication of test report is invalid without the stamp of test department on it.
3. Test report is invalid without the signatures of writer, verification and approval.
4. Test report is invalid if altered.
5. The test results are only responsible for the delivered samples.

 Xi'an Brictec Engineering Co.,LTD
 info@brictec.com
 WhatsApp:+86 181 8262 2677

Chemical Composition Report

Physical Property Report

No. of Report: (2014) 029

Raw material type	Clay	Source of material	Delivery
Client	MEK	Delivery date	Jul 28, 2014
Delivery unit	MEK	Testing item	Physical test
Analysis result (%)			
Material type	Clay		
Test item			
SiO ₂	63.33		
Al ₂ O ₃	13.56		
Fe ₂ O ₃	5.44		
CaO	0.90		
MgO	0.42		
K ₂ O	1.39		
Na ₂ O	0.17		
SO ₃	0.14		
TiO ₂	0.78		
Loss on ignition	9.18		
Remark			
Date of report	Aug 11, 2014	Date of issue	

Accounts Manager



Company

Website: www.brictec.com E-mail: info@brictec.com Xi'an Brictec Engineering Co.,LTD

Service Number
#BR-Aug-11-2014

Date
11-11-2014

Client

MEK Clay Sintered Bricks Production Line
Industrial Experiment Report

Notice

1. Test report is invalid without the stamp of test department on it.
2. Duplication of test report is invalid without the stamp of test department on it.
3. Test report is invalid without the signatures of writer, verification and approval.
4. Test report is invalid if altered.
5. The test results are only responsible for the delivered samples.

Xi'an Brictec Engineering Co.,LTD
info@brictec.com
WhatsApp: +86 181 8262 2677

Heating Value Report

Physical Property Report

No. of Report: (2014) 029

Raw material type	Clay	Source of material	Delivery
Client	MEK	Delivery date	Jul 28, 2014
Delivery unit	MEK	Testing item	Physical test
Test results			
Test item Material type	Heating Value (KJ/kg)		
Coal	27578.60 (6597.75kCal/kg)		
Remark			
Date of report	Aug 11, 2014	Date of issue	

Accounts Manager

Mazharul Basu

Company

Website: www.brictec.com E-mail: info@brictec.com Xi'an Brictec Engineering Co.,LTD