RICOH THERMAL FILM
TYPE 135FTS-L<100>

1.FILM PROPERTIES

Item	Unit	Specification	Test Method
Basis Weight	g/㎡	83±5	ISO 536
Thickness	μm	101±6	ISO 534
Whitenes	%	85 min	ISO 2470
Smmothness (Face)	s	1000 min	Oken type instrument

2.IMAGE PROPERTIES

Item	Unit	Specification	Test Method
Image Color	-	Black	Visual Inspection
Dynamic Image	-	1.25 min	Ricoh standard simulator
Dynamic Image Sensitivity	mJ/dot	0.35 max	

3. PRESERVATION

Item		Unit	Specification	Test Method
Plasticizer Resistance	Image	-	1.20 min	40℃,DRY,15h
	Background	-	0.20 max	
Vegetable Oil Resistance	Image	-	1.00 min	80℃,Dry,24h
	Background	-	0.20 max	
Water Resistance	Image	-	1.20 min	20℃, 15h
	Background		0.20 max	
Heat Resistance	Image	-	1.20 min	90℃,Dry,1h
	Background	-	0.25 max	
Humidity Resistance	Image	-	1.20 min	40℃,90%,24h
	Background	-	0.20 max	
Light Resistance	Image	-	1.20 min	5000lx,100h
	Background	-	0.20 max	

<Quality Assurance Condition>

① Unit：Face roll, 1 roll.

② Storage Conditions：Keep in-door, avoiding high temperature(such as beside heat source), high humidity and direct sun light.

③ Usage Condition：5～40℃, 30～95% RH.

④ Quality Assurance：24 months after production.

Note:

1) The Specifications and process flow of the product will be renewed without notice.

2) The Specification is only for reference ,and please no hesitate to connect with us if any puzzle.

3) Our company reserve the rights of final interpretation to the Specification.

- Ricoh Thermal Media (Wuxi)Co.,Ltd
  Tel: 0510-8533-0555 Fax: 0510-8533-0022
- Ricoh International (Shanghai)Co.,Ltd
  Tel: 021-6485-1058 Fax: 021-6495-8662
- Ricoh Thermal Media (Wuxi)Co.,Ltd Beijing Branch
  Tel: 010-8879-7580 Fax: 010-8879-7572
- Ricoh Thermal Media (Wuxi)Co.,Ltd Guangzhou Branch
  Tel: 020-3463-2828 Fax: 020-3463-1991

01/2024