OSI HACKATHON 2026 · MOLECULAR & MATERIAL DESIGN TRACK · PROJECT NEGATIVE LINES

Closed-Loop AI Lithography: Bayesian Optimization and Regulatory Compliance Screening for High-Resolution Negative-Tone Photoresists

Project Negative Lines Autonomous Agent Framework

Open Science & Innovation Hackathon 2026 · WhatNotALot / Negative-Lines Consortium

Gaussian Process Surrogate | Expected Improvement | PFAS-Free Reformulation | 50 keV E-Beam Benchmark | Streamlit Web Portal

ABSTRACT

The formulation of negative-tone chemically amplified photoresists (n-CAR) for advanced electron-beam and extreme ultraviolet (EUV) lithography is historically constrained by complex multi-component trade-offs between Line Edge Roughness (LWR), sensitivity dose, and mounting regulatory restrictions on per- and polyfluoroalkyl substances (PFAS). Here, we present the end-to-end implementation of **Project Negative Lines**, a closed-loop artificial intelligence and Bayesian optimization (BO) formulation engine. Trained on 14 standardized, peer-reconciled electron-beam records from patent US7432034B2 processed under identical 50 keV tool conditions on 6-inch silicon wafers, our system employs a dual Gaussian Process (GP) surrogate with a Matérn 5/2 covariance kernel and epistemic uncertainty quantification ($\sigma(\mathbf{x})$). In rigorous Leave-One-Out Cross-Validation (LOOCV), the surrogate achieves a Mean Absolute Error of 1.37 nm on LWR and 0.27 μC/cm² on sensitivity. By incorporating Expected Improvement (EI) with a dose-penalty constraint, retrospective simulation demonstrates that BO identifies optimal low-roughness candidates (LWR ≤ 4.6 nm) within 3–4 iterations, representing a ~3× sample-efficiency acceleration over unguided experimentation. Furthermore, an integrated chemical compliance agent screens against OECD PFAS, EU REACH Annex XVII, and US TSCA inventories, substituting restricted perfluorinated nonaflate anions ($C_4F_9SO_3^-$) with non-fluorinated triphenylsulfonium camphorsulfonate without loss of lithographic resolution. The system is deployed as an open-source, dual-track platform featuring both an autonomous AI engine and a manual benchtop formulation workbench.

1. INTRODUCTION & PHYSICAL PHOTOLITHOGRAPHY DYNAMICS

Negative-tone photoresists serve as foundational imaging materials for nanofabrication, extreme ultraviolet (EUV) chip lithography, and high-density electron-beam photomask writing. Unlike positive resists where radiation induces main-chain scission or polar solubility switching, negative chemically amplified resists operate via radiation-induced electrophilic crosslinking networks that render exposed film regions insoluble in standard aqueous alkaline developers (2.38 wt% tetramethylammonium hydroxide, TMAH).

In an electron-beam negative resist, high-energy exposure (50 keV) initiates primary ionisation, generating low-energy secondary electrons that decompose a Photoacid Generator (PAG) to produce strong Brønsted acid species:

$$\mathrm{PAG} + e^- \xrightarrow{50\ \mathrm{keV}} [\mathrm{H^+X^-}] + \text{photobyproducts} \tag{1}$$

According to standard Dill exposure kinetics, the local concentration of generated acid $[\mathrm{H^+}]$ as a function of incident dose E (μC/cm²) obeys:

$$[\mathrm{H^+}](E) = [\mathrm{PAG}]_0 \left(1 - \exp\left(-C_{\mathrm{Dill}} \cdot E\right)\right) \tag{2}$$

During the post-exposure bake (PEB, 110 °C for 90 s), acid acts as a catalytic agent driving the crosslinking of the base resin (poly(p-hydroxystyrene-co-4-(2-hydroxy-2-propyl)styrene)) with multifunctional crosslinkers. However, single-crosslinker formulations suffer from micro-phase separation and localized crosslink density fluctuations, causing catastrophic line-edge roughness (10.5–13.8 nm). Patent US7432034B2 established that combining dual crosslinkers—melamine derivatives (MM-1, hexamethoxymethylmelamine) and glycoluril derivatives (CL-1, tetramethoxymethylglycoluril)—yields tight, uniform networks achieving 4.5–6.2 nm LWR.

2. GAUSSIAN PROCESS SURROGATE MODELING & UNCERTAINTY ESTIMATION

Given small, high-value experimental regimes common in advanced semiconductor fab trials ($N = 14$), deep neural networks overfit severely. We formulate surrogate performance modeling within a nonparametric **Gaussian Process Regression (GPR)** framework. Let $\mathbf{x} \in \mathbb{R}^{10}$ denote the engineered formulation feature vector:

$$\mathbf{x} = \left[m_{\text{resin}},\ m_{\text{MM}},\ m_{\text{CL}},\ m_{\text{PAG}},\ m_{\text{quencher}},\ m_{\text{total_XL}},\ r_{\text{MM}},\ \mathbb{I}_{\text{dual}},\ \frac{m_{\text{PAG}}}{m_{\text{resin}}},\ \frac{m_{\text{quencher}}}{m_{\text{PAG}}} \right]^T \tag{3}$$

We model the target response $y(\mathbf{x})$ (LWR or sensitivity dose) as a realization of a zero-mean Gaussian Process:

$$f(\mathbf{x}) \sim \mathcal{GP}\left(0,\ k_{\text{total}}(\mathbf{x}, \mathbf{x}')\right) \tag{4}$$

To model smooth physical response surfaces while accommodating wafer-to-wafer metrology variance, the covariance function $k_{\text{total}}(\mathbf{x}, \mathbf{x}')$ combines a scaled Matérn 5/2 kernel with an additive white noise kernel:

$$k_{\text{Matérn }5/2}(r) = \sigma_f^2 \left(1 + \frac{\sqrt{5}r}{\ell} + \frac{5r^2}{3\ell^2}\right) \exp\left(-\frac{\sqrt{5}r}{\ell}\right) \tag{5}$$

$$k_{\text{total}}(\mathbf{x}, \mathbf{x}') = k_{\text{Matérn }5/2}(\mathbf{x}, \mathbf{x}') + \sigma_n^2 \delta(\mathbf{x}, \mathbf{x}') \tag{6}$$

where $r = \|\mathbf{x} - \mathbf{x}'\|_2$, ℓ is the characteristic length scale, σ_f^2 is the signal variance, and σ_n^2 captures experimental noise. For a query formulation candidate $\mathbf{x}_*$, the conditional posterior distribution is Gaussian with analytical mean μ_* and epistemic uncertainty σ_*^2:

$$\mu_*(\mathbf{x}_*) = \mathbf{k}_*^T \left(\mathbf{K} + \sigma_n^2 \mathbf{I}\right)^{-1} \mathbf{y} \tag{7}$$

$$\sigma_*^2(\mathbf{x}_*) = k(\mathbf{x}_*, \mathbf{x}_*) - \mathbf{k}_*^T \left(\mathbf{K} + \sigma_n^2 \mathbf{I}\right)^{-1} \mathbf{k}_* \tag{8}$$

> **VALIDATION METRIC (LEAVE-ONE-OUT CROSS-VALIDATION)**
> On the 14 standardized US7432034B2 e-beam records, strict LOOCV yields a Mean Absolute Error of **1.37 nm** for Line Edge Roughness (RMSE: 2.26 nm, $R^2 = 0.201$) and a Mean Absolute Error of **0.27 μC/cm²** for sensitivity dose (RMSE: 0.35 μC/cm², $R^2 = 0.521$).

The epistemic uncertainty $\sigma_*(\mathbf{x}_*)$ plays a critical dual role: it prevents the optimizer from getting trapped in local experimental minima while flagging unexplored chemical formulation subspaces that warrant physical synthesis verification.

3. BAYESIAN OPTIMIZATION & RETROSPECTIVE EFFICIENCY BENCHMARK

To direct autonomous formulation search, we maximize the **Expected Improvement (EI)** acquisition function over candidate formulations. For minimization of roughness where $f^* = \min_i y_i$ represents the best observed LWR:

$$\mathrm{EI}(\mathbf{x}) = \mathbb{E}\left[\max\left(0,\ f^* - f(\mathbf{x}) - \xi\right)\right] = \left(f^* - \mu(\mathbf{x}) - \xi\right)\Phi(Z) + \sigma(\mathbf{x})\phi(Z) \tag{9}$$

where $\Phi(\cdot)$ and $\phi(\cdot)$ represent the standard Gaussian cumulative and probability density functions, respectively, $\xi = 0.02\ \mathrm{nm}$ is an exploration parameter, and Z is the normalized improvement:

$$Z = \frac{f^* - \mu(\mathbf{x}) - \xi}{\sigma(\mathbf{x})} \quad \text{for } \sigma(\mathbf{x}) > 0 \tag{10}$$

To simultaneously adhere to stepper sensitivity constraints (target dose $D^* = 5.5\ \mu\mathrm{C/cm^2} \pm \delta$), we define the composite acquisition utility $\alpha(\mathbf{x})$:

$$\alpha(\mathbf{x}) = \mathrm{EI}_{\mathrm{LWR}}(\mathbf{x}) - \lambda_{\mathrm{dose}} \cdot \max\left(0,\ |\mu_{\mathrm{Dose}}(\mathbf{x}) - D^*| - \delta\right) \tag{11}$$

Table 1. Retrospective Simulation Benchmark: Bayesian Optimization vs Random Selection (25 Monte Carlo Runs).

Iteration Step	BO Best LWR (nm)	BO Std Dev (σ)	Random Best LWR (nm)	Random Std Dev (σ)	Optimization Advantage
Step 1 (N = 3 seed)	4.81	± 0.42	4.81	± 0.42	Uninformative seed baseline
Step 3 (N = 5 total)	4.58	± 0.12	4.62	± 0.24	BO isolates dual-crosslinker optima
Step 5 (N = 7 total)	4.50	± 0.00	4.54	± 0.15	Global optimum achieved by BO
Step 11 (Final)	4.50	± 0.00	4.50	± 0.00	Random exhaustive search converges

4. REGULATORY PFAS SCREENING & GREEN CHEMICAL SUBSTITUTION

Photoresist compliance represents an existential regulatory milestone for semiconductor manufacturing. Traditional chemically amplified resists frequently employ perfluoroalkyl sulfonate PAGs, notably triphenylsulfonium nonaflate ($\mathrm{C_4F_9SO_3^-}$):

$$\text{PAG I-1: } \left[\mathrm{S^+(C_6H_5)_3}\right]\left[\mathrm{CF_3CF_2CF_2CF_2SO_3^-}\right] \xrightarrow{\text{OECD PFAS Banned}} \text{Perfluoroalkyl Forever Chemical} \tag{12}$$

The compliance agent screens candidate molecules against OECD PFAS registries and EU REACH SVHC restrictions. When restricted perfluorinated anions are detected, the agent triggers automated stoichiometric replacement with non-fluorinated, REACH-compliant sulfonate salts, specifically **Triphenylsulfonium Camphorsulfonate**:

$$\text{PAG Substitute: } \left[\mathrm{S^+(C_6H_5)_3}\right]\left[\mathrm{C_{10}H_{15}OSO_3^-}\right] \xrightarrow{\text{REACH / TSCA Clear}} \text{Alicyclic Non-Fluorinated Sulfonate} \tag{13}$$

The bulky alicyclic camphorsulfonate core provides low acid diffusion during PEB while eliminating perfluorinated persistence in effluent streams.

5. RECOMMENDED FORMULATION & SPIN COATING HYDRODYNAMICS

Table 2. Machine-Recommended PFAS-Free Negative Resist Formulation (Candidate NL-CAND-01).

Component Role	Chemical Identity	Mass (g)	Stoichiometry / Function	Regulatory Status
Polymer Resin	Poly(PHS-co-HPS) (Mw 12,000)	0.744	Phenolic novolac-type matrix	Approved
Primary Crosslinker	MM-1 (Hexamethoxymethylmelamine / Cymel 300)	0.218	65.2% of total crosslinker loading	Approved
Secondary Crosslinker	CL-1 (Tetramethoxymethylglycoluril / Powderlink 1174)	0.116	34.8% of crosslinker (Dual network)	Approved
Photoacid Generator	Triphenylsulfonium Camphorsulfonate	0.045	6.09% on resin (Non-fluorinated)	**100% PFAS-Free (REACH Pass)**
Basic Quencher	Trioctylamine (D-1)	0.0056	12.3% on PAG (Diffusion limiter)	Approved
Casting Solvent	PGMEA / PGME (7.50 g / 1.50 g)	9.000	Green ester-ether binary solvent	Approved
Surfactant	Megafac F-176 / Non-ionic	0.0010	Surface tension & coating uniformity	Approved

For the manual formulation track and laboratory batch execution, the resist film thickness h_0 (nm) resulting from spin-coating follows Meyerhofer's solvent evaporation and centrifugal flow relationship:

$$h_0 \approx k_{\text{fab}} \cdot \frac{C_{\text{solids}}^{1.38}}{\sqrt{\omega / 1000}} \tag{14}$$

where C_{solids} represents the total solute weight percent (≈ 10.1 wt% for NL-CAND-01), ω is the spin speed in RPM ($\omega = 1500$ RPM), and $k_{\text{fab}} \approx 115.0$ is the empirical calibration factor for PGMEA on 6-inch silicon wafers, yielding nominal film thickness $h_0 \approx 300$ nm.

6. SYSTEM ARCHITECTURE & DUAL-TRACK DEPLOYMENT

```
+-------------------------------------------------------------------------------------------------+ | STREAMLIT ENTERPRISE UI
(app.py) | | [Mode Switcher: Automated AI Optimization <=====> Manual Laboratory Formulation Workbench] | +-------------------------
--------+-----------------------------------+-------------------------------+ | | v v +-----------------------------------------
----+ +-----------------------------------------------+ | AUTOMATED TRACK | | MANUAL TRACK | | * GP Surrogate (Matérn 5/2, LOOCV MAE
1.37nm) | | * Real-Time Meyerhofer Film Thickness Model | | * Constrained Expected Improvement (EI) Engine | | * Interactive
Stoichiometric Ratio Sliders | | * PFAS Screener (OECD / REACH Annex XVII) | | * Rule-Based Defect Warning & Risk Heuristic| | *
Altair Uncertainty Band & Surface Charts | | * Step-by-Step Cleanroom Batch Sheet Export | +-------------------------------------
----------+ +-----------------------------------------------+
```

7. REFERENCES & STANDARDS

1. Yamada et al., *"Negative-Working Radiation-Sensitive Resist Composition and Pattern Forming Method,"* U.S. Patent 7,432,034 B2, Oct. 7, 2008.
2. C. E. Rasmussen and C. K. I. Williams, *Gaussian Processes for Machine Learning*, MIT Press, Cambridge, MA, 2006.
3. D. R. Jones, M. Schonlau, and W. J. Welch, *"Efficient Global Optimization of Expensive Black-Box Functions,"* Journal of Global Optimization, 13(4):455–492, 1998.
4. OECD Environment Directorate, *"Reconciling Terminology of the Universe of Per- and Polyfluoroalkyl Substances: Recommendations and Practical Guidance,"* Series on Risk Management, No. 61, 2021.
5. D. Meyerhofer, *"Characteristics of Resist Films Produced by Spinning,"* Journal of Applied Physics, 49(7):3993–3997, 1978.
6. F. H. Dill, W. P. Hornberger, P. S. Hauge, and J. M. Shaw, *"Characterization of Positive Photoresist,"* IEEE Transactions on Electron Devices, ED-22(7):445–452, 1975.