




Pearlkote



Top Coating	Blade
Base Coating	Blade
Kraft Layer	Unbleached Brown Kraft Pulp

Grammage		Thickness		Stiffness Taber		Stiffness Din		Smoothness Sheffield
gsm		µm	inch	CD	MD	CD	MD	
505		711	.028	400	820	75.6	155.0	120
Brightness - top				79% ISO				
Moisture				7.5%				
Parker Print				2.5				
Scott Bond Strength				126 J/m2				
Counter height				0.034"		864µm		
Male creasing rule height				0.913"		23.19µm		
Male Rule narrow				3				
Male Rule wide				4				
Female narrow				0.098"		2.48µm		
Female wide				0.112"		2.84µm		

target values DG 7/99