

Pull test should be tested by pull tester with fixing stand, see below, and client not accept inspector done pull test without fixing stand during inline inspection. 如果没有请汇报

ACCEPTED



NOT ACCEPTED



拉力易烂的地方，线缝补位（后背，颈，脚底，裤衩，手肘底），塑胶眼鼻等，如下图： Pull test for easily open or broken areas and parts.



Failure Part Photo:



Failure Part Photo:



Failure Summary:
EN71-1

During seam tension test, the seam was broken, 12 mm diameter rod can be inserted more than 6 mm.

Failure Part Photo:



所有布玩具拉力必须用如下左图的圆钳（塑胶眼鼻用下右图三勾, 没有至少用双勾），其他塑胶件选适合的工具），注意力度在 3-5 秒内到达 90N 且要保持固定 10 秒

Seam area need use seam clam, Pulling 3- 5 seconds to reach 90N, then keep 10 seconds



如果以 10N 的力用 0.4MM 片规能插入眼鼻 2mm，就要拉力

If 0.4mm feeler can insert 2mm with 10N force then need pull eye and nose

Plastic eye check



线缝位拉力要用二圆钳离线位都半寸距离钳住布进行（不能钳住里面的棉）
Near seam 1/2" and can not clam stuffing(only fabric)



拉最长边，如左手或耳到右脚，要尽量钳到尾部：
Biggest diameter pulling test



对拉二脚，要尽量钳到尾部：
must clam in the end area as possible



所有需要做测试的部位都要做拉力测试，而不是只是拉要拍相片的部位（如有二个手的玩具，可只拍一个手相片，但实际要所有部位，如左右手，左右脚，所有线缝位），因时间有限，就要按经验或请教去评估能代表质量的足够的部位进行测试

All parts need pull test according to sample size requested, photos at least one set to be taken, for example need pull both leg, and both hand, you can take photo for one leg and one hand are ok.

下图是 **X** 错的，因为钳没钳到尾部，而且手捉得太近了，有保护作用

Wrong pull test method (must catch on end, hand catch too close)



下图是 **X** 错的，因为右钳没钳到尾部

Wrong pull test method (must catch on end)



Seam allowance distance measurement



Seam allowance check



8 stitches per inch



Inner material check(all stuffing need put out)



Humidity test

