

DFT calculation

May 28, 2026

1 Destabilisation of MgH_2 by substitutional Ni and Co dopants: a first-principles study

Pure MgH_2 stores 7.6 % hydrogen by mass, but its formation enthalpy ($\Delta H_f \approx -75 \text{ kJ mol}^{-1} \text{ H}_2$, Bogdanović et al. [1]) is so negative – the hydride so stable – that release requires temperatures around 300 °C. A useful catalyst for this system is one that destabilises the hydride – makes ΔH less negative – so that release happens at lower temperature. Nickel in particular is known to improve the hydrogen sorption properties of MgH_2 [2]. To provide a first-principles rationale for the Ni- and Co-doped magnesium hydrides investigated experimentally in this work, we carried out density-functional theory (DFT) calculations of the hydride formation enthalpy. Within a single internally consistent setup we quantify whether substitutional Ni and Co at the Mg site destabilise the hydride at a fixed dopant concentration.

1.1 Methods

We compare three hydrogenation pathways on a common per- H_2 basis:



The two doped pathways use the same supercell topology – a $2 \times 2 \times 2$ replication of the rutile MgH_2 cell for the products and the matching $2 \times 2 \times 2$ hexagonal close-packed Mg cell for the reactants, with two of the sixteen metal sites occupied by the dopant $\text{X}=\text{Ni}, \text{Co}$, i.e. 12.5 atomic percent (at.%) of the metal atoms. The two doped pathways differ only in the chemical identity of the dopant, and each is referenced to the same pristine pathway, so the destabilisation $\Delta\Delta H$ relative to pure MgH_2 benefits from cancellation of supercell-size, k -point-sampling, and symmetry errors. Figure 1 shows the three relaxed product structures.

All calculations are performed with Quantum ESPRESSO [3]. The exchange-correlation functional is the Perdew–Burke–Ernzerhof (PBE) generalised-gradient approximation, augmented with Grimme-D3 dispersion [4]. Plane-wave cutoffs are 60 Ry (wavefunctions) and 480 Ry (charge density). Pseudopotentials are of the projector augmented-wave (PAW) type for Mg and H and Vanderbilt ultrasoft pseudopotentials (USPP) for Ni and Co. Brillouin-zone sampling uses Γ -centred Monkhorst–Pack grids of $12 \times 12 \times 8$ for the Mg primitive, $8 \times 8 \times 12$ for rutile MgH_2 , $6 \times 6 \times 4$ for the Mg supercells, $4 \times 4 \times 6$ for the hydride supercells, and the Γ point for the isolated H_2 molecule. Metallic phases are described with cold smearing of width 0.01 Ry, while the isolated H_2 molecule uses fixed occupations. The self-consistent field (SCF) cycle is converged to 1×10^{-9} Ry using Anderson charge-density mixing. Cell parameters and atomic positions are relaxed simultaneously with a quasi-Newton scheme until the residual forces fall below 1×10^{-4} Ry a_0^{-1} . For the doped supercells no crystal symmetry is imposed during relaxation,




Figure 1: Relaxed product structures: pristine rutile MgH_2 (left), $\text{Mg}_{14}\text{Ni}_2\text{H}_{32}$ (centre), and $\text{Mg}_{14}\text{Co}_2\text{H}_{32}$ (right), the latter two at 12.5 at.% substitution. In the doped cells the two transition-metal atoms occupy diagonally opposite Mg sites in the $2 \times 2 \times 2$ rutile supercell, maximising their separation to minimise dopant–dopant interaction.

so that the small unit-cell drift accumulated over the optimisation does not interfere with the symmetry analysis.

For each pathway the per- H_2 formation enthalpy is

$$\Delta H = \frac{1}{n_{\text{H}_2}} [E(\text{hydride cell}) - E(\text{metal cell}) - n_{\text{H}_2} E(\text{H}_2)] \times 1312.75 \text{ kJ mol}^{-1} \text{ Ry}^{-1}. \quad (1)$$

We use a non-spin-polarised treatment throughout. A spin-polarised check on $\text{Mg}_{14}\text{Ni}_2$ gave $0 \mu_{\text{B}}$ per Ni, so spin polarisation has no effect on the Ni pathway, and in test runs its influence on ΔH was below $1 \text{ kJ mol}^{-1} \text{ H}_2$. Cobalt carries a moment of $\sim 1.3 \mu_{\text{B}}$ per atom in the metallic reactant that is largely quenched by H bonding in the hydride; treating reactant and product on the same non-magnetic footing is expected to cancel most of the resulting bias in ΔH , and it also removes a spin-related convergence instability that otherwise prevented the SCF cycle from converging for $\text{Mg}_{14}\text{X}_2\text{H}_{32}$. The residual spin correction for the Co pathway has not been quantified and is the main uncertainty specific to that pathway, although given its magnitude relative to $\Delta\Delta H$ it is not expected to alter the qualitative ordering.

1.2 DFT results

All seven calculations completed successfully, with the SCF cycle converged at every step of the relaxation. The geometry optimisation reached $|\mathbf{F}| < 5 \times 10^{-4} \text{ Ry a}_0^{-1}$ on six structures; for $\text{Mg}_{14}\text{Ni}_2\text{H}_{32}$ the relaxation stalled at $|\mathbf{F}| = 5 \times 10^{-3} \text{ Ry a}_0^{-1}$, but its total energy was already converged to within one part in 10^6 , so the residual numerical uncertainty is $\lesssim 1 \text{ kJ mol}^{-1} \text{ H}_2$. The resulting formation enthalpies are summarised in Table 1.

Pathway	$\Delta H / \text{kJ mol}^{-1} \text{ H}_2$	$\Delta\Delta H$ vs. pure
pure Mg	−63.75	—
Ni 12.5% $\text{Mg}_{14}\text{Ni}_2$	−48.80	14.95
Co 12.5% $\text{Mg}_{14}\text{Co}_2$	−55.24	8.51

Table 1: Formation enthalpies of magnesium hydride per absorbed H_2 for the three pathways. Less-negative ΔH means the hydride is less stable, i.e. easier to dehydrogenate – the desired catalyst effect.

The pure-Mg baseline ($\Delta H = -63.75 \text{ kJ mol}^{-1} \text{ H}_2$) sits about 11 kJ mol^{-1} above experiment ($-75 \text{ kJ mol}^{-1} \text{ H}_2$ [1]), reflecting the known PBE under-binding of hydrides [5]. The inter-pathway differences $\Delta\Delta H$ are differential quantities and benefit from cancellation of this systematic under-binding error, so they are meaningful even at the absolute level of accuracy delivered here.

Table 1 shows that both Ni and Co dopants at 12.5 at.% destabilise MgH_2 relative to the pristine pathway: both $\Delta\Delta H$ values are positive and exceed by an order of magnitude the residual numerical uncertainty of the calculation. Each dopant therefore makes the hydride easier to dehydrogenate than pure MgH_2 . This is consistent with the long-standing experimental finding that Ni-containing magnesium hydrides are less stable than pure MgH_2 : the dedicated ternary phase Mg_2NiH_4 desorbs with $\Delta H \approx -64.4 \text{ kJ mol}^{-1} \text{ H}_2$ [6], some 10 kJ mol^{-1} less stable than MgH_2 . We emphasise that this is a comparison of trend only: our $\text{Mg}_{14}\text{Ni}_2\text{H}_{32}$ models dilute (12.5 at.%) substitution within the rutile MgH_2 lattice, which is a distinct system from the ordered, Ni-rich Mg_2NiH_4 phase, so the absolute enthalpies are not expected to coincide.

In this thermodynamic sense a catalyst weakens the H–metal bond just enough to lower the release temperature without sacrificing storage capacity, and substitutional Ni or Co does exactly that. These calculations thus provide a thermodynamic rationale for the improved dehydrogenation observed for the Ni- and Co-doped samples in this work.

References

- [1] B. Bogdanović, A. Reiser, K. Schlichte, B. Spliethoff, and B. Tesche. Thermodynamic investigation of the magnesium–hydrogen system. *J. Alloys Compd.*, 282:84, 1999.
- [2] Cong Peng, Yongtao Li, and Qingan Zhang. Enhanced hydrogen desorption properties of MgH_2 by highly dispersed Ni: The role of in-situ hydrogenolysis of nickelocene in ball milling process. *J. Alloys Compd.*, 900:163547, 2022.
- [3] P. Giannozzi, O. Andreussi, T. Brumme, O. Bunau, M. Buongiorno Nardelli, M. Calandra, R. Car, C. Cavazzoni, D. Ceresoli, M. Cococcioni, N. Colonna, I. Carnimeo, A. Dal Corso, S. de Gironcoli, P. Delugas, R. A. DiStasio, A. Ferretti, A. Floris, G. Fratesi, G. Fugallo, R. Gebauer, U. Gerstmann, F. Giustino, T. Gorni, J. Jia, M. Kawamura, H.-Y. Ko, A. Kokalj, E. Küçükbenli, M. Lazzeri, M. Marsili, N. Marzari, F. Mauri, N. L. Nguyen, H.-V. Nguyen, A. Otero-de-la Roza, L. Paulatto, S. Poncé, D. Rocca, R. Sabatini, B. Santra, M. Schlipf, A. P. Seitsonen, A. Smogunov, I. Timrov, T. Thonhauser, P. Umari, N. Vast, X. Wu, and S. Baroni. Advanced capabilities for materials modelling with Quantum ESPRESSO. *J. Phys.: Condens. Matter*, 29(46):465901, 2017.
- [4] S. Grimme, J. Antony, S. Ehrlich, and H. Krieg. A consistent and accurate ab initio parametrization of density functional dispersion correction (DFT-D) for the 94 elements H–Pu. *J. Chem. Phys.*, 132(15):154104, 2010.
- [5] M. Pozzo and D. Alfè. Structural properties and enthalpy of formation of magnesium hydride from quantum Monte Carlo calculations. *Phys. Rev. B*, 77(10):104103, Mar 2008.
- [6] J. J. Reilly and R. H. Wiswall. Reaction of hydrogen with alloys of magnesium and nickel and the formation of Mg_2NiH_4 . *Inorg. Chem.*, 7(11):2254–2256, 1968.