



3D PRINTING PARAMETERS		
PARAMETER	TYPICAL VALUE	DESCRIPTION
LAYER HEIGHT	0.20 mm	Vertical resolution per layer.
WALL THICKNESS	1.2 mm (≈3 walls)	Number of perimeter walls.
INFILL DENSITY	15-35 %	Internal structure fill percentage.
PRINTING SPEED	~60 mm/s (standard)	Linear print speed of nozzle.
NOZZLE TEMPERATURE	260 °C (ABS)	Extruder temperature.
BED TEMPERATURE	100 °C (ABS)	Heated bed temperature.
COOLING FAN SPEED	0-10 %	Low cooling to reduce warping; keep chamber warm/closed.
SUPPORTS	Enabled	Use as needed for overhangs/bridges.
ADHESION TYPE	Brim	Improves bed adhesion on PEI textured plate.

CREATED BY	RULOBOT TEAM 08/06/2025
DOCUMENT NAME	RULOBOT_ASSEMBLY
TITLE	Drive_Wheel_Support
MANUFACTURING TECHNOLOGY	FDM 3D PRINTING

APPROVED BY WILMER DE JESÚS REYES 08/12/2025		
EVENT WRO SINGAPORE INTERNATIONAL FINAL		
MATERIAL PLA		
REV	DATE OF ISSUE	SHEET
REV1	08/12/2025	1
		