



Live Safer™

NSF International

NSF International.
789 Dixboro Road, Ann Arbor, Michigan 48105-9723 USA
1-800-NSF-MARK 734-769-8010
www.nsf.org

TEST REPORT

Send To: C0096491

Facility: C0096493

ANPING COUNTY PFM SCREEN CO.,LTD

ANPING COUNTY PFM SCREEN CO.,LTD

INDUSTRIAL PARK ZONE OF SOUTH ANPING
COUNTY, HEBEI CHINA

INDUSTRIAL PARK ZONE OF SOUTH ANPING
COUNTY, HEBEI CHINA

Result Pass

Report Date 30-Oct-2013

Customer Name ANPING COUNTY PFM SCREEN CO.,LTD

Description Stainless steel strainer

Test Type Test Only

Job Number J-00131026

Sample Reception Date 23-Oct-2013

Testing Completion Date 30-Oct-2013

Summary of Results

Testing Parameters and Standards	Result
Determination of Extractive Residue according to US FDA 21 CFR 177.1630	Pass

Report Authorization

Date 30-Oct-2013

Kurtis Kneen - Director of Chemistry Laboratories



1. Determination of Extractive Residue according to US FDA 21 CFR 177.1630

1.1 Testing procedure:

Extract samples at the extractive solvent and extractive condition, weight the extractives residue and calculate the contacted area of the samples


1.2 Testing result:

Testing Parameter	Testing Condition	Unit	Result	Acceptance	Conclusion
Extractive residue (Water)	49°C, 24h	mg/in ²	ND(0.1)	0.5	Pass
Extractive residue (8% ethanol)	49°C, 24h	mg/in ²	ND(0.1)	0.5	Pass
Extractive residue (n-heptane)	49°C, 24h	mg/in ²	ND(0.1)	0.5	Pass

Remark

ND=Not Detected, less than reporting limit.

Picture of Sample



Polyester Mesh

End of Report