

PLATFORM® Resin ETM090NC-China

Essential Information

Material Type	: POM-Polyoxymethylene		
Material Shape	: Granules		
Flame Rating	: HB		
Application	: Automotive, electrical & electronic, sanitary and industrial applications		
Material Description	: Standard grade		
Color	: Natural		

Typical Properties

Physical Properties	Nominal Value Unit	Test Method	Value
Density	g/cm ³	ISO 1183	1.41
Melt Flow Rate (MFI) (195°C/2.16 kg)	g/10 min	ISO 1133	9
Molding Shrinkage	%	Internal Method	1.8-2.0
Water Absorption	%	ISO 62	0.2
Mechanical Properties	Nominal Value Unit	Test Method	Value
Tensile Strength	MPa	ISO 527	60
Tensile Strain at Break	%	ISO 527	30
Flexural Strength	MPa	ISO 178	85
Flexural Modulus	MPa	ISO 178	2500
Impact Properties	Nominal Value Unit	Test Method	Value
Charpy Notched Impact Strength	kJ/m ²	ISO 179/1eA	7.5
Izod Notched Impact Strength	kJ/m ²	ISO 180/1A	7
Thermal Properties	Nominal Value Unit	Test Method	Value
Melting Temperature	°C	ISO 11357	165
Heat Deflection Temperature (1.8 MPa)	°C	ISO 75-2	95
Coefficient of Linear Thermal Expansion, CLTE	×10 ⁻⁵ /°C	ISO 11359	12
Electrical Properties	Nominal Value Unit	Test Method	Value
Volume Resistivity	Ω·cm	Internal Method	1×10 ¹⁴
Surface Resistivity	Ω	Internal Method	1×10 ¹⁶
Dielectric Strength	kV/mm	Internal Method	19

Processing Information

Injection Molding	Nominal Value Unit	Test Method	Value
Drying Temperature	°C		85
Drying Time	h		2
Suggested Max Moisture	%		5
Hopper Temperature	°C		95
Rear Temperature	°C		165
Middle Temperature	°C		175
Front Temperature	°C		185
Nozzle Temperature	°C		190
Melt Temperature	°C		200
Mold Temperature	°C		30-60