

A NORSOK APPROVED & DNV APPROVAL OF MANUFACTURER, AN ISO 9001:2015, ISO 14001:2015, BS OHSAS 18001:2007, PED & ADW / AD - 2000 - W0 Certified Company

MFG. & EXPORTER OF STAINLESS STEEL SEAMLESS & WELDED PIPES / TUBES / U-TUBES GOVT. RECOGNISED EXPORT HOUSE

CIN: U27106GJ2006PTC049217

F/QAC/12 REV.01 INSPECTION CERTIFICATE AS PER EN 10204 - 3.2 T.C.NO:-MTCPL/2020-2021/1492/A CUSTOMER NAME :- M/s. L&T HYDROCARBON ENGINEERING LIMITED. DATE :- 31/01/2021 :- REFINERY/75000-79317/KKM DATE :- 23.12.2020 :- 2020-21/12/00834/DOM PRODUCT :- AUSTENITIC S.S. SEAMLESS (P.E.) PIPES. (COLD DRAWN, SOLUTION ANNEALED, PICKLED & PASSIVATED) DATE :- 24.12.2020 MAT.SPEC. :- ASTM A-312-18a, TP-304L EIL SPECIFICATION NO.: 6-44-0051 REV.6 DATE:- 25.09.2014 MATERIAL/SERVICE CODE: PPS4CGGN1DZZZS3PB STANDARD QAP FOR SS & AS SEAMLESS PIPE DOC NO.; B016-VRMP-LT-000-QC-QD-0011 REV. NO.; 00 DATE:- 28.02.2018 SHOP QC AND INSPECTION PROCEDURE DOC. NO.: B016-VRMP-LT-COM-QA-QD-0003 REV. NO.: 01 DATE:- 25.01.2018 TECHNICAL SPECIFICATION FOR PROCUREMENT OF PIPING ITEMS DOC. NO.: B016-HCUV-LT-503-PP-SP-0002 REV. NO.: 2 DATE:- 10.05.2018 POSITIVE MATERIAL IDENTIFICATION PROCEDURE (SHOP) DOC. NO.: B016-VRMP-LT-COM-QA-QD-0005 REV. NO.: 02 DATE:- 08.03.2018 STANDARD SPECIFICATION FOR COLOUR CODING OF PIPING MATERIAL :- 6-82-0003 REV.2 DATE:- 25.06.2014 HEAT NO. NO. DIMENSIONS NO.OF PCS TOTAL METER 200222AB08 1 1.1/2" NB X SCH 40S X 5 TO 7 MTR R.L. (P.E.) "GENERAL" 24 140,400 CHEMICAL TEST CHEMICAL COMPOSITION % ITEM HEAT C Si Mn P NO. S NO. Ni Cr 0.035 Mo 1.000 N 2.000 S 0.045 0.030 8.000 18 000 MAX MAX MAX MAX MAX 13.000 20.000 H 0.023 0.660 0.980 0.038 0.003 1 200222AB08 8.060 18.090 P1 0.024 0.644 1.012 0.039 0.004 8.045 18,111 P2 0.022 0.678 0.967 0.037 0.005 8.094 18.065 MECHANICAL TEST ELON. A%, TENSILE ITEM YIELD. G.L=50 MM. STRENGTH STRENGTH FLARING NO. HYDRO TEST PRESSURE AT HARDNESS REVERSE BEND G.W=12.70 Mpa FLATTENING TEST Mpa TEST 2000 psi (g) 10 SEC. MM TEST REQ. 485 [MIN] 170 [MIN] HOLDING TIME (WATER 35% [MIN] 90 HRB MAX USED FOR HYDRO TEST 1 587.66 297.43 52.00% 78 TO 81 HRB HAS CHLORIDE CONTENT NA OK NA LESS THAN 50 ppm) REMARKS:-[1] HEAT TREATMENT: SOLUTION ANNEALED AT TEMPERATURE BETWEEN 1044°C TO 1059°C AND QUENCHED IN WATER. [2] PRODUCT ANALYSIS CONDUCTED BY MTCPL & REPORT REVIEWED BY TUV INDIA - FOUND SATISFACTORY. [3] MECHANICAL TEST CONDUCTED BY MTCPL & WITNESSED BY TUV INDIA - FOUND SATISFACTORY. [4] IGC TEST ACCORDANCE TO ASTM A-262 PRACTICE "E" (WITH 20X & 250X MAGNIFICATION) CONDUCTED BY MTCPL & WITNESSED BY TUV INDIA - FOUND SATISFACTORY. [5] 100% HYDRO TEST CARRIED OUT BY MTCPL & 10% WITNESSED BY TUV INDIA - FOUND SATISFACTORY. [6] 100% VISUAL CHECKED BY MTCPL & 100% WITNESSED BY TUV INDIA - FOUND SATISFACTORY. [7] 100% DIMENSION CHECKED BY MTCPL & 10% WITNESSED BY TUV INDIA - FOUND SATISFACTORY. [8] 100% PMI TEST CARRIED OUT BY MTCPL & 20% WITNESSED BY TUV INDIA - FOUND SATISFACTORY. [9] PICKLING & PASSIVATION CARRIED OUT BY MTCPL & REPORT REVIEWED BY TUV INDIA - FOUND SATISFACTORY. [10] MARKING ON PIPES CARRIED OUT BY MTCPL & RANDOM WITNESSED BY TUV INDIA - FOUND SATISFACTORY. [11] MARKING ON PRODUCT:- MAXIM S.S. SEAMLESS (P.E.) PIPE, SIZE, SPEC, GRADE, HEAT NO, P.O.NO, MATERIAL CODE, ITEM NO, "PMI OK" "GENERAL" [12] 10% WITNESSED PIPES DOUBLE STAMPED AND BALANCE ARE SINGLE STAMPED AS " NOTE:- S= SPECIFICATION, P= PRODUCT ANALYSIS, H= HEAT ANALYSIS, G.L.= GAUGE LENGTH GW. " (ELECTRO-ETCHED) FOR IDENTIFICATION. GAUGE WIDTH, N.A= NOT APPLICABLE REVIEWED / NOTED nspection%WITNES CLIENT'S SIGN PO.ITEM :- COMPLETE WE HEREBY CERTIFY THAT THE MATERIAL IS AS PER SIZE & SPECIFICATION MENTIONED IN ORDER MANAGER (Q.A.

Regd. Office & Works: Survey No. 105/106, Nr. 66 KV Sub-Station, Chhatral-Pansar Road, Ahmedabad-Mehsana Highway, Chhatral-382729, Ta. Kalol, Dist. Gandhinagar, Gujarat, INDIA. Domestic Phone No.: +91 99090 98844, F: +91 2764 234477, E: info@maximtubes.com E: mtcpl@maximtubes.com Admin Office: B-92, Riviera Antilia, Nr. Pinnacle Corporate Road, Prahladnagar, Vejalpur, Ahmedabad, Gujarat-380051, INDIA. www.maximtubes.com



A NORSOK APPROVED & DNV APPROVAL OF MANUFACTURER, AN ISO 9001:2015, ISO 14001:2015, BS 0HSAS 18001:2007, PED & ADW / AD - 2000 - W0 Certified Company

MFG. & EXPORTER OF STAINLESS STEEL SEAMLESS & WELDED PIPES / TUBES / U-TUBES
GOVT. RECOGNISED EXPORT HOUSE CIN: U27106GJ2006PTC049217

F/QAC/12 REV.01 INSPECTION CERTIFICATE AS PER EN 10204 - 3.2 T.C.NO:-MTCPL/2020-2021/1492/B CUSTOMER NAME :- M/s. L&T HYDROCARBON ENGINEERING LIMITED. DATE :- 31/01/2021 :- REFINERY/75000-79317/KKM O.A.NO. :- 2020-21/12/00834/DOM DATE :- 23.12.2020 PRODUCT :- AUSTENITIC S.S. SEAMLESS (P.E.) PIPES. (COLD DRAWN, SOLUTION ANNEALED, PICKLED & PASSIVATED) DATE :- 24.12.2020 MAT.SPEC. :- ASTM A-312-18a, TP-304L EIL SPECIFICATION NO.: 6-44-0051 REV.6 DATE:- 25.09.2014 MATERIAL/SERVICE CODE: PPS4CGGN01ZZZS3PB STANDARD QAP FOR SS & AS SEAMLESS PIPE DOC NO.: B016-VRMP-LT-000-QC-QD-0011 REV. NO.: 00 DATE:- 28.02.2018 SHOP QC AND INSPECTION PROCEDURE DOC. NO.: B016-VRMP-LT-COM-QA-QD-0003 REV. NO.: 01 DATE:- 25.01.2018 TECHNICAL SPECIFICATION FOR PROCUREMENT OF PIPING ITEMS DOC. NO.: B016-HCUV-LT-503-PP-SP-0002 REV. NO.: 2 DATE:- 10.05.2018 POSITIVE MATERIAL IDENTIFICATION PROCEDURE (SHOP) DOC. NO.: B016-VRMP-LT-COM-QA-QD-0005 REV. NO.: 02 DATE:- 08.03.2018 STANDARD SPECIFICATION FOR COLOUR CODING OF PIPING MATERIAL :- 6-82-0003 REV.2 DATE:- 25.06.2014 HEAT NO. NO. DIMENSIONS NO.OF PCS TOTAL METER J3100565 1" NB X SCH 40S X 5 TO 7 MTR R.L. (P.E.) "GENERAL" 59.750 CHEMICAL TEST CHEMICAL COMPOSITION % ITEM HEAT C Si Mn NO. NO. S Ni Cr 0.035 1.000 2.000 N S 0.045 0.030 8.000 18.000 MAX MAX MAX MAX MAX 13.000 20 000 Н 0.023 0.480 0.990 0.037 0.002 2 13100565 8.060 18.080 P1 0.021 0.512 1.025 0.038 0.004 8.078 18,115 P2 0.022 0.467 1.047 0.036 0.003 8.112 18.060 MECHANICAL TEST ELON. A%, TENSHE YIELD ITEM G.L=50 MM. STRENGTH STRENGTH FLARING NO. HYDRO TEST PRESSURE AT HARDNESS REVERSE BEND G.W=FULL FLATTENING TEST Mpa Mpa TEST SPECIMEN TEST 2500 psi (g) 10 SEC. REO 485 [MIN] 170 [MIN] HOLDING TIME (WATER 35% [MIN] 90 HRR MAY USED FOR HYDRO TEST 2 613.58 291.89 64.00% 80 TO 82 HRB HAS CHLORIDE CONTENT NA OK NA REMARKS:-LESS THAN 50 ppm) [1] HEAT TREATMENT: SOLUTION ANNEALED AT TEMPERATURE BETWEEN 1045°C TO 1059°C AND QUENCHED IN WATER. [2] PRODUCT ANALYSIS CONDUCTED BY MTCPL & REPORT REVIEWED BY TUV INDIA - FOUND SATISFACTORY. [3] MECHANICAL TEST CONDUCTED BY MTCPL & WITNESSED BY TUV INDIA - FOUND SATISFACTORY. [4] IGC TEST ACCORDANCE TO ASTM A-262 PRACTICE "E" (WITH 20X & 250X MAGNIFICATION) CONDUCTED BY MTCPL & WITNESSED BY TUV INDIA - FOUND [5] 100% HYDRO TEST CARRIED OUT BY MTCPL & 10% WITNESSED BY TUV INDIA - FOUND SATISFACTORY. [6] 100% VISUAL CHECKED BY MTCPL & 100% WITNESSED BY TUV INDIA - FOUND SATISFACTORY. [7] 100% DIMENSION CHECKED BY MTCPL & 10% WITNESSED BY TUV INDIA - FOUND SATISFACTORY. [8] 100% PMI TEST CARRIED OUT BY MTCPL & 20% WITNESSED BY TUV INDIA - FOUND SATISFACTORY. [9] PICKLING & PASSIVATION CARRIED OUT BY MTCPL & REPORT REVIEWED BY TUV INDIA - FOUND SATISFACTORY. [10] MARKING ON PIPES CARRIED OUT BY MTCPL & RANDOM WITNESSED BY TUV INDIA - FOUND SATISFACTORY. [11] MARKING ON PRODUCT:- MAXIM S.S. SEAMLESS (P.E.) PIPE, SIZE, SPEC, GRADE, HEAT NO, P.O.NO, MATERIAL CODE, ITEM NO, "PMI OK" "GENERAL" [12] 10% WITNESSED PIPES DOUBLE STAMPED AND BALANCE ARE SINGLE STAMPED AS " NOTE:- S= SPECIFICATION. P= PRODUCT ANALYSIS, H= HEAT ANALYSIS, G.L.= GAUGE LENGTH/G. " (ELECTRO-ETCHED) FOR IDENTIFICATION. V.=GAUGE WIDTH, N.A= NOT APPLICABLE REVIEWED / NOTER INSRECTOR'S COLENT'S SIGN PO.ITEM :- COMPLETE WE HEREBY CERTIFY THAT THE MATERIAL IS AS PER SIZE & SPECIFICATION MENTIONED IN ORDER

Regd. Office & Works: Survey No. 105/106, Nr. 66 KV Sub-Station, Chhatral-Pansar Road, Ahmedabad-Mehsana Highway, Chhatral-382729, Ta. Kalol, Dist. Gandhinagar, Gujarat, INDIA.

Domestic Phone No.: +91 99090 98844, F: +91 2764 234477, E: info@maximtubes.com E: mtcpl@maximtubes.com

Admin Office: B-92, Riviera Antilia, Nr. Pinnacle Corporate Road, Prahladnagar,

Vejalpur, Ahmedabad, Gujarat-380051, INDIA.



A NORSOK APPROVED & DNV APPROVAL OF MANUFACTURER, AN ISO 9001:2015, ISO 14001:2015, BS OHSAS 18001:2007, PED & ADW / AD - 2000 - W0 Certified Company

MFG. & EXPORTER OF STAINLESS STEEL SEAMLESS & WELDED PIPES / TUBES / U-TUBES GOVT. RECOGNISED EXPORT HOUSE CIN: U27106GJ2006PTC049217

F/QAC/12 REV.01 INSPECTION CERTIFICATE AS PER EN 10204 - 3.2 T.C.NO:-MTCPL/2020-2021/1492/C CUSTOMER NAME :- M/s. L&T HYDROCARBON ENGINEERING LIMITED. DATE :- 31/01/2021 :- REFINERY/75000-79317/KKM DATE :- 23.12.2020 :- 2020-21/12/00834/DOM PRODUCT: - AUSTENITIC S.S. SEAMLESS (B.E.) PIPES. (COLD DRAWN, SOLUTION ANNEALED, PICKLED & PASSIVATED) DATE :- 24.12.2020 MAT.SPEC. :- ASTM A-312-18a, TP-304L MATERIAL/SERVICE CODE: PPS4CGGN02ZZZS3BB EIL SPECIFICATION NO.: 6-44-0051 REV.6 DATE:- 25.09.2014 STANDARD QAP FOR SS & AS SEAMLESS PIPE DOC NO.: B016-VRMP-LT-000-QC-QD-0011 REV. NO.: 00 DATE:- 28.02.2018 SHOP QC AND INSPECTION PROCEDURE DOC. NO.: B016-VRMP-LT-COM-QA-QD-0003 REV. NO.: 01 DATE:- 25.01.2018 TECHNICAL SPECIFICATION FOR PROCUREMENT OF PIPING ITEMS DOC. NO.: B016-HCUV-LT-503-PP-SP-0002 REV. NO.: 2 DATE:- 10.05.2018 POSITIVE MATERIAL IDENTIFICATION PROCEDURE (SHOP) DOC. NO.: B016-VRMP-LT-COM-QA-QD-0005 REV. NO.: 02 DATE:- 08.03.2018 STANDARD SPECIFICATION FOR COLOUR CODING OF PIPING MATERIAL: - 6-82-0003 REV.2 DATE: - 25.06.2014 HEAT NO. NO. DIMENSIONS NO OF PCS TOTAL METER 3 200222AB08 2" NB X SCH 40S X 5 TO 7 MTR R.L. (B.E.) "GENERAL" 31 199.460 CHEMICAL TEST CHEMICAL COMPOSITION % ITEM HEAT C Si Mn S NO. Ni Cr NO. N 0.035 1.000 2.000 0.045 S 0.030 8.000 18.000 MAX MAX MAX MAX MAX 13.000 20.000 H 0.023 0.660 0.980 0.038 0.003 8.060 18.090 200222AB08 3 P1 0.024 0.694 1 014 0.037 0.002 8.078 18.138 P2 0.025 0.712 1.045 0.036 0.005 8.105 18.118 MECHANICAL TEST ELON. A%. TENSILE YIELD ITEM G.L=50 MM, STRENGTH FLARING STRENGTH HYDRO TEST PRESSURE AT HARDNESS REVERSE BEND NO. G.W=12.70 FLATTENING TEST Mpa Mpa TEST 1700 psi (g) 10 SEC. TEST MM REQ. 485 [MIN] HOLDING TIME (WATER 170 IMINI 35% [MIN] 90 HRB MAX USED FOR HYDRO TEST 3 577.55 326.82 56.00% 79 TO 82 HRB HAS CHLORIDE CONTENT NA OK NA LESS THAN 50 ppm) REMARKS:-[1] HEAT TREATMENT: SOLUTION ANNEALED AT TEMPERATURE BETWEEN 1044°C TO 1058°C AND QUENCHED IN WATER. [2] PRODUCT ANALYSIS CONDUCTED BY MTCPL & REPORT REVIEWED BY TUV INDIA - FOUND SATISFACTORY. [3] MECHANICAL TEST CONDUCTED BY MTCPL & WITNESSED BY TUV INDIA - FOUND SATISFACTORY. [4] IGC TEST ACCORDANCE TO ASTM A-262 PRACTICE "E" (WITH 20X & 250X MAGNIFICATION) CONDUCTED BY MTCPL & WITNESSED BY TUV INDIA - FOUND [5] 100% HYDRO TEST CARRIED OUT BY MTCPL & 10% WITNESSED BY TUV INDIA - FOUND SATISFACTORY. [6] 100% VISUAL CHECKED BY MTCPL & 100% WITNESSED BY TUV INDIA - FOUND SATISFACTORY. [7] 100% DIMENSION CHECKED BY MTCPL & 10% WITNESSED BY TUV INDIA - FOUND SATISFACTORY. [8] 100% D.P. TEST ON BEVEL EDGES CARRIED OUT BY MTCPL & 10% WITNESSED BY TUV INDIA - FOUND SATISFACTORY. [9] 100% PMI TEST CARRIED OUT BY MTCPL & 20% WITNESSED BY TUV INDIA - FOUND SATISFACTORY. [10] PICKLING & PASSIVATION CARRIED OUT BY MTCPL & REPORT REVIEWED BY TUV INDIA - FOUND SATISFACTORY. [11] MARKING ON PIPES CARRIED OUT BY MTCPL & RANDOM WITNESSED BY TUV INDIA - FOUND SATISFACTORY. [12] MARKING ON PRODUCT:- MAXIM S.S. SEAMLESS (B.E.) PIPE, SIZE, SPEC, GRADE, HEAT NO, P.O.NO, MATERIAL CODE, ITEM NO, "PMI OK" "GENERAL" [13] 10% WITNESSED PIPES DOUBLE STAMPED AND BALANCE ARE SINGLE STAMPED AS " NOTE:- S= SPECIFICATION, P= PRODUCT ANALYSIS, H= HEAT ANALYSIS, G.L.= GAUGE LENGTH, G.W.-GAUGE WIDTH, N.A= NOT APPLICABLE " (ELECTRO-ETCHED) FOR IDENTIFICATION. REVIEWED / NOTED CLIENT'S SIGN PO.ITEM :- COMPLETE WE HEREBY CERTIFY THAT THE MATERIAL IS AS PER SIZE & SPECIFICATION MENTIONED IN ORDER MANAGER (Q.A.)TR

Regd. Office & Works: Survey No. 105/106, Nr. 66 KV Sub-Station, Chhatral-Pansar Road, Ahmedabad-Mehsana Highway, Chhatral-382729, Ta. Kalol, Dist. Gandhinagar, Gujarat, INDIA.

Domestic Phone No.: +91 99090 98844, F: +91 2764 234477, E: info@maximtubes.com E: mtcpl@maximtubes.com

Admin Office: B-92, Riviera Antilia, Nr. Pinnacle Corporate Road, Prahladnagar,

Vejalpur, Ahmedabad, Gujarat-380051, INDIA.